
**Resilient floor coverings — Identification
of linoleum and determination of cement
content and ash residue**

*Revêtements de sol résilients — Identification du linoléum et
détermination de la teneur en ciment et du taux de cendres*

STANDARDSISO.COM : Click to view the full PDF of ISO 26985:2008



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 26985:2008



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 26985 was prepared by Technical Committee ISO/TC 219, *Floor coverings*.

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 26985:2008

Resilient floor coverings — Identification of linoleum and determination of cement content and ash residue

1 Scope

This International Standard specifies methods for identifying linoleum and determining the cement content and ash residue of linoleum floor coverings.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1

ash residue

residue that remains following incineration at 500 °C for 3 h

2.2

linoleum cement

binder in linoleum, consisting of a mixture of linseed oil and/or vegetable drying oils, rosin and drying oil catalysts, which is converted to a semi-elastic mass by an oxidative curing process

3 Principles

3.1 Identification

A small specimen is saponified in a solution of potassium hydroxide in methanol to identify linoleum from other floor coverings.

3.2 Composition

3.2.1 Cement content

A specimen without the backing material is crumbled and mixed with a mixture of potassium hydroxide in methanol. After intensive stirring at 20 °C to 25 °C, the mixture is filtered and carefully dried. The difference between the initial mass and the mass of the residue is the defined mass of linoleum cement.

3.2.2 Ash residue

To determine the amount of ash residue, a specimen without the backing material is incinerated and the mass of the residual ash is measured.

4 Apparatus and materials

4.1 Apparatus

4.1.1 Grater.

4.1.2 Tared beakers.

4.1.3 Porcelain crucibles.

4.1.4 Desiccator (vacuum type), containing a suitable desiccant, e.g. silica gel.

4.1.5 Furnace, capable of being controlled at $500\text{ }^{\circ}\text{C} \pm 10\text{ }^{\circ}\text{C}$.

4.1.6 Balance, having an accuracy of 0,1 mg.

4.1.7 Laboratory sieve, with a nominal aperture size of 0,5 mm.

4.1.8 Ultrasonic bath, or equivalent device.

4.1.9 Centrifuge or vacuum filter (type A2) and suction device, e.g. a water-jet pump.

4.1.10 Bunsen burner.

4.2 Materials

4.2.1 Methanol (methyl alcohol), analytical grade.

4.2.2 Potassium hydroxide (analytical grade) in methanol solution, with a concentration of 0,5 mol/l.

5 Sampling and preparation of specimens

5.1 Sampling

Take a representative sample from the available material. Take five specimens, each with a minimum area of 50 cm^2 , from across the width of the sample, or from individual tiles, the distance between the edge of the sample and the nearest edge of the specimen being at least 100 mm.

Cut a square of approximately $20\text{ mm} \times 20\text{ mm}$ from a specimen.

5.2 Determination of cement content

Remove the backing material and grate the specimen. Use that part which passes through a 0,5 mm sieve.

5.3 Determination of ash residue

Remove the backing material and cut the specimen into small pieces of approximately $5\text{ mm} \times 5\text{ mm}$.

6 Atmosphere for conditioning and testing

Condition the specimen, at a temperature of $23 \pm 2\text{ }^{\circ}\text{C}$ and a relative humidity of $50 \pm 5\%$, for a minimum of 24 h. Maintain these conditions during the test.

7 Test procedure

7.1 Identification

Saponify the specimen in excess potassium hydroxide/methanol solution without stirring. After 24 h, record whether complete disintegration of the linoleum has taken place. If disintegration has not taken place, the sample is not identified as linoleum, so do not carry out the tests described in 7.2 and 7.3.

7.2 Determination of cement content

Weigh approximately 1 g of the grated specimen, with particle size $\leq 0,5$ mm, in a tared beaker.

Add approximately 10 ml of the potassium hydroxide/methanol solution and stir for $10 \pm 0,5$ min. Ensure that the temperature does not exceed 25°C , because wood- and/or cork-flour can be affected.

Weigh the type A2 filter (if used) and record the mass to the nearest 0,01 g.

Centrifuge or vacuum filter the mixture using the type A2 filter and rinse the residue at a temperature of 40°C . Condition the dry residue in the filter or centrifuge, as described in Clause 6, for a minimum of 24 h, and record the mass (including the A2 filter, if used) to the nearest 0,01 g.

7.3 Determination of ash residue

Determine the tared mass of a porcelain crucible as follows. Prepare a crucible by heating in the furnace at 500°C for at least 3 h. Allow cooling in the desiccator for at least 1 h and weigh the crucible. Repeat the process of heating, cooling and weighing until the results of two consecutive weighings do not differ from each other by more than 0,5 mg, i.e. the mass is virtually constant.

Weigh approximately 2 g of the crumbled specimen in the tared porcelain crucible. Heat the crucible using a Bunsen burner, in a way that allows the specimen to burn in a controlled manner. Place the crucible and contents in a furnace at $500 \pm 10^{\circ}\text{C}$, for at least 3 h, to allow incineration to proceed to completion, i.e. when no carbonaceous matter remains in the crucible.

Transfer the crucible and contents to the desiccator and allow to cool for at least 1 h. Determine the mass of the crucible and residue to the nearest 0,01 g. Repeat the process of incineration, cooling and weighting until the results of two consecutive weighings do not differ from each other by more than 0,5 mg, i.e. the mass is virtually constant.

8 Calculation and expression of results

8.1 Identification

Record whether complete disintegration takes place.

8.2 Determination of cement content

Calculate the linoleum cement content, as a percentage by mass, using the following formula:

$$\frac{m_1 - m_2}{m_1} \times 100$$

where

m_1 is the initial mass of the specimen;

m_2 is the mass of the dry residue (excluding the A2 filter if used).

Express the linoleum cement content as the average of the results for the number of specimens tested, and record these to the nearest 0,5 %.

8.3 Determination of ash residue

Calculate the ash residue, as a percentage by mass, using the following formula:

$$\frac{m_3}{m_1} \times 100$$

where

m_1 is the initial mass of the specimen;

m_3 is the mass of the ash residue.

Express the inorganic filler content as the average of the results for the number of specimens tested, and record these to the nearest 0,5 %.

9 Precision statement

A round-robin test will be conducted to determine the precision of this test method.

10 Test report

The test report shall contain the following information:

- a statement that the tests were performed in accordance with this International Standard (ISO 26985:2008);
- a complete identification of the product tested, including type, source, colour, and manufacturer's reference numbers;
- previous history of the sample;
- a statement as to whether the sample has been identified as linoleum;
- the average cement content and the average ash residue, as a percentage, if relevant;
- any deviation from this International Standard which could have affected the results;
- the date of the test.