
INTERNATIONAL STANDARD



2947

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Textiles — Integrated conversion table for replacing traditional yarn numbers by rounded values in the Tex System

First edition — 1973-11-01

STANDARDSISO.COM : Click to view the full PDF of ISO 2947:1973

UDC 677.017.272.2

Ref. No. ISO 2947-1973 (E)

Descriptors : textiles, yarns, units of measurement, Tex system, linear density.

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 2947 was drawn up by Technical Committee ISO/TC 38, *Textiles*, and circulated to the Member Bodies in August 1972.

It has been approved by the Member Bodies of the following countries :

Australia	India	Spain
Austria	Ireland	Sweden
Belgium	Israel	Switzerland
Canada	Japan	Thailand
Czechoslovakia	Mexico	Turkey
Denmark	Netherlands	United Kingdom
Egypt, Arab Rep. of	New Zealand	U.S.A.
France	Portugal	U.S.S.R.
Germany	Romania	
Hungary	South Africa, Rep. of	

No Member Body expressed disapproval of the document.

Textiles — Integrated conversion table for replacing traditional yarn numbers by rounded values in the Tex System

0 INTRODUCTION

To facilitate the implementation of the Tex System the conversion table which is the subject of this International Standard has been developed with the collaboration of experts from the following international organizations :

- Association Européenne de Moulinage
- Association of European Jute Industries
- Comité International de la Rayonne et des Fibres Synthétiques (CIRFS)
- Eurocoton
- Fédération Internationale de la Filterie
- International Association of Users of Man-made Fibres (AIUFFAS)
- International Bureau for the Standardization of Man-made Fibres (BISFA)
- International Federation of Cotton and Allied Textile Industries (IFCATI)
- International Wool Textile Organization (IWTO)
- Secrétariat International des Industries de la Maille

In compiling this conversion table, the principle has been to choose rounded values in the Tex System each of which would accommodate as many yarn counts as possible from the traditional systems without encroaching on spinners' tolerances. While in many cases rounding has been determined by purely numerical considerations, account has been taken of existing international practices or agreements. For example, where specific English cotton

counts are related to metric counts, this is reflected in the rounded tex value. The rounded values included for denier numbers form a limited selection from the range of "Continental Rounded Decitex Values", which embraces the bulk of deniers produced and is already in use by the major man-made fibre producers.

To ensure a smooth transition to the Tex System it is necessary to maintain a degree of flexibility in regard to both the choice of unit and satisfying the reasonable requirements of spinners' customers. Adoption of the rounded values in the conversion table would, however, make a substantial contribution to rationalization since 466 traditional yarn counts would be replaced by 205 rounded tex values.

When the Tex System has been fully adopted, it is hoped that a range of tex values will ultimately evolve which will have more rational intervals between linear densities than those determined pragmatically and embodied in this International Standard.

1 SCOPE AND FIELD OF APPLICATION

This International Standard is intended to facilitate the changeover by industry and commerce from traditional yarn numbering systems to the Tex System (see ISO/R 1144).

It provides a range of recommended rounded linear densities in the Tex System to replace the yarn numbers in the six main traditional numbering systems referred to in section 6 and covers the great majority of yarns currently produced.

The rounded tex values for count systems not covered by section 6 (e.g. Dewsbury count) may be ascertained by applying the principle on which the conversion table is based, viz. by using the relevant conversion factor from ISO/R 1144 to give the exact Tex System equivalents and then choosing a range of rounded numbers which are, as far as possible, not more than 2 % different from the exact equivalents.

2 REFERENCE

ISO/R 1144, *Textiles — Universal system for designating linear density (Tex System)*.

3 CHOICE OF UNIT

Although the rounded Tex System values in the conversion table have been expressed in terms of the basic unit, tex, the decitex equivalents have also been included because they can be used throughout the whole count range without employing decimal fractions.

The choice of unit is entirely a matter to be determined by individual sectors (or even between spinner and customer); the decitex unit, for example, is particularly suitable for fine yarns (whether spun or filament) and the tex unit for medium and coarse yarns.

4 SYMBOLS AND ABBREVIATIONS

The count systems referred to in the headings of columns 2 to 7 of the conversion table are given in Tables 1 and 2.

5 APPLICATION OF THE INTEGRATED CONVERSION TABLE

5.1 While covering the majority of spun and filament yarn production, the rounded values in the six traditional systems are not exhaustive. Where a customer requires a yarn of a specific linear density not included in the conversion table, production of such a yarn should be arranged between spinner and customer. This is particularly relevant to yarns used for the production of sewing threads, where it is necessary to work to especially fine tolerances.

5.2 With a few exceptions, fractional traditional counts have been omitted from the conversion table; the rounded Tex System values for most fractional traditional counts can usually be obtained by taking the rounded value for a count in the table having the same digits and making the necessary adjustment of the decimal sign (this is of particular significance where yarns for the carpet and tyre industries are concerned, Ne_c 0,98 and Ne_c 1,05 being quite common).

5.3 This International Standard is not intended to apply to the product designation of sewing threads, for which special systems are recognized by producers and customers.

TABLE 1 — Indirect systems

Symbolic abbreviation	Yarn count system	Unit of length used	Unit of mass used	Unit of yarn count number
Ne_c	Cotton (English)	840 yards	1 pound	840 yd/lb
Nm	Metric	1 kilometre	1 kilogram	km/kg
Ne_w	Worsted	560 yards	1 pound	560 yd/lb
Ne_L	Linen (wet or dry spun)	300 yards	1 pound	300 yd/lb

TABLE 2 — Direct systems

Symbolic abbreviation	Yarn count (number) system	Unit of mass used	Unit of length used	Unit of yarn count number
T_j	Jute, hemp linen (dry spun)	1 pound	14 400 yards (spyndle unit)	lb/14 400 yd
T_d	Denier	1 gram	9 kilometres	g/9 000 m
T_t	Tex	1 gram	1 kilometre	g/km

6 INTEGRATED CONVERSION TABLE

Columns A and B are for information only.

1	2	3	4	5	6	7	8	A	B
Rounded value	Traditional counts or numbers						Rounded value	Exact equivalent	Deviation
	Cotton (English)	Metric	Worsted	Linen	Jute	Denier			
tex	Ne _c	Nm	Ne _w	Ne _L	Tj	Td	dtex	dtex	%
1						9	10	10,00	0,0
1,1						10	11	11,11	− 1,0
1,2						11	12	12,22	− 1,8
1,3						12	13	13,33	− 2,5
1,6						14	16	15,56	+ 2,8
1,7						15	17	16,67	+ 2,0
2						18	20	20,00	0,0
2,2						20	22	22,22	− 1,0
2,6						23	26	25,56	+ 1,7
2,8						25	28	27,78	+ 0,8
3						27	30	30,00	0,0
3,1						28	31	31,11	− 0,4
3,3						30	33	33,33	− 1,0
3,5						32	35	35,56	− 1,6
4						35	40	38,89	+ 2,9
4,4						40	44	44,44	− 1,0
4,8						43	48	47,78	+ 0,5
5	120	200				45	50	49,21	+ 1,6
	118							50,00	0,0
								50,04	− 0,1
5,1	116						51	50,91	+ 0,2
	115							51,35	− 0,7
5,2	114					47	52	51,80	+ 0,4
								52,22	− 0,4
5,3	112	190					53	52,63	+ 0,7
	110							52,72	+ 0,5
								53,68	− 1,3
5,5	108						55	54,68	+ 0,6

1	2	3	4	5	6	7	8	A	B
Rounded value	Traditional counts or numbers						Rounded value	Exact equivalent	Deviation
	Cotton (English)	Metric	Worsted	Linen	Jute	Denier			
tex	Ne _C	Nm	Ne _W	Ne _L	Tj	Td	dtex	dtex	%
5,6	106 105	180				50	56	55,56 55,71 56,24	+ 0,8 + 0,5 - 0,4
5,7	104						57	56,78	+ 0,4
5,8	102					52	58	57,78 57,89	+ 0,4 + 0,2
5,9	100	170					59	58,82 59,05	+ 0,3 - 0,1
6	98						60	60,26	- 0,4
6,2	96 95					56	62	61,51 62,16 62,22	+ 0,8 - 0,3 - 0,4
6,3	94	160					63	62,50 62,82	+ 0,8 + 0,3
6,4	92						64	64,18	- 0,3
6,6	90	150					66	65,61 66,67	+ 0,6 - 1,0
6,7	88						67	67,10	- 0,1
6,9	86	145					69	68,66 68,97	+ 0,5 0,0
7	85 84						70	69,47 70,30	+ 0,8 - 0,4
7,1	82	140					71	71,43 72,01	- 0,6 - 1,4
7,2						65	72	72,22	- 0,3
7,4	80 79	135					74	73,81 74,07	+ 0,3 - 0,1
7,5	79						75	74,75	+ 0,3
7,6	78						76	75,71	+ 0,4
7,7	77	130					77	76,69 76,92	+ 0,4 + 0,1
7,8	76					70	78	77,70 77,78	+ 0,4 + 0,3
7,9	75						79	78,73	+ 0,3
8	74	125					80	79,80 80,00	+ 0,3 0,0
8,1	73						81	80,89	+ 0,1

1	2	3	4	5	6	7	8	A	B
Rounded value	Traditional counts or numbers						Rounded value	Exact equivalent	Deviation
	Cotton (English)	Metric	Worsted	Linen	Jute	Denier			
tex	Ne _c	Nm	Ne _w	Ne _L	Tj	Td	dtex	dtex	%
8,2	72						82	82,01	0,0
8,4	71	120				75	84	83,17	+ 1,0
	70							83,33	+ 0,8
8,5	69						85	84,36	- 0,4
								85,58	- 0,7
8,7	68	115					87	86,84	+ 0,2
								86,96	0,0
8,8	67						88	88,13	- 0,1
9	66					80	90	88,89	+ 1,2
								89,47	+ 0,6
9,1	65	110					91	90,85	+ 0,2
								90,91	+ 0,1
9,2	64						92	92,27	- 0,3
9,4	63						94	93,73	+ 0,3
9,5	62	105					95	95,24	- 0,3
9,7	61						97	96,80	+ 0,2
10	60	100				90	100	98,42	+ 1,6
	59							100,0	0,0
10,2	58						102	100,1	- 0,1
								101,0	- 1,0
10,5	57	98					105	101,8	+ 0,2
								102,0	0,0
10,8	56	96					108	103,1	- 1,1
								103,6	+ 1,4
11	55	95					110	104,2	+ 0,8
								105,3	- 0,3
11,2	54	94					112	105,4	- 0,4
								106,4	- 1,3
11,5	53	93	80			100	115	107,4	+ 0,6
								107,5	+ 0,5
11,8	52	92	79				120	108,9	- 0,8
								109,4	+ 0,5
12,0	51	91	78				125	109,9	+ 0,1
								110,7	- 0,6
12,5	50	90	77				130	111,1	- 1,0
								111,4	+ 0,5
13,0	49	89					140	112,1	- 0,1
								112,4	- 0,4
14,0	48	88					150	113,6	+ 1,2
								114,9	+ 0,1
15,0	47	87					160	115,0	0,0

1	2	3	4	5	6	7	8	A	B
Rounded value	Traditional counts or numbers						Rounded value	Exact equivalent	Deviation
	Cotton (English)	Metric	Worsted	Linen	Jute	Denier			
tex	Ne _C	Nm	Ne _W	Ne _L	Tj	Td	dtex	dtex	%
11,7	51	86	76				117	115,8 116,3 116,6	+ 1,0 + 0,6 + 0,3
12	50 49	85 84 83	75 74	140			120	117,6 118,1 119,0 119,7 120,5	+ 2,0 + 1,6 + 0,8 + 0,3 - 0,4
12,2		82	73				122	121,3 122,0	+ 0,6 0,0
12,5	48 47	81 80 79	72 71 70			112	125	123,0 123,5 124,4 124,8 125,0 125,6 126,5 126,6 127,2	+ 1,6 + 1,2 + 0,5 + 0,2 0,0 - 0,5 - 1,2 - 1,3 - 1,7
13	46 45	78 77 76	69 68 67				130	128,2 128,4 129,9 130,3 131,2 131,6 132,2	+ 1,4 + 1,2 + 0,1 - 0,2 - 0,9 - 1,2 - 1,7
13,5	44 43	75 74 73	66 65				135	133,3 134,2 135,1 136,3 137,0 137,3	+ 1,3 + 0,6 - 0,1 - 1,0 - 1,5 - 1,7
14	42	72 71	64 63	120		125	140	137,8 138,4 138,9 140,6 140,8	+ 1,6 + 1,2 + 0,8 - 0,4 - 0,6
14,5	41 40	70 69 68	62 61 60				145	142,9 144,0 144,9 145,2 147,1 147,6	+ 1,5 + 0,7 + 0,1 - 0,1 - 1,4 - 1,8
15	39	67 66	59	110		135	150	149,3 150,0 150,1 150,3 151,4 151,5	+ 0,5 0,0 - 0,1 - 0,2 - 0,9 - 1,0

1	2	3	4	5	6	7	8	A	B
Rounded value	Traditional counts or numbers						Rounded value	Exact equivalent	Deviation
	Cotton (English)	Metric	Worsted	Linen	Jute	Denier		dtex	%
tex	Ne _c	Nm	Ne _w	Ne _L	Tj	Td	dtex		
15,5	38	65 64	58 57				155	152,7 153,9 155,4 156,3	+ 1,5 + 0,7 - 0,3 - 0,8
16	37	63 62	56 55			145	160	158,2 158,7 159,6 161,1 161,3	+ 1,1 + 0,8 + 0,3 - 0,7 - 0,8
16,5	36	61 60	54	100			165	163,9 164,0 165,4 166,7	+ 0,7 + 0,6 - 0,2 - 1,0
16,7			53			150	167	166,7 167,1	+ 0,2 - 0,1
17	35	59 58	52				170	168,7 169,5 170,3 172,4	+ 0,8 + 0,3 - 0,2 - 1,4
17,5	34	57	51 50				175	173,7 175,4 177,2	+ 0,7 - 0,2 - 1,3
18	33	56 55	49	90			180	178,6 178,9 180,8 181,8 183,7	+ 0,8 + 0,6 - 0,4 - 1,0 - 2,0
18,5	32	54	48				185	184,5 185,2	+ 0,3 - 0,1
19	31	53 52	47 46			170	190	188,5 188,7 188,9 190,5 192,3 192,6	+ 0,8 + 0,7 + 0,6 - 0,3 - 1,2 - 1,4
19,5		51					195	196,1	- 0,6
20	30	50	45 44			180	200	196,8 200,0 201,3	+ 1,6 0,0 - 0,6
20,5	29	49	43				205	203,6 204,1 206,0	+ 0,7 + 0,4 - 0,5
21	28	48	42	80			210	206,7 208,3 210,9	+ 1,6 + 0,8 - 0,4

1	2	3	4	5	6	7	8	A	B
Rounded value	Traditional counts or numbers						Rounded value	Exact equivalent	Deviation
	Cotton (English)	Metric	Worsted	Linen	Jute	Denier		dtex	%
tex	Ne _C	Nm	Ne _W	Ne _L	Tj	Td	dtex		
21,5		47 46	41				215	212,8 216,0 217,4	+ 1,0 - 0,5 - 1,1
22	27	45	40			200	220	218,7 221,5 222,2	+ 0,6 - 0,7 - 1,0
22,5	26	44	39				225	227,1 227,3	- 0,9 - 1,0
23,5	25	43	38			210	235	232,6 233,1 233,3 236,2	+ 1,0 + 0,8 + 0,7 - 0,5
24		42 41	37	70			240	236,3 238,1 239,4 243,9	+ 1,6 + 0,8 + 0,3 - 1,6
25	24	40	36 35			225	250	246,0 246,1 250,0 253,1	+ 1,6 + 1,6 0,0 - 1,2
26	23	39	34				260	256,4 256,7 260,5	+ 1,4 + 1,3 - 0,2
26,5		38					265	263,2	+ 0,7
27	22	37	33				270	268,4 270,3	+ 0,6 - 0,1
28	21	36 35	32 31	60		250	280	275,6 276,8 277,8 281,2 285,7	+ 1,6 + 1,2 + 0,8 - 0,4 - 2,0
29,5		34*					295	294,1	+ 0,3
30	20	34* 33	30				300	294,1 295,3 303,0	+ 2,0 + 1,6 - 1,0
31	19	32	29				310	305,4 310,8 312,5	+ 1,5 - 0,3 - 0,8
32		31	28			290	320	316,4 322,2 322,6	+ 1,1 - 0,7 - 0,8

* 34 metric = 295 decitex for worsted spun yarns
34 metric = 300 decitex for all other yarns

1	2	3	4	5	6	7	8	A	B
Rounded value	Traditional counts or numbers						Rounded value	Exact equivalent	Deviation
	Cotton (English)	Metric	Worsted	Linen	Jute	Denier			
tex	Ne _c	Nm	Ne _w	Ne _L	Tj	Td	dtex	dtex	%
33	18	30	27	50			330	328,1 330,7 333,3	+ 0,6 - 0,2 - 1,0
34			26				340	340,7	- 0,2
35	17	29	25				350	344,8 347,4 354,3	+ 1,5 + 0,7 - 1,2
36		28					360	357,1	+ 0,8
37	16	27	24				370	369,1 370,4	+ 0,2 - 0,1
38,5		26	23				385	384,6 385,1	+ 0,1 0,0
40	15	25	22			360	400	393,7 400,0 402,6	+ 1,6 0,0 - 0,6
42	14	24	21	40			420	413,4 416,7 421,8	+ 1,6 + 0,8 - 0,4
44		23	20			400	440	434,8 442,9 444,4	+ 1,2 - 0,7 - 1,0
45	13	22					450	454,2 454,5	- 0,9 - 1,0
47			19			420	470	466,2 466,7	+ 0,8 + 0,7
48		21		35			480	472,4 476,2	+ 1,6 + 0,8
50	12	20	18			450	500	492,1 500,0	+ 1,6 0,0
52			17			470	520	521,1 522,2	- 0,2 - 0,4
53	11	19					530	526,3 536,8	+ 0,7 - 1,3
56		18	16	30			560	551,2 553,6 555,6	+ 1,6 + 1,2 + 0,8
58						520	580	577,8	+ 0,4
59	10	17	15				590	588,2 590,5	+ 0,3 - 0,1

1	2	3	4	5	6	7	8	A	B
Rounded value	Traditional counts or numbers						Rounded value	Exact equivalent	Deviation
	Cotton (English)	Metric	Worsted	Linen	Jute	Denier			
tex	Ne _c	Nm	Ne _w	Ne _L	Tj	Td	dtex	dtex	%
63		16	14				630	625,0 632,7	+ 0,8 - 0,4
64						580	640	644,4	- 0,7
66	9	15		25			660	656,1 661,4 666,7	+ 0,6 - 0,2 - 1,0
68			13		2		680	681,4 689,0	- 0,2 - 1,3
71		14					710	714,3	- 0,6
72						650	720	722,2	- 0,3
74	8		12				740	738,1 738,2	+ 0,2 + 0,2
76				22			760	751,6	+ 1,1
77		13					770	769,2	+ 0,1
80			11			720	800	800,0 805,3	0,0 - 0,7
84	7	12		20			840	826,8 833,3 843,6	+ 1,6 + 0,8 - 0,4
86					2,5		860	861,2	- 0,1
89			10			800	890	885,8 888,9	+ 0,5 + 0,1
91		11					910	909,1	+ 0,1
92				18			920	918,6	+ 0,2
94						840	940	933,3	+ 0,7
100	6	10	9				1 000	984,2 1 000	+ 1,6 0,0
105				16	3		1 050	1 033	+ 1,6
110		9	8			1 000	1 100	1 107 1 111	- 0,6 - 1,0
120	5			14	3,5	1 080	1 200	1 181 1 200 1 206	+ 1,6 0,0 - 0,5
125		8	7				1 250	1 250 1 265	0,0 - 1,2
140				12	4	1 260	1 400	1 378 1 400	+ 1,6 0,0