
**Textiles — Professional care,
drycleaning and wetcleaning of fabrics
and garments —**

**Part 2:
Procedure for testing performance
when cleaning and finishing using
tetrachloroethene**

Textiles — Entretien professionnel, nettoyage à sec et nettoyage à l'eau des étoffes et des vêtements —

Partie 2: Mode opératoire pour évaluer la résistance au nettoyage et à la finition lors du traitement au tétrachloroéthylène



STANDARDSISO.COM : Click to view the full PDF of ISO 3175-2:2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Reagents.....	2
6 Apparatus.....	2
7 Conditioning.....	3
8 Test specimens.....	4
9 Procedure.....	4
9.1 General.....	4
9.2 Procedure for normal materials.....	4
9.3 Procedures for sensitive materials.....	5
10 Test report.....	5
Bibliography.....	7

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 2, *Cleansing, finishing and water resistance tests*.

This third edition cancels and replaces the second edition (ISO 3175-2:2010), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the consistency in the structure of ISO 3175-2 and ISO 3175-3 has been improved;
- in [Clause 3](#), the term “very sensitive material” (3.5) has been withdrawn;
- in [6.1.4](#), an automatic solvent dryness control of the drycleaning machine has been added;
- in [6.3](#), technical specifications for ballasts (mass per unit area) have been added;
- in [Clause 7](#), clarification about the test specimen conditioning and the standard atmosphere has been made;
- in [Clause 8](#), clarification about the test specimen preparation has been made;
- in [Table 1](#), “5 min minimum until the temperature is lower than 45 °C” has been added for deodorization time.

A list of all parts in the ISO 3175 series can be found on the ISO website.

This corrected version of ISO 3175-2:2017 incorporates the following corrections:

- in [8.2](#), the test specimen dimensions have been corrected.

Introduction

Drycleaning is a process for cleaning textiles in an organic solvent that dissolves oils and fats and disperses particulate dirt substantially without the swelling and creasing associated with washing or wet cleaning. Small quantities of water may be incorporated in the solvent with the aid of a surfactant for the purpose of obtaining better soil and stain removal. Some moisture-sensitive articles are preferably drycleaned without the addition of water to the solvent. A surfactant is often used to assist with soil removal and reduce the risk of greying, but it should be borne in mind that surfactants contain varying amounts of water in their formulations.

Drycleaning is normally followed by an appropriate restorative finishing procedure. In most cases, this comprises some form of steam treatment and/or hot pressing.

Properties of the textile or garment may change progressively on drycleaning and steaming and/or pressing and in some cases, a single treatment can give little indication of the extent of dimensional and other changes that can arise after repeated treatments and which can affect the useful life of the article. Generally, most of the potential changes become apparent after three to five of the drycleaning and finishing treatments specified in this document. These progressive changes should be borne in mind when the interested parties determine the number of repeat cycles which is given.

The properties which should be considered in an assessment for drycleanability together with the methods for their assessment are given in ISO 3175-1.

STANDARDSISO.COM : Click to view the full PDF of ISO 3175-2:2017

Textiles — Professional care, drycleaning and wetcleaning of fabrics and garments —

Part 2:

Procedure for testing performance when cleaning and finishing using tetrachloroethene

SAFETY PRECAUTIONS — When using drycleaning equipment, official regulations and normal safety precautions should be observed.

1 Scope

This document specifies drycleaning procedures for tetrachloroethene (perchloroethylene), using commercial drycleaning machines, for fabrics and garments. It comprises procedures for normal and sensitive materials.

Localized staining and stain removal fall outside the scope of this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 139, *Textiles — Standard atmospheres for conditioning and testing*

ISO 3175-1, *Textiles — Professional care, drycleaning and wetcleaning of fabrics and garments — Part 1: Assessment of performance after cleaning and finishing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

material

garment, *composite test specimen* (3.2) or fabric

3.2

composite test specimen

test specimen consisting of all component parts used in the finished item, and combined in a representative assembly

[SOURCE: ISO 3175-1:2017, 3.1]

3.3

normal material

material (3.1) consisting of all component parts which is able to withstand the normal drycleaning process as specified in this document without modification

Note 1 to entry: Giving careful consideration to the comments on progressive change described in the Introduction, textile items tested in the procedures intended for normal materials in Table 1, and which perform satisfactorily in the assessments described in ISO 3175-1, may be labelled with the $\textcircled{\text{P}}$ symbol, as described in ISO 3758.

3.4

sensitive material

material (3.1) consisting of all component parts which may require restrictions as to mechanical action and/or drying temperatures and/or water additions

EXAMPLES Fibre type: acrylic, modacrylic, silk, angora. Fabric type: crepe.

Note 1 to entry: Giving careful consideration to the comments on progressive change described in the Introduction, textile items tested in the procedures intended for sensitive materials in Table 1, and which perform satisfactorily in the assessments described in ISO 3175-1, may be labelled with the $\textcircled{\text{P}}$ symbol, as described in ISO 3758.

4 Principle

The specimen is drycleaned in a commercial machine and finished according to one of the specified procedures. This process is a precursor to the assessment of the cleaned specimen in accordance with ISO 3175-1.

5 Reagents

5.1 Tetrachloroethene, $\text{CCl}_2 = \text{CCl}_2$ distilled, sold for the purpose of drycleaning.

5.2 Sorbitan mono-oleate.

In order to prevent foaming, it is important to use redistilled, clean solvent solution and not overfill the still.

NOTE Sorbitan mono-oleate is used as a model for a standard drycleaning detergent. Sorbitan mono-oleate is used as an emulsifier for water in the drycleaning solvent.

6 Apparatus

6.1 Drycleaning machine, consisting of a reversible rotating cage type, totally enclosed machine, intended for use with tetrachloroethene.

The diameter of the rotating cage shall be 600 mm minimum and 1 080 mm maximum. Its depth shall be 300 mm minimum. It shall be fitted with three or four lifters. The speed shall be such as to give a *g*-factor of between 0,5 and 0,8 for cleaning and between 60 and 120 for extraction.

The g -factor is calculated according to [Formula \(1\)](#):

$$g = 5,6 n^2 d \times 10^{-7} \quad (1)$$

where

n is the rotational frequency, in rotations per minute;

d is the rotating cage diameter, in millimetres.

6.1.1 The machine shall be fitted with the means to control solvent and air temperature as required (see [Table 1](#)).

6.1.2 The machine shall have suitable facilities to allow the emulsion (see [9.2.3](#)) to be introduced gradually into the solvent between the cage and drum below the level of the solvent.

6.1.3 The machine shall be equipped with a means of measuring the temperature of the solvent during washing and either the incoming or the outgoing air during drying to within ± 2 °C.

6.1.4 The machine shall be equipped with an automatic solvent dryness control.

6.2 Apparatus for applying the appropriate finishing treatment to the test pieces, consisting of the following.

6.2.1 Iron, with an approximate mass of 1,5 kg and a sole surface area of 150 cm² to 200 cm².

6.2.2 Steam press, consisting of two bucks, one fixed and the other movable, each buck having a surface area of approximately 0,35 m². Steam being conducted to the bucks shall be released under a pressure of approximately 500 kPa. The pressure exerted by the bucks shall be approximately 350 kPa.

6.2.3 Steam table, having a shape and dimensions suitable to the dimensions of the specimens. The steam shall be released at a pressure of approximately 500 kPa.

6.2.4 Steam former (mannequin), which may or may not be specific in shape for garments. The steam shall be released at a pressure of approximately 500 kPa.

6.2.5 Steam cabinet, which needs to be specific in shape for garments. The steam shall be released at a pressure of approximately 500 kPa.

6.3 Ballast, consisting of clean textile pieces which shall be either white or of a light colour and which shall consist of approximately 80 % wool pieces (230 $\pm$ 10) g/m² and 20 % cotton pieces (180 $\pm$ 10) g/m² by mass. Each piece shall comprise two layers of fabric sewn together at the edges and shall be (300 $\pm$ 30) mm $\times$ (300 $\pm$ 30) mm.

7 Conditioning

Condition all specimens, except the first, for at least 16 h in the standard atmosphere (20 °C, 65 % RH) for conditioning and testing textiles specified in ISO 139. Specimens shall be tested immediately after removal from the conditioning atmosphere; otherwise, they shall be placed in sealed plastic bags and tested within 30 min.

8 Test specimens

8.1 Garments shall be tested in the as-received condition.

8.2 Fabrics shall be cut into test pieces, preferably not smaller than 500 mm × 500 mm and stitched on all sides with polyester thread to prevent unravelling.

8.3 Composite test specimens (see 3.2) are prepared as for fabrics (8.2) or are tested in the as-received condition.

8.4 If assessments/comparisons are required according to ISO 3175-1, at least two identical test specimens shall be required (one for comparison, one for testing).

Testing may be an iterative procedure since alternative processes of varying severity may be used, and it is advisable to obtain sufficient specimens for all the testing which may be required.

9 Procedure

9.1 General

Apply appropriate parameters as given in Table 1 to normal materials (see 9.2) or sensitive materials (see 9.3).

If parties have not agreed on the number of test cycles, there shall be a minimum of three.

Selection of the procedure to be used (normal, sensitive) depends on the textile item. It also should take into consideration the end use of the item since this has a bearing on the likely type and degree of soiling.

NOTE Generally, the less severe the process is, the less effective the cleaning is.

9.2 Procedure for normal materials.

9.2.1 The mass of the complete load, measured to $\pm 0,1$ %, shall be calculated from the cage volume. Unless the mass of a single specimen (fabric, composite or garment) exceeds 50 % of the mass of the load, the mass of the test specimen(s) shall not exceed 10 % of the mass of the load. The remainder of the load shall consist of ballast.

9.2.2 Place the conditioned load in the machine and load the machine with distilled tetrachloroethene solvent (charged with 1 g/l detergent as shown in Table 1), so that the liquor ratio, calculated from the volume of solvent in the drum, is $(5,0 \pm 0,5)$ l/kg of the load. Maintain the solvent at (30 ± 3) °C throughout the cleaning operation.

9.2.3 Prepare a fresh emulsion by mixing, per kilogram of load, 10 ml sorbitan mono-oleate (to bring the detergent concentration to 3 g/l as shown in Table 1) with 30 ml of tetrachloroethene solvent and then, while stirring, adding 20 ml of water. This corresponds to 2 % of water calculated on the mass of the load.

If the mixing of the detergent with tetrachloroethene outside the machine is not permitted, a mixture of the detergent and water may be added directly into the machine. Precautions shall be taken to avoid uneven distribution of the individual components in the load. Any deviation from the procedure shall be noted in the test report.

Start the machine with the filter circuit shut off, and 2 min after the cage inlet has closed, add the emulsion slowly over a period of (30 ± 5) s to the machine between the cage and the drum below the level of the solvent.

9.2.4 Switch the machine on and allow it to run for cleaning cycle time (wash). Do not use the filter circuit for the duration of the test.

9.2.5 Drain the solvent and centrifugally extract the solvent from the load for cleaning cycle time (inter extract) including at least 1 min at full extraction speed.

9.2.6 Introduce pure dry solvent at the same liquor ratio as that given in 9.2.2 and rinse for cleaning cycle time (rinse). Drain and extract again for appropriate time (including at least 2 min at full extraction speed).

9.2.7 Dry the load in the machine air for an appropriate time depending on technology used for equipment 6.1 and 6.1.4 load type.

After drying, blow air, at ambient temperature, through the rotating load for deodorization time.

9.2.8 Immediately remove the test piece from the machine. Place garments individually on hangers and place fabric specimens on a flat surface, for at least 30 min before finishing.

9.2.9 Carry out finishing treatments appropriate to the test specimen from the following methods and record the processing conditions used:

- method A: no finishing required;
- method B: finishing with an iron;
- method C: finishing with a steam press;
- method D: steaming on a press or table;
- method E: steaming on a mannequin or in a cabinet;
- method F: no suitable finishing method could be found. Report methods and conditions attempted and reasons for unsuitability.

Record actual steaming times to allow for the reaction times of steam pedal switches and timer mechanisms.

The purpose of finishing after drycleaning is to restore an article to its original condition before use. The amount and type of finishing should be consistent with the fabric/garment properties and the restorative requirements.

Steaming in method C shall be top steam, only to equate to good pressing practice.

NOTE Steaming/vacuuming times for methods C and D vary, e.g. from (2 ± 1) s actual steam/ (5 ± 1) s vacuum for a light weight garment to (4 ± 1) s/ (8 ± 1) s for heavy garments.

9.3 Procedures for sensitive materials

Proceed as in 9.2 except 9.2.3, but with the appropriate parameters at the reduced levels given in Table 1.

10 Test report

The test report shall include the following information:

- a) a reference to this document, i.e. ISO 3175-2:2017;
- b) the name of testing authority and report identification;
- c) the date of testing;