
INTERNATIONAL STANDARD



3346

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Wood — Determination of ultimate tensile stress perpendicular to grain

Bois — Détermination de la contrainte de rupture en traction perpendiculaire aux fibres

First edition — 1975-12-01

STANDARDSISO.COM : Click to view the full PDF of ISO 3346:1975

UDC 674.03 : 539.42

Ref. No. ISO 3346-1975 (E)

Descriptors : wood, tests, tension tests, measurement, rupture stress.

Price based on 2 pages

FOREWORD

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO Member Bodies). The work of developing International Standards is carried out through ISO Technical Committees. Every Member Body interested in a subject for which a Technical Committee has been set up has the right to be represented on that Committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the Technical Committees are circulated to the Member Bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 3346 was drawn up by Technical Committee ISO/TC 55, *Sawn timber and sawlogs*, and circulated to the Member Bodies in February 1974.

It has been approved by the Member Bodies of the following countries :

Belgium	India	Spain
Bulgaria	Ireland	Sweden
Canada	Netherlands	Thailand
Czechoslovakia	New Zealand	Turkey
Egypt, Arab Rep. of	Norway	United Kingdom
Finland	Poland	U.S.S.R.
France	Romania	Yugoslavia
Hungary	South Africa, Rep. of	

The Member Body of the following country expressed disapproval of the document on technical grounds :

Germany

Wood — Determination of ultimate tensile stress perpendicular to grain

1 SCOPE AND FIELD OF APPLICATION

This International Standard specifies a method for determining the ultimate tensile stress of wood perpendicular to grain in the radial and tangential directions.

2 REFERENCES

ISO 3129, *Wood — Sampling methods and general requirements for physical and mechanical tests.*¹⁾

ISO 3130, *Wood — Determination of moisture content in physical and mechanical tests.*¹⁾

3 PRINCIPLE

Determination of the ultimate tensile stress perpendicular to grain by the application of a gradually increasing load to a test piece.

4 APPARATUS

4.1 Tensile machine ensuring the rate of loading of the test piece or of movement of the loading head according to 6.2 and allowing measurement of the load to 1 %.

The grips of the machine shall ensure that the load is applied along the longitudinal axis of the test piece and shall prevent longitudinal twisting of the test piece.

4.2 Measuring instrument for determining the cross-sectional dimensions of the gauge portion of test pieces to an accuracy of 0,1 mm.

4.3 Equipment for the determination of moisture content in accordance with ISO 3130.

5 PREPARATION OF TEST PIECES

5.1 The gauge portion of the test piece shall have a rectangular or square cross-section with one dimension

from 10 to 25 mm, and the other from 20 to 50 mm. If the gauge portion is in the form of a right prism, its length shall be not less than 5 mm. If not, the radius of curvature between the ends shall be not less than 12 mm. The ends shall be shaped to ensure the failure of the test piece within the gauge portion.

It is permitted to use test pieces with laminated ends.

5.2 The preparation, moisture content and number of test pieces shall be in accordance with ISO 3129.

6 PROCEDURE

6.1 Measure the cross-sectional dimensions of the gauge portion of the test piece to an accuracy of 0,1 mm.

6.2 Clamp the ends of the test piece at a distance of 10 to 15 mm from the gauge portion.

Load the test piece at a constant rate. The rate of testing (with a constant rate of loading or a constant rate of movement of the loading head of the machine) shall be such that the test piece is broken in 1,5 to 2 min from the moment of loading. Read the maximum load to the accuracy specified in 4.1.

Discard results obtained on test pieces which fail outside the gauge portion.

6.3 After the test has been completed, determine the moisture content of the test pieces according to ISO 3130.

Take the gauge portion of the test piece as the sample for determination of moisture content. To determine the mean moisture content, it is permissible to use only some of the test pieces. The minimum number of test pieces for moisture content determination shall be in accordance with ISO 3129.

1) At present at the stage of draft.