
**Rubber, vulcanized or
thermoplastic — Determination of
stress relaxation in compression —**

**Part 2:
Testing with temperature cycling**

*Caoutchouc vulcanisé ou thermoplastique — Détermination de la
relaxation de contrainte en compression —*

Partie 2: Essais avec cycles de température

STANDARDSISO.COM : Click to view the full PDF of ISO 3384-2:2019



STANDARDSISO.COM : Click to view the full PDF of ISO 3384-2:2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
6 Calibration	3
7 Test piece	3
7.1 Type and preparation of test pieces	3
7.1.1 General	3
7.1.2 Cylindrical test pieces	3
7.1.3 Ring test pieces	4
7.2 Measurement of dimensions of test pieces	4
7.3 Number of test pieces	4
7.4 Time interval between forming and testing	4
7.5 Conditioning of test pieces	4
8 Duration, temperature and test liquid	5
8.1 Duration of test	5
8.2 Temperature of exposure	5
8.3 Immersion liquids	5
9 Procedure	5
9.1 Preparation	5
9.2 Thickness measurement	5
9.2.1 Cylindrical test pieces	5
9.2.2 Ring test pieces	5
9.3 Method A	6
9.4 Method B	7
10 Expression of results	8
11 Precision	9
12 Test report	9
Annex A (normative) Calibration schedule	11
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analysis*.

This second edition cancels and replaces the first edition (ISO 3384-2:2012), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the requirement for compression device (5.1) has been harmonized with other International Standards;
- other changes have been made to keep the consistency with ISO 3384-1 throughout the document.

A list of all parts in the ISO 3384 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

When a constant strain is applied to rubber, the force necessary to maintain that strain is not constant but decreases with time; this behaviour is called “stress relaxation”. Conversely, when rubber is subjected to a constant stress, an increase in the deformation takes place with time; this behaviour is called “creep”.

Tests in compression are normally made under continuous stress conditions (i.e. the test piece remains strained throughout the test), and are hence a measure of sealing force. Note that the terms continuous and discontinuous used in this standard refer to whether the measure of force is made continuously or at intervals.

Tests to use stress relaxation in tension as a measure of ageing are given in ISO 6914.

The processes responsible for stress relaxation can be physical or chemical in nature, and under all normal conditions both types of process will occur simultaneously. However, at normal or low temperatures and/or short times, stress relaxation is dominated by physical processes, while at high temperatures and/or long times chemical processes are dominant.

If the life-time of a material is to be investigated, it can be determined using the method described in ISO 11346.

In addition to the need to specify the temperatures and time intervals in a stress relaxation test, it is necessary to specify the initial stress and the previous mechanical history of the test piece since these can also influence the measured stress relaxation, particularly in rubbers containing fillers.

The most important factor in achieving good repeatability and reproducibility when making stress relaxation tests is to keep the compression constant during all measurements.

The two cycling test methods specified are designed to carry out the following:

- age the test piece by stress relaxation and determine the sealing force at low temperatures (method A);
- introduce thermal stress by stress relaxation and determine the sealing force at low temperatures (method B).

For products used in outdoor applications where the temperature can cycle between a low temperature (e.g. $-40\text{ }^{\circ}\text{C}$) and a high temperature (e.g. $150\text{ }^{\circ}\text{C}$), it is important to also consider the shrinking of the rubber at low temperatures when assessing performance in the anticipated application and life-time.

For polymers that crystallize at low temperature, the crystallization will add to the shrinking of the rubber. For example, for hoses and seals in automotive applications, the product might work satisfactorily at the normal working temperature, but might leak at a low temperature.

STANDARDSISO.COM : Click to view the full PDF of ISO 3384-2:2019

Rubber, vulcanized or thermoplastic — Determination of stress relaxation in compression —

Part 2: Testing with temperature cycling

WARNING 1 — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to determine the applicability of any other restrictions.

WARNING 2 — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

1 Scope

This document specifies two methods for determining the decrease in counterforce exerted by a test piece of vulcanized or thermoplastic rubber which has been compressed to a constant deformation and then undergoes temperature cycling.

Method A: The temperature is cycled at intervals between a high temperature for ageing and a low temperature for checking the sealing force at this low temperature.

Method B: The temperature is cycled continuously between a high temperature and a low temperature to introduce thermal stress in the test piece.

The counterforce is determined by means of a continuous-measurement system.

Two forms of test pieces are specified in this document: cylindrical test pieces and rings. Comparison of results is valid only when made on test pieces of similar size and shape.

The use of ring test pieces is particularly suitable for the determination of stress relaxation in liquid environments.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37:2017, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*

ISO 188:2011, *Rubber, vulcanized or thermoplastic — Accelerated ageing and heat resistance tests*

ISO 18899:2013, *Rubber — Guide to the calibration of test equipment*

ISO 23529:2016, *Rubber — General procedures for preparing and conditioning test pieces for physical test methods*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

compression stress relaxation

reduction in compressive force, expressed as a percentage of the initial force, which occurs with time after the application of a constant compressive strain

3.2

thermal stress

mechanical stress induced in a body when some or all of its parts are not free to expand or contract in response to changes in temperature

4 Principle

A test piece of vulcanized or thermoplastic rubber is compressed to a constant deformation at which it is maintained. The decrease in counterforce is then measured.

The temperature is cycled between a high temperature and a low temperature to check the sealing force at this low temperature. The shrinkage of the rubber in going from the high to the low temperature decreases the counterforce.

5 Apparatus

5.1 Compression device, consisting of two parallel, flat, highly polished plates made of chromium-plated steel or stainless-steel or any corrosion-resistant material, between the faces of which the test piece is compressed.

The plates shall be:

- sufficiently rigid to ensure that, with a test piece under load, no compression plate bends by more than 0,01 mm;
- of sufficient size to ensure that the whole of the test piece, when compressed between the plates, remains within the area of the plates and can expand freely laterally.

NOTE A surface finish not worse than $Ra\ 0,4\ \mu\text{m}$ (see ISO 4287) has been found to be suitable. Such an Ra can be obtained by a grinding or polishing operation.

When the apparatus is assembled without a test piece, the gap between the plates shall not vary by more than $\pm 0,1\ \text{mm}$.

For ring test pieces, the plates shall have holes of at least 2 mm diameter drilled through their centre portions to allow equalization of pressure and circulation of fluid inside the ring-shaped test piece.

It shall be possible to connect the compression device to suitable equipment for compressing the test piece to the specified compression at the specified speed and for measuring the counterforce exerted by the compressed test piece with an accuracy of 1 % of the measured value.

The device shall be capable of setting the compression and maintaining it during the whole duration of the test, and it shall be possible to keep the device in an oven at the specified test temperatures. Care shall be taken to ensure that there is no loss of heat from the test piece, for example by conduction through metal parts which are connected with the outside of the oven.

5.2 Counterforce-measuring device, capable of measuring compression forces in the desired range with an accuracy of 1 % of the measured value.

The continuous-measurement system monitors the test piece during the whole duration of the test, thus making continuous measurement of the change in counterforce with time possible. The deformation of the test piece shall be kept within $\pm 0,01$ mm for the duration of the test. If it is not possible to keep the deformation constant within this tolerance due to the spring effect in load cells, a correction may be done mechanically or mathematically.

5.3 Test environment

5.3.1 For tests in gaseous media, an air oven in accordance with the requirements of ISO 188 shall be used. An oven meeting the requirements specified for one of the ovens used in ISO 188:2011, method A, is recommended.

For cycling the temperature, the oven shall have a cooling and heating capability and be able to change the temperature at a rate of $1,0\text{ °C/min} \pm 0,5\text{ °C/min}$.

If the testing is done in nitrogen, oxidative ageing will be eliminated and the result will be due to thermal ageing only. This can be used to simulate conditions where the product is not exposed to air, such as seals used in oil or steam.

5.3.2 For tests in liquids, the compression device shall be totally immersed in a liquid in a bath, or a closed vessel for volatile or toxic fluids, such that free circulation of the liquid can take place through the holes in the compression plates. The liquid shall be maintained at the specified temperature by proper control of a heater and circulation of the liquid in the bath or, alternatively, by placing the liquid bath and compression device within an air oven as specified above.

5.3.3 It is recommended that the air used for air exchange be passed through an air dryer to give it a dew point not higher than -40 °C in order to avoid ice formation which can introduce friction in the measuring system.

5.4 Temperature-measuring equipment, with a sensing element of appropriate precision. The temperature-sensing element shall be installed in such a way that it accurately measures the temperature of the test piece.

NOTE A Pt100 sensor has been found to be suitable for temperature measurement.

6 Calibration

The requirements for calibration of the test apparatus are given in [Annex A](#).

7 Test piece

7.1 Type and preparation of test pieces

7.1.1 General

Test pieces shall be prepared either by moulding or by cutting from moulded sheets or products, in accordance with ISO 23529.

NOTE The results obtained from test pieces of different sizes are not comparable.

7.1.2 Cylindrical test pieces

The test piece shall be a cylindrical disc of diameter $13,0\text{ mm} \pm 0,5\text{ mm}$ and thickness $6,3\text{ mm} \pm 0,3\text{ mm}$.

7.1.3 Ring test pieces

The preferred ring test piece is a ring of square cross-section cut from a flat sheet of the test material by means of rotary cutters. For a suitable machine for the preparation of small ring test pieces, see Annex A of ISO 37:2017.

The dimensions of test pieces shall be:

- thickness: 2,0 mm $\pm$ 0,2 mm;
- inner diameter: 15,0 mm $\pm$ 0,2 mm;
- radial width: 2,0 mm $\pm$ 0,2 mm.

The sheets may be prepared by moulding or from finished articles by cutting and buffing.

Alternatively, an O-ring, size code ISO 3601-1-14 $\times$ 2,65-G-N, as specified in ISO 3601-1:2012 (internal diameter 14 mm and diameter of the cross-section 2,65 mm), may be used as the standard test piece.

O-rings of other dimensions, together with seals or gaskets of other configurations, may be used as non-standard test pieces, where appropriate.

7.2 Measurement of dimensions of test pieces

The dimensions of test pieces shall be measured as specified in ISO 23529.

7.3 Number of test pieces

The preferred number of test pieces is three, but for routine and screening tests two test pieces are acceptable.

7.4 Time interval between forming and testing

The interval between forming and testing shall be in accordance with ISO 23529.

7.5 Conditioning of test pieces

7.5.1 Prior to testing, the test pieces shall undergo first thermal and then mechanical conditioning as detailed in 7.5.2 and 7.5.3. When using method A at elevated temperature, the thermal conditioning might not be required, as the preheating of the test piece before compression acts as thermal conditioning.

7.5.2 Thermal conditioning shall be carried out by heating the test pieces at 70 °C for 3 h. Following thermal conditioning, the test pieces shall be allowed to stand for a period of not less than 16 h and not more than 48 h at standard laboratory temperature prior to mechanical conditioning or testing.

NOTE Some test samples, especially of thermoplastic elastomers, might contain moulding stresses, and thermal conditioning to relieve these stresses might improve the reproducibility of the results.

7.5.3 Mechanical conditioning shall be carried out at one of the standard laboratory temperatures specified in ISO 23529, as follows.

Compress the test pieces to the same compression that will be used during the rest of the test and then immediately return them to zero stress; repeat this procedure to give a total of five cycles of deformation and immediate return.

Following mechanical conditioning, the test pieces shall be allowed to stand for a period of not less than 16 h and not more than 48 h at standard laboratory temperature prior to testing.

Mechanical conditioning has been found to improve test reproducibility, particularly for compounds containing substantial proportions of filler, but is not always appropriate for finished products and can, therefore, lead to results that are not typical of service. Such conditioning may be omitted provided thermal conditioning is still undertaken. This omission shall be mentioned in the test report.

8 Duration, temperature and test liquid

8.1 Duration of test

Unless otherwise specified, the duration of test shall be at least one week ($168 \text{ h} \pm 2 \text{ h}$).

The test period begins after the initial compression.

8.2 Temperature of exposure

The temperature of exposure shall be chosen from the list of test temperatures in ISO 23529. Temperatures of exposure which cause rapid degradation or evaporation of the test liquid shall be avoided. The temperature shall be kept as constant as possible during the test in accordance with ISO 23529.

For the cyclic tests specified in this document, one high temperature and one low temperature shall be chosen.

8.3 Immersion liquids

The test liquid shall be chosen according to the particular application, but should preferably be one of those listed in ISO 1817.

Some liquids which are ageing faster than the rubber might need to be replaced during testing. The time for changing the liquid should not be included in the test time and the change should be mentioned in the test report.

9 Procedure

9.1 Preparation

Carefully clean the operating surfaces of the compression device. When testing in a gaseous medium, apply a thin coating of a lubricant having substantially no action on the rubber.

NOTE A silicone or fluorosilicone fluid (having a kinematic viscosity of about $0,01 \text{ m}^2/\text{s}$) and molybdenum disulfide have been found to be suitable lubricants.

9.2 Thickness measurement

9.2.1 Cylindrical test pieces

Measure the thickness of each test piece at the central portion with an accuracy of $0,01 \text{ mm}$, after thermal conditioning and before mechanical conditioning, at the chosen standard laboratory temperature, as specified in ISO 23529:2016, method A.

Use this measurement to calculate the necessary compression.

9.2.2 Ring test pieces

Measure the axial thickness of each test piece with an accuracy of $0,01 \text{ mm}$ at four points approximately 90° apart around the ring after thermal conditioning and before mechanical conditioning, at the chosen standard laboratory temperature, as specified in ISO 23529. Use the average of the measurements to

calculate the necessary compression. Individual measurements, on a single test piece, shall not differ by more than 0,05 mm. If they do, discard the test piece.

9.3 Method A

9.3.1 In this method, the test piece is aged at a high temperature, and the temperature is lowered once a week to a low temperature, at which the remaining counterforce is measured. A material or product specification can specify the temperatures and the minimum remaining counterforce (or the minimum value of F_{tx}/F_0) (see [Clause 10](#)) required at each temperature.

An example of a temperature cycle is shown in [Figure 1](#).

9.3.2 Bring the compression device and the oven to the high test temperature.

9.3.3 When testing in a liquid, the test piece and the operating surfaces of the compression device shall be gently lubricated with the test liquid. When testing in a gaseous medium, a thin coating of a lubricant having substantially no action on the rubber shall be applied (see [9.1](#)).


9.3.4 Place the test piece in the preheated compression device ([5.1](#)) and wait until the test temperature is reached.

9.3.5 Compress the test piece by (25 ± 2) % in the compression device at the test temperature or, if a compression of 25 % cannot be obtained, use a compression of (15 ± 2) % or lower, in steps of 5 %. Compress the test piece in a time between 30 s and 120 s. When reached, the final compression shall be fixed and maintained during the entire test period.

9.3.6 Measure the initial counterforce F_0 with an accuracy of 1 % of the measured value, at the test temperature, 30 min $\pm$ 1 min after completing the compression.

9.3.7 After 168 h, lower the temperature at a rate of 1 °C/min $\pm$ 0,5 °C/min to the low temperature. Keep the low temperature steady for 1 h. Then increase the temperature at a rate of 1 °C/min $\pm$ 0,5 °C/min to the high temperature again. Repeat this cycle weekly. The time for cooling down and the time at the low temperature are not included in the ageing time, but the time to increase the temperature is included.

9.3.8 Measure the counterforce F_{tx} continuously, starting with a measurement interval of e.g. 1 min on the first day and continuing with an interval of e.g. 10 min.



Key

X time, h

Y temperature, °C

Figure 1 — Example of a temperature cycle used in method A

9.4 Method B

9.4.1 In this method, temperature cycling is used to introduce thermal stress, starting at standard laboratory temperature and cycling between a high and a low temperature. A material or product specification can specify the number of cycles, the temperatures and the minimum remaining counterforce (or the minimum value of F_{tx}/F_0) required at each temperature.

An example of a temperature cycle is shown in [Figure 2](#).

9.4.2 Bring the compression device and the oven to standard laboratory temperature.

9.4.3 When testing in a liquid, the test piece and the operating surfaces of the compression device shall be gently lubricated with the test liquid. When testing in a gaseous medium, a thin coating of a lubricant having substantially no action on the rubber shall be applied (see [9.1](#)).


9.4.4 Compress the test piece by $(25 \pm 2) \%$ in the compression device at a standard laboratory temperature or; if a compression of 25 % cannot be obtained, use a compression of $(15 \pm 2) \%$ or lower, in steps of 5 %. Compress the test piece in a time between 30 s and 120 s. When reached, the final compression shall be fixed and maintained during the entire test period.

9.4.5 Measure the initial counterforce F_0 with an accuracy of 1 % of the measured value, at standard laboratory temperature, 30 min $\pm$ 1 min after completing the compression.

9.4.6 Increase the temperature at a rate of $1,0 \text{ °C/min} \pm 0,5 \text{ °C/min}$ to the high temperature. Keep the test piece at this temperature for 1 h. Then decrease the temperature at a rate of $1,0 \text{ °C/min} \pm 0,5 \text{ °C/min}$

to the sub-zero temperature and keep the test piece at this temperature for 1 h. Repeat this cycle 2 to 4 times daily, giving a total of 3 to 5 cycles. The precise number of cycles carried out per day will depend on the high and the low temperature used, and of the rate of increase and decrease of the temperature.

9.4.7 Measure the counterforce F_{tx} continuously, with a measurement interval of 5 min maximum.



Key

X time, h

Y temperature, °C

Figure 2 — Example of a temperature cycle used in method B

10 Expression of results

NOTE The rubber industry uses the term equation for the relationships herein termed formula. The term formula is used to describe the table of ingredients in a rubber compound.

The compression stress relaxation $R(tx)$ after a specified duration of test t , expressed as a percentage of the initial counterforce, is given by [Formula \(1\)](#):

$$R(tx) = \frac{F_0 - F_{tx}}{F_0} \times 100 \quad (1)$$

where

F_0 is the initial counterforce, measured after 30 min;

F_{tx} is the counterforce measured after the specified duration of test t ;

x is replaced by h for the high temperature and by l for the low temperature.

The median value of the results for the test pieces shall be taken. The individual values for the test pieces shall agree to within 10 % of the median value. If they do not, the test shall be repeated.

The counterforce at the high temperature, F_{th} , is determined after the specified time, e.g. 168 h, and the counterforce at the low temperature is determined, during the following low-temperature part of the cycle, after 1 h at the low temperature.

Stress relaxation values measured after different times of exposure can be plotted as a function of time on a logarithmic or linear scale to facilitate the interpretation of test data. For some applications, it is more useful to calculate compression stress ratio values, i.e. F_{tx}/F_0 , after different times of exposure, rather than stress relaxation values. In this case, compression stress ratio values shall be presented graphically as a function of logarithmic or linear time. See [Figure 3](#).



Key

X time, h
Y F_{tx}/F_0

Figure 3 — Force curve shown as F_{tx}/F_0 recorded during a method A test

11 Precision

An interlaboratory test programme has not yet been conducted.

12 Test report

The test report shall include the following information:

a) sample details:

- 1) a full description of the sample and its origin;
- 2) the method of preparation of the test pieces from the sample, e.g. whether moulded or cut;
- 3) the compound details and cure conditions, where appropriate;

b) test method:

- 1) a full reference to the test method used, i.e. the number of this document and the method utilized;
- 2) the test procedure used;

- 3) the type of test piece used;
- c) test details:
 - 1) the number of test pieces tested;
 - 2) any special information concerning the apparatus, e.g. the method used for measuring the counterforce;
 - 3) the standard laboratory temperature used;
 - 4) the duration and temperature of conditioning of the test pieces prior to testing;
 - 5) the test duration and the high and low temperatures used;
 - 6) the number of cycles used;
 - 7) the compression used: 25 % or other (give details);
 - 8) the type of oven used;
 - 9) the lubricant used;
 - 10) any deviation, by agreement or otherwise, from the specified test procedure;
- d) the individual test results and the median value for both the high temperature, i.e. for $R(th)$, and for the low temperature, i.e. for $R(tl)$. Also, the remaining absolute force in N at the low temperature shall be reported;
- e) the dates of the test, when it was started and finished.

Annex A (normative)

Calibration schedule

A.1 Inspection

Before any calibration is undertaken, the condition of the items to be calibrated shall be ascertained by inspection and recorded on any calibration report or certificate. It shall be reported whether calibration is carried out in the “as-received” condition or after rectification of any abnormality or fault.

It shall be ascertained that the apparatus is generally fit for the intended purpose, including any parameters specified as approximate and for which the apparatus does not therefore need to be formally calibrated. If such parameters are liable to change, then the need for periodic checks shall be written into the detailed calibration procedures.

A.2 Schedule

Verification/calibration of the test apparatus is a mandatory part of this document. However, the frequency of calibration and the procedures used are, unless otherwise stated, at the discretion of the individual laboratory, using ISO 18899 for guidance.

The calibration schedule given in [Table A.1](#) has been compiled by listing all of the parameters specified in the test method for the apparatus, together with the specified requirement. A parameter and requirement can relate to the main test apparatus, to part of that apparatus or to an ancillary apparatus necessary for the test.

For each parameter, a calibration procedure is indicated by reference to ISO 18899, to another publication or to a procedure particular to the test method which is detailed (whenever a calibration procedure which is more specific or detailed than that in ISO 18899 is available, it shall be used in preference).

The verification frequency for each parameter is given by a code-letter. The code-letters used in the calibration schedule are:

- C requirement to be confirmed but no measurement;
- N initial verification only;
- S standard interval as given in ISO 18899;
- U in use.