

International Standard



35

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Rubber latex, natural — Determination of mechanical stability

Latex de caoutchouc — Détermination de la stabilité mécanique

Second edition — 1982-04-01

STANDARDSISO.COM : Click to view the full PDF of ISO 35:1982

UDC 678.4.031 : 678.021.122 : 620.1

Ref. No. ISO 35-1982 (E)

Descriptors : rubber, natural rubber, latex, tests, mechanical tests, determination, stability, stability tests.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 35 was developed by Technical Committee ISO/TC 45, *Rubber and rubber products*, and was circulated to the member bodies in June 1980.

It has been approved by the member bodies of the following countries :

Austria	Ireland	Spain
Belgium	Italy	Sri Lanka
Canada	Korea, Rep. of	Sweden
Czechoslovakia	Malaysia	Thailand
Denmark	Mexico	Turkey
Egypt, Arab Rep. of	Netherlands	United Kingdom
France	Poland	USA
Germany, F.R.	Portugal	USSR
Hungary	Romania	
India	South Africa, Rep. of	

No member body expressed disapproval of the document.

This second edition cancels and replaces the first edition (i.e. ISO 35-1972).

Rubber latex, natural — Determination of mechanical stability

1 Scope and field of application

This International Standard specifies a method for the determination of the mechanical stability of natural rubber latex which contains preservative agents and which has been submitted to some type of concentration process. It also applicable to vulcanized natural rubber latex.

The method is not necessarily suitable for latices preserved with potassium hydroxide, latices from natural sources other than *Hevea brasiliensis*, or for compounded latex, or artificial dispersions of rubber, and is not applicable to synthetic rubber latices.

2 References

ISO 124, *Rubber latices — Determination of total solids content*.

ISO 125, *Rubber — Natural latex — Determination of alkalinity*.

3 Principle

Dilution of a sample of the latex to 55 % total solids content and stirring at high speed. Recording of the time required to initiate visible flocculation, this being regarded as a measure of the mechanical stability.

NOTE — The mechanical stability of latex may be adversely affected by lowering its temperature. Care should therefore be taken to ensure that the sample is not cooled significantly between sampling and testing. This effect is most marked on fresh latex.

4 Reagents

The ammonia solutions (4.1 and 4.2) shall be prepared from ammonium hydroxide of recognized analytical reagent quality and shall be stored in closed containers.

Carbonate-free distilled water or water of equivalent purity shall be used wherever water is specified.

4.1 Ammonia solution, containing 1,6 % (m/m) of ammonia (NH₃), for use with latex having an alkalinity of at least 0,30 % (calculated relative to the latex).

4.2 Ammonia solution containing 0,6 % (m/m) of ammonia (NH₃), for use with latex having an alkalinity of less than 0,30 % (calculated relative to the latex).

5 Apparatus

5.1 Mechanical stability measuring apparatus¹⁾, consisting of the following items :

5.1.1 Latex container, flat-bottomed, cylindrical, at least 90 mm high, with an internal diameter of 58 ± 1 mm and a wall thickness of approximately 2,5 mm. The inner surface shall be smooth.

A poly(methyl methacrylate) or glass container is suitable.

5.1.2 Stirring apparatus, consisting of a vertical stainless steel shaft of sufficient length to reach to the bottom of the latex container (5.1.1) and tapering to approximately 6,3 mm in diameter at its lower end where an exactly centered, horizontal, smooth, stainless steel disk, $20,83 \pm 0,03$ mm in diameter and $1,57 \pm 0,05$ mm thick, is attached. The apparatus shall maintain stirring at a rotational frequency of $14\,000 \pm 200$ min⁻¹ (233 ± 3 s⁻¹)²⁾ throughout a test, at which frequency the shaft shall not run out of true by more than 0,25 mm.

5.1.3 Holder, for the latex container (5.1.1). The holding arrangement shall ensure that the axis of the rotating shaft is concentric with that of the latex container and that the bottom of the stirring disk is 13 ± 1 mm from the inner surface of the bottom of the latex container.

1) Suitable instruments are available commercially. Details may be obtained from the Secretariat of ISO/TC 45 (BSI).

2) $1 \text{ s}^{-1} = 1 \text{ Hz}$ [= 1 revolution per second (r/s)].