
Plain bearings — Wrapped bushes —
Part 2:
Test data for outside and inside
diameters

Paliers lisses — Bagues roulées —

Partie 2: Données d'essai pour le diamètre extérieur et le diamètre intérieur

STANDARDSISO.COM : Click to view the full PDF of ISO 3547-2:2023



STANDARDSISO.COM : Click to view the full PDF of ISO 3547-2:2023



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Symbols and units.....	1
5 Presentation of data on drawing.....	2
6 Tests.....	3
6.1 Test A.....	3
6.2 Test B.....	3
6.3 Test C.....	3
6.4 Test D.....	4
7 Test A.....	4
7.1 Description.....	4
7.2 Calculation basis.....	4
7.2.1 Elastic reduction, v , of outside diameter, D_o	4
7.2.2 Calculation of diameter of checking block, $d_{ch,1}$	4
7.2.3 Effective cross-sectional area of the bush, A_{cal}	4
7.2.4 Calculation of checking load, F_{ch}	5
7.2.5 Limits for Δz	6
7.3 Obtaining data — Example.....	6
7.4 Presentation of data on drawing — Example.....	7
8 Test B.....	7
8.1 Description.....	7
8.2 Obtaining data — Example.....	8
8.3 Presentation of data on drawing — Example.....	8
9 Test C.....	8
9.1 Description.....	8
9.2 Obtaining data — Example.....	9
9.3 Presentation of data on drawing — Example.....	9
10 Test D.....	10
10.1 Description.....	10
10.2 Obtaining data — Example.....	10
10.3 Presentation of data on drawing — Example.....	10
11 Designation of tests according to this document.....	11
Bibliography.....	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 3, *Dimensions, tolerances and construction details*.

This fourth edition cancels and replaces the third edition (ISO 3547-2:2017), of which it constitutes a minor revision. The changes are as follows:

- the units in [Table 1](#) have been corrected;
- in [7.2.3](#), the correct term for A_{cal} has been implemented.

A list of all the parts in the ISO 3547 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Plain bearings — Wrapped bushes —

Part 2:

Test data for outside and inside diameters

1 Scope

This document specifies the test data for outside and inside diameters of wrapped bushes made of mono and multi-layer bearing material for plain bearing applications. It also specifies test designations.

Since the wall thickness of the bush is measured in the free condition, no special test data are required for this on the drawing (see ISO 3547-5 and ISO 3547-6).

NOTE Depending on the manufacturing method, the back of the bushes can show isolated light depressions and, similarly, bushes with lubrication holes, grooves and bore indentations can show distortion. It is therefore suggested to measure the wall thickness away from these areas.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 286-2, *Geometrical product specifications (GPS) — ISO code system for tolerances on linear sizes — Part 2: Tables of standard tolerance classes and limit deviations for holes and shafts*

ISO 3547-1:2018, *Plain bearings — Wrapped bushes — Part 1: Dimensions*

ISO 3547-4, *Plain bearings — Wrapped bushes — Part 4: Materials*

ISO 4378-1, *Plain bearings — Terms, definitions, classification and symbols — Part 1: Design, bearing materials and their properties*

ISO 4378-4, *Plain bearings — Terms, definitions, classification and symbols — Part 4: Basic symbols*

ISO 12301, *Plain bearings — Quality control techniques and inspection of geometrical and material quality characteristics*

ISO 13715, *Technical product documentation — Edges of undefined shape — Indication and dimensioning*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4378-1 and ISO 4378-4 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Symbols and units

See [Table 1](#).

Table 1 — Symbols and units

Symbol	Description	Unit
A_{cal}	Effective cross-sectional area of the bush (calculated value)	mm ²
B	Width of the bush	mm
C_i	Inside chamfer	mm
C_o	Outside chamfer	mm
D_{fl}	Flange diameter	mm
D_H	Housing bore diameter	mm
D_i	Inside diameter of the bush	mm
$D_{i, ch}$	Inside diameter of the bush in the ring gauge	mm
D_o	Outside diameter of the bush	mm
F_{ch}	Checking load	N
$d_{ch, 1}$	Diameter of the checking block or ring gauge	mm
$d_{ch, 2}$	Diameter of the setting plug or plug gauge	mm
r	Flange radius	mm
s_1	Thickness of the backing layer ^a	mm
s_2	Thickness of the bearing material layer ^a	mm
s_3	Wall thickness ^a	mm
s_{fl}	Flange thickness	mm
ΔD_o	Tolerance of D_o	mm
ν	Elastic reduction of the outside diameter under checking load F_{ch}	mm
z	Distance apart of the halves of the checking block	mm
Δz	Indicator reading	mm
Δz_D	Circumference indicator reading for test D	mm


^a For bushes which are made of a single material, $s_1 = s_2$ or $s_2 = s_3$.

5 Presentation of data on drawing


The drawing should show either:

- the outside diameter, D_o , and the wall thickness, s_3 ;
- the outside diameter, D_o , and the inside diameter, D_i .

Wall thickness, s_3 , and inside diameter, D_i , shall not be specified together on the same drawing. See [Figure 1](#).



a) Type C cylindrical bush



b) Type F flanged bush

Key

- 1 butt joint
- a Thickness of the bearing material layer; only valid as a basis for calculation in accordance with [7.2](#).
- b C_i may be a chamfer or break edge; in accordance with ISO 13715.
- c 0,2 mm min. for nominal wall thickness 0,5 mm.
- d $r_{\max} = s_3$.

Figure 1 — Cylindrical and flanged bush taken from ISO 3547-1**6 Tests****6.1 Test A**

Check the outside diameter, D_o , using a checking block in a test rig and setting plug, in accordance with [Clause 7](#).

6.2 Test B

Check the outside diameter, D_o , using two ring gauges, in accordance with [Clause 8](#).

6.3 Test C

Check the inside diameter, D_i , of a bush pressed into a ring gauge, in accordance with [Clause 9](#).

6.4 Test D

Check the outside diameter, D_o , using precision measuring tape, in accordance with [Clause 10](#).

7 Test A

7.1 Description

This test is applicable to D_o up to 180 mm.

The test rig consists of a base on which the two parts of the checking block are mounted (see ISO 3547-5).

A setting plug is inserted in the checking block and the two halves of the checking block are pressed towards one another using the given checking load, F_{ch} , and the indicator reading set.

The setting plug is then removed and replaced by the bush to be checked, and the checking load reapplied.

After the bush has been inserted, the distance, z , between the two halves of the checking block changes under checking load F_{ch} and the distance indicator reading, Δz , is recorded.

From this, D_o can be calculated.

Flanged bushes may be checked either before or after flange forming at the option of the manufacturer.

7.2 Calculation basis

7.2.1 Elastic reduction, v , of outside diameter, D_o

The elastic reduction, v , of the outside diameter, D_o , is the difference between D_o under zero load and the resultant diameter when the checking load, F_{ch} , is applied. Force F_{ch} shall be sufficient to ensure that the bush conforms properly to the surface of the test housing and that the results in the elastic reduction, v , of the outside diameter are in accordance with [Table 2](#).

Table 2 — Elastic reduction, v , of the outside diameter, D_o , under checking load, F_{ch}

Dimensions in millimetres

D_o nominal		v
	≤ 6	0,003
> 6	≤ 12	0,006
> 12	≤ 80	0,013
> 80	≤ 180	0,025

7.2.2 Calculation of diameter of checking block, $d_{ch,1}$

The diameter of the checking block can be calculated from the specified upper limit of the outside diameter, $D_{o,max}$, of the bush from [Formula \(1\)](#):

$$d_{ch,1} = D_{o,max} - v \quad (1)$$

7.2.3 Effective cross-sectional area of the bush, A_{cal}

In order to calculate the checking load, F_{ch} , the effective cross-sectional area of the bush, A_{cal} , shall first be determined.

A_{cal} depends on the material type, bush width B , s_1 and s_2 . See [Table 3](#).

Table 3 — Nominal dimensions for wall thickness, s_3 , backing material, s_1 , and bearing layer, s_2

Dimensions in millimetres

Nominal thicknesses		
Wall thickness (see ISO 3547-1)	Backing material of bushes made from multi-layer materials	Bearing material layer of bushes made from multi-layer ma- terials
s_3	s_1	s_2
0,5	0,3	0,2
0,75	0,53	0,22
1,0	0,68	0,32
1,5	1,1	0,4
2,0	1,55	0,45
2,5	2,05	0,45

The nominal size for B , s_1 and s_2 shall then be substituted into the corresponding equation given in [Table 4](#).

Table 4 — Calculation of effective cross-sectional area of the bush, A_{cal}

Material designation key (according to ISO 3547-4)	Calculation of effective cross-sectional area of the bush A_{cal}
D1, D2, P1, P2, T2, Z1	$A_{\text{cal}} = B \times s_1$
B1, B2, D3, W1, W2, Y1, Y2	$A_{\text{cal}} = B \times \frac{s_1}{2}$
D4	$A_{\text{cal}} = B \times \frac{s_1}{3}$
R1, R2, R3, R4	—
S1, S2, S3, S4, S5, S6	$A_{\text{cal}} = B \times \left(s_1 + \frac{s_2}{2} \right)$

7.2.4 Calculation of checking load, F_{ch}

See [Table 5](#).

Table 5 — Formulae for F_{ch}

Dimensions in millimetres

D_0 nominal		F_{ch}
	≤ 6	$1\,500 \times \frac{A_{\text{cal}}}{d_{\text{ch},1}}$ (rounded up 100 N)
> 6	≤ 12	$3\,000 \times \frac{A_{\text{cal}}}{d_{\text{ch},1}}$ (rounded up 250 N)
NOTE When calculating F_{ch} , the factor 1 500, 3 000, 6 000 or 12 000 has the unit N/mm.		

Table 5 (continued)

D_o nominal		F_{ch}
> 12	≤ 80	$6\,000 \times \frac{A_{cal}}{d_{ch,1}}$ (rounded up 500 N)
> 80	≤ 180	$12\,000 \times \frac{A_{cal}}{d_{ch,1}}$ (rounded up 500 N)
NOTE When calculating F_{ch} , the factor 1 500, 3 000, 6 000 or 12 000 has the unit N/mm.		

Lubrication grooves can reduce A_{cal} , depending upon their shape, position and method of manufacture. If the proportion is over 10 %, this shall be considered in the calculation.

For bushes which are not made in accordance with ISO 3547-1, the arithmetic average of the two limiting dimensions rounded up to the nearest 0,1 mm shall be used for B , s_1 and s_2 .

7.2.5 Limits for Δz

Upper limit: 0

Lower limit: $-\frac{\pi}{2} \times \Delta D_o$
(rounded up to the nearest 0,005 mm)

7.3 Obtaining data — Example

Given:

Bush ISO 3547 — 30A 34 × 30 — S3

Outside diameter: $D_o = (34^{+0,085}_{+0,045})$ mm
(in accordance with ISO 3547-1:2018, Table 7)

Nominal wall thickness: $s_3 = 2$ mm

Nominal thickness of the steel backing: $s_1 = 1,55$ mm (see [Table 3](#))

$$\begin{aligned} s_2 &= s_3 - s_1 \\ &= 2 \text{ mm} - 1,55 \text{ mm} \end{aligned}$$

$$s_2 = 0,45 \text{ mm}$$

Nominal width: $B = 30$ mm

Material: steel/copper alloy S3 (in accordance with ISO 3547-4)

Results:

From [7.2.2](#):

$$\begin{aligned} d_{ch,1} &= D_{o,max} - v \\ &= 34,085 \text{ mm} - 0,013 \text{ mm} \end{aligned}$$

$$d_{ch,1} = 34,072 \text{ mm}$$

From 7.2.3:

$$\begin{aligned}
 A_{\text{cal}} &= B \times \left(s_1 + \frac{s_2}{2} \right) \\
 &= 30 \times \left(1,55 + \frac{0,45}{2} \right) \text{ mm}^2 \\
 A_{\text{cal}} &= 53,25 \text{ mm}^2
 \end{aligned}$$

From 7.2.4:

$$\begin{aligned}
 F_{\text{ch}} &= 6\,000 \times \frac{A_{\text{cal}}}{d_{\text{ch},1}} \\
 &= 6\,000 \times \frac{53,25}{34,072} = 9\,377 \text{ N} \\
 F_{\text{ch}} &= 9\,500 \text{ N (rounded up to the nearest 500 N)}
 \end{aligned}$$

From 7.2.5:

Upper limit:

$$\Delta z$$


$$0$$

Lower limit:

$$\begin{aligned}
 &-\frac{\pi}{2} \times \Delta D_o \\
 &-\frac{\pi}{2} \times 0,040 \text{ mm} = -0,0628 \text{ mm} = -0,065 \text{ mm} \\
 &\text{(rounded up to the nearest 0,005 mm)}
 \end{aligned}$$

7.4 Presentation of data on drawing — Example

See Figure 2 for an example of how the data obtained in 7.3 should be presented on the drawing.



Test A to ISO 3547-2

Checking block and setting plug $d_{\text{ch},1} = d_{\text{ch},2} = 34,072 \text{ mm}$

Checking load $F_{\text{ch}} = 9\,500 \text{ N}$

Limit for $\Delta z = 0 \text{ and } -0,065 \text{ mm}$

Outside diameter $D_o = 34,045 \text{ to } 34,085 \text{ mm}$

Key

- 1 position of butt joint
- 2 checking block

Figure 2 — Example of presentation of data on drawing

8 Test B

8.1 Description

The test is applicable to D_o up to 180 mm.

The test is carried out with two ring gauges, a GO ring gauge and a NO GO ring gauge.

The gauge diameters are determined empirically, based on the maximum and minimum values of the outside diameter (see ISO 3547-1:2018, Table 7) to be checked, and shall be agreed between supplier and user.

It shall be possible to press the bush into the GO ring gauge with hand pressure (maximum force 250 N). However, with the same force it shall not be possible for the bush to enter the NO GO ring gauge (see ISO 3547-5).

NOTE In some cases, the accuracy of the check could be affected, e.g. by the out of roundness of the bush or by butt joints which are not closed. For this reason, Test A is preferred.

8.2 Obtaining data — Example

Given:

Bush ISO 3547 — 30A 34 × 30 — S3

Outside diameter: $D_o = \left(34 \begin{smallmatrix} +0,085 \\ +0,045 \end{smallmatrix} \right) \text{ mm}$

Material: steel/copper alloy S3 (in accordance with ISO 3547-4)

GO gauge diameter = 34,085 mm (found empirically)

NO GO gauge diameter = 34,045 mm (found empirically)

8.3 Presentation of data on drawing — Example

The data obtained should be presented on the drawing as in the following example:

Test B to ISO 3547-2

GO gauge diameter = 34,085 mm

NO GO gauge diameter = 34,045 mm

9 Test C

9.1 Description

In order to check the inside diameter, D_i , the bush is pressed into a ring gauge, whose nominal diameter corresponds to the dimension specified in [Table 6](#). Other details of the ring gauge should be according to ISO 3547-6.

The test is applicable to D_o up to 180 mm.

Inside diameter $D_{i, \text{ch}}$ shall be measured with a three-point measuring instrument in accordance with ISO 12301, or checked with a GO and NO GO plug gauge.

The plug gauges are calculated from the ring gauge diameter, $d_{\text{ch}, 1}$, as follows.

GO plug: $d_{\text{ch}, 1} - 2 \times s_{3, \text{max}}$

NO GO plug: $d_{\text{ch}, 1} - 2 \times s_{3, \text{min}}$

The GO plug gauge shall enter the bush with minimum effort; the NO GO plug gauge shall not enter the bush manually (maximum force 250 N).

When the bush is pressed into the ring gauge, it is possible that there will be a permanent reduction in the outside diameter.

In order to enable the supplier and user to compare results, the test method should be agreed between them.

Table 6 — Ring gauge inside diameter, $d_{ch,1}$, for checking bush inside diameter, $D_{i,ch}$

Dimensions in millimetres

D_o nominal		$d_{ch,1}^a$
	≤ 10	$D_o + 0,008$
> 10	≤ 18	$D_o + 0,009$
> 18	≤ 30	$D_o + 0,011$
> 30	≤ 50	$D_o + 0,013$
> 50	≤ 80	$D_o + 0,015$
> 80	≤ 120	$D_o + 0,018$
> 120	≤ 180	$D_o + 0,020$

^a The size of $d_{ch,1}$ is made up of D_o and the rounded average value of the tolerance class H7 in accordance with ISO 286-2.

9.2 Obtaining data — Example

Given:

Bush ISO 3547 — 30B 34 × 30

Material: multilayer material P1 (in accordance with ISO 3547-4)

Ring gauge inside diameter: $d_{ch,1} = 34,013$ mm (in accordance with [Table 6](#))


Wall thickness: $s_3 = \left(2^{+0,005}_{-0,030} \right)$ mm
(in accordance with ISO 3547-1:2018, Table 5, series B)

GO plug diameter: $d_{ch,2,min} = d_{ch,1} - 2 \times s_{3,max}$
 $= 34,013 \text{ mm} - 2 \times 2,005 \text{ mm}$
 $= 30,003 \text{ mm}$

NO GO plug diameter: $d_{ch,2,max} = d_{ch,1} - 2 \times s_{3,min}$
 $= 34,013 \text{ mm} - 2 \times 1,97 \text{ mm}$
 $= 30,073 \text{ mm}$

9.3 Presentation of data on drawing — Example

See [Figure 3](#) for an example of how the data obtained in [9.2](#) should be presented on the drawing.



Test C — Gauging — to ISO 3547-2

^a With bush pressed into a ring gauge with $d_{ch,1} = 34,013$ mm.

Figure 3 — Example of presentation of data on drawing

10 Test D

10.1 Description

This method is applicable to bushes with D_o above 120 mm.

A precision measuring tape is used to measure the circumference of the bush.

Details of this text shall be agreed between supplier and user.

10.2 Obtaining data — Example

Given:

Bush ISO 3547 — 200A 205 × 100 — S3

Outside diameter: $D_o = (205^{+0,225}_{+0,125})$ mm

Material: steel/copper alloy S3 (in accordance with ISO 3547-4)

10.3 Presentation of data on drawing — Example

See [Figure 4](#) for an example of how the data obtained in [10.2](#) should be presented on the drawing.