
Fluid power systems — O-rings —

Part 1:

**Inside diameters, cross-sections,
tolerances and designation codes**

AMENDMENT 1

Transmissions hydrauliques et pneumatiques — Joints toriques —

*Partie 1: Diamètres intérieurs, sections, tolérances et codes
d'identification dimensionnelle*

AMENDEMENT 1





COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 131, *Fluid power systems*, Subcommittee SC 7, *Sealing devices*.

A list of all parts in the ISO 3601 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

STANDARDSISO.COM : Click to view the full PDF of ISO 3601-1:2012/Amd 1:2019

Fluid power systems — O-rings —

Part 1: Inside diameters, cross-sections, tolerances and designation codes

AMENDMENT 1

Page 1, Scope

Replace the Scope with the following:

This document specifies the inside diameters, cross-sections, tolerances and designation codes for O-rings used in fluid power systems for general industrial and aerospace applications.

The ISO 3601 series of standards basically addresses O-rings with moulded cross-sections without a radial joint. The dimensions and tolerances specified in this document are suitable for any elastomeric material, provided that suitable tooling is available.

NOTE The tooling most commonly available is based on 70 IRHD NBR shrinkage rates (see ISO 48). For materials that shrink differently from this standard NBR compound, a special mould can be required to maintain the mean diameters and the tolerance limits listed.

Page 31, Table A.1

Replace [Table A.1](#) with the following (three tolerance ranges for non-standard O-rings with cross section diameters $d_2 > 8,4$ mm have been added):

Table A.1 — Tolerances of cross-section diameters for non-standard O-rings

Cross-section d_2 mm	Tolerance mm	Cross-section d_2 in	Tolerance in
$0,80 \leq d_2 \leq 3,15^a$	$\pm 0,08$	$0,031 \leq d_2 \leq 0,124^a$	$\pm 0,003$
$0,80 \leq d_2 \leq 2,25^b$	$\pm 0,08$	$0,031 \leq d_2 \leq 0,089^b$	$\pm 0,003$
$2,25 < d_2 \leq 3,15^b$	$\pm 0,09$	$0,089 < d_2 \leq 0,124^b$	$\pm 0,004^c$
$3,15 < d_2 \leq 4,50$	$\pm 0,10$	$0,124 < d_2 \leq 0,177$	$\pm 0,004^c$
$4,50 < d_2 \leq 6,30$	$\pm 0,13$	$0,177 < d_2 \leq 0,248$	$\pm 0,005$
$6,30 < d_2 \leq 8,40$	$\pm 0,15$	$0,248 < d_2 \leq 0,331$	$\pm 0,006$
$8,40 < d_2 \leq 10,00^d$	$\pm 0,20$	$0,331 < d_2 \leq 0,394^d$	$\pm 0,008$
$10,00 < d_2 \leq 12,00^d$	$\pm 0,25$	$0,394 < d_2 \leq 0,472^d$	$\pm 0,010$

^a Applies to class A only.

^b Applies to class B only.

^c Differences between tolerance values are due to conversion of dimensions from metric to inch and rounding rules.

^d Tolerances apply to O-rings with inside diameters $d_1 \leq 660$ mm (25,98 in). Tolerances for diameters $d_1 > 660$ mm (25,98 in) shall be agreed upon between customer and manufacturer.

Table A.1 (continued)

Cross-section d_2 mm	Tolerance mm	Cross-section d_2 in	Tolerance in
$12,00 < d_2 \leq 14,00^d$	$\pm 0,28$	$0,472 < d_2 \leq 0,551^d$	$\pm 0,011$
^a Applies to class A only. ^b Applies to class B only. ^c Differences between tolerance values are due to conversion of dimensions from metric to inch and rounding rules. ^d Tolerances apply to O-rings with inside diameters $d_1 \leq 660$ mm (25,98 in). Tolerances for diameters $d_1 > 660$ mm (25,98 in) shall be agreed upon between customer and manufacturer.			