
International Standard



429

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Wrought copper-nickel alloys — Chemical composition and forms of wrought products

Alliages cuivre-nickel corroyés — Composition chimique et formes des produits corroyés

Second edition — 1983-10-15

STANDARDSISO.COM : Click to view the full PDF of ISO 429:1983

UDC 669.35.24-13

Ref. No. ISO 429-1983 (E)

Descriptors : copper alloys, copper nickel alloys, chemical composition, wrought products.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been authorized has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 429 was developed by Technical Committee ISO/TC 26, *Copper and copper alloys*, and was circulated to the member bodies in November 1981.

It has been approved by the member bodies of the following countries:

Austria	France	Romania
Belgium	Germany, F.R.	South Africa, Rep. of
Brazil	Hungary	Spain
Bulgaria	Italy	Sweden
Canada	Japan	Switzerland
China	Korea, Dem. P. Rep. of	Turkey
Czechoslovakia	Netherlands	United Kingdom
Egypt, Arab Rep. of	Norway	USA
Finland	Poland	USSR

No member body expressed disapproval of the document.

This second edition cancels and replaces the first edition (i.e. ISO 429-1973).

Wrought copper-nickel alloys — Chemical composition and forms of wrought products

1 Scope and field of application

This International Standard specifies the chemical composition of wrought copper-nickel alloys and lists the forms of wrought products in which they are currently available in commercial quantities.

2 References

ISO 197, *Copper and copper alloys — Terms and definitions*
Part 1: Materials.
Part 3: Wrought products.

ISO 1190/1, *Copper and copper alloys — Code of designation — Part 1: Designation of materials.*

ISO 1634, *Wrought copper and copper alloys — Mechanical properties*

*Part 1: Plate, sheet and strip for general purposes.*¹⁾

*Part 2: Plate and sheet for boilers, pressure vessels and condensers.*¹⁾

ISO 1635, *Wrought copper and copper alloys — Round tubes for general purposes — Mechanical properties.*¹⁾

ISO 1636, *Wrought copper and copper alloys — Seamless condenser and heat-exchanger tubes — Technical conditions of delivery.*¹⁾

ISO 1637, *Wrought copper and copper alloys — Rod and bar — Mechanical properties.*²⁾

ISO 1638, *Wrought copper and copper alloys — Wire — Mechanical properties.*²⁾

ISO 6957, *Wrought copper alloys — Strip for springs.*¹⁾

3 Definitions

For the purpose of this International Standard, the definitions given in ISO 197/1 and ISO 197/3 apply.

4 Chemical composition

The chemical composition of the copper alloys is given in table 1. The composition limits do not preclude the possible presence of other elements not specified. If the purchaser's requirements necessitate limits for any other element not specified, these shall be agreed upon between the supplier and the purchaser. Percentage content of elements shown as "remainder" is usually calculated by difference from 100 %.

The designations used are in accordance with the principles laid down in ISO 1190/1.

5 Forms of wrought products and mechanical properties

The forms of wrought products in which these copper alloys are available are given in table 2. The mechanical properties for all forms of wrought products for which the symbol X is given, are defined in the following International Standards :

ISO 1634/1, ISO 1634/2, ISO 1635, ISO 1636, ISO 1637, ISO 1638, ISO 6957.

1) At present at the stage of draft.

2) Under revision.