

INTERNATIONAL STANDARD

ISO
5755

Second edition
2001-04-15

Sintered metal materials — Specifications

Matériaux métalliques frittés — Spécifications

STANDARDSISO.COM : Click to view the full PDF of ISO 5755:2001



Reference number
ISO 5755:2001(E)

© ISO 2001

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 5755:2001

© ISO 2001

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Sampling	1
4 Test methods for normative properties.....	2
4.1 General.....	2
4.2 Chemical analysis.....	2
4.3 Open porosity.....	2
4.4 Radial crushing strength	2
4.5 Tensile strength	2
4.6 Tensile yield strength.....	2
4.7 Mechanical properties.....	2
5 Specifications.....	3
6 Designations	3
Annex A (normative) Designation system	15
Annex B (informative) Microstructures	17
Bibliography	19

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 5755 was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*, Subcommittee SC 5, *Specifications for powder metallurgical materials (excluding hardmetals)*.

This second edition cancels and replaces the first edition (ISO 5755:1996), which has been technically revised.

Annex A forms a normative part of this International Standard. Annex B is for information only.

Sintered metal materials — Specifications

1 Scope

This International Standard specifies the requirements for the chemical composition and the mechanical and physical properties of sintered metal materials used for bearings and structural parts.

When selecting powder metallurgical materials, it should be taken into account that the properties depend not only on the chemical composition and density, but also on the production methods. The properties of sintered materials giving satisfactory service in particular applications may not necessarily be the same as those of wrought or cast materials that might otherwise be used. Therefore liaison with prospective suppliers is recommended.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 2738, *Sintered metal materials, excluding hardmetals — Permeable sintered metal materials — Determination of density, oil content and open porosity.*

ISO 2739, *Sintered metal bushes — Determination of radial crushing strength.*

ISO 2740, *Sintered metal material, excluding hardmetals — Tensile test pieces.*

ISO 2795, *Plain bearings — Sintered bushes — Dimensions and tolerances.*

ISO 6892, *Metallic materials — Tensile testing at ambient temperature.*

3 Sampling

Sampling shall be carried out in accordance with the relevant International Standards.

4 Test methods for normative properties

4.1 General

The following test methods shall be used to determine the normative properties given in Tables 1 to 11.

4.2 Chemical analysis

Whenever possible, and always in cases of dispute, the methods of chemical analysis shall be those specified in the relevant International Standards. If no International Standard is available, the method may be agreed upon and specified at the time of enquiry and order.

4.3 Open porosity

The open porosity shall be determined in accordance with ISO 2738.

4.4 Radial crushing strength

The radial crushing strength shall be determined in accordance with ISO 2739.

4.5 Tensile strength

The ultimate tensile strength shall be determined in accordance with ISO 2740 and ISO 6892.

4.6 Tensile yield strength

The yield strength shall be determined in accordance with ISO 2740 and ISO 6892.

4.7 Mechanical properties

4.7.1 General

The mechanical properties given in Tables 1 to 11 were determined on pressed and sintered test pieces at mean chemical composition and are intended as a guide to initial selection of materials (see clause 1). They may also be used as a basis for specifying any special tests that may be indicated on the drawing.

The mechanical properties shall neither be calculated from hardness values, nor be determined on tensile test pieces taken from a component and used for verifying the values given in Tables 1 to 11. If the customer requires that a specified level of mechanical properties be obtained by tests on the component, these shall be agreed with the supplier and shall be stated on the drawing and/or any technical documentation of the customer referred to on the drawing.

4.7.2 Tensile properties

The normative values for yield strength shall be determined in accordance with ISO 6892, using pressed and sintered test pieces made in accordance with ISO 2740. For heat-treated materials, tensile strength and yield strength are approximately equal and in this case tensile strength, determined on machined test pieces according to ISO 2740, is specified.

4.7.3 Radial crushing strength

The radial crushing strength shall be determined in accordance with ISO 2739. The wall thicknesses of test pieces to be used shall be in the range covered by ISO 2795. For test pieces outside this range, the specified radial crushing strength values are different and shall be agreed between customer and supplier.

5 Specifications

The chemical composition and mechanical properties are given in Tables 1 to 11.

The liquid lubricant content of materials for bearings, impregnated with liquid lubricant, shall be not less than 90 % of the measured open porosity.

6 Designations

Designations shall be in accordance with annex A.

STANDARDSISO.COM : Click to view the full PDF of ISO 5755:2001

Table 1 — Materials for bearings: iron, iron-copper, iron-bronze and iron-carbon-graphite

Parameter	Symbol	Unit	Iron		Iron-copper		Iron-bronze ^a				Iron-carbon-graphite ^a	
			Grade ^b		Grade ^b		Grade ^b				Grade ^b	
			-F-00-K170	-F-00-K220	-F-00-K200	-F-00-K250	-F-03C36T-K90	-F-03C36T-K120	-F-03C45T-K70	-F-03C45T-K100	-F-03G3-K70	-F-03G3-K80
Chemical composition												
C combined ^c		%	< 0,3	< 0,3	< 0,3	< 0,3	< 0,5	< 0,5	< 0,5	< 0,5	< 0,5	< 0,5
Cu		%	—	—	1 to 4	1 to 4	34 to 38	34 to 38	43 to 47	43 to 47	—	—
Fe		%	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance
Sn		%	—	—	—	—	3,5 to 4,5	3,5 to 4,5	4,5 to 5,5	4,5 to 5,5	—	—
Graphite		%	—	—	—	—	0,3 to 1,0	0,3 to 1,0	< 1,0	< 1,0	2,0 to 3,5	2,0 to 3,5
Total other elements max.		%	2	2	2	2	2	2	2	2	2	2
Open porosity	min.	%	22	17	22	17	24	19	24	19	20	13
Radial crushing strength	min.	MPa	170	220	200	250	90 to 265	120 to 345	70 to 245	100 to 310	70 to 175	80 to 210
Density (dry)	ρ	g/cm ³	5,8	6,2	5,8	6,2	5,8	6,2	5,6	6,0	5,6	6,0
Coefficient of linear expansion ^d		10 ⁻⁶ K ⁻¹	12	12	12	12	14	14	14	14	12	12

^a The range of values given for radial crushing strength (K) indicates the necessity to maintain a balance between combined carbon and free graphite.

^b All materials can be impregnated.

^c On the basis of iron phase only.

^d Informative values.

Table 2 — Non-ferrous materials for bearings

Parameter	Symbol	Unit	Bronze		Bronze with graphite		
			Grade ^a		Grade ^a		
Chemical composition			-C-T10-K110	-C-T10-K140	-C-T10-K180	-C-T10G-K90	-C-T10G-K120
Cu		%	Balance 8,5 to 11,0	Balance 8,5 to 11,0	Balance 8,5 to 11,0	Balance 8,5 to 11,0	Balance 8,5 to 11,0
Sn		%	—	—	—	0,5 to 2,0	0,5 to 2,0
Graphite		%	2	2	2	2	2
Total other elements max.		%	27	22	15	27	22
Open porosity	<i>P</i>	min.	110	140	180	90	120
Radial crushing strength	<i>K</i>	min.	6,1	6,6	7,0	5,9	6,4
Density (dry)	ρ	g/cm ³	18	18	18	18	18
Coefficient of linear expansion ^b		10 ⁻⁶ K ⁻¹					
Normative values							
a All materials can be impregnated.							
b Informative values.							

Table 3 — Ferrous materials for structural parts: iron and carbon steel

Parameter		Symbol	Unit	Iron		Carbon steel								Normative values		Informative values							
				Grade		Grade																	
Chemical composition				F-00-100	-F-00-120	-F-00-140	-F-05-140	-F-05-170	-F-05-340H a	-F-05-480H a	-F-08-210	-F-08-240	-F-08-450H b	-F-08-550H b									
C combined		%	< 0,3	< 0,3	< 0,3	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,6 to 0,9	0,6 to 0,9	0,6 to 0,9	0,6 to 0,9									
Cu		%	—	—	—	—	—	—	—	—	—	—	—	—									
Fe		%	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance									
Total other elements max.		%	2	2	2	2	2	2	2	2	2	2	2	2									
Tensile yield strength	min.	MPa	100	120	140	140	170				210	240											
Ultimate tensile strength	min.	MPa							340	480			450	550									
Apparent hardness		HV5	62	75	85	90	120	280 HV10	300 HV10	120	140	320 HV10	360 HV10										
		Rockwell	60 HRF	70 HRF	80 HRF	40 HRB	60 HRB	20 HRC	25 HRC	60 HRB	70 HRB	28 HRC	33 HRC										
Density		ρ	g/cm ³	6,7	7,0	7,3	6,6	7,0	6,6	7,0	6,6	7,0	6,6	7,0									
Tensile strength		R _m	MPa	170	210	260	220	275	410	550	290	390	520	620									
Tensile yield strength		R _{p0,2}	MPa	120	150	170	160	200	a	a	240	260	c	c									
Elongation		A ₂₅	%	3	4	7	1	2	nm ^d	nm ^d	1	1	nm ^d	nm ^d									
Young's Modulus			GPa	120	140	160	115	140	115	140	115	140	115	140									
Poisson's ratio				0,25	0,27	0,28	0,25	0,27	0,25	0,27	0,25	0,27	0,25	0,27									
Unnotched Charpy Impact			J	8	24	47	5	8	4	5	5	7	5	7									
Compressive yield strength	(0,1 %)		MPa	120	125	130	210	225	300	420	290	290	400	550									
Transverse rupture strength			MPa	340	500	660	440	550	720	970	510	690	790	950									
Fatigue limit 90 % survival ^e			MPa	65	80	100	80	105	160	220	120	170	210	260									
NOTE These materials may be supplied with additives to improve machinability. The properties remain unchanged.																							
^a Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,5 % carbon potential, oil quenched and tempered at 180 °C for 1 h.																							
^b Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,8 % carbon potential, oil quenched and tempered at 180 °C for 1 h.																							
^c Tensile strength and tensile yield strength are approximately the same for heat treated materials.																							
^d nm = not measurable.																							
^e 90 % fatigue endurance limit in rotating bending tests. Machined test pieces in accordance with ISO 3928.																							

Table 4 — Ferrous materials for structural parts: copper steel and copper-carbon steel

Parameter	Symbol	Unit	Copper-carbon steel									
			Copper steel		Grade							
Chemical composition			-F-00C2-140	-F-00C2-175	-F-05C2-270	-F-05C2-300	-F-05C2-500H ^a	-F-05C2-620H ^a	-F-08C2-350	-F-08C2-390	-F-08C2-500H ^b	-F-05C2-620H ^b
C combined		%	< 0,3	< 0,3	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,6 to 0,9	0,6 to 0,9	0,6 to 0,9	0,6 to 0,9
Cu		%	1,5 to 2,5	1,5 to 2,5	1,5 to 2,5	1,5 to 2,5	1,5 to 2,5	1,5 to 2,5	1,5 to 2,5	1,5 to 2,5	1,5 to 2,5	1,5 to 2,5
Fe		%	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance
Total other elements max.		%	2	2	2	2	2	2	2	2	2	2
Tensile yield strength min.	$R_{p0,2}$	MPa	140	175	270	300	c	c	350	390	c	c
Ultimate tensile strength min.	R_m	MPa					500	620			500	620
Apparent hardness		HV5	70	90	115	150	310 HV 10	390 HV 10	140	165	360 HV 10	430 HV 10
		Rockwell	26 HRB	39 HRB	57 HRB	68 HRB	27 HRC	36 HRC	70 HRB	78 HRB	33 HRC	40 HRC
Density	ρ	g/cm ³	6,6	7,0	6,6	7,0	6,6	7,0	6,6	7,0	6,6	7,0
Tensile strength	R_m	MPa	210	235	325	390	580	690	390	480	570	690
Tensile yield strength	$R_{p0,2}$	MPa	180	205	300	330	c	c	360	420	c	c
Elongation	A_{25}	%	2	3	nm ^d	1	nm ^d	nm ^d	nm ^d	nm ^d	nm ^d	nm ^d
Young's Modulus		GPa	115	140	115	140	115	140	115	140	115	140
Poisson's ratio			0,25	0,27	0,25	0,27	0,25	0,27	0,25	0,27	0,25	0,27
Unnotched Charpy Impact		J	7	8	7	10	5	7	7	8	6	6
Compressive yield strength (0,1 %)		MPa	160	185	380	400	560	660	450	480	560	690
Transverse rupture strength		MPa	390	445	620	760	800	930	800	980	830	1 000
Fatigue limit 90 % survival ^e		MPa	80	89	130	200	220	260	150	200	230	270
Fatigue limit 50 % survival ^f		MPa			110	160			120	150		
NOTE These materials may be supplied with additives to improve machinability. The properties remain unchanged.												
^a Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,5 % carbon potential, oil quenched and tempered at 180 °C for 1 h.												
^b Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,8 % carbon potential, oil quenched and tempered at 180 °C for 1 h.												
^c Tensile strength and tensile yield strength are approximately the same for heat-treated materials.												
^d nm = not measurable.												
^e 90 % fatigue endurance limit in rotating bending tests. Machined test pieces in accordance with ISO 3928.												
^f 50 % fatigue endurance limit in 4-point plane bending. Non-machined test pieces in accordance with ISO 3928.												

Table 5 — Ferrous materials for structural parts: phosphorus steels

Parameter	Symbol	Unit	Phosphorus steel ^a		Phosphorus carbon steel		Copper-phosphorus steel		Copper-phosphorus-carbon steel	
			Grade	Grade	Grade	Grade	Grade	Grade	Grade	Grade
Chemical composition			-F-00P05-180	-F-00P05-210	-F-05P05-270	-F-05P05-320	-F-00C2P-260	-F-00C2P-300	-F-05C2P-320	-F-05C2P-380
C combined		%	< 0,1	< 0,1	0,3 to 0,6	0,3 to 0,6	< 0,3	< 0,3	0,3 to 0,6	0,3 to 0,6
Cu		%	—	—	—	—	1,5 to 2,5	1,5 to 2,5	1,5 to 2,5	1,5 to 2,5
P		%	0,40 to 0,50	0,40 to 0,50	0,40 to 0,50	0,40 to 0,50	0,40 to 0,50	0,40 to 0,50	0,40 to 0,50	0,40 to 0,50
Fe		%	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance
Total other elements max.		%	2	2	2	2	2	2	2	2
Tensile yield strength min.	$R_{p0,2}$	MPa	180	210	270	320	260	300	320	380
Apparent hardness		HV5	70	120	130	150	120	140	140	160
		Rockwell	40 HRB	60 HRB	65 HRB	72 HRB	60 HRB	69 HRB	69 HRB	74 HRB
Density	ρ	g/cm ³	6,6	7,0	6,6	7,0	6,6	7,0	6,6	7,0
Tensile strength	R_m	MPa	300	400	400	480	400	500	450	550
Tensile yield strength	$R_{p0,2}$	MPa	210	240	305	365	300	340	360	400
Elongation	A_{25}	%	4	9	3	5	3	6	2	3
Young's Modulus		GPa	115	140	115	140	115	140	115	140
Poisson's ratio			0,25	0,27	0,25	0,27	0,25	0,27	0,25	0,27
Unnotched Charpy Impact		J	18	30	9	15				
Transverse rupture strength		MPa	600	900	700	1000			820	1120
Fatigue limit 50 % survival ^b		MPa	110	140	140	175	130	160	150	180

^a Consultation with the supplier is recommended before these materials are used in magnetic applications. Some soft magnetic PM materials are standardized in IEC 60404-8-9.

^b 50 % fatigue endurance limit in 4-point plane bending. Non-machined test pieces in accordance with ISO 3928.

Table 7 — Ferrous materials for structural parts: diffusion-alloyed nickel-copper-molybdenum steels

Parameter	Symbol	Unit	Nickel-copper-molybdenum steels ^a									
			Grade									
Chemical composition			-FD-05N2C-360	-FD-05N2C-400	-FD-05N2C-440	-FD-05N2C-950H b	-FD-05N2C-1100H b	-FD-05N4C-400	-FD-05N4C-420	-FD-05N4C-450	-FD-05N4C-930H b	-FD-05N4C-1100H b
C combined		%	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6	0,3 to 0,6
Ni		%	1,5 to 2,0	1,5 to 2,0	1,5 to 2,0	1,5 to 2,0	1,5 to 2,0	3,5 to 4,5	3,5 to 4,5	3,5 to 4,5	3,5 to 4,5	3,5 to 4,5
Cu		%	1,0 to 2,0	1,0 to 2,0	1,0 to 2,0	1,0 to 2,0	1,0 to 2,0	1,0 to 2,0	1,0 to 2,0	1,0 to 2,0	1,0 to 2,0	1,0 to 2,0
Mo		%	0,4 to 0,6	0,4 to 0,6	0,4 to 0,6	0,4 to 0,6	0,4 to 0,6	0,4 to 0,6	0,4 to 0,6	0,4 to 0,6	0,4 to 0,6	0,4 to 0,6
Fe		%	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance
Total other elements		%	2	2	2	2	2	2	2	2	2	2
Tensile yield strength	$R_{p0.2}$	MPa	360	400	440	c	c	400	420	450	c	c
Ultimate tensile strength	R_m	MPa					1100				930	1100
Apparent hardness		HV5	155	180	210							
		Rockwell	73 HRB	80 HRB	86 HRB			82 HRB	86 HRB	92 HRB	36 HRC	43 HRC
Density	ρ	g/cm ³	6,9	7,1	7,4		7,4	6,9	7,1	7,4	7,1	7,4
Tensile strength ^d	R_m	MPa	540	590	680		1170	650	750	875	1000	1170
Tensile yield strength ^d	$R_{p0.2}$	MPa	390	420	460		c	440	460	485	c	c
Elongation	A_{25}	%	2	3	4		nm ^e	1	2	3	nm ^e	nm ^e
Young's Modulus		GPa	135	150	170		170	135	150	170	150	170
Poisson's ratio			0,27	0,27	0,28		0,28	0,27	0,27	0,28	0,27	0,28
Unnotched Charpy Impact		J	14	22	38		15	21	28	39	10	15
Compressive yield strength (0,1 %)		MPa	350	380	430		1 380	410	440	510	1 060	1 240
Transverse rupture strength		MPa	1 040	1 200	1 450		1 650	1 220	1 380	1 630	1 420	1 650
Fatigue limit 90 % survival ^f		MPa	190	220	260		490	200	240	290	350	410
Fatigue limit 50 % survival ^g		MPa	170	200	240		—	190	220	260	—	—

^e nm = not measurable.

^a These materials are produced from diffusion-alloyed powders with the addition of elemental graphite.

^c Tensile strength and tensile yield strength are approximately equal for heat-treated materials.

^b Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,5 % carbon potential, oil quenched and tempered at 180 °C for 1 h.

^d Properties were derived from pressed, sintered and heat treated test pieces (not machined) in accordance with ISO 2740.

^f 90 % fatigue endurance limit in rotating bending tests. Machined test pieces in accordance with ISO 3928.

^g 50 % fatigue endurance limit in 4 point plane bending tests. Non machined test pieces in accordance with ISO 3928.

Table 8 — Ferrous materials for structural parts: pre-alloyed nickel-molybdenum-manganese steels

Parameter	Symbol	Unit	Nickel-molybdenum-manganese steels ^a					
			Grade					
Chemical composition			-FL-05M07N-620H ^{b, c}	-FL-05M07N-830H ^{b, c}	-FL-05M1-940H ^{c, d}	-FL-05M1-1120H ^{c, d}	-FL-05N2M-650H ^{c, e}	-FL-05N2M-860H ^{c, e}
			0,4 to 0,7 0,4 to 0,5 0,55 to 0,85 0,2 to 0,5 Balance 2	0,4 to 0,7 0,4 to 0,5 0,55 to 0,85 0,2 to 0,5 Balance 2	0,4 to 0,7 — 0,75 to 0,95 0,10 to 0,25 Balance 2	0,4 to 0,7 — 0,75 to 0,95 0,10 to 0,25 Balance 2	0,4 to 0,7 1,75 to 1,90 0,50 to 0,85 0,1 to 0,6 Balance 2	0,4 to 0,7 1,75 to 1,90 0,50 to 0,85 0,1 to 0,6 Balance 2
Total other elements max.		%	2	2	2	2	2	2
Tensile yield strength min.	$R_{p0,2}$	MPa	f	f	f	f	f	f
Ultimate tensile strength min.	R_m	MPa	620	830	940	1 120	650	860
Apparent hardness	HV10		340	380	350	380	320	380
	Rockwell		30 HRC	36 HRC	32 HRC	36 HRC	28 HRC	35 HRC
Density	ρ	g/cm ³	6,7	7,0	7,0	7,2	6,7	7,0
Tensile strength ^g	R_m	MPa	690	900	1 020	1 190	720	930
Elongation ^g	A_{25}	%	nm ^h	nm ^h	nm ^h	nm ^h	nm ^h	nm ^h
Young's Modulus		GPa	120	140	140	155	120	140
Poisson's ratio			0,25	0,27	0,27	0,27	0,25	0,27
Unnotched Charpy Impact		J	8	11	10	15	7	12
Compressive yield strength (0,1 %)		MPa	650	970	1 140	1 270	750	1 000
Transverse rupture strength		MPa	1 020	1 280	1 480	1 750	1 100	1 390
Fatigue limit 90 % survival ⁱ		MPa	240	300	310	360	250	330

^a These materials are produced from pre-alloyed powders with the addition of elemental graphite.

^b Pre-alloy base powder with a nominal composition 0,45 % Ni, 0,7 % Mo, 0,35 % Mn, balance Fe.

^c Austenitized for 30 min at 850 °C in a protective atmosphere with a 0,6 % carbon potential, oil quenched and tempered for 1 h at 180 °C.

^d Pre-alloy base powder with a nominal composition 0,85 % Mo, 0,2 % Mn, balance Fe.

^e Pre-alloy base powder with a nominal composition 1,8 % Ni, 0,7 % Mo, 0,3 % Mn, balance Fe.

^f Tensile strength and tensile yield strength are approximately the same for heat-treated materials.

^g As heat treated tensile properties are derived from machined test bars in accordance with ISO 2740.

^h nm = not measurable.

ⁱ 90 % fatigue endurance limit in rotating bending tests. Machined test pieces in accordance with ISO 3928.

Table 9 — Ferrous materials for structural parts: copper or copper alloy infiltrated steels

Parameter		Symbol	Unit	Copper infiltrated steels			
				Grade			
				-FX-08C10-340	-FX-08C10-760H a	-FX-08C20-410	-FX-08C20-620H a
Chemical composition							
C Combined b			%	0,6 to 0,9	0,6 to 0,9	0,6 to 0,9	0,6 to 0,9
Cu			%	8 to 15	8 to 15	15 to 25	15 to 25
Fe			%	Balance	Balance	Balance	Balance
Total other elements max.			%	2	2	2	2
Tensile yield strength min.		R _{p0,2}	MPa	340	c	410	c
Ultimate tensile strength min		R _m	MPa		760		620
Apparent hardness			HV5	210	460 HV 10	210	390 HV 10
Density			Rockwell	89 HRB	43 HRC	90 HRB	36 HRC
			g/cm ³	7,3	7,3	7,3	7,3
Tensile strength		R _m	MPa ^f	600	830	550	690
Tensile yield strength		R _{p0,2}	MPa	410	c	480	c
Elongation		A ₂₅	%	3	nm ^d	1	nm ^d
Young's Modulus e			GPa	160	160	145	145
Poisson's ratio e				0,28	0,28	0,24	0,24
Unnotched Charpy Impact			J	14	9	9	7
Compressive yield strength		(0,1 %)	MPa	490	790	480	510
Transverse rupture strength			MPa	1 140	1 300	1 080	1 100
Fatigue limit 90 % survival f			MPa	230	280	160	190
NOTE All data are based on single pass infiltration.							
a Austenitized at 850 °C for 30 min in a protective atmosphere with a 0,8 % carbon potential, oil quenched and tempered at 180 °C for 1 h.							
b On the basis of iron phase only.							
c Tensile strength and tensile yield strength are approximately equal for heat-treated materials.							
d nm = not measurable.							
e Values derived from ultrasonic resonance testing.							
f 90 % fatigue endurance limit in rotating bending tests. Machined test pieces in accordance with ISO 3928.							

Table 10 — Ferrous materials for structural parts: austenitic, martensitic and ferritic stainless steels

Parameter	Symbol	Unit	Austenitic				Martensitic		Ferritic		
			-FL303-170N a	-FL304-210N a	-FL304-260N b	-FL316-170N a	-FL316-260N b	-FL316-150 c	-FL410-140 e	-FL430-170 e	-FL434-170 e
Type			303	304	304	316	316	316 L	410 L	430 L	434 L
Chemical composition											
Cr		%	17 to 19	18 to 20	18 to 20	16 to 18	16 to 18	16 to 18	11,5 to 13,5	16 to 18	16 to 18
Ni		%	8 to 13	8 to 12	8 to 12	10 to 14	10 to 14	10 to 14	—	—	—
Mo		%	—	—	—	2 to 3	2 to 3	2 to 3	—	—	—
S		%	0,15 to 0,30	—	—	—	—	—	< 0,03	< 0,03	0,75 to 1,25
C		%	< 0,15	< 0,08	< 0,08	< 0,08	< 0,08	< 0,03	< 0,03	< 0,03	< 0,03
N		%	0,2 to 0,6	0,2 to 0,6	0,2 to 0,6	0,2 to 0,6	0,2 to 0,6	< 0,03	< 0,03	< 0,03	< 0,03
Fe		%	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance	Balance
Total other elements max.		%	3	3	3	3	3	3	3	3	3
Tensile yield strength min.	$R_{p0,2}$	MPa	170	210	260	170	260	150	140	170	170
Ultimate tensile strength min.	R_m	MPa									
Apparent hardness		HV5									
Density	ρ	g/cm ³	7,8	7,8	7,8	7,8	7,8	7,8	7,8	7,8	7,8
Tensile strength	R_m	MPa	270	300	480	280	480	390	330	340	340
Tensile yield strength	$R_{p0,2}$	MPa	220	260	310	230	310	210	180	210	210
Elongation	A_{25}	%	nm g	nm g	8	nm g	13	21	16	20	15
Young's Modulus		GPa	105	105	140	105	140	140	165	170	165
Poisson's ratio			0,25	0,25	0,27	0,25	0,27	0,27	0,27	0,27	0,27
Unnotched Charpy Impact		J	5	5	34	7	65	88	68	108	88
Compressive yield strength (0,1 %)		MPa	260	260	320	250	320	220	190	230	230
Transverse rupture strength		MPa	590	nm g	nm g	nm g	nm g	nm g	nm g	nm g	nm g
Fatigue limit 90 % survival h		MPa	90	105	160	75	130	115	125	170	150
NOTE 1 The corrosion properties of sintered stainless steel are not necessarily the same as those of solid stainless steels. In general the austenitic materials can be ranked as type 316L being the best followed by 304 and then 303. These are all better than any of the martensitic or ferritic materials. Type 434 is the best of these materials.											
NOTE 2 Sintering may also affect corrosion resistance so that grade -FL 316-150 may be more resistant than the grades sintered in nitrogen-containing atmospheres.											
NOTE 3 Before using any sintered stainless steel a corrosion test under expected environmental conditions is recommended.											
a Grades -FL303-170N, -FL304-210N and -FL316-170N sintered in a nitrogen-containing atmosphere e.g. dissociated ammonia at 1 150 °C.											
b Grades -FL303-260N, -FL304-260N and -FL316-260N sintered in a nitrogen-containing atmosphere e.g. dissociated ammonia at 1 290 °C.											
c Grade -FL316-150 sintered in a nitrogen-free atmosphere e.g. hydrogen or vacuum backfilled with argon, at 1 290 °C.											
d Grade FL410-620H sintered in a nitrogen-containing atmosphere e.g. dissociated ammonia, at 1 150 °C, hardened by rapid cooling and tempered at 180 °C for 1 h.											
e Grades -FL410-140, -FL430-170 and -FL434-170 sintered in a nitrogen-free atmosphere e.g. hydrogen or vacuum backfilled with argon at 1 290 °C.											
f Tensile strength and tensile yield strength are approximately the same for heat treated materials.											
g nm = not measurable.											
h 90 % fatigue endurance limit in rotating bending tests. Machined test pieces in accordance with ISO 3928.											

Table 11 — Non-ferrous materials for structural parts: copper based alloys

Parameter	Symbol	Unit	Brass				Bronze	Nickel silver
			Grade					
Chemical composition			-CL-Z20-75	-CL-Z20-80	-CL-Z30-100	-CL-Z30-110	-C-T10-90R ^a	-CL-N18Z-120
Sn		%	— Balance	— Balance	— Balance	— Balance	8,5 to 11,0 —	— Balance
Zn		%	—	—	—	—	—	16 to 20
Ni		%	—	—	—	—	—	62 to 66
Cu		%	77 to 80 2	77 to 80 2	68 to 72 2	68 to 72 2	Balance 2	2
Total other element max.		%	2	2	2	2	2	2
Tensile yield strength	$R_{p0,2}$	MPa	75	80	100	110	90	120
Apparent hardness		HV5	50	68	72	84	68	82
		Rockwell	73 HRH	82 HRH	84 HRH	92 HRH	82 HRH	90 HRH
Density	ρ	g/cm ³	7,6	8,0	7,6	8,0	7,2	7,9
Tensile strength	R_m	MPa	160	240	190	230	150	230
Tensile yield strength	$R_{p0,2}$	MPa	90	120	110	130	110	140
Elongation	A_{25}	%	9	18	14	17	4	11
Young's Modulus		GPa	85	100	80	90	60	95
Poisson's ratio (compression)			0,31	0,31	0,31	0,31	0,31	0,31
Unnotched Charpy Impact		J	37	61	31	52	5	33
Compressive yield strength	(0,1 %)	MPa	80	100	120	130	140	170
Transverse rupture strength		MPa	360	480	430	590	310	500
a The letter R indicates that the material has been repressed.								

Annex A (normative)

Designation system

A.1 Designation of materials

The designation system to be used for sintered metal materials specified in this International Standard is in accordance with ISO/IEC Directives Part 2:1992.

A.2 Description block

The description block shall contain the letter P, denoting powder metallurgical materials.

A.3 Identity block

The identity block shall contain the number of this International Standard, ISO 5755, followed by the individual item block.

A.4 Individual item block

A.4.1 First group

The first group of the individual item block shall consist of one to three capital letters, describing the base metal and ways of adding alloying elements:

- F = Plain iron powder or iron powder with admixed alloying additives
- FD = Iron powder with diffusion-alloyed additives
- FL = Pre-alloyed steel powder
- FX = Copper-infiltrated steel
- C = Copper powder with admixed alloying additives
- CL = Pre-alloyed copper-base powder
- FLD = Pre-alloyed steel powder with diffusion-alloyed additives (this will be used in future revisions)
- FLA = Pre-alloyed steel powder with admixed alloying additives (this will be used in future revisions)