



INTERNATIONAL STANDARD ISO 5794-1:2005
TECHNICAL CORRIGENDUM 2

Published 2007-05-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Rubber compounding ingredients — Silica, precipitated, hydrated —

Part 1: Non-rubber tests

TECHNICAL CORRIGENDUM 2

Ingrédients de mélange du caoutchouc — Silices hydratées précipitées —

Partie 1: Essais sur le produit brut

RECTIFICATIF TECHNIQUE 2

Technical Corrigendum 2 to ISO 5794-1:2005 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

Page 25

Replace G.6.3.3 and G.6.3.4 by the following text:

G.6.3.3 Separation using a syringe

G.6.3.3.1 Fill a suitable syringe with 20 cm³ of the silica suspension.

G.6.3.3.2 Fix the filter to the syringe and push the test portion through the filter.

G.6.3.3.3 Take a portion of the filtrate for titration (see G.6.4).