
International Standard



6274

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Concrete — Sieve analysis of aggregates

Béton — Analyse par tamisage des granulats

First edition — 1982-06-01

STANDARDSISO.COM : Click to view the full PDF of ISO 6274:1982

UDC 691.322 : 620.168.32

Ref. No. ISO 6274-1982 (E)

Descriptors : concretes, aggregates, sieves, sieve analysis, openings, dimensions.

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards institutes (ISO member bodies). The work of developing International Standards is carried out through ISO technical committees. Every member body interested in a subject for which a technical committee has been set up has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work.

Draft International Standards adopted by the technical committees are circulated to the member bodies for approval before their acceptance as International Standards by the ISO Council.

International Standard ISO 6274 was developed by Technical Committee ISO/TC 71, *Concrete, reinforced concrete and pre-stressed concrete*, and was circulated to the member bodies in August 1978.

It has been approved by the member bodies of the following countries :

Australia	Germany, F. R.	Poland
Austria	India	Romania
Bulgaria	Israel	South Africa, Rep. of
Canada	Italy	Spain
Chile	Korea, Rep. of	Sweden
China	Mexico	Switzerland
Czechoslovakia	Netherlands	USA
Denmark	New Zealand	USSR
Egypt, Arab Rep. of	Norway	Yugoslavia

The member bodies of the following countries expressed disapproval of the document on technical grounds :

Belgium
France
United Kingdom

Concrete — Sieve analysis of aggregates

1 Scope and field of application

This International Standard specifies a method, using test sieves, for the determination of the particle size distribution of normal weight aggregates for concrete.

Any additional sizes shall be chosen from ISO 565.

For aperture size of 4,00 mm and above, perforated plate sieves are recommended.

2 References

ISO 565, *Test sieves — Woven metal wire cloth and perforated plate — Nominal size of apertures.*

ISO 2395, *Test sieves and test sieving — Vocabulary.*

ISO 2591, *Test sieving.*

ISO 3310/1, *Test sieves — Technical requirements and testing — Part 1 : Test sieves of metal wire cloth.*

ISO 3310/2, *Test sieves — Technical requirements and testing — Part 2 : Test sieves of metal perforated plate.*

ISO 4847, *Concrete — Sampling of normal weight aggregates.*¹⁾

3 Sampling

The sample shall be taken and reduced in accordance with ISO 4847.

4 Apparatus

4.1 Balance or scale, accurate to 0,1 % of the total mass of the test sample.²⁾

4.2 Test sieves, with square apertures, complying with the requirements of ISO 565, ISO 2591 and ISO 3310. The sieves used shall conform to one of the series given in the table, series A being recommended.

Table — Test sieve aperture sizes

Values in millimetres

Series A	Series B	Series C
63,0	75,0	80,0
31,5	37,5	40,0
16,0	19,0	20,0
8,00	9,50	10,0
4,00	4,75	5,00
2,00	2,36	2,50
1,00	1,18	1,25
0,500	0,600	0,630
0,250	0,300	0,315
0,125	0,150	0,160
0,063	0,075	0,080

4.3 Tightly fitting pan and lid, for the sieves.

4.4 Well ventilated oven, thermostatically controlled to maintain a temperature of 105 ± 5 °C.³⁾

5 Procedure

5.1 Preparation of test sample

The minimum dry-mass of the test sample, in kilograms, shall be 0,2 times the nominal maximum aggregate size, in millimetres. Aggregates containing substantial amounts of fine particles may be moistened before reduction to minimize segregation and loss of dust. Reduction shall be carried out by use of a sample divider or by quartering, and shall yield a test sample of mass larger than the minimum but not of an exact predetermined value. Before weighing and sieving, the

1) At present at the stage of draft.

2) For field applications, a reduced accuracy of 0,5 % of the sample mass is considered sufficient.

3) If such an oven is not available under field conditions, other suitable equipment for drying the aggregates to constant mass may be used.