
**Micrographics — Aperture cards —
Method of measuring thickness of buildup
area**

*Micrographie — Cartes à fenêtre — Méthode de mesurage de la zone
de surépaisseur*



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 6342:2003

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 6342 was prepared by Technical Committee ISO/TC 171, *Document imaging applications*, Subcommittee SC 2, *Application issues*.

This second edition cancels and replaces the first edition (ISO 6342:1993), which has been technically revised.

Introduction

Aperture cards are widely used in many microfilm systems. As the various kinds differ in the thickness of the buildup area, a method of measuring the buildup thickness is necessary.

STANDARDSISO.COM : Click to view the full PDF of ISO 6342:2003

Micrographics — Aperture cards — Method of measuring thickness of buildup area

1 Scope

This International Standard specifies a method of measuring the thickness of the buildup area on aperture cards (camera and copy cards) for manufacturing and inspection purposes.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 534:1988, *Paper and board — Determination of thickness and apparent bulk density or apparent sheet density*

ISO 6196-1:1993, *Micrographics — Vocabulary — Part 1: General terms*

ISO 6196-4:1998, *Micrographics — Vocabulary — Part 4: Materials and packaging*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6196-1 and ISO 6196-4 apply.

4 Apparatus

4.1 Dial micrometers, of the dead-weight type, either motor- or manually operated. The motor-operated micrometer is preferred. The lowering speed shall be approximately 0,8 mm/s. The movable face or pressure foot shall be circular with a diameter of 16 mm $\pm$ 0,5 mm. The fixed face or anvil shall be of a size that allows the whole area of the pressure foot to be in contact with the anvil in the zero position. The pressure foot shall move on an axis perpendicular to the anvil. The pressure foot shall exert a steady pressure on the test sample of 50 kPa $\pm$ 5 kPa, based on the area of the pressure foot.

Values of micrometer characteristics are given in Table 1, in accordance with ISO 534:1988, Table 2.

Table 1 — Micrometer values

Micrometer characteristic	Maximum permitted value
Indication error	2,5 μ or 0,5 %
Error of parallelism between pressure faces	5 μ or 1 %
Repeatability of measurement (as a standard deviation)	2,5 μ or 0,5 %
NOTE 1 The maximum permitted value of a micrometer characteristic is the greater of the two values quoted for it in this table.	
NOTE 2 Where a tolerance is expressed in the form of a percentage, it is based upon the thickness of the test piece under test. Thus, it is possible for a given micrometer to comply with the requirements of this table for some materials, but not for others.	

5 Conditioning and testing atmosphere

All test samples shall be conditioned, loosely assembled, for at least 6 h before testing. Samples shall be conditioned and tested at a temperature of $23^{\circ}\text{C} \pm 1^{\circ}\text{C}$ and a relative humidity of $(50 \pm 2) \%$.

6 Measurement

6.1 General


If a manually operated micrometer is used, the pressure foot shall either be lowered to within 0,007 5 mm of the surface of the test sample and then released, or be lowered onto the surface at a velocity less than 12 mm/s, but not less than 0,8 mm/s, specified for the motor-operated micrometer. The pressure foot shall maintain the dead-weight loading for at least 2 s. All measurements shall be made on the same card.

6.2 Card thickness

Make at least four measurements at separate places with the pressure foot at least 6,35 mm away from the edges of the card and the buildup area. The greatest of these measurements shall be taken as the thickness of the card.

6.3 Buildup-area thickness

Make at least four measurements, one on each side of the buildup-area rectangle, as illustrated in Figure 1.



Key

- 1 outside perimeter of buildup area
- 2 inside perimeter of buildup area

Figure 1 — Pressure-foot position for measuring buildup-area thickness

The pressure foot shall be centred across the width of the buildup area (see Annex A). The greatest of these measurements shall be taken as the thickness of the buildup area.

6.4 Buildup thickness

The buildup thickness of the aperture card shall be taken as the difference between the thickness of the buildup area, as measured in 6.3, and the thickness of the card of the same test sample, as measured in 6.2.