
**Internal combustion engines —
Piston rings —**

**Part 4:
Half keystone rings made of steel**

Moteurs à combustion interne — Segments de piston —

Partie 4: Segments semi-trapézoïdaux en acier



STANDARDSISO.COM : Click to view the full PDF of ISO 6624-4:2016



COPYRIGHT PROTECTED DOCUMENT

© ISO 2016, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Overview	1
4 Ring types and designation examples	1
4.1 Type HK — Straight faced half keystone ring 7°	1
4.1.1 General features	1
4.1.2 Designation	2
4.2 Type HKB — Barrel faced half keystone ring 7°	2
4.2.1 General features	2
4.2.2 Designation	4
4.3 Type HKBA — Asymmetrical Barrel faced half keystone ring 7° (not recommended for nitrided rings of code NT)	4
4.3.1 General features	4
4.3.2 Designation	6
5 Common features	6
5.1 Type HK, HKB and HKBA — Half keystone rings	6
5.1.1 Nitrided rings (not recommended for HKBA rings with Nitrided code NT)	6
5.1.2 PVD rings	6
5.1.3 Chromium plated or spray coated rings	7
5.2 Type HK, HKB and HKBA rings — Outside and inside rounded edges	7
5.3 Type HK, HKB and HKBA rings (fully faced and inlaid) — Plating/coating thickness	8
5.4 Type HK, HKB and HKBA rings — Nitrided case depth	9
6 Force factors	10
7 Dimensions and forces	10
Annex A (normative) Calculation of measurement width h_3 of half keystone rings	19
Bibliography	20

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

The committee responsible for this document is ISO/TC 22, *Road vehicles*, Subcommittee SC 34, *Propulsion, powertrain and powertrain fluids*.

This second edition cancels and replaces the first edition (ISO 6624-4:2003), which has been technically revised.

ISO 6624 consists of the following parts, under the general title *Internal combustion engines — Piston rings*:

- *Part 1: Keystone rings made of cast iron*
- *Part 2: Half keystone rings made of cast iron*
- *Part 3: Keystone rings made of steel*
- *Part 4: Half keystone rings made of steel*

Introduction

ISO 6624 is one of a number of series of International Standards dealing with piston rings for reciprocating internal combustion engines. Others are ISO 6621,^{[2][3][4][5]} ISO 6622,^{[6][7]} ISO 6623,^[8] ISO 6625,^[9] ISO 6626,^{[10][11][12]} and ISO 6627.^[13]

STANDARDSISO.COM : Click to view the full PDF of ISO 6624-4:2016

STANDARDSISO.COM : Click to view the full PDF of ISO 6624-4:2016

Internal combustion engines — Piston rings —

Part 4: Half keystone rings made of steel

1 Scope

This part of ISO 6624 specifies the essential dimensional features of half keystone rings made of steel, types HK, HKB and HKBA, having nominal diameters from 50 mm up to, and including, 160 mm, used in reciprocating internal combustion piston engines for road vehicles and other applications.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6621-4, *Internal combustion engines — Piston rings — Part 4: General specifications*

3 Overview

The half keystone ring types are specified in [Tables 1](#) and [2](#) and [Figures 1](#), [2](#) and [3](#). Their common features and the dimensions of those features are specified in [Tables 3](#) to [6](#) and [Figures 4](#) to [10](#). [Table 7](#) gives the force factors for the different ring types, while [Table 8](#) gives the dimensions and forces of half keystone rings.

The common features and dimensional tables presented in this part of ISO 6624 constitute a broad range of variables and, in selecting a particular ring type, the designer shall bear in mind the conditions under which it will be required to operate.

It is also essential that the designer refer to the specifications and requirements of ISO 6621-3^[4] and ISO 6621-4 before completing selection.

4 Ring types and designation examples

NOTE For the angle of half keystone rings, the same definition and measurement apply as for keystone rings (see ISO 6621-2).


4.1 Type HK — Straight faced half keystone ring 7°

4.1.1 General features

[Figure 1](#) shows the general features of piston ring type HK.

See [Table 7](#) for dimensions and forces.

h_3 values are calculated based on [Annex A](#).



Key

- 1 reference plane (ring is positioned flat against datum A)
- 2 top side identification mark
- a Nominal.
- b $t = 0,006 \times h_1$.

Figure 1 — Type HK

4.1.2 Designation

EXAMPLE Designation of a piston ring complying with the requirements of ISO 6624-4, being a 7° half keystone ring made of steel with a straight faced peripheral surface (HK), of nominal diameter $d_1 = 60$ mm (60), of nominal ring width $h_1 = 1,2$ mm (1,2), made of CrSi alloyed steel subclass 62 (MC62), and having a chromium plated peripheral surface with a minimum thickness of 0,1 mm (CR2). Parameters in parenthesis are used in the ISO ring designation:

Piston ring ISO 6624-4 HK - 60 × 1,2 - MC62/CR2


4.2 Type HKB — Barrel faced half keystone ring 7°

4.2.1 General features

[Figure 2](#) shows the general features of piston ring type HKB.

See [Table 7](#) for dimensions and forces.

h_3 values are calculated based on [Annex A](#).



Key

- 1 reference plane (ring is positioned flat against datum A)
- 2 top side identification mark
- a Nominal.

Figure 2 — Type HKB

Table 1 — Symmetrical barrel dimensions and gauge width (h_8)

Dimensions in millimetres

h_1	h_{25}	h_{26}	h_{26} tol.	h_{27}	t_2, t_3	h_8^a
1,2	0,30	0,60	$\pm 0,20$	0,90	0,002...0,012	0,60
1,5	0,35	0,75	$\pm 0,25$	1,15	0,003...0,015	0,80
1,75	0,35	0,85	$\pm 0,30$	1,35		1,00
2,0	0,40	1,00	$\pm 0,30$	1,60		1,20
2,5	0,45	1,25	$\pm 0,40$	2,05		1,60
3,0	0,50	1,50	$\pm 0,50$	2,50	0,005...0,020	2,00
3,5	0,55	1,75	$\pm 0,50$	2,95		2,40

^a Gauge width (h_8) only informative; may be used only if agreed between manufacturer and customer.

4.2.2 Designation

EXAMPLE Designation of a piston ring complying with the requirements of ISO 6624-4, being a half keystone ring made of steel with a barrel faced peripheral surface (HKB), of nominal diameter $d_1 = 60$ mm (60), of nominal ring width $h_1 = 1,5$ mm (1,5), made of martensitic steel 11 %Cr (min.) subclass 65 (MC65), and nitrided on the peripheral surface and side faces (NT) to a depth of 0,050 mm min. on the peripheral surface (050), with an associated side face depth of 0,015 mm min. Parameters in parenthesis are used in the ISO ring designation:

Piston ring ISO 6624-4 HKB - 60 × 1,5 - MC65/NT050

4.3 Type HKBA — Asymmetrical Barrel faced half keystone ring 7° (not recommended for nitrided rings of code NT)

4.3.1 General features

See [Table 7](#) for dimensions and forces.

h_3 values are calculated based on [Annex A](#).

1 reference plane (ring is positioned flat against datum A)
2 top side identification mark
a Nominal.

Table 2 — Asymmetrical barrel dimensions

Dimensions in millimetres

h_1	h_{25}^a	h_{26}	$h_{26} \text{ tol.}$	h_{27}	t_2^b	t_3^b
1,75	0,35	0,55	$\pm 0,20$	1,35	0...0,007	0,008...0,025
2,0	0,40	0,60		1,50		0,009...0,030
2,5	0,45	0,70	$\pm 0,25$	1,80	0...0,008	0,011...0,035
3,0	0,55	0,80		2,10		0,012...0,038
3,5	0,60	0,90	$\pm 0,30$	2,40	0...0,009	0,012...0,040

^a h_{25} may be lowered for rings with reduced edge dimensions.

^b t_2 and/or t_3 may be varied as agreed between manufacturer and customer.

4.3.2 Designation

EXAMPLE Designation of a piston ring complying with the requirements of ISO 6624-4, being a half keystone ring made of steel with an asymmetrical barrel faced peripheral surface (HKBA), of nominal diameter $d_1 = 80$ mm (80), of nominal ring width $h_1 = 2,0$ mm (2,0), made of martensitic steel 11 %Cr min. subclass 65 (MC65), and PVD on the peripheral surface (PC) to a depth of 0,010 mm min. on the peripheral surface (010). Parameters in parenthesis are used in the ISO ring designation:

Piston ring ISO 6624-4 HKBA - 80 × 2,0 - MC65/PC010

5 Common features

5.1 Type HK, HKB and HKBA — Half keystone rings

5.1.1 Nitrided rings (not recommended for HKBA rings with Nitrided code NT)



Key

1 top side identification mark

Figure 4 — Nitrided rings

5.1.2 PVD rings




Key

1 top side identification mark

Figure 5 — PVD rings

5.1.3 Chromium plated or spray coated rings

5.1.3.1 Fully faced




Key

1 top side identification mark

Figure 6 — Fully faced rings

5.1.3.2 Inlaid (not recommended for chromium plated rings)



Key

1 top side identification mark

Figure 7 — Inlaid rings

5.2 Type HK, HKB and HKBA rings — Outside and inside rounded edges




Figure 8 — Outside and inside rounded edges

Table 3 — h_x and h_y dimensions

Dimensions in millimetres

h_1	h_x max.	h_y max.
1,2	0,25	0,3
1,5	0,3	0,35
1,75		
2,0	0,3	0,4
2,5		
3,0		
3,5		

5.3 Type HK, HKB and HKBA rings (fully faced and inlaid) — Plating/coating thickness**Figure 9 — Plating/coating thickness****Table 4 — Chromium plating/spray coating thickness**

Dimensions in millimetres

Chromium plating code	Spray coating code	Thickness min.
CRF	—	0,005
CR1	SC1	0,05
CR2	SC2	0,10
CR3 ^a	SC3 ^a	0,15
CR4 ^a	SC4 ^a	0,20

^a Not recommended for rings $h_1 \leq 1,5$.

Table 5 — PVD coating thickness

Dimensions in millimetres


Code	Peripheral surface min.
PC001	0,001
PC003	0,003
PC005	0,005

^a not typical for Diamond Like Carbon coatings (DLC)

Table 5 (continued)

Code	Peripheral surface min.
PC010 ^a	0,010
PC020 ^a	0,020
PC030 ^a	0,030
PC040 ^a	0,040
PC050 ^a	0,050
^a not typical for Diamond Like Carbon coatings (DLC)	

5.4 Type HK, HKB and HKBA rings — Nitrided case depth



Key

1 top side identification mark

Figure 10 — Nitrided case depth

Table 6 — Nitrided case depth of peripheral surface and bottom side face

Dimensions in millimetres

Code	Nitrided case depth min.	
	Peripheral surface	Bottom side face
NB030	0,03	0,010
NB050	0,05	0,015
NB070	0,07	0,020
NB090	0,09	0,020
NB110	0,11	0,030
NB130	0,13	0,030
NOTE Nitrided case depth on top side face and on inside surface not specified.		

Table 7 — Nitrided case depth of peripheral surface and side faces (not recommended for HKBA rings)

Dimensions in millimetres

Code	Nitrided case depth min.	
	Peripheral surface	Side faces
NT030	0,03	0,010
NT050	0,05	0,015
NT070	0,07	0,020
NT090	0,09	0,020
NT110	0,11	0,030
NOTE Nitrided case depth on inside surface not specified.		

Table 7 (continued)

Code	Nitrided case depth min.	
	Peripheral surface	Side faces
NT130	0,13	0,030
NOTE Nitrided case depth on inside surface not specified.		

6 Force factors

The tangential and diametral forces given in [Table 9](#) shall be corrected when additional features are being used.

For common features, multiplier correction factors given in [Table 8](#) shall be used. The force correction factors for the ratio $m/(d_1 - a_1)$, specified in ISO 6621-4, shall be used.

Table 8 — Force correction factors for chromium plated, spray coated, PVD coated and nitrided HK, HKB and HKBA rings

d_1 mm	Factor						
	CRF / PC001 ... PC030	CR1 / PC040	CR2/SC1	CR3/SC2	CR4/SC3	SC4	NB030...NB130 NT030...NT130
$50 \leq d_1 < 75$	1	0,87	0,81	0,75	0,69	0,64	1,03
$75 \leq d_1 < 100$	1	0,91	0,86	0,82	0,78	0,74	1,03
$100 \leq d_1 < 125$	1	0,93	0,89	0,86	0,82	0,79	1,03
$125 \leq d_1 \leq 160$	1	0,94	0,91	0,89	0,86	0,83	1,03

7 Dimensions and forces

See [Table 9](#).

Table 9 — Dimensions and forces of HK, HKB and HKBA half keystone

Dimensions in millimetres

Nominal diameter d_1	Radial wall thickness a_1	Nominal value of ring width h_1						a_6 Ref.	a_7	Method A							Method B						Measured value ^b a_6		
										Measured value, h_3^{ab} For h_1 shown in column						h_3 (ref.) Column									
		Column								1	2	3	4	5	6	Tol.	1	2	3	4	5	6		Tolerance	
		Tolerance	1	2	3	4	5			6	1	2	3	4	5	6	Tol.	1	2	3	4	5		6	Tolerance
50	1,7																								
51																									
52																									
53	1,9																								
54									0,5 max.	1,118	1,418						1,11	1,41						1,10	
55																									
56																									
57																									
58																									
59	2,1	±0,15 Within a ring: 0,15 max.			—	—		1,0											—	—					+0,08/ -0,19 For phosphated PO surface
60			1,2	1,5			—	—																	0/-0,19
61																									
62																									
63																									
64																									
65	2,3								0,6 max.	1,116	1,416							1,10	1,40						1,09
66																									
67																									
68																									
69																									
70																									
71	2,5																								
72					1,75	2,0		1,5	0,7 max.	1,053	1,353	1,603	1,853				1,04	1,34	1,59	1,84				1,60	
73																									

Table 9 — (continued)

Closed gap		Tangential force							Diametral force							Nominal diameter
s_1	Tolerance	F_t N For h_1 shown in column						Tol.	F_d N For h_1 shown in column						Tolerance	d_1
		1	2	3	4	5	6		1	2	3	4	5	6		
0,15		4,2	5,3						9,0	11,4						50
		4,8	6,1						10,3	13,1						51
		4,8	6,1						10,3	13,1						52
		4,7	6,0						10,1	12,9						53
		4,7	6,0			—	—		10,1	12,9						54
		4,7	6,0						10,1	12,9			—			55
		4,6	5,9						9,9	12,7						56
		5,3	6,8						11,4	14,6						57
		5,2	6,7						11,2	14,4						58
		5,2	6,6						11,2	14,2						59
0,2	+0,2 0	5,1	6,5	—	—			±30 % if $F_t < 10$ N	11,0	14,0		—			±30 % if $F_d < 21,$ 5 N	60
		5,0	6,4						10,8	13,8						61
		5,7	7,3						12,3	15,7						62
		5,6	7,2					±20 % if $F_t \geq 10$ N	12,0	15,5					±20 % if $F_d \geq 21,5$ N	63
		5,6	7,2						12,0	15,5						64
		5,5	7,1						11,8	15,3						65
		5,5	7,0						11,8	15,1						66
		5,4	6,9						11,6	14,8						67
		6,2	7,9						13,3	17,0						68
		6,1	7,8						13,1	16,8						69
		6,0	7,7	9,2	10,6				12,9	16,6	19,8	22,8				70
		6,0	7,7	9,1	10,5				12,9	16,6	19,6	22,5				71
		5,9	7,6	9,0	10,4				12,7	16,3	19,4	22,3				72
		5,8	7,5	8,9	10,2				12,5	16,1	19,1	22,0				73

Table 9 — (continued)

Nominal diameter meter	Radial wall thickness	Nominal value of ring width						a_6 Ref.	a_7	Method A							Method B						Measured value ^b a_6	
		Tolerance	h_1							Measured value, h_3^{ab}							h_3 (ref.)							
			Column							For h_1 shown in column							Column							
			1	2	3	4	5			6	1	2	3	4	5	6	Tol.	1	2	3	4	5		6
74	2,7																							
75																								
76																								
77																								
78																								
79	2,9																							
80																								
81																								
82		1,2	1,5	1,75	2,0		—	1,5		1,053	1,353	1,603	1,853				1,04	1,34	1,59	1,84			1,60	
83																								
84	3,1																							
85																								
86																								
87		±0,15					—						—											
88		Within a ring:																						
89	0,15 max.																							
90	3,3																							
91																								
92									0,7 max.					—										
93																								
94		1,5								1,289							1,28							
95	3,5																							
96																								
97																								
98																								
99																								
100	3,7		1,75	2,0	2,5			2,0			1,539	1,789	2,289				1,53	1,78	2,28			2,07		
101																								
102		±0,20																						
103		Within a ring:																						
104		0,20 max.																						
105	3,9	—				3,0				—			2,789				—			2,78				
106																								
107																								
108																								
109																								

Table 9 — (continued)

Closed gap		Tangential force							Diametral force							Nominal diameter		
s_1	Tolerance	F_t N						Tolerance	F_d N						Tolerance	d_1		
		For h_1 shown in column							For h_1 shown in column									
		1	2	3	4	5	6		1	2	3	4	5	6				
0,2	+0,2 0	6,6	8,5	10,1	11,7	—	—	—	14,2	18,3	21,7	25,1	—	—	—	74		
0,25		6,5	8,4	9,9	11,5				14,0	18,1	21,3	24,7				75		
		6,4	8,2	9,8	11,3				13,8	17,6	21,1	24,2				76		
		6,3	8,1	9,6	11,1				13,5	17,4	20,6	23,8				77		
		6,1	7,9	9,4	10,9				13,1	17,0	20,2	23,3				78		
		7,0	9,0	10,7	12,4				15,1	19,4	23,0	26,6				79		
		6,9	8,9	10,6	12,2				14,8	19,1	22,8	26,2				80		
		6,8	8,8	10,4	12,1				14,6	18,9	22,4	26,0				81		
		6,7	8,7	10,3	11,9				14,4	18,7	22,1	25,6				82		
		6,6	8,6	10,2	11,8				14,2	18,5	21,9	25,4				83		
		6,5	8,4	10,0	11,6				14,0	18,1	21,5	24,9				84		
		7,4	9,6	11,4	13,2				15,9	20,6	24,5	28,4				85		
		7,3	9,5	11,3	13,0				15,7	20,4	24,3	28,0				86		
		7,2	9,3	11,1	12,9				15,5	20,0	23,9	27,7				87		
		7,1	9,2	11,0	12,7				15,3	19,8	23,7	27,3				88		
		7,0	9,1	10,8	12,5				15,1	19,6	23,2	26,9				89		
0,3	+0,25 0	9,0	10,6	12,3	15,7	—	—	±30 % if $F_t < 10$ N ±20 % if $F_t \geq 10$ N	19,2	22,8	26,4	33,8	—	—	±30 % if $F_d < 21,5$ N ±20 % if $F_d \geq 21,5$ N	90		
		10,1	12,1	14,0	17,9				21,8	26,0	30,1	38,5				91		
		10,0	11,9	13,8	17,6				21,4	25,6	29,7	37,8				92		
		9,8	11,6	13,5	17,2				21,0	24,9	29,0	37,0				93		
		9,6	11,4	13,2	16,9				20,5	24,5	24,5	36,3				94		
		9,3	11,1	12,9	16,5				20,1	23,9	27,7	35,5				95		
		10,6	12,6	14,7	18,8				22,8	27,1	31,6	40,4				96		
		10,4	12,5	14,5	18,5				22,5	26,9	31,2	39,9				97		
		10,3	12,3	14,3	18,3				22,1	26,4	30,7	39,3				98		
		10,2	12,1	14,1	18,0				21,8	26,0	30,3	38,7				99		
		—	17,7	13,9	17,7				21,6	—	38,1	29,8				38,1	46,4	100
			17,4	13,6	17,4				21,2		37,5	29,3				37,5	45,7	101
			19,8	15,5	19,8				24,2		42,7	33,3				42,7	52,0	102
			19,6	15,3	19,6				23,9		42,1	32,8				42,1	51,3	103
			19,3	15,1	19,3				23,5		41,5	32,4				41,5	50,5	104
19,0	14,8		19,0	23,1	40,8	31,9	40,8	49,8	105									
18,7	14,6		18,7	22,8	40,2	31,4	40,2	49,0	106									
18,4	14,3		18,4	22,4	39,5	30,8	39,5	48,1	107									
20,9	16,3		20,9	25,5	44,9	35,0	44,9	54,8	108									
20,5	15,9	20,5	25,0	44,0	34,3	44,0	53,7	109										

Table 9 — (continued)

d_1	Radial wall thickness a_1	Nominal value of ring width h_1						a_6 Ref.	a_7	Method A Measured value, $h_3^{a, b}$							Method B h_3 (ref.)						Measured value ^b a_6	
		Tolerance	Column							For h_1 shown in column							Column							
			1	2	3	4	5			6	1	2	3	4	5	6	Tol.	1	2	3	4	5		6
110	3,9	$\pm 0,20$ Within a ring: 0,20 max.	—	—	2,0	2,5	3,0	3,5	2,0	0,7 max.	—	—	2,289	2,789	—	0/-0,029 For phosphated PO surface: +0,01/ -0,029	—	—	2,28	2,78	3,28	2,07	0/-0,23 For phosphated PO surface: +0,08/ -0,23	
111																								
112																								
113																								
114																								
115																								
116																								
117																								
118																								
119																								
120																								
121																								
122																								
123																								
124																								
125	4,5	0,20 max.	—	—	2,0	2,5	3,0	3,5	2,0	0,7 max.	—	—	2,289	2,789	—	0/-0,029 For phosphated PO surface: +0,01/ -0,029	—	—	2,28	2,78	3,28	2,07	0/-0,23 For phosphated PO surface: +0,08/ -0,23	
126																								
127																								
128																								
129																								
130																								
131																								
132																								
133																								
134																								
135																								
136																								
137																								
138																								
139																								
140																								
141																								
142																								
143																								
144																								
145																								

Table 9 — (continued)

Closed gap		Tangential force							Diametral force							Nominal diameter d_1
s_1	Tolerance	F_t N						Tolerance	F_d N						Tolerance	
		For h_1 shown in column							For h_1 shown in column							
		1	2	3	4	5	6		1	2	3	4	5	6		
0,35	$+0,25$ 0	—	—	19,1	19,6	20,0	20,3		—	—	41,0	42,2	43,0	43,6	$\pm 30\%$ if $F_d < 21,5$ N $\pm 20\%$ if $F_d \geq 21,5$ N	110
				18,6	19,2	19,6	19,8				40,1	41,3	42,0	42,6		111
				18,2	18,7	19,1	19,3				39,1	40,3	41,1	41,6		112
				20,6	21,3	21,7	22,0				44,4	45,8	46,7	47,4		113
				20,3	21,0	21,4	21,7				43,7	45,1	46,0	46,7		114
				20,0	20,7	21,1	21,4				43,0	44,4	45,3	45,9		115
				19,7	20,3	20,7	21,0				42,3	43,7	44,6	45,2		116
				19,4	20,0	20,4	20,7				41,6	42,9	43,8	44,4		117
				19,0	19,6	20,0	20,3				40,9	42,2	43,0	43,6		118
				21,6	22,3	22,8	23,1				46,4	47,9	49,0	49,7		119
				21,2	22,0	22,4	22,8				45,7	47,2	48,2	48,9		120
				20,9	21,6	22,1	22,4				44,9	46,4	47,4	48,1		121
				20,6	21,2	21,7	22,0				44,2	45,7	46,6	47,3		122
				20,2	20,9	21,3	21,6				43,4	44,9	45,8	46,5		123
				19,8	20,5	20,9	21,2				42,6	44,1	45,0	45,7		124
				22,5	23,3	23,8	24,2				48,3	50,0	51,2	52,0		125
				22,0	22,8	23,3	23,6				47,3	49,0	50,1	50,8		126
				21,5	22,3	22,8	23,1				46,2	47,9	48,9	49,7		127
				21,0	21,7	22,2	22,6				45,1	46,7	47,8	48,5		128
				20,5	21,2	21,7	22,0				44,0	45,6	46,6	47,3		129
0,4		—	—	24,1	24,6	25,0		—	—	—	51,7	52,9	53,8		130	
				23,7	24,2	24,6					50,9	52,0	53,0		131	
				23,3	23,8	24,2					50,0	51,2	52,1		132	
				22,9	23,4	23,8					49,2	50,3	51,2		133	
				22,5	23,0	23,4					48,3	49,5	50,3		134	
				22,0	22,6	22,9					47,4	48,6	49,3		135	
				25,0	25,6	26,1					53,8	55,0	56,1		136	
				24,6	25,2	25,7					52,9	54,2	55,2		137	
				24,2	24,8	25,2					52,0	53,3	54,2		138	
				23,8	24,4	24,8					51,1	52,5	53,3		139	
				23,3	23,9	24,3					50,1	51,4	52,3		140	
				22,9	23,5	23,9					49,2	50,5	51,3		141	
				25,9	26,6	27,1					55,8	57,2	58,3		142	
				25,5	26,2	26,7					54,9	56,3	57,3		143	
				25,1	25,7	26,2					53,9	55,3	56,3		144	
				24,6	25,3	25,7					52,9	54,4	55,3		145	