
**Solid mineral fuels — Coke —
Determination of moisture in the general
analysis test sample**

*Combustibles minéraux solides — Coke — Détermination de l'humidité
de l'échantillon pour analyse*

STANDARDSISO.COM : Click to view the full PDF of ISO 687:2010



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

STANDARDSISO.COM : Click to view the full PDF of ISO 687:2010



COPYRIGHT PROTECTED DOCUMENT

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Definitions	1
4 Principle.....	1
5 Apparatus	1
6 Preparation of the test sample	2
7 Procedure	2
8 Expression of results	2
9 Precision.....	3
10 Test report.....	3

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 687 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This third edition cancels and replaces the second edition (ISO 687:2004), of which it constitutes a minor revision.

Introduction

The determination of the moisture in the general analysis test sample is required to correct the results of certain analytical determinations, e.g. volatile matter and hydrogen, for the effect of water in the determination and to allow all determinations to be corrected to a dry basis.

Since coke is hygroscopic, its moisture varies with a change in humidity of the atmosphere, and it is required, therefore, that the moisture in the general analysis test sample be determined whenever portions are weighed out for other analytical determinations. If test portions for several analytical determinations are weighed out at the same time, a single simultaneous moisture determination suffices to correct these analyses.

STANDARDSISO.COM : Click to view the full PDF of ISO 687:2010

STANDARDSISO.COM : Click to view the full PDF of ISO 687:2010

Solid mineral fuels — Coke — Determination of moisture in the general analysis test sample

1 Scope

This International Standard specifies a method for determining the moisture in the general analysis test sample of coke. It can be used for the determination of moisture in blast-furnace coke, foundry-coke and other high-temperature carbonization products.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1213-2, *Solid mineral fuels — Vocabulary — Part 2: Terms relating to sampling, testing and analysis*

3 Definitions

For the purposes of this International Standard, the definitions given in ISO 1213-2 apply.

4 Principle

A known mass of the coke is heated in air at 120 °C to 200 °C and maintained at this temperature until a constant mass is obtained. The moisture content is calculated from the loss in mass of the coke. Coke is not liable to oxidation under the conditions stated.

5 Apparatus

5.1 Analytical balance, capable of weighing to the nearest 0,1 mg.

5.2 Oven, capable of being controlled at a temperature of 120 °C to 200 °C and with a means to allow a flow of air or nitrogen.

5.3 Weighing dish, shallow, of glass or of corrosion-resistant metal, with a well fitting cover, of such a size that the coke layer does not exceed 0,20 g/cm².

5.4 Cooling vessel, e.g. **desiccator**, without desiccant, containing a porcelain or a metal plate, preferably of aluminium or copper.

The vessel may be provided with the means to pass air or nitrogen through it during the cooling period.

6 Preparation of the test sample

The coke used for the determination of moisture content is the general analysis test sample (see ISO 1213-2). Ensure that the moisture content of the sample is in equilibrium with the laboratory atmosphere, exposing it, if necessary, in a thin layer for the minimum time required to achieve equilibrium.

Before commencing the determination, thoroughly mix the equilibrated test sample for at least 1 min, preferably by mechanical means.

7 Procedure

Weigh a clean, dry, empty weighing dish with its cover to the nearest 0,1 mg. Add $1 \text{ g} \pm 0,1 \text{ g}$ of the coke sample in an even layer and reweigh. Heat the uncovered dish in the oven at 120 °C to 200 °C.

When the drying period is complete, remove the dish with the dried sample from the oven and replace the cover immediately. If the size of the oven allows, replace the cover while the dish is still in the oven. Allow the dish to cool on a thick metal plate for 10 min. At the end of the 10 min cooling period, transfer the dish to a cooling vessel (5.4) and allow to cool to room temperature. As soon as room temperature is reached, reweigh to the nearest 0,1 mg.

NOTE 1 If a cooling vessel with air or nitrogen flow is used the dish can be transferred directly without cooling on a metal plate.

If there is any doubt that drying is complete, reheat at 120 °C to 200 °C for further 30 min periods until the change in mass between successive weighings does not exceed 1 mg.

For a particular oven, the times required to ensure constancy in mass shall be verified by experiments.

NOTE 2 Heating for 4 h is normally sufficient.

The time taken for the determination can be considerably shortened if drying is carried out at a temperature of 320 °C in a nitrogen atmosphere, when heating for 1 h usually suffices. For this procedure, a minimum free space oven may be used.

If appropriate, the drying can be done at lower temperature, e.g. 105 °C to 110 °C, as for hard coal. It is necessary to verify by experiments the times required to ensure constancy in mass.

8 Expression of results

The moisture in the coke as analysed, $\omega_{\text{H}_2\text{O,ad}}$, expressed as a percentage mass fraction is given by Equation (1):

$$\omega_{\text{H}_2\text{O,ad}} = \frac{m_2 - m_3}{m_2 - m_1} \times 100 \quad (1)$$

where

m_1 is the mass, expressed in grams, of the empty dish plus cover;

m_2 is the mass, expressed in grams, of the dish plus cover plus coke before heating;

m_3 is the mass, expressed in grams, of the dish plus cover plus coke after heating.

Report the result, as the mean of duplicate determinations, to the nearest 0,1 % mass fraction.