
**Dentistry — Preclinical evaluation of
biocompatibility of medical devices used in
dentistry — Test methods for dental
materials**

*Art dentaire — Évaluation préclinique de la biocompatibilité des dispositifs
médicaux utilisés en art dentaire — Méthodes d'essai des matériaux
dentaires*



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 7405 was prepared by Technical Committee ISO/TC 106, *Dentistry*, in conjunction with the World Dental Federation (FDI).

This first edition cancels and replaces ISO/TR 7405:1984, which has been technically revised (see Introduction) and converted into an International Standard.

Annexes A, B and C of this International Standard are for information only.

STANDARDSISO.COM : Click to view the full PDF of ISO 7405:1997

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Introduction

This International Standard concerns the preclinical testing of dental materials in medical devices used in dentistry. It has been developed from and supersedes ISO/TR 7405:1984, *Biological evaluation of dental materials*, and its supplements, and should be read in conjunction with the ISO 10993, *Biological evaluation of medical devices*, series of standards. This International Standard differs from ISO/TR 7405 in several important ways. Firstly, it contains details of test methods applicable only to dental materials. Many test methods previously included in ISO/TR 7405 are now included in the ISO 10993 series of standards and details of them have therefore been excluded from this standard. Secondly, only test methods for which the members of the committee considered there was sufficient published data have been included. Thirdly, in recommending test methods, the need to minimize the use of animals was given a high priority.

The annexes are informative, to encourage the development of *in vitro* and *in vivo* test methods which will further reduce the use of animals in the preclinical evaluation of the biocompatibility of medical devices used in dentistry.

STANDARDSISO.COM : Click to view the full PDF of ISO 7405:1997

Page blanche

STANDARDSISO.COM : Click to view the full PDF of ISO 7405:1997

Dentistry — Preclinical evaluation of biocompatibility of medical devices used in dentistry — Test methods for dental materials

1 Scope

This International Standard specifies methods for the evaluation of biological effects of dental materials. It includes testing of pharmacological agents that are an integral part of the device under test.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 1942-2:1989, *Dental vocabulary — Part 2: Dental materials*

ISO 10993-1:—¹⁾, *Biological evaluation of medical devices — Part 1: Evaluation and testing*

ISO 10993-2:1992, *Biological evaluation of medical devices — Part 2: Animal welfare requirements*

ISO 10993-3:1992, *Biological evaluation of medical devices — Part 3: Tests for genotoxicity, carcinogenicity and reproductive toxicity*

ISO 10993-5:1992, *Biological evaluation of medical devices — Part 5: Tests for cytotoxicity: in vitro methods*

ISO 10993-6:1994, *Biological evaluation of medical devices — Part 6: Tests for local effects after implantation*

ISO/TR 10993-9:1994, *Biological evaluation of medical devices — Part 9: Degradation of materials related to biological testing*

ISO 10993-10:1995, *Biological evaluation of medical devices — Part 10: Tests for irritation and sensitization*

ISO 10993-11:1993, *Biological evaluation of medical devices — Part 11: Tests for systemic toxicity*

ISO 10993-12:—²⁾, *Biological evaluation of medical devices — Part 12: Sample preparation and reference materials*

ISO 10993-13:—²⁾, *Biological evaluation of medical devices — Part 13: Identification and quantification of degradation products from polymers*

ISO 10993-14:—²⁾, *Biological evaluation of medical devices — Part 14: Identification and quantification of degradation products from ceramics*

ISO 10993-15:—²⁾, *Biological evaluation of medical devices — Part 15: Identification and quantification of degradation products from coated and uncoated metals and alloys*

ISO 10993-16:—²⁾, *Biological evaluation of medical devices — Part 16: Toxicokinetic study design for degradation products and leachables.*

1) To be published. (Revision of ISO 10993-1:1992)

2) To be published

3 Definitions

For the purposes of this International Standard, the definitions given in ISO 10993-1, ISO 1942-2 and the following definitions apply.

3.1 medical device: Any instrument, apparatus, appliance, material or other article, including software, whether used alone or in combination, intended by the manufacturer to be used for human beings solely or principally for the purpose of

— diagnosis, prevention, monitoring, treatment or alleviation of disease, injury or handicap;

— investigation, replacement or modification of the anatomy or of a physiological process;

— control of conception;

and which does not achieve its principal intended action in or on the human body by pharmacological, immunological or metabolic means, but which may be assisted in its function by such means.

NOTE 1 Devices are different from drugs, and their biological evaluation requires a different approach.

NOTE 2 In this International Standard, the term "medical device" is understood to include dental devices and dental materials.

3.2 dental material: Substance or combination of substances specially prepared and/or presented for the use of authorized persons in the practice of dentistry and/or its associated procedures.

3.3 final product: Medical device in its "as-used" state.

NOTE — Many dental materials are used in a freshly mixed state, and evaluation of the materials in both freshly mixed and set conditions should be considered.

3.4 positive-control material: Material or substance which, when tested by the procedure described, demonstrates the suitability of the procedure to yield a reproducible, appropriate positive or reactive response in the test system.

3.5 negative-control material; reference material: Material or substance which, when tested by the procedure described, demonstrates the suitability of the procedure to yield a reproducible, appropriate negative, nonreactive or background response in the test system.

4 Categorization of medical devices used in dentistry

4.1 Categorization by nature of contact

For the purposes of this International Standard, the classification of medical devices used in dentistry is derived from ISO 10993-1. If a device or material can be placed in more than one category, the more rigorous testing requirements shall apply. With multiple exposures the decision into which category a device is placed shall take into account the potential cumulative effect, bearing in mind the period of time over which these exposures occur.

4.1.1 Noncontact devices

These devices do not contact the patient's body directly or indirectly, and are not included in ISO 10993.

4.1.2 Surface-contacting devices

These devices include those that contact the surface of intact or breached skin, the surface of intact or breached oral mucosa, and those that contact the external surfaces of dental hard tissue, including enamel, dentine and cementum.

NOTE — Dentine and cementum are considered as surfaces; e.g. after gingival recession.

4.1.3 External communicating devices

These devices include dental devices that penetrate and are in contact with oral mucosa, dental hard tissues, dental pulp tissue or bone, or any combination of these, and are exposed to the oral environment.

4.1.4 Implant devices (see ISO 10993-1)

These devices include dental devices and implants that are partially or fully embedded within the soft tissue, bone or pulpodentinal system of the tooth, or any combination of these, and are not exposed to the oral environment.

4.2 Categorization by duration of contact

For the purposes of this International Standard, medical devices used in dentistry are classified by duration of contact as described in ISO 10993-1, i.e.:

4.2.1 Limited exposure devices

Devices whose single or multiple use or contact is likely to be up to 24 h;

4.2.2 Prolonged exposure devices

Devices whose single, multiple or long-term use or contact is likely to exceed 24 h but not 30 days;

4.2.3 Permanent contact devices

Devices whose single, multiple or long-term use or contact exceeds 30 days.

5 Selection of biological evaluation test

5.1 The general guidance for the selection of biological evaluation tests stated in ISO 10993-1 shall apply. Tests should be selected from the methods described in the ISO 10993 series of standards or in this International Standard or in both. If tests not included in these International Standards are selected, a statement shall be made that indicates that the tests described in the International Standards have been considered and shall include a justification for the selection of other tests.

5.2 The selection of tests and the overall assessment of the results shall be carried out by an expert who has appropriate chemical, physical and biological data concerning the device and who is aware of the intended conditions of use.

5.3 The selection of test methods shall be based upon consideration of:

- a) the intended use of the material;
- b) the tissue(s) which the material may contact;
- c) the duration of the contact.

5.4 According to the categorization of the device, tests shall be considered for use as summarized in table 1. This table indicates which types of test method shall be considered, but not that they are necessarily required to be carried out. A decision not to carry out a type of test identified in table 1 shall be justified in the test report on each device. The types of test listed are regarded as a framework for the preclinical evaluation of the biocompatibility of dental materials. For most types of test, particular methods are identified, although for some devices it is recognized that alternative methods not included in the International Standards listed may be more appropriate.

Table 1 — Types of test for preclinical evaluation of biocompatibility of dental materials

		Group I			Group II								Group III			
Nature of contact	Duration of contact	Cytotoxicity tests ISO 7405, 6.1 and 6.2	Cytotoxicity tests ISO 10993-5	Cytotoxicity tests ISO 7405, annex A	Acute systemic toxicity — Oral application ISO 10993-11, 6.5.1	Acute systemic toxicity — Oral application ISO 7405, annex B	Acute systemic toxicity — Application by inhalation ISO 10993-11, 6.5.3	Subchronic systemic toxicity — Oral application ISO 10993-11, 6.7.1	Skin irritation and intra-cutaneous reactivity ISO 10993-10, 5.2 and 5.4	Sensitization ISO 10993-10, 6.2 and 6.3	Subchronic systemic toxicity — Application by inhalation ISO 10993-11, 6.7.3	Genotoxicity ISO 10993-3, clause 4	Local effects after implantation ISO 10993-6, clauses 4, 5 and 6	Pulp and dentine usage test ISO 7405, 6.3	Pulp capping test ISO 7405, 6.4	Endo-dontic usage test ISO 7405, 6.5
Surface-contacting devices	≤ 24 h	X	X				X		X	X						
	> 24 h to 30 days	X	X				X	X	X	X	X					
	> 30 days	X	X				X	X	X	X	X	X				
External communicating devices	≤ 24 h	X	X	X	X	X	X		X	X				X		
	> 24 h to 30 days	X	X	X			X	X	X	X	X	X	X	X		
	> 30 days	X	X	X			X	X	X	X	X	X	X	X		
Implant devices	≤ 24 h	X	X						X	X					X	X
	> 24 h to 30 days	X	X					X	X	X		X	X		X	X
	> 30 days	X	X					X	X	X		X	X		X	X
NOTE — X indicates test shall be considered for use.																

A justification for the choice of all methods shall be included in the test report of each device. This is of particular importance when methods not included in this International Standard are used.

For convenience, the types of test have been listed in three groups.

a) Group I

This group comprises *in vitro* tests of cytotoxicity. General guidance for *in vitro* cytotoxicity tests is presented in ISO 10993-5 and shall be followed. Detailed test protocols for the agar diffusion and filter diffusion methods, appropriate to dental materials, are included in this International Standard. The *in vitro* cytotoxicity methods include:

- 1) agar diffusion test (6.1);
- 2) filter diffusion test (6.2);
- 3) direct contact or extract tests in accordance with ISO 10993-5;
- 4) dentine barrier tests (annex A).

NOTE 1 The order of listing does not indicate any preference for one method over another.

NOTE 2 The use of dentine barrier tests is encouraged and reference to these is presented in annex A.

b) Group II

This group comprises tests in accordance with ISO 10993 and particular tests, where appropriate, are identified:

- 1) acute systemic toxicity — oral application (ISO 10993-11, 6.5.1 and annex B);
- 2) acute systemic toxicity — application by inhalation (ISO 10993-11, 6.5.3);
- 3) subchronic systemic toxicity — oral application (ISO 10993-11, 6.7.1);
- 4) skin irritation and intracutaneous reactivity (ISO 10993-10, 5.2 and 5.4);
- 5) sensitization (ISO 10993-10, 6.2 and 6.3);
- 6) subchronic systemic toxicity — application by inhalation (ISO 10993-11, 6.7.3);
- 7) genotoxicity (ISO 10993-3, clause 4);
- 8) local effects after implantation (ISO 10993-6, clauses 4, 5 and 6).

NOTE 1 Alternatives to the LD₅₀ tests are encouraged for acute toxicity testing, and information regarding this point is presented in annex B.

NOTE 2 In the evaluation of materials following local implantation in accordance with ISO 10993-6, examination of undemineralized sections, in addition to routine demineralized sections, is recommended.

c) Group III

This group comprises tests, specific for dental materials, not referred to in ISO 10993:

- 1) pulp and dentine usage test (6.3);
- 2) pulp capping test (6.4);
- 3) endodontic usage test (6.5).

5.5 A device shall be considered for re-evaluation of its biocompatibility as described in 5.4 when revisions or modifications to the formula, quality and/or performance specifications are made.

6 Test procedures specific to dental materials

6.1 Agar diffusion test

6.1.1 Objective

The test is designed to demonstrate the nonspecific cytotoxicity of test materials after diffusion through agar or agarose.

6.1.2 Cell line

American Type Culture Collection CCL 1 fibroblasts (NCTC clone 929) shall be used; other cell lines may be used if reproducibility and accuracy of the response can be demonstrated.

NOTE — Alternative cell lines are presented in annex C.

6.1.3 Culture medium, reagents and equipment

Use Eagle's Basal Medium containing 2,2 g/l sodium bicarbonate, 3,0 g/l HEPES and 50 ml/l new-born calf serum. Prepare a double concentration of Eagle's Basal Medium omitting HEPES and reducing sodium bicarbonate to 1 g/l. Prepare either 3 % agar or 3 % agarose in distilled water.

Sterilize agar by autoclaving and medium by filtration.

Prepare the vital stain by diluting a stock solution of 1 % aqueous neutral red solution (record source) 1/100 with 0,01 ml/l phosphate-buffered saline solutions immediately before use. Store neutral red solutions protected from the light. Use Petri dishes of diameter 50 mm to 100 mm suitable for tissue culture.

6.1.4 Sample preparation

For the preparation of test materials, the manufacturer's recommended instructions shall be followed. The test shall be performed on either an extract of the material or the material itself, according to the guidance in ISO 10993-5, clause 4.

For solid materials, prepare circular test specimens of approximately 5 mm diameter, with a flat surface to ensure adequate contact with the agar overlay.

For setting materials, insert the freshly mixed material into glass or polytetrafluoroethylene rings of internal diameter 5 mm and height 5 mm. When testing materials in the freshly mixed state, place the rings on the agar prior to inserting the material. When testing after various setting periods, fill the rings so that the material is flush with the rim and allow it to set at $(37 \pm 2)^\circ\text{C}$ and a relative humidity of $(90 \pm 10) \%$ until ready for testing.

For fluid specimens or extracts, imbibe 0,1 ml of the fluid on a borosilicate microglass filter disc of 5 mm diameter, placed on the agar.

NOTE — Suitable discs can be prepared from prefilters³⁾.

6.1.5 Control specimens

Use control specimens as defined in ISO 10993-5, clause 3.

6.1.6 Test procedure

Culture the cells until they reach the end of the log growth phase. Pipette 10 ml of cell suspension ($2,5 \times 10^5$ cells/ml) into a sufficient number of Petri dishes and incubate at $(37 \pm 2)^\circ\text{C}$ in a water-saturated atmosphere with 5 % (V/V) carbon dioxide for 24 h. Heat the sterile agar to 100°C in a water bath and allow it to cool to 48°C . Mix 1 part of agar with 1 part of double-concentration, freshly prepared nutrient medium and heat to 48°C . Aspirate the liquid nutrient medium from each Petri dish and replace with 10 ml of freshly prepared agar/nutrient medium mixture.

3) Millipore prefilter AP2502200 is an example of a suitable product available commercially. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of this product.

Allow the agar nutrient medium to solidify at room temperature (approximately 30 min). Add 10 ml neutral red solution and keep dark for 15 min to 20 min. Aspirate excess neutral red solution.

Protect the culture from light in the presence of neutral red, as the cells can be damaged.

Apply to each dish two samples of test material, one positive control, one negative control and one extraction medium control if the last was used. Keep the specimens as far as possible from each other and from the wall of the Petri dish. Incubate at $(37 \pm 2) ^\circ\text{C}$ in a water-saturated atmosphere with 5 % (V/V) carbon dioxide for 24 h. Examine each test material at least in quadruplicate (i.e. two dishes per test material).

6.1.7 Parameters of assessment

The decolorization zone around the test materials and controls shall be assessed using an inverted microscope with a calibrated screen, and a Decolorization Index and a Lysis Index determined for each specimen in accordance with the following criteria:

a) Decolorization Index Description

0	No decolorization detectable
1	Decolorization only under the test substance
2	Decolorization zone not greater than 5,0 mm from the test substance
3	Decolorization zone not greater than 10,0 mm from the test substance
4	Decolorization zone greater than 10,0 mm from the test substance
5	The total culture is decolorized

b) Lysis Index Description

0	No cell lysis detectable
1	Less than 20 % cell lysis
2	20 % to 40 % cell lysis
3	> 40 % to < 60 % cell lysis
4	60 % to 80 % cell lysis
5	More than 80 % cell lysis

Calculate the median Decolorization Index and Lysis Index for each test material and present the cell response as follows:

$$\text{Cell response} = \text{Decolorization Index/Lysis Index}$$

If the index values for the four replicates of the test substance differ by more than 2 units in the range 0 to 3, repeat the test. With indices of 4 and 5, no repetition is necessary. When extracts are tested, subtract the median index of the extraction medium alone from the median index of the extraction medium containing test substance to obtain the index for the test substance alone. If the median index for the extraction medium serving as a control is greater than 1, repeat the test using a different extraction medium.

NOTE — For a valid test, an intact cell layer should be found under the negative control.

6.1.8 Assessment of results

All information gathered in the test shall be taken into account in assessing the test results, particularly any differences in results between the experimental and control groups. The cell response is based on the median

Decolorization index and Lysis index of at least four replicate tests. The cell response is therefore not necessarily an integer and the scale used for interpreting the cell response should be continuous. A useful way to grade test materials is presented below.

Scale	Cell response	Interpretation
0	0/0	Noncytotoxic
1	1/1	Mildly cytotoxic
2	2/2 to 3/3	Moderately cytotoxic
3	4/4 to 5/5	Severely cytotoxic

The results of the assessment shall be included in the test report.

6.1.9 Test report

The results shall be submitted in a test report that includes a complete record of all procedures followed, all results obtained and any other data necessary for the assessment of results as described in 6.1.8. Details of the preparation and methods of application of the test material, together with the batch number of the material when appropriate, shall be included.

6.2 Filter diffusion test

6.2.1 Objective

The test is designed to demonstrate the nonspecific cytotoxicity of test materials after diffusion through a cellulose acetate filter.

6.2.2 Cell line

American Type Culture Collection CCL1 fibroblasts (NCTC clone 929) shall be used; other cell lines may be used if reproducibility and accuracy of the response can be demonstrated.

NOTE — Alternative cell lines are presented in annex C.

6.2.3 Culture medium, reagents and equipment

Prepare culture medium and agar for use as an overlayer as described in 6.1.3. Prepare solutions either for succinate dehydrogenase staining or for nonspecific hydrolase staining.

For succinate dehydrogenase staining, prepare the following stock solutions:

- succinate solution**, 13,6 g sodium succinate in 100 ml phosphate buffer, pH 7,6;
- nitro blue tetrazolium chloride solution**, 100 mg nitro blue tetrazolium chloride in 100 ml phosphate buffer, pH 7,6;
- phenazine methosulfate solution**, 4 mg phenazine methosulfate in 10 ml distilled water, fresh.

Prepare a staining solution of 1 ml succinate solution, 9 ml nitro blue tetrazolium chloride solution and 1 ml phenazine methosulfate solution.

For nonspecific hydrolase staining, prepare a stock solution of fluorescein diacetate consisting of 5 mg fluorescein diacetate in 1 ml acetone. For use add 20 µl of stock solution to 100 ml phosphate-buffered saline. Use Petri dishes of 50 mm to 100 mm diameter, suitable for tissue culture.

Use cellulose acetate filters, 47 mm diameter, 0,45 µm pore size⁴⁾.

4) Millipore HAWD 04753, HA TF 047 SO is an example of a suitable product available commercially. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of this product.

6.2.4 Sample preparation

Prepare the samples in accordance with 6.1.4. All samples, including solid materials, shall be placed on the filter rather than the agar overlay. The mass of the test specimens shall not exceed 3,5 g. For the preparation of test materials, the manufacturer's recommended instructions shall be followed.

6.2.5 Control specimens

Use control specimens as defined in ISO 10993-5, clause 3.

6.2.6 Test procedure

Culture the cells until they reach the end of the log growth phase. Place cellulose acetate filters in the bottom of a sufficient number of Petri dishes and pipette 6 ml of cell suspension ($2,5 \times 10^5$ cells/ml) into each. Incubate at $(37 \pm 2)^\circ\text{C}$ in a water-saturated atmosphere with 5 % (V/V) carbon dioxide for 24 h.

Pipette 5 ml of freshly prepared agar nutrient medium mixture (see 6.1.6) kept at 48°C into a sufficient number of Petri dishes and allow it to solidify at room temperature. Aspirate the excess nutrient medium from the dishes containing cellulose acetate filters, wash the filters with phosphate-buffered saline at $(37 \pm 2)^\circ\text{C}$ and place them on top of the agar, cell side down. Apply three to five test specimens on top of the filter in each dish and incubate for a further 2 h at $(37 \pm 2)^\circ\text{C}$ in a water-saturated atmosphere with 5 % (V/V) carbon dioxide. Ensure that the specimens are in close contact with the surface of the filter. If the test material does not show toxicity after 2 h incubation, repeat the test with 24 h incubation. In each dish include one positive control and one negative control. In addition, further controls of a filter with a cell monolayer but without test specimens, and of a filter without cells but with test specimens shall be used. When extracts are tested, a control using the extraction medium alone shall also be used. Each test specimen shall be examined at least in quadruplicate.

After incubation, remove the test specimens and gently loosen the filter from the agar. Assess cytochemically the area of reduced cell enzyme activity by method A or method B.

a) Method A

Demonstrate succinate dehydrogenase (enzyme classification 1.3.99.1) according to the method of Barka and Anderson [1963]. The incubation period is 3 h at $(37 \pm 2)^\circ\text{C}$. Wash the filter in distilled water and air-dry prior to measurement.

b) Method B

Demonstrate nonspecific hydrolase by incubation with fluorescein diacetate solution for 30 min at 4°C . Examine the filter under ultraviolet light.

6.2.7 Assessment of cell damage

Cell damage shall be assessed either

- by measuring the area of decolorization (e.g. by means of an image analysis system) or
- by using the following scale.

Scale	Grading assessment	Area of decolorization
0	No difference in staining intensity across the filter	None
1	A zone of reduced staining intensity, or an unstained zone with a diameter less than that (5 mm) of the test specimen	$< 20 \text{ mm}^2$
2	An unstained zone 5 mm to 7 mm in diameter	20 mm^2 to 40 mm^2
3	An unstained zone greater than 7 mm in diameter	$> 40 \text{ mm}^2$

NOTE — The filters beneath negative control specimens and the control filters should be uniformly stained dark blue (if succinate dehydrogenase is used) or light green (if nonspecific hydrolase is used). The control filters without cells allow determination of a possible effect of the test specimen on the filter.

6.2.8 Assessment of results

All information gathered in the test shall be taken into account in assessing the test results, particularly any differences in results between the experimental and control groups. A useful way to grade test materials is presented below.

Scale	Interpretation
0	Noncytotoxic
1	Mildly cytotoxic
2	Moderately cytotoxic
3	Severely cytotoxic

The results of the assessment shall be included in the test report.

6.2.9 Test report

The results shall be submitted in a test report that includes a complete record of all procedures followed, all results obtained and any other data necessary for the assessment of results as described in 6.2.8. Details of the preparation and methods of application of the test material, together with the batch number of the material when appropriate, shall be included.

6.3 Pulp and dentine usage test

6.3.1 Objective

The test is designed to assess the biocompatibility of dental materials with the dentine and dental pulp. Procedures necessary for the proposed clinical use of the material are included in the assessment.

6.3.2 Animals and animal welfare

6.3.2.1 Animal welfare shall be in accordance with either:

- ISO 10993-2, or
- national regulatory requirements for laboratory animals.

NOTE — The animals should be housed individually and have free access to food and water.

6.3.2.2 Nonrodent mammals of one species shall be used. They shall be of such an age that their dentition contains intact permanent teeth with closed mature apices.

NOTE 1 Monkeys, dogs, ferrets or miniature pigs are suitable species. Other species may be suitable for special purposes.

NOTE 2 Suitable monkeys, dogs and miniature pigs are those in which all the permanent teeth, other than M3, have erupted. Suitable ferrets are those in which the four permanent canines have erupted, as only those teeth are suitable.

6.3.3 Test procedure

6.3.3.1 Preparation of animals

Select sufficient animals to provide at least seven teeth containing test material for each time period.

Anaesthetize the animals and carry out the procedure described in 6.3.3.2.

6.3.3.2 Treatment of teeth

6.3.3.2.1 Remove all calculus and debris from the tooth surfaces. Clean and disinfect the surfaces of the teeth to be used by swabbing with 3 % (V/V) hydrogen peroxide followed by a disinfectant consisting of povidone-iodine or chlorhexidine. Prepare the required number of midcrown Class V buccal or labial cavities using sharp burs under an adequate air-water spray. Prepare all cavities to a depth such that their remaining dentine thickness is less than 1,0 mm but the pulp is not exposed. Rinse the cavities with water and dry them with cotton wool unless the method of insertion of the test material requires a different procedure.

NOTE — If animals have marked gingival inflammation, it may be necessary to carry out a calculus and debris removal a few days before cavity preparation, and even repeatedly until gingival inflammation is controlled.

6.3.3.2.2 For the preparation of test materials, follow the manufacturer's recommended instructions. If the manufacturer of the test material recommends its use with a lining material or cavity treatment agent (e.g. a dentine adhesive agent), use these additional procedures as recommended by the manufacturer.

6.3.3.2.3 For each time period, restore at least seven cavities with the test material and four cavities with a negative-control material on the basis of a random allocation. If necessary, for each time period, restore up to four cavities with a positive material. For laboratories which possess a data bank for previous positive-control materials, further studies are unnecessary other than on an occasional basis to confirm a positive reaction.

NOTE 1 If monkeys, dogs or miniature pigs are used, one animal should be used for each time period. If ferrets are used, at least three animals should be used for each time period.

NOTE 2 A quick-setting zinc oxide-eugenol cement is an appropriate negative-control material. The investigator has the option to cover the zinc oxide-eugenol cement with a resin composite restoration utilizing a bonding technique or a glass ionomer cement (especially for long-term studies). A restorative material or technique not involving exposure of the pulp, which consistently results in moderate to severe pulpal response, is an appropriate positive control.

6.3.3.2.4 Observe each animal on a regular basis during the period of the study for signs of changes in eating habits or of inflammation or suppuration in the oral tissues.

6.3.3.3 Preparation of slides

6.3.3.3.1 After (7 ± 2) days, (28 ± 3) days and (70 ± 5) days, kill with an overdose of anaesthetic a sufficient number of animals to provide at least seven teeth containing test material. Examine the restorations, the teeth and their supporting tissues and record details of any abnormalities. Remove each treated tooth, together with its surrounding hard and soft tissues, and fix in a suitable fixing agent.

NOTE — Vascular perfusion of the tissues with fixative at the time of sacrifice prior to their removal provides better fixation.

6.3.3.3.2 After fixation, demineralize the teeth in a suitable reagent (e.g. 10 % formic acid or 0,5 mol/l ethylenediaminetetraacetic acid at pH 7,4) and prepare serial sections, 5 μ m to 10 μ m thick, through each cavity in the longitudinal axis of the tooth. Stain alternate slides with haematoxylin and eosin. Stain intermediate slides with an appropriate bacterial stain (e.g. Brown and Brenn) or other stains as necessary for detection of microleakage.

6.3.3.4 Assessment of dentine and dental pulp

Examine the sections without prior knowledge of whether the specimen is experimental or control. For each series of sections, record a full description of all the histological features in the dentine, pulp and periapical tissues, including any that may have arisen from the cavity preparation technique. From the serial sections, select at least five evenly spaced through the cavity and grade separately the inflammatory infiltrate in the superficial tissues (odontoblast layer, cell-free zone and cell-rich zone) and the remainder (deeper) pulp tissue on the following scale.

Scale	Observation
0	No inflammation
1	Mild inflammation
2	Moderate inflammation
3	Severe inflammation
4	Abscess formation or extended lesions not localized to the tissue beneath the cavity floor

For each section graded, record the minimum remaining dentine thickness, either in a straight line at right angles from the floor of the cavity to the pulp or by measuring along the course of the dentinal tubules.

Calculate an index of response for both sites of inflammation at each time interval by summing the individual grades and dividing by the total number of observations. Present the data separately for cavities filled with the test material, including the lining material or cavity treatment agent if recommended by the manufacturer, cavities filled with the negative control alone, and cavities used as positive controls (the last data may be obtained from previous studies). In addition, record the mean remaining dentine thickness and the number of cavities containing bacteria at each time interval.

6.3.4 Assessment of results

All information gathered in the test shall be taken into account in assessing the test results, particularly any differences in results between the experimental and control groups.

The results of the assessment shall be recorded in the test report.

6.3.5 Test report

The results shall be submitted in a test report that includes a complete record of all procedures followed, results obtained and any other data necessary for the assessment of results as described in 6.3.4. Details of the preparation and methods of application of the test material, together with the batch number of the material, shall be included.

6.4 Pulp capping test

6.4.1 Objective

The test is designed to assess the biocompatibility of pulp capping materials with the dental pulp. Procedures necessary for the proposed clinical use of the material are included in the assessment.

NOTE — With a few modifications, this test can be used for pulpotomy testing.

6.4.2 Animals and animal welfare

Animal welfare shall be in accordance with 6.3.2.1.

A minimum of two nonrodent mammals of one species shall be used, as described in 6.3.2.2.

6.4.3 Test procedure

6.4.3.1 Preparation of animals

Select sufficient animals to provide at least seven teeth containing test material for each time period.

Anaesthetize the animals and carry out the procedure described in 6.4.3.2.

6.4.3.2 Treatment of teeth

6.4.3.2.1 Remove all calculus and debris from the tooth surfaces. Place a rubber dam to isolate the teeth to be used. Clean the tooth surface and the operating field and dry. Disinfect by swabbing with 3 % (V/V) hydrogen peroxide followed by a disinfectant consisting of povidone-iodine or chlorhexidine. Prepare the required number of midcrown Class V buccal or labial cavities using sharp burs under an adequate air-water spray. The preparations should be bordered by enamel but extending into the mesial and distal surfaces of the tooth and into the inner one-third of the dentine. In the centre of the cavity, carefully make a pulpal exposure of approximately 0,5 mm to 1,0 mm diameter under a spray of sterile saline solution [0,9 % (*m/m*)] without plunging the bur into the tissue. Thoroughly irrigate the exposure site with sterile saline solution until haemostasis is achieved. Dry with sterile cotton pellets.

NOTE — If animals have marked gingival inflammation, it may be necessary to carry out a calculus and debris removal a few days before cavity preparation and even repeatedly until gingival inflammation is controlled..

6.4.3.2.2 For the preparation of test materials, follow the manufacturer's recommended instructions. If the manufacturer recommends other irrigating solutions or reagents for the termination of haemorrhage or specific pre-treatment of the pulp wound, follow the manufacturer's instructions.

6.4.3.2.3 For each time period fill at least ten cavities with the test material and five with a suitable reference material on the basis of a random allocation. Mix the capping and control materials on a slab (pad), avoiding microbial contamination. Apply the materials to the pulp wound without pressure. Restore the cavity with a zinc oxide-eugenol material or a polycarboxylate cement covered by a resin composite restoration utilizing a bonding technique or a glass ionomer cement.

NOTE 1 If monkeys, dogs or miniature pigs are used, at least one animal should be used for each time period. If ferrets are used, at least four animals should be used for each time period.

NOTE 2 Calcium hydroxide freshly mixed with sterile 0,9 % (*m/m*) saline solution to a putty consistency, is an appropriate reference control.

6.4.3.2.4 Observe the animals as in 6.3.3.2.4.

6.4.3.3 Preparation of slides

6.4.3.3.1 After (7 ± 2) days and (70 ± 5) days, kill with an overdose of anaesthetic a sufficient number of animals to provide at least ten teeth containing test material. Examine the restorations, the teeth and their supporting tissues and record details of any abnormalities. Remove each treated tooth, together with its surrounding hard and soft tissues, in a single block and fix in a suitable fixing agent.

NOTE — Vascular perfusion of the tissues with fixative at the time of sacrifice prior to their removal provides better fixation.

6.4.3.3.2 After fixation take a radiograph of each tissue block to determine whether radiographic changes have occurred. Prepare sections for examination as in 6.3.3.3.2.

6.4.3.4 Assessment of dental pulp

Examine the sections, describe the histological features, grade the inflammatory infiltrate and calculate the index of response as in 6.3.3.4. In addition, grade the degree of bridging of the exposure by tertiary dentine on a scale of none, partial or complete.

6.4.4 Assessment of results

The results shall be assessed as in 6.3.4.

6.4.5 Test report

The results shall be submitted in a test report as in 6.3.5.

6.5 Endodontic usage test

6.5.1 Objective

The test is designed to assess the biocompatibility of endodontic materials with the remaining apical pulp tissues (stumps) and the periapical tissues. Procedures necessary for the proposed clinical use of the material are included in the assessment.

6.5.2 Animals and animal welfare

Animal welfare shall be in accordance with 6.3.2.1.

A minimum of four nonrodent mammals of one species shall be used as described in 6.3.2.2. They shall be of such an age that their dentition contains intact permanent teeth with closed (mature) apices; the use of incisors, canines and premolars is preferred. The use of premolars is optional if two roots are present.

6.5.3 Test procedure

6.5.3.1 Preparation of animals

Select sufficient animals to provide at least ten teeth containing test material for each time period.

NOTE — In some breeds of dogs the morphology of the apical part of the root canals may make root preparation difficult.

Anaesthetize the animals and carry out the procedure described in 6.5.3.2.

6.5.3.2 Treatment of teeth

6.5.3.2.1 Take periapical radiographs of the teeth to be filled. Clean and isolate the teeth as in 6.4.3.2.1.

NOTE — If animals have marked gingival inflammation, it may be necessary to carry out calculus and debris removal a few days before cavity preparation, and even repeatedly until gingival inflammation is controlled.

Prepare the required number of teeth for placement of root canal fillings. Make an appropriate opening into the pulp chamber using sharp burs, under aseptic conditions. Debride the exposed pulp with saline solution [0,9 % (*m/m*)] and dry with sterile cotton pellets. Use a new sterile root canal file or a barbed broach to sever the pulp ($1,0 \pm 0,5$) mm from the apical foramen, using the radiography as a guide during instrumentation. Irrigate the root canal repeatedly with 1,5 % to 3,5 % (*m/m*) sodium hypochlorite solution followed by sterile 0,9 % (*m/m*) saline solution.

Enlarge the root canal using progressively larger, sterile, root canal files, calibrated in length to the level at which the pulp has been severed, until it is a suitable size for filling. Every effort shall be made to eliminate dentinal chips from the root canal that could block the tooth apex and prevent the endodontic material from contacting the apical tissue. Following completion of the instrumentation, flush the root canal with 1,5 % to 3,5 % (*m/m*) sodium hypochlorite solution followed by sterile 0,9 % (*m/m*) saline solution and dry with sterile cotton pellets and large, blunted, sterile paper points without contacting the apical pulpal stump.

6.5.3.2.2 For the preparation of test materials, follow the manufacturer's recommended instructions. If the manufacturer recommends preparation procedures different from those described above, follow the manufacturer's instructions.

6.5.3.2.3 For each time period, fill at least ten teeth with the test material and at least five with a suitable reference material, on the basis of a random allocation. Mix the endodontic and reference materials on a slab (pad), avoiding microbial contamination. Fill the root canal with either the test or reference material, utilizing gutta percha to the point of pulp severance. Obturate the access cavity with a reinforced zinc oxide-eugenol cement covered with either a polycarboxylate or glass ionomer cement or a resin composite restoration utilizing a bonding technique.

NOTES

1 If monkeys, dogs or miniature pigs are used, at least two animals should be used for each time period. If ferrets are used, at least four animals should be used for each time period.

2 Zinc oxide-eugenol cement, either alone or with other additives as in Grossman's sealer, is an appropriate reference material.

6.5.3.2.4 Observe the animals as in 6.3.3.2.4.

6.5.3.3 Preparation of slides

6.5.3.3.1 After (28 ± 3) days and (90 ± 5) days, kill with an overdose of anaesthetic a sufficient number of animals to provide at least ten teeth containing test material. Examine the restorations, the teeth and supporting tissues and record details of any abnormalities. Remove each treated tooth, together with its surrounding hard and soft tissues in a single block, and fix in a suitable fixing agent.

NOTE — Vascular perfusion of the tissues with fixative at the time of sacrifice prior to their removal provides better fixation.

6.5.3.3.2 After fixation, take a radiograph of each tissue block to determine whether radiographic changes have occurred. Prepare sections for examination as in 6.3.3.3.2, parallel to the long axis of the tooth through the root canal and its ramifications, showing the material/pulp tissue interface and the adjacent periapical tissues.

6.5.3.4 Assessment of tissues

Examine the sections without prior knowledge of whether the specimen is experimental or control. For each series of sections, record a full description of all the histological features in the pulp, periapical tissues, dentine and cementum in the apical part of the tooth. For each specimen, grade the tissue changes according to the following scale.

Scale	Observation
0	No inflammation.
1	Mild inflammation: specimens display a scattering of inflammatory cells, predominately chronic inflammatory cells, and the structural characteristics of residual pulp still identifiable.
2	Moderate inflammation: specimens display focal accumulations of inflammatory cells but no tissue necrosis, and disruption of the structural characteristics of the residual pulp and periapical tissues.
3	Severe inflammation: extensive replacement of the residual pulp or periapical tissues by an inflammatory cell infiltrate.
4	Abscess formation.

6.5.4 Assessment of results

The results shall be assessed as in 6.3.4.

6.5.5 Test report

The results shall be submitted in a test report as in 6.3.5.