

INTERNATIONAL STANDARD

ISO
8130-6

First edition
1992-12-15

AMENDMENT 1
1998-05-01

Coating powders —

Part 6:

Determination of gel time of thermosetting
coating powders at a given temperature

AMENDMENT 1

Poudres pour revêtement —

*Partie 6: Détermination du temps de gélification à une température donnée
de poudres thermodurcissables*

AMENDEMENT 1



Reference number
ISO 8130-6:1992/Amd.1:1998(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Amendment 1 to ISO 8130-6:1992 was prepared by ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Coating powders —

Part 6:

Determination of gel time of thermosetting coating powders at a given temperature

AMENDMENT 1

Page 3

Clause 8

In paragraph 5, line 4, after “start the timer (6.4)”, add “and commence stirring the material.”

New clause 9

Add the following clause:

“9 Precision

9.1 Repeatability, r

The value below which the absolute difference between two single test results obtained on identical material by one operator in one laboratory within a short interval of time using the standardized test method may be expected to lie with a 95 % probability is 5 %.

9.2 Reproducibility, R

Due to the nature of the material, reproducibility cannot be determined.”

Renumber the current clause 9 (Test report) as clause 10.