



**International
Standard**

ISO 8575

**Aerospace series — Fluid systems
— Hydraulic system tubing**

*Série aérospatiale — Systèmes de fluides — Tubes pour systèmes
hydrauliques*

**Third edition
2024-03**

STANDARDSISO.COM : Click to view the full PDF of ISO 8575:2024

STANDARDSISO.COM : Click to view the full PDF of ISO 8575:2024



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Requirements.....	1
4.1 General.....	1
4.2 Pressure lines.....	2
4.2.1 Tubing material.....	2
4.2.2 Tube sizes.....	2
4.2.3 Qualification.....	2
4.3 Suction and return lines.....	2
4.3.1 Tubing material.....	2
4.3.2 Tube sizes.....	2
Annex A (informative) Aerospace hydraulic tubing materials.....	8
Bibliography.....	9

STANDARDSISO.COM : Click to view the full PDF of ISO 8575:2024

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO document should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 20, *Aircraft and space vehicles*, Subcommittee SC 10, *Aerospace fluid systems and components*.

This third edition cancels and replaces the second edition (ISO 8575:2016), which has been technically revised.

The main changes are as follows:

- in [Table A.1](#) corresponding national standards for tubing materials have been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

The purpose of this document is to provide information relating to the sizes and materials of tubing for use in aerospace hydraulic pressure and return and suction lines.

International Standards use the International System of units (SI); however, large segments of the aerospace industry make use of other measurement systems as a matter of common working practice. Although tube sizes were originally defined (and are frequently cited) using non-SI units, all dimensions used in this document are given in SI units, with inch units also indicated for the convenience of the user.

The decimal sign used in International Standards is the comma (","); however, the comma is not used in common working practice for inch dimensions. Therefore, in common with many other aerospace standards, the decimal point is used in this document when providing dimensions in inches.

NOTE The use of non-SI units and the decimal point in this document does not constitute general acceptance of measurement systems other than SI within International Standards.

STANDARDSISO.COM : Click to view the full PDF of ISO 8575:2024

[STANDARDSISO.COM](https://standardsiso.com) : Click to view the full PDF of ISO 8575:2024

Aerospace series — Fluid systems — Hydraulic system tubing

1 Scope

This document provides information relating to the sizes and materials of tubing for use in aerospace hydraulic pressure and return and suction lines. For pressure lines, the requirements apply to the pressure and temperature ranges covered by pressure class D, E and J and temperature type 13 and type 20 as specified in ISO 6771.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 8574, *Aerospace — Hydraulic system tubing — Qualification tests for bent tubes*

ISO 6771, *Aerospace — Fluid systems and components — Pressure and temperature classifications*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.1

inch tubing

tubing diameters and wall thickness in fractional inch increments and based on industry standards

3.2

metric tubing

tubing diameters and wall thickness in SI-metric units

Note 1 to entry: Metric tubing follows ISO 2964.

4 Requirements

4.1 General

The pipe dimensions quoted are in common use for the stated materials in the different pressure and temperature classes. Inclusion of a dimension under a pressure and temperature class in this document does not constitute a guarantee of fitness for the purpose in all circumstances. Aircraft systems designers should verify each tube assembly application with the appropriate stress authority.

4.2 Pressure lines

4.2.1 Tubing material

Material for tubing used in hydraulic system pressure line shall be in accordance with [Table 1](#) and shall conform to the appropriate physical properties specified in [Table 1](#).

4.2.2 Tube sizes

The outside diameters, wall thicknesses and materials of tubing used in the manufacture of tube assemblies shall conform, where applicable, to the relevant requirements given in [Table 2](#) or [Table 3](#) for inch tubing and [Table 4](#) or [Table 5](#) for metric tubing.

Where no wall thickness is shown in the tables for a particular combination of tube outside diameter and material and it is desired to use that combination, a suitable wall thickness shall be selected and verified by testing in accordance with ISO 8574.

4.2.3 Qualification

Tubing having outside diameters, wall thicknesses and materials as specified in [Table 2](#) and [Table 3](#) shall be verified by testing in accordance with the requirements of ISO 8574.

4.3 Suction and return lines

4.3.1 Tubing material

Materials for tubing used in hydraulic system suction and return lines may be as given in [Table 1](#) and verified in accordance with ISO 8574 or at the discretion of the aircraft designer.

4.3.2 Tube sizes

Unless otherwise specified, the outside diameters for inch tubing used in suction and return lines shall be selected from those specified in [Table 2](#) or [Table 3](#) for inch tubing, and from [Table 4](#) or [Table 5](#) for metric tubing.

The corresponding wall thicknesses shall be selected and verified in accordance with [Table 2](#) to [Table 5](#) or at the discretion of the aircraft designer.

Table 1 — Tubing materials

Material		Ultimate tensile strength		Yield strength		Percent elongation $A_{\min.}$
Code no.	Description	R_m min. MPa	min. (psi)	$R_{p0,2}$ min. MPa	min. (psi)	%
1	Cold worked corrosion resistant steel 304-1/8H	725	(105 000)	515	(75 000)	20
2	High strength corrosion resistant steel 21-6-9	980	(142 000)	825	(120 000)	20
3	Re-annealed corrosion resistant steel UNS S32100	500	(72 500)	210	(30 500)	40
4	Cold-worked and stress relieved titanium Ti-3AL-2,5V	860	(125 000)	720	(105 000)	10
5		690	(100 000)	655	(95 000)	14
6	Unalloyed titanium TiCP	350	(50 000)	250	(35 000)	28
7	Aluminium alloy (6061), Solution treated and artificially aged (T6)	290	(42 000)	240	(34 000)	10

NOTE While waiting for the publication of International Standards for the materials described in [Table 1](#), national and industry standards accepted by the corresponding country conforming to the requirements specified in this table are given in [Annex A](#) for information.

Table 2 — Outside diameters, wall thicknesses and materials for hydraulic tubing, pressure lines — Inch tubing

Temperature ^a		Type 13 -55 °C to 135 °C (-65 °F to 275 °F)											
Pressure class ^a Design-operating-pressure (DOP)		Class D 21 000 kPa (3 000 psi)						Class J 35 000 kPa (5 000 psi)					
Material code no.		1		2		4 or 5		4 or 5					
Material designation		304-1/8H		21-6-9		Ti-3AL-2,5V		Ti-3AL-2,5V					
Tube outside diameter		Tube wall thickness											
		Type A										Type B	
Dash size	mm	(inch)	mm	(inch)	mm	(inch)	mm	(inch)	mm	(inch)	mm	(inch)	
4	6,35	(.250)	0,51	(.020)	0,41	(.016)	0,41	(.016)	0,64	(.025)	0,55	(.022)	
6	9,525	(.375)	0,71	(.028)	0,51	(.020)	0,48	(.019)	0,76	(.030)	0,81	(.032)	
8	12,70	(.500)	0,89	(.035)	0,66	(.026)	0,66	(.026)	1,02	(.040)	1,09	(.043)	
10	15,875	(.625)	1,24	(.049)	0,84	(.033)	0,81	(.032)	1,27	(.050)	1,37	(.054)	
12	19,05	(.750)	1,47	(.058)	0,99	(.039)	0,99	(.039)	1,50	(.059)	1,65	(.065)	
16	25,4	(1.000)	1,65	(.065)	1,32	(.052)	1,32	(.051)	2,01	(.079)	2,23	(.088)	
20	31,75	(1.250)			1,78	(.070)	1,78	(.070)	2,49	(.098)	2,67	(.105)	
24	38,1	(1.500)									3,18	(.125)	
32	50,8	(2.000)											
^a Temperature and pressure classes shall be in accordance with ISO 6771.													

Table 3 — Outside diameters, wall thicknesses and materials for hydraulic tubing, suction and return lines — Inch tubing

Temperature ^a		Type 13 -55 °C to 135 °C (-65 °F to 275 °F)									
Pressure class ^a Design-operating-pressure (DOP)		Class N/A ^b 1 500 kPa (220 psi)		Class A 4 200 kPa (600 psi)		Class N/A ^b or B 7 000 or 10 500 kPa ^c (1 000 or 1 500 psi) ^c		Class A or N/A ^b 4 200 or 7 000 kPa ^c (600 or 1 000 psi) ^c			
Material code no.		3		7		2					
Material designation		6061-T6									
Tube outside diameter		Tube wall thickness		Tube wall thickness		Tube wall thickness		Tube wall thickness			
Dash size	mm	(inch)	Mm	(inch)	mm	(inch)	mm	(inch)	mm	(inch)	
4	6,35	(.250)					0,89	(.035)			
6	9,525	(.375)					0,89	(.035)			
8	12,70	(.500)					0,89	(.035)			
10	15,875	(.625)					0,89	(.035)			
12	19,05	(.750)					0,89	(.035)			
16	25,4	(1.000)					1,22	(.048)			
20	31,75	(1.250)			1,24	(.049)	1,52	(.060)	0,61	(.024)	
24	38,1	(1.500)			1,24	(.049)	1,85	(.073)	0,61	(.024)	
32	50,8	(2.000)	0,71	(.028)							
^a Temperature and pressure classes shall be in accordance with ISO 6771.											
^b No pressure class definition in ISO 6771 at the time of the preparation of this document.											
^c Dimensions used for different DOPs.											

Table 4 — Outside diameter, wall thicknesses, and materials for hydraulic tubing pressure and return lines — Metric tubing

Temperature ^a		Type 13 ^b -55 °C to 135 °C (-65 °F to 275 °F)												
Pressure ^a		Class H 14 000 kPa (2 000 psi)				Class D 21 000 kPa (3 000 psi)				Class E 28 000 kPa (4 000 psi)				
Material code no.		1		2		4		1		2		4		
Material designation		304-1/8H		21-6-9		Ti-3AL-2,5V		304-1/8H		21-6-9		Ti-3AL-2,5V		
Tube outside diameter		Tube wall thickness				Tube wall thickness				Tube wall thickness				
DN Size	mm	(inch)	mm	(inch)	mm	(inch)	mm	(inch)	mm	(inch)	mm	(inch)	mm	(inch)
DN05	5	(.196)	—	—	(0,4) ^c 0,5	(.015) (.019)	0,4	(.015)	0,4	(.015)	0,6	(.023)	(0,4) ^c 0,5	(.015) (.019)
DN06	6	(.236)	—	—	(0,4) ^c 0,5	(.015) (.019)	0,5	(.019)	0,4	(.015)	0,6	(.023)	0,5	(.019)
DN08	8	(.314)	—	—	(0,4) ^c 0,5	(.015) (.019)	0,5	(.019)	0,5	(.019)	0,8	(.031)	0,6	(.023)
DN10	10	(.393)	—	—	0,5	(.019)	0,7	(.028)	0,5	(.019)	0,8	(.031)	0,8	(.031)
DN12	12	(.472)	—	—	0,5	(.019)	0,8	(.031)	0,7	(.028)	0,9	(.035)	0,9	(.035)
DN14	14	(.551)	—	—	0,5	(.019)	1,0	(.039)	0,8	(.031)	—	—	1,0	(.039)
DN16	16	(.660)	—	—	0,6	(.023)	1,0	(.039)	0,8	(.031)	1,2	(.047)	1,2	(.047)
DN18	18	(.709)	—	—	0,7	(.028)	—	—	—	—	—	—	1,3	(.051)
DN20	20	(.787)	—	—	0,7	(.028)	1,5	(.059)	1,0	(.039)	1,5	(.059)	1,5	(.059)
DN22	22	(.866)	—	—	0,8	(.031)	—	—	—	—	—	—	1,6	(.063)
DN25	25	(.984)	—	—	0,9	(.035)	1,6	(.063)	1,3	(.051)	1,9	(.075)	1,8	(.071)
DN28	28	(1.102)	—	—	1,0	(.031)	—	—	—	—	—	—	2,0	(.078)
DN32	32	(1.260)	—	—	1,2	(.039)	2,2	(.087)	—	—	2,2	(.087)	2,2	(.087)

^a Temperature and pressure classes shall be in accordance with ISO 6771.

^b For higher temperatures (Type 20), refer to [Table 5](#).

^c Values in () are based on calculation only. Values below 0,5 mm wall thickness are critical due to manufacturing reason.

**Table 5 — Outside diameter, wall thicknesses, and materials for hydraulic tubing pressure lines —
Metric tubing**

Temperature ^a			Type 20 - 55 °C to 200 °C (- 65 °F to 400 °F)			
Pressure ^a			Class D 21 000 kPa (3 000 psi)		Class D 21 000 kPa (3 000 psi)	
Material code no.			4			
Material designation			Ti-3AL-2,5V			
Tube outside diameter			Tube wall thickness			
DN size	mm	(inch)	mm	(inch)	mm	(inch)
DN05	5	(.196)	—	—	—	—
DN06	6	(.236)	0,4	(.015)	0,7	(.028)
DN08	8	(.314)	—	—	—	—
DN10	10	(.393)	0,6	(.023)	0,9	(.035)
DN12	12	(.472)	0,7	(.028)	1,0	(.039)
DN14	14	(.551)	—	—	—	—
DN16	16	(.660)	0,9	(.035)	1,3	(.051)
DN18	18	(.709)	—	—	—	—
DN20	20	(.787)	1,1	(.043)	1,8	(.063)
DN22	22	(.866)	—	—	—	—
DN25	25	(.984)	1,4	(.055)	2,2	(.087)
DN28	28	(1.102)	—	—	—	—
DN32	32	(1.260)	1,6	(.063)	2,5	(.098)

^a Temperature and pressure classes shall be in accordance with ISO 6771.

Annex A

(informative)

Aerospace hydraulic tubing materials

National and industry standards for tubing material accepted by the corresponding countries conforming to the requirements specified in [Table 1](#) are given in [Table A.1](#).

Table A.1 — Corresponding national standards for tubing materials

Code no ^a	Alloy	ISO	Standards from other international bodies		National standards					Industry standards
			EN	SAE	China	France	Germany	UK	USA	
1	304-1/8H			AMS-T-6845 AMS 5566	YB 678-71					
2	21-6-9			AMS 5561						ASNA 3288 DAN 41-2 ABM7-3058 BMS 7-185 BMS7-378
3	321/347			AMS 5557 AMS 5570 AMS 5571		AIR 9423 AIR 9160		BS T66 BS T72		ABS 5249 DAN 41-1 NSA 3512 NSA 3507
4/5	Ti-3AL-2,5V	ISO 18487-1	EN 3120	AMS 4943 AMS 4944 AMS 4945 AMS 4946 AS 5620						ABS 5004 ABS 5141 MBBN6001 MBBN6002 MBBN6003 MBBN6004
6	Ti CP			AMS 4941					ASTM B 338	ABS 5012
7	6061-T6		EN 2070	AMS 4083		AIR 9302 AIR 9049	LN 9222 LN 1795	BS L117 BS L118		ABS 5144 ABS 5151 ASNA 3410 DAN 40 ABM 2-3025 ABM 2-3026 BAMS 517-001

^a Code numbers cross-referenced with [Table 1](#).