

INTERNATIONAL STANDARD

ISO
9022-2

Third edition
2015-03-01

AMENDMENT 1
2023-07

Optics and photonics — Environmental test methods —

Part 2: Cold, heat and humidity

AMENDMENT 1

Optique et photonique — Méthodes d'essais d'environnement —

Partie 2: Froid, chaleur et humidité

AMENDEMENT 1

STANDARDSISO.COM : Click to view the full PDF of ISO 9022-2:2015/Amd 1:2023



Reference number
ISO 9022-2:2015/Amd.1:2023(E)

© ISO 2023



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 172, *Optics and Photonics*, Subcommittee SC 1, *Fundamental standards*.

A list of all parts in the ISO 9022 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

STANDARDSISO.COM : Click to view the full PDF of ISO 9022-2:2015/Amd 1:2023

Optics and photonics — Environmental test methods —

Part 2: Cold, heat and humidity

AMENDMENT 1

4.2.2:

Replace 4.2.2 by the following:

4.2.2 Conditioning method 10: Cold

See Table 1.

Table 1 — Degrees of severity for conditioning method 10: Cold

Degree of severity	01	02	03	04	05	06	07	08	09	10	11	12	13	14
Test chamber temperature [°C]	-0 ± 3	-10 ± 3	-15 ± 3	-20 ± 3	-25 ± 3	-30 ± 3	-35 ± 3	-40 ± 3	-55 ± 3	-65 ± 3	-65 ± 3	-65 ± 3	-145 ± 3	-45 ± 3
Exposure time [h]	16										2	5	16	
State of operation	0 or 1 or 2 ^a									0 or 1			0 or 1 or 2 ^a	

^a When testing to degree of severity 09 or 14 is required, state of operation 2 should be justified in the relevant specification.

4.2.3:

Replace 4.2.3 by the following:

4.2.3 Conditioning method 11: Dry heat

See Table 2.

Table 2 — Degrees of severity for conditioning method 11: Dry heat

Degree of severity	01	02	03	04	05	06	07	08	09	10	11
Test chamber temperature [°C]	10 ± 2	40 ± 2	55 ± 2	63 ± 2	70 ± 2	85 ± 2	70 ± 2	85 ± 2	70 ± 2	50 ± 2	35 ± 2
Relative humidity [%]	<40										
Exposure time [h]	16				6	6	2	2	5	16	16
State of operation	0 or 1 or 2					0 or 1	0 or 1 or 2	0 or 1	0 or 1 or 2		

4.2.4:

Replace 4.2.4 by the following:

4.2.4 Conditioning method 12: Damp heat

See Table 3.

Table 3 — Degrees of severity for conditioning method 12: Damp heat

Degree of severity	01	02	03	04	05	06	07	08	09	10	11	12	13	14
Test chamber temperature [°C]	40 ± 2					55 ± 2		50 ± 2	10 ± 2	30 ± 2	35 ± 2	35 ± 2	45 ± 2	50 ± 2
Relative humidity [%]	90 to 95							95 to 100				40 to 85	95 to 100	
Exposure time	24 h	4 d	10 d	21 d	56 d	6 h	16 h	24 h	16 h					
State of operation	0 or 1 or 2 ^a													
^a State of operation 2 during the last 4 h of exposure only.														