

INTERNATIONAL STANDARD

**ISO
9384**

First edition
1991-06-15

AMENDMENT 1
2004-09-01

Fibre-cement siding shingles

AMENDMENT 1

Bardeaux en fibres-ciment

AMENDEMENT 1

STANDARDSISO.COM : Click to view the full PDF of ISO 9384:1991/Amd 1:2004



Reference number
ISO 9384:1991/Amd.1:2004(E)

© ISO 2004

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

Amendment 1 to ISO 9384:1991 was prepared by Technical Committee ISO/TC 77, *Products in fibre reinforced cement*.

Fibre-cement siding shingles

AMENDMENT 1

Page 1, Clause 2

Replace the contents of Clause 2 with the following:

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 390:1993, *Products in fibre-reinforced cement — Sampling and inspection*

ISO 395:1983, *Asbestos-cement slates*

ISO 2602:1980, *Statistical interpretation of test results — Estimation of the mean — Confidence interval*

Page 2, subclause 5.2

Replace the text and table by:

5.2 Mechanical characteristics

When tested as specified in 6.1.4, the shingles shall have a minimum modulus of rupture, R_f , at least equal to the values given in Table 1. This shall be the average of values obtained from testing the test specimen in both directions.

Table 1

Category	Minimum modulus of rupture	
	R_f MPa wet	ambient
I	7	10
II	13	16

Page 2

Add a new subclause, 5.3.6

5.3.6 Soak dry

When shingles are tested as specified in 6.2.5, the limit L_i of the average ratio, r , as defined in 6.2.5.4, shall be greater than 0,75.

Page 2

Add a new subclause, 5.4

5.4 Reaction to fire

The details of the specifications and acceptance criteria of reaction to fire may be defined by national standards.

Page 2, subclause 6.1.1

Replace the text by:

6.1.1 General

The objective of an acceptance test is to establish whether a batch of products conforms to a specification. The tests are performed on samples drawn either from continuous production or from a consignment.

NOTE Test methods and specification limit values are defined in this International Standard. Sampling levels and acceptance criteria are defined in national documents or by default, in ISO 390.

Acceptance tests as described in 6.1.2 to 6.1.6. shall be performed on shingles as-delivered.

Page 3, subclause 6.1.4

Replace the text by:

6.1.4 Bending test (obligatory)

The test shall be carried out on full size shingles or cut specimens. These specimens shall be preconditioned in ambient (above 5 °C) or wet conditions or as specified by national standards. In the absence of national standards, this test shall be carried out on wet-conditioned specimens (except for shingles of category 1, where the time of immersion shall be reduced to 2 h). Specimens shall be tested immediately after removal from water.

Page 3, subclause 6.1.4.1.2

Replace the text by:

6.1.4.1.2 Micrometer, reading to 0,05 mm with flat metal jaws between 6 mm and 15 mm in diameter.

Page 5, subclause 6.2.1

Replace the text by:

6.2.1 General

A type-test is concerned with the approval of a new product and/or a fundamental change in formulation and/or method of manufacture. The test is performed on the as-delivered product. The test is required to demonstrate conformity of a generic product to a specification but is not required for each production batch.

The temperature and the relative humidity shall be indicated in the test report.

Page 5, subclause 6.2.3.1

Replace the text by:

6.2.3.1 Apparatus

The apparatus consists of any suitable construction with a vertical frame into which the shingles shall be mounted and alternately heated uniformly by radiant heat then sprayed with water.

The total area of the shingles to be tested shall be approximately square, between 3 m² and 5 m².

The specimen shall be tested at 90° pitch for façades and at any angle defined by national standards for roofs.

A water-sprinkling device, with an output of approximately

1,0 l/min/m² for façades

2,5 l/min/m² for roofing

delivering water at an ambient temperature higher than 5 °C.

The heating device shall be calibrated in order to maintain a uniform black body⁷⁾ surface temperature equal to 70 °C ± 5 °C for roofs and 60 °C ± 5 °C for façades, during the heating period.

It should provide an approximately uniform power output during this period.

Page 5, subclause 6.2.3.2

Replace the text by:

6.2.3.2 Procedure

The test shall be carried out on full size shingles as delivered. The test specimens shall be submitted to a preliminary conditioning as follows:

- immersion for 24 h in water at ambient temperature (> 5 °C);
- storage for 7 d in a laboratory atmosphere with separation to allow air circulation.

The shingles shall be fixed according to national codes or, in their absence, manufacturer's recommendations.

The shingles shall be submitted to 25 test cycles of heat-rain, each part of the cycle having the duration as given in Table 2.

7) For the definition of a black body see ASTM E 638-78. For this test an aluminium plate of 1 mm thickness painted with matt black paint is used as a black body.

The measurement device is a thermocouple or a similar device fixed on the surface of the aluminium plate.

Table 2 — Heat-rain cycle

Operation	Duration
Water spray 1,0 l/min/m ² for façades 2,5 l/min/m ² for roofs	2 h 50 min
Pause	10 min
Radiant heating 60 °C ± 5 °C for façades 70 °C ± 5 °C for roofs	2 h 50 min
Pause	10 min
Total	6 h

Page 6

Add a new clause, 6.2.5

6.2.5 Soak dry (optional)

6.2.5.1 Preparation of specimen

Sample 10 shingles, as delivered by the producer. Cut 10 sets of paired specimens to suit the bending test described in 6.1.4. Each pair of specimens shall be given the same number for later comparison of results.

6.2.5.2 Apparatus

The apparatus includes the following items:

6.2.5.2.1 ventilated oven, capable of attaining a temperature of 60 °C ± 5 °C and a relative humidity ≤ 20 % with a full load of specimens.

6.2.5.2.2 bath, filled with water at ambient temperature of more than 5 °C.

6.2.5.2.3 testing equipment, for determination of bending strength as defined in 6.1.4.1.1.

6.2.5.3 Procedure

Divide the paired specimens to form two lots of 10 specimens each. After the conditioning procedure, submit the first lot of 10 specimens to the bending tests as described in 6.1.4.

At the same time submit the second lot to 25 soak dry cycles consisting of

- immersion in water at ambient temperature (above 5 °C) for 18 h;
- drying in a ventilated oven at 60 °C ± 5 °C and relative humidity < 20 % for 6 h.

If necessary, an interval up to 72 h between cycles is allowed. During this interval, the specimens shall be stored in immersed conditions.

After 25 cycles, place the specimens in a laboratory atmosphere for 7 d.

At the end of this period, carry out the wet bending test as specified in 6.1.4.1.1.

6.2.5.4 Expression and interpretation of results

For each pair of specimens i ($i = 1$ to 10), calculate the individual ratio, r_i , as follows:

$$r_i = R_{fi} / R_{fci}$$

where

R_{fi} is the modulus of rupture of the i th test specimen after the soak-dry cycling;

R_{fci} is the modulus of rupture of the i th reference test specimen (from the first lot).

Calculate the average, $\bar{r}$, and standard deviation, s , of the individual ratios, r_i (see ISO 2602). Calculate the 95 % lower confidence limit, L_i , of the average ratio $\bar{r}$, as follows:

$$L_i = \bar{r} - 0,58s$$

Assess the ratio against the specifications of 5.3.6.

Page 6, subclause 8.1

Replace the text by:

8.1 Conformity with requirements

The manufacturer shall establish and maintain an effective documented quality control system developed, e.g., on the basis of the standards of the series ISO 9000.

For the acceptance tests, 90 % of the delivered products shall fulfil the requirements of 5.1. to 5.3. In the absence of national documents, the sampling schemes prescribed in ISO 390 with an AQL of 4 % and an inspection level S_3 ensure that for large batches approximately 90 % of the items fulfil these requirements. Other methods may be used provided they give the same level of quality.

For each type-test, in the absence of a fundamental change to the formulation and/or method of manufacture, results from one test performed should be taken as a reference of conformity to the specification.

8.2 Evidence of conformity of consignment of finished products

When tenders and/or orders do not specify receiving inspection, the lots delivered are presumed to be in conformity with this International Standard.

Inspection of a consignment of finished products should take place only where there is no third party certification.

It is conducted, e.g., in accordance with ISO 390, which gives an AQL of 4 % with an inspection level S_3 and in accordance with Annex A.

For special applications, different levels of quality may be applied after agreement between manufacturer and purchaser.