

# ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

## ISO RECOMMENDATION R 1337

WROUGHT COPPERS

1st EDITION

April 1971

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 1337:1971

## BRIEF HISTORY

The ISO Recommendation R 1337, *Wrought coppers*, was drawn up by Technical Committee ISO/TC 26, *Copper and copper alloys*, the Secretariat of which is held by the Deutscher Normenausschuss (DNA).

Work on this question led to the adoption of Draft ISO Recommendation No. 1337, which was circulated to all the ISO Member Bodies for enquiry in October 1967. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

|                |                      |                       |
|----------------|----------------------|-----------------------|
| Australia      | India                | Portugal              |
| Belgium        | Iran                 | South Africa, Rep. of |
| Brazil         | Israel               | Spain                 |
| Canada         | Italy                | Sweden                |
| Chile          | Japan                | Switzerland           |
| Czechoslovakia | Korea, Dem.P.Rep. of | Turkey                |
| Finland        | Mexico               | U.A.R.                |
| France         | Netherlands          | United Kingdom        |
| Germany        | Norway               | U.S.S.R.              |
| Greece         | Poland               | Yugoslavia            |

No Member Body opposed the approval of the Draft.

This Draft ISO Recommendation was subsequently divided into two parts, which were submitted by correspondence to the ISO Council. The latter decided to accept them as ISO RECOMMENDATIONS.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 1337:1971

## WROUGHT COPPERS

### 1. SCOPE

This ISO Recommendation relates to chemical compositions, electrical properties and forms of semi-manufactured products of wrought coppers, currently available in commercial quantities.

Principles of classification are given in an Appendix.

### 2. CHEMICAL COMPOSITION

If the purchaser's requirements necessitate limits for any element not specified in Table 1, these should be agreed upon between supplier and purchaser.

TABLE 1

| Designation    | Chemical composition %                  | Average density    |
|----------------|-----------------------------------------|--------------------|
|                |                                         | kg/dm <sup>3</sup> |
| <b>Cu-ETP</b>  | Cu (+ Ag) min. 99.90                    | 8.9                |
| <b>Cu-FRHC</b> | Cu (+ Ag) min. 99.90                    | 8.9                |
| <b>Cu-FRTP</b> | Cu (+ Ag) min. 99.85                    | 8.9                |
| <b>Cu-OF</b>   | Cu (+ Ag) min. 99.95                    | 8.9                |
| <b>Cu-DLP</b>  | Cu (+ Ag) min. 99.90<br>P 0.005 – 0.012 | 8.9                |
| <b>Cu-DHP</b>  | Cu (+ Ag) min. 99.85<br>P 0.013 – 0.050 | 8.9                |

## 3. ELECTRICAL PROPERTIES

TABLE 2

| Designation | Electrical properties in the annealed temper |                                             |                                 |
|-------------|----------------------------------------------|---------------------------------------------|---------------------------------|
|             | Maximum resistivity at 20 °C                 | Minimum conductivity at 20 °C               |                                 |
|             | $\frac{\Omega \cdot \text{mm}^2}{\text{m}}$  | $\frac{\text{m}}{\Omega \cdot \text{mm}^2}$ | % IACS                          |
| Cu-ETP      | 0.017 241 ... <sup>(1)</sup>                 | 58.00 <sup>(1)</sup>                        | 100.0 <sup>(1)</sup>            |
|             | 0.017 544 ...                                | 57.00                                       | 98.28                           |
| Cu-FRHC     | 0.017 241 ... <sup>(1)</sup>                 | 58.00 <sup>(1)</sup>                        | 100.0 <sup>(1)</sup>            |
|             | 0.017 544 ...                                | 57.00                                       | 98.28                           |
| Cu-FRTP     | ( $\approx 0.02$ ) <sup>(2)</sup>            | ( $\approx 50$ ) <sup>(2)</sup>             | ( $\approx 86$ ) <sup>(2)</sup> |
| Cu-OF       | 0.017 241 ...                                | 58.00                                       | 100.0                           |
| Cu-DLP      | ( $\approx 0.017\ 8$ ) <sup>(3)</sup>        | ( $\approx 56$ ) <sup>(3)</sup>             | ( $\approx 97$ ) <sup>(3)</sup> |
| Cu-DHP      | ( $\approx 0.025$ ) <sup>(2)</sup>           | ( $\approx 40$ ) <sup>(2)</sup>             | ( $\approx 69$ ) <sup>(2)</sup> |

(1) Wire is usually supplied with maximum resistivity of  $0.017\ 241\ \Omega \cdot \text{mm}^2/\text{m}$  at 20 °C (minimum conductivity 100.0 % IACS or  $58.00\ \text{m}/\Omega \cdot \text{mm}^2$ ), if the national standards do not specify anything else.

Other forms, however, are only so supplied if agreed between supplier and purchaser.

(2) For information only, but not specified.

(3) For information only; electrical property requirements should be agreed between supplier and purchaser.

## 4. FORMS OF SEMI-MANUFACTURED PRODUCTS

TABLE 3

| Designation | Plate Sheet | Strip | Rod Bar | Extruded sections <sup>(1)</sup> | Tube <sup>(2)</sup> | Wire | Forgings |
|-------------|-------------|-------|---------|----------------------------------|---------------------|------|----------|
| Cu-ETP      | X           | X     | X       | (X)                              | X                   | X    | (X)      |
| Cu-FRHC     | X           | X     | X       | (X)                              | X                   | X    | (X)      |
| Cu-FRTP     | X           | X     | X       | (X)                              |                     |      |          |
| Cu-OF       | X           | X     | X       | (X)                              | (X)                 | (X)  | (X)      |
| Cu-DLP      | (X)         | (X)   | X       | (X)                              | (X)                 |      |          |
| Cu-DHP      | X           | X     | X       | (X)                              | X <sup>(3)</sup>    |      |          |

X indicates the main manufactured forms (see section 5).

(X) indicates forms manufactured in smaller quantities, for example in certain countries only or for special purposes.

If no symbol is given, the form is not considered of importance for that type of copper, but it does not necessarily indicate that such a product cannot be manufactured.

(1) Sections or shapes made by extruding or by a combination of extruding and drawing.

(2) Tubes for general purposes.

(3) Also for condenser and heat exchanger tubes.