

# ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

## ISO RECOMMENDATION R 2076

GENERIC NAMES FOR MAN-MADE FIBRES

1st EDITION

July 1971

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 2076:1971

## BRIEF HISTORY

The ISO Recommendation R 2076, *Generic names for man-made fibres*, was drawn up by Technical Committee ISO/TC 38, *Textiles*, the Secretariat of which is held by the British Standards Institution (BSI).

Work on this question led to the adoption of Draft ISO Recommendation No. 2076, which was circulated to all the ISO Member Bodies for enquiry in May 1970. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

|                |                       |                |
|----------------|-----------------------|----------------|
| Australia      | Germany               | Spain          |
| Belgium        | Greece                | Sweden         |
| Brazil         | India                 | Switzerland    |
| Canada         | Iran                  | Turkey         |
| Chile          | Israel                | U.A.R.         |
| Czechoslovakia | Netherlands           | United Kingdom |
| Denmark        | New Zealand           | U.S.A.         |
| Finland        | Norway                | U.S.S.R.       |
| France         | South Africa, Rep. of |                |

The following Member Body opposed the approval of the Draft :

Japan

This Draft ISO Recommendation was then submitted by correspondence to the ISO Council, which decided to accept it as an ISO RECOMMENDATION.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 2076:1971

## GENERIC NAMES FOR MAN-MADE FIBRES

### 1. SCOPE

This ISO Recommendation gives a list of generic names\*, for technical and commercial use, of the different categories of man-made fibres at present manufactured on an industrial scale for textile and other purposes.


### 2. GENERAL DEFINITIONS

Man-made fibres include filament yarn, tows and staple fibres manufactured from natural or synthetic polymers.

The use of the generic names given in the first column of the following Table applies to fibres which comprise at least 85 % of the polymer described in the second column, the remaining portion up to 100 % being made up of additives not chemically linked with the said polymer.

\* In the English and French languages the generic names need not be written with initial capital letters.

TABLE — Generic names

| Generic name                 | Constitution of polymer                                                                                                                            | Typical examples, chemical formulae or characteristics                                                                                                                                                                                                                                             |
|------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>cupro*</b>                | cellulose II                                                                                                                                       | regenerated cellulose obtained by cuprammonium process                                                                                                                                                                                                                                             |
| <b>viscose*</b>              | cellulose II                                                                                                                                       | regenerated cellulose obtained by the viscose process                                                                                                                                                                                                                                              |
| <b>modal*</b>                | cellulose II                                                                                                                                       | regenerated cellulose obtained by processes giving a high tenacity and a high wet modulus. These fibres or filaments should be able to resist in the wet state a load per unit linear density of 22.0 cN per tex. Under this load the elongation in the wet state should not be greater than 15 %. |
| <b>deacetylated acetate*</b> | cellulose II                                                                                                                                       | regenerated cellulose obtained by approximately complete deacetylation of a cellulose acetate                                                                                                                                                                                                      |
| <b>acetate</b>               | secondary cellulose acetate                                                                                                                        | cellulose acetate wherein less than 92 % but at least 74 % of the hydroxyl groups are acetylated                                                                                                                                                                                                   |
| <b>triacetate</b>            | cellulose triacetate                                                                                                                               | cellulose acetate wherein at least 92 % of the hydroxyl groups are acetylated                                                                                                                                                                                                                      |
| <b>protein</b>               | regenerated natural protein                                                                                                                        | casein, arachin, zein, etc.                                                                                                                                                                                                                                                                        |
| <b>alginate</b>              | metallic salts of alginic acid                                                                                                                     | calcium alginate :<br>                                                                                                                                                                                         |
| <b>acrylic</b>               | linear macromolecules comprising at least 85 % (by mass) in the chain of the recurring unit<br><br>$-CH_2-\underset{\text{CN}}{\underset{ }{CH}}-$ | polyacrylonitrile : $-(CH_2-\underset{\text{CN}}{\underset{ }{CH}})_p-$<br><br>and<br>acrylic copolymer :<br>$-\left[ (CH_2-\underset{\text{CN}}{\underset{ }{CH}})_m - (CH_2-\underset{\text{Y}}{\underset{ }{\overset{\text{X}}{C}}})_n \right]_p -$                                             |

\* The name "rayon", in French *rayonne*, was not used by ISO in this document because this name, used generically for regenerated cellulose fibres in some countries, does not have the same meaning everywhere. Each Member Body must determine its own position on this question and, should it be deemed necessary, define that position in its national standards.