

Transformed

ISO

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION

**ISO RECOMMENDATION
R 713**

CHEMICAL ANALYSIS OF ZINC

POLAROGRAPHIC DETERMINATION OF LEAD AND CADMIUM

1st EDITION
May 1968

COPYRIGHT RESERVED

The copyright of ISO Recommendations and ISO Standards belongs to ISO Member Bodies. Reproduction of these documents, in any country, may be authorized therefore only by the national standards organization of that country, being a member of ISO.

For each individual country the only valid standard is the national standard of that country.

Printed in Switzerland

Also issued in French and Russian. Copies to be obtained through the national standards organizations.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 713:1968

BRIEF HISTORY

The ISO Recommendation R 713, *Chemical analysis of zinc – Polarographic determination of lead and cadmium*, was drawn up by Technical Committee ISO/TC 18, *Zinc and zinc alloys*, the Secretariat of which is held by the Institut Belge de Normalisation (IBN).

Work on this question by the Technical Committee began in 1963 and led, in 1965, to the adoption of a Draft ISO Recommendation.

In September 1966, this Draft ISO Recommendation (No. 992) was circulated to all the ISO Member Bodies for enquiry. It was approved, subject to a few modifications of an editorial nature, by the following Member Bodies :

Argentina	Ireland	Switzerland
Belgium	Italy	Thailand
Brazil	Japan	Turkey
Canada	Korea, Rep. of	U.A.R.
Chile	Korea, D.P. Rep. of	United Kingdom
Czechoslovakia	New Zealand	U.S.A.
France	Norway	U.S.S.R.
Germany	South Africa,	Yugoslavia
Hungary	Rep. of	
India	Spain	

One Member Body opposed the approval of the Draft :

Australia

The Draft ISO Recommendation was then submitted by correspondence to the ISO Council which decided, in May 1968, to accept it as an ISO RECOMMENDATION.

STANDARDSISO.COM : Click to view the full PDF of ISO/R 713:1968

CHEMICAL ANALYSIS OF ZINC

POLAROGRAPHIC DETERMINATION OF LEAD AND CADMIUM

1. SCOPE

This ISO Recommendation describes a polarographic method for the simultaneous determination of lead and cadmium in zinc.

The method applies to the following types of zinc : Zn 99.995, Zn 99.99 and Zn 99.95,* defined in ISO Recommendation R 752, *Zinc ingots*.

It is suitable for the determination of lead and cadmium contents between 0.001 and 0.05 %.

2. PRINCIPLE OF THE METHOD

Simultaneous polarographic determination of lead and cadmium in a very slightly acid chloride medium.

3. REAGENTS

All reagents should be of analytical reagent grade.

Distilled or demineralized water should be used for preparing solutions and during the actual determination.

3.1 *Inert gas*, oxygen-free.

3.2 *Hydrochloric acid* ($d = 1.19$), free from lead and cadmium.

Check the purity by the following test :

3.2.1 Take three 5 g test portions of Zn 99.995 zinc or Zn 99.99 zinc for die castings.

3.2.2 Attack the first and second test portion with 35 to 40 ml of hydrochloric acid (3.2), as indicated under clause 6.3 starting at clause 6.3.2.

3.2.3 To the second test portion, add 1 ml of the standard solution (3.9).

3.2.4 Attack the third test portion with 100 ml of hydrochloric acid (3.2).

3.2.5 The acid is suitable for use if the differences in step heights between the first and third test portions are less than those between the first and second test portions. If these conditions are satisfied the volume of acid used for the dissolution contains less than 0.005 mg of lead and less than 0.005 mg of cadmium.

3.3 *Hydrogen peroxide*, 30 % H_2O_2 (m/m)

3.4 *Nitric acid* ($d = 1.3$ to 1.4).

3.5 *Hydroxylammonium chloride*

3.6 *Nickel chloride solution* containing 2 g of $NiCl_2 \cdot 6H_2O$ per litre.

* Although these types of zinc do not normally contain any thallium or indium, these two elements, if present, can interfere in this determination.

3.7 *Standard solution of lead and cadmium No. 1*

In a 100 ml beaker, place 0.5 g of pure lead and 0.5 g of pure cadmium, weighed with an accuracy of ± 0.001 g. Cover with approximately 10 ml of water and dissolve with about 5 ml of nitric acid (3.4). Drive off the nitrous fumes. Cool. Transfer quantitatively into a 500 ml volumetric flask. Make up the volume to 500 ml with water. Mix. 1 ml of the solution contains 1 mg of lead and 1 mg of cadmium.

3.8 *Standard solution of lead and cadmium No. 2*

Dilute the standard solution of lead and cadmium No. 1 (3.7) in the proportion of one part to nine parts of water. 1 ml of the solution contains 0.1 mg of lead and 0.1 mg of cadmium.

3.9 *Standard solution of lead and cadmium No. 3*

Dilute the standard solution of lead and cadmium No. 2 (3.8) in the proportion of one part to nine parts of water. 1 ml contains 0.01 mg of lead and 0.01 mg of cadmium.

3.10 *Solution of zinc chloride, free from lead and cadmium*

Dissolve 100 g of Zn 99.995 zinc in 400 ml of hydrochloric acid (3.2). Evaporate to a syrupy consistency. Take up with 400 ml of water. Transfer to a 500 ml volumetric flask. Add 20 g of zinc dust. Agitate from time to time for at least 30 minutes. Make up to volume with water. Mix. Allow to settle. Filter the solution without washing. This solution contains approximately 200 mg of zinc per millilitre.

Verify that the step heights are less than those produced by adding 0.5 ml of the standard solution of lead and cadmium No. 3 (3.9) to 25 ml of the solution of zinc chloride.

This test determines whether 25 ml of the solution of zinc chloride contains less than 0.005 mg of lead and less than 0.005 mg of cadmium.

4. APPARATUS

4.1 *Ordinary laboratory equipment*

4.2 *Polarograph*

4.3 *Thermostatically controlled water bath*

5. SAMPLING

The requirements of ISO Recommendation R ..., * *Selection and preparation of samples for analysis*, should apply.

6. PROCEDURE

6.1 *Test portion*

Weigh 5 g of the test sample with an accuracy of ± 0.01 g.

6.2 *Plotting of the calibration curve*

Prepare a calibration curve such that it will include the expected content.

As an example, assuming that a calibration curve is to be established by 3 steps corresponding to lead and cadmium contents of 0.001, 0.002 and 0.005 %, then

6.2.1 Into a series of 100 ml beakers, transfer 25 ml of the solution of zinc chloride (3.10) corresponding to 5 g of metallic zinc. Add 5 ml, 10 ml and 25 ml respectively of the standard solution of lead and cadmium No. 3 (3.9).

6.2.2 Evaporate to a syrupy consistency and proceed as outlined in clauses 6.3.3 to 6.3.5, then polarograph as outlined in clause 6.4.

* To be prepared later.