
**Test methods for repair materials for
water-leakage cracks in underground
concrete structures —**

**Part 6:
Test method for response to the
substrate movement**

*Méthodes d'essai pour matériaux de réparation pour fissures dues à
l'eau dans les structures en béton —*

Partie 6: Méthode d'essai de la réponse aux mouvements du substrat



STANDARDSISO.COM : Click to view the full PDF of ISO/TS 16774-6:2017



COPYRIGHT PROTECTED DOCUMENT

© ISO 2017, Published in Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Ch. de Blandonnet 8 • CP 401
CH-1214 Vernier, Geneva, Switzerland
Tel. +41 22 749 01 11
Fax +41 22 749 09 47
copyright@iso.org
www.iso.org

Contents

	Page
Foreword.....	iv
Introduction.....	v
1 Scope.....	1
2 Normative reference.....	1
3 Terms and definitions.....	1
4 Principle.....	2
5 Apparatus.....	2
6 Preparation of the test specimen and artificial crack conditions.....	2
7 Procedure.....	3
7.1 Substrate behaviour stress test.....	3
7.2 Permeability test.....	3
8 Presentation of results.....	3
9 Test report.....	4
9.1 Information on the repair material of the test target.....	4
9.1.1 General.....	4
9.1.2 Other information.....	4
9.2 Information on the test.....	4
Annex A (informative) Example test method.....	5
Bibliography.....	15

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html

The committee responsible for this document is ISO/TC 71, *Concrete, reinforced concrete and pre-stressed concrete*, Subcommittee SC 7, *Maintenance and repair of concrete structures*.

A list of all parts in the ISO 16774 series can be found on the ISO website.

Introduction

ISO/TR 16475 outlines six basic properties and the required performance levels of water-leakage repair materials, and ISO/TS 16774-1 through ISO/TS 16774-6 provide test methods designed to evaluate the respective properties of these repair materials.

These test methods are intended to serve as references for nations that have not yet developed a test method on the six proposed required performance properties of water leakage repair materials. If other forms of test methods that are simpler, more accurate or more organized are available, such methods are recommended for use instead.

Many of the dependent variables outlined in the ISO 16774 series of reference test methods are subject to change in accordance with the environmental conditions (temperature; chemical substance and concentration; relative humidity; width of movement activity; water pressure or water flow velocity, etc.) outlined in the standards and testing parameters used in respective countries.

In ISO/TS 16774-1, ISO/TS 16774-5 and ISO/TS 16774-6, for the purpose of objectively comparing the performance of injected repair materials, artificial cracks of same volume were used to control the usage of repair materials for each testing cycle and enable repetition of the same test methods under the same conditions.

STANDARDSISO.COM : Click to view the full PDF of ISO/TS 16774-6:2017

Test methods for repair materials for water-leakage cracks in underground concrete structures —

Part 6:

Test method for response to the substrate movement

1 Scope

This document specifies a laboratory test method for evaluating the substrate (crack) movement response of water-leakage crack repair materials through permeability testing.

The repair material injected into a test specimen with an artificial crack undergoes simulated movements normally caused by thermal expansion, settlement and vibrations in leakage cracks found in concrete structures under the applied conditions outlined in different national testing parameters that reflect different environmental conditions. As such, the results are only intended to provide a comparative performance evaluation of the waterproofing repair materials between different products of the same type of repair material.

This document outlines general guidelines and procedures for the test method. Specific variables that control the quantifiable parameters of the testing are filled in using relevant national standardizations and/or testing parameters.

NOTE 1 This test method classifies and categorizes materials that are tested into families of similar properties for the purpose of making relative comparisons with the data results.

NOTE 2 Each individual repair material can be further tested in an actual construction site application for a complete assessment.

2 Normative reference

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO/TR 16475, *Guidelines for the repair of water-leakage cracks in concrete structures*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TR 16475 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org.obp>

3.1

repair material

<water-leakage cracks>material used for preventing the escape of water at cracks in concrete

EXAMPLE Injection type grouts, such as synthetic rubberized asphalt, mastic, urethane, poly-urea, etc.

Note 1 to entry: In this document, target ingredients are limited to injection materials outlined in ISO/TR 16475.

4 Principle

Response to loss, deterioration and other physical changes by the behavioral movement of leakage crack (such as crack movements caused by thermal shrinkage and expansions, differential settlement, and/or vibrations) is one of the fundamental properties that water leakage repair materials should possess. To evaluate the leakage crack repair material's **responsiveness to substrate movement**, this test method uses two separate procedures: 1) a substrate movement test method and 2) a permeability test method.

The test specimen with an artificial crack is injected with repair material, and the specimen goes through an induced tensile/compressive stress test for a specified number of cycles using a substrate movement simulating apparatus, such as a Universal Testing Machine (UTM). To evaluate whether the repair material loses its waterproofing property due to tensile/compressive stress (substrate/crack movement), the specimen goes through water permeability test for the last stage of the test method.

5 Apparatus

5.1 Substrate movement apparatus, which must be able to exert a cycle of predetermined width of compressive and tensile force per one minute.

NOTE A Universal Testing Machine (UTM) is recommended for this testing method.

5.2 Air compressor, which should be able to handle minimum air pressure value of 0,1 N/mm² to 0,3 N/mm².

5.3 Permeability test chamber, which should be able to handle minimum water pressure value of 0,1 N/mm² to 0,3 N/mm² (output method).

NOTE Conditions outlined in 5.2 and 5.3 are subject to change in accordance to different national testing parameters and requirements.

6 Preparation of the test specimen and artificial crack conditions

- 1) Two separate concrete or mortar substrate parts should be cured to form a water-leakage crack test specimen. The parts consist of upper and bottom parts, and they should be flat and cylindrical in shape and made using concrete or mortar.

NOTE The mix proportion is (water: cement: fine aggregate = 1: 2: 6, mass ratio). The curing period for the mortar or concrete substrate parts is approximately 72 hours, but subject to change in accordance to different national testing parameters and requirements.

- 2) The bottom substrate is drilled with evenly spaced holes (Ø2,5 mm) near the centre of the substrate. The pinholes shall be drilled all the way through from one surface of the substrate part to the other.

NOTE The purpose of these pinholes is to check for signs of leakage during repair material injection and during permeability testing.

3. Spacers are placed on one surface of the bottom substrate part without covering the pinholes, and the upper substrate part is placed on top of the spacers. The substrate parts, now having formed the test specimen with the artificial crack, is held together with tape, silicone sealants or other applicable materials along the exterior side. The spacer height represents the width of the crack and can vary depending on the different national testing parameters and requirements.

NOTE Any material can be used to hold the two substrate parts together with a crack space in between, but should leave an inlet in one side for material injection.

4. The injection space should be flushed out with water before injecting the repair material to remove any debris as well as to verify that the interior mortar surface is sufficiently wet for repair material injection. After making sure the substrate parts are held together tightly, place the test specimen

under water for a specified amount of time. After taking the specimen out of the water, inject the repair material into the specimen crack space.

The injection method varies according to different national testing parameters and requirements. If manufacturer's instructions are available, this method is recommended instead. If debris and other substances are present they should be cleared prior to material injection.

7 Procedure

7.1 Substrate behaviour stress test

- 1) Once the test specimens have been injected with the repair materials and taken out of the water after the specified duration, attach the fixing bolt to the upper substrate that will connect to the jig on the substrate movement apparatus (Universal Testing Machine).
- 2) Place the test specimen on the substrate movement apparatus.
- 3) Run the substrate movement test.

NOTE The substrate movement simulation test will consist of applying tensile and compressive stress on the test specimen through repeated cycles of induced motion. The apparatus jig will pull on the upper part of the specimen for a specified width and press down the same length. This procedure will repeat until sufficient amount of tensile/compressive stress has been applied on to the specimen. Duration, width and cycle number are subject to change in accordance with different national test parameters and requirements.

- 4) Remove the specimen from the substrate movement apparatus and record its conditions. Proceed to the permeability test.

NOTE For detailed and clearer explanation, refer to [Annex A](#).

7.2 Permeability test

- 1 Place the specimen in the permeability test chamber.

NOTE The procedure outlined will follow the steps required for the output method of this permeability test. Other methods, if applicable, can be used for this step.

- 2 Fill the chamber with water. Connect the air compressor valves to the air compression chamber.
- 3 Run the permeability test.

NOTE Water/air pressure values are subject to change in accordance to different national test parameter requirements.

- 4 Observe and record to see if there is leakage or not with the test specimen.

Photos of the specimen and equipment conditions must be taken at every stage possible during each and every test procedure for recording and information purposes.

NOTE For detailed and clearer explanation, refer to [Annex A](#).

8 Presentation of results

The continually induced physical stress of the test cycles can affect the repair material's performance level. This test method evaluates the physical properties of the repair materials under the prescribed conditions of permeability testing through a qualitative evaluation of whether the repair material can maintain adequate waterproofing properties. These results can be used in the future as a data base for a guideline on selecting appropriate repair materials with the required responsive properties against substrate/crack movement in leakage crack surfaces of underground concrete structures.

9 Test report

9.1 Information on the repair material of the test target

9.1.1 General

The test report should record the following information on repair material of the test target:

- 1) Producer (name, address, phone number).
- 2) Production date, time, place of the repair material.
- 3) Type, storage method and authentication of the repair material.
- 4) Manufacturer's product instructions and relevant repair material guidelines.
- 5) Data on chemical composition of repair material as indicated in manufacturer's data sheet.

9.1.2 Other information

The following information is recorded on demand, if required:

- 1) Project of the test target.
- 2) Application areas of the test specimen.
- 3) Result of some eco-toxicological performance tests to account for the release of hazardous substances and the subsequent effects on health and safety.

9.2 Information on the test

The test report should record the following information on the test:

- 1) Test manager.
- 2) Name, purpose of the test.
- 3) Ambient condition of the lab (temperature, relative humidity, safety conditions etc.).
- 4) Production time and place of the specimens.
- 5) Shape and size of the specimens, and the number of replicates of the specimens for repeat test.
- 6) Identification of the specimens (Lot No. etc.).
- 7) Curing and storage conditions.
- 8) Information on the test repair material (name, producer, validity etc.).
- 9) Test data (production, measurement, test period etc.).
- 10) Type of facilities, equipment, tools.
- 11) Status of test equipment, tools.
- 12) Test results.
- 13) Details on other test programmes and procedures.

Annex A (informative)

Example test method

A.1 Principle

This example test method evaluates a repair material's resistance to tensile/compressive stress caused by substrate movement using artificial cracked test specimens. The repair material is injected into these specimens and is placed on a UTM (Universal Testing Machine) where the specimen will undergo a detailed and specific substrate movement cycles. Afterwards, a permeability test can be conducted to see if leakages occur to determine whether the substrate movement stress changed the repair material's waterproofing properties.

This example test method employs test parameters and environmental conditions outlined in the test standards used in Korea.

NOTE This test method requires the usage of fabricated and simulated artificial cracks as illustrated with the specimen used in this example.


A.2 Apparatus

A.2.1 Universal Testing Machine (UTM), which can exert a minimum cycle of 0 mm ~ 2,5 mm width of compressive and tensile force per minute.

A.2.2 Air compressor, which should be able to handle minimum air pressure value of 0,1 N/mm² to 0,3 N/mm².

A.2.3 Permeability test chamber, which should be able to handle a minimum water pressure value of 0,1 N/mm² to 0,3 N/mm² (output method).

NOTE Refer to [Figure A.1 a\) and b\)](#).



a) Permeability test chamber (output)

b) Compressor and water pressure chamber

Key

1	watertightness chamber	a	pressure: 0,3 N/mm ²
2	pressure regulator	b	water: 1 L
3	air compressor	c	see Figure A.2
4	test specimen		

Figure A.1 — Apparatus for example test method

A.2.4 Test specimen.

NOTE Refer to [Figures A.2](#) and [A.3](#).

A.2.4.1 Fixing jig for connecting test specimen to Universal Testing Machine (UTM)($\varnothing$ 6 mm).

A.2.4.2 Upper substrate part (acrylic, $\varnothing$ 100 mm $\times$ 30 mm).


A.2.4.3 Repair material.

A.2.4.4 Concrete or mortar substrate part (water: cement: fine aggregate = 1: 2: 6, mass ratio). Height of the concrete or mortar mould is 15 mm.

A.2.4.5 Steel plate for setting the concrete or mortar substrate in place (STS 304, $\varnothing$ 220 mm $\times$ 5 mm).

A.2.4.6 Non-woven fabric for filtering repair material particulates when testing cementitious grout material (synthetic fibre, $\varnothing$ 100, 180 g/m²).


A.2.4.7 Acrylic plate for setting the non-woven fabric in place (acrylic, $\varnothing$ 100 mm $\times$ 5 mm).



Key

- | | | | |
|---|--|----|--|
| 1 | O-ring (width 5 mm) | 9 | steel plate for fixing mortar substrate ($\varnothing$ 220 $\times$ 5 mm) |
| 2 | acrylic band for seal | 10 | bolt for fixing with chamber ($\varnothing$ 6 mm) |
| 3 | bolt for connecting upper substrate | 11 | bolt for fixing acrylic plate ($\varnothing$ 6 mm) |
| 4 | fixing nut for connecting mortar substrate ($\varnothing$ 6 mm) | 12 | non-woven fabric for filtering repair material |
| 5 | upper substrate (acrylic, $\varnothing$ 100 $\times$ 30 mm) | 13 | acrylic plate for fixing non-woven fabric |
| 6 | repair material | 14 | inlet cover for injecting ($\varnothing$ 12 mm) |
| 7 | fixing jig | a | injection hole ($\varnothing$ 10 mm) |
| 8 | mortar substrate | b | leakage hole ($\varnothing$ 2,5 mm) |

Figure A.2 — Diagram of the test specimen



Key

- | | |
|--|---|
| 1 acrylic band for seal | 13 O-ring (width: 5 mm) |
| 2 fixing nut for fixing mortar substrate ($\varnothing$ 6 mm) | 14 non-woven fabric for filtering repair material |
| 3 bolts for fixing connecting jig ($\varnothing$ 6 mm) | 15 acrylic plate for fixing non-woven fabric |

4	nut for connection (Ø 12 mm)	16	bolt for fixing acrylic plate (Ø 6 mm)
5	connecting jig	17	inlet bar for injection (Ø 12 mm)
6	nut for fixing (Ø 6 mm)	a	hole for fixing (Ø 7 mm)
7	level instrument	b	hole for connecting bolt (Ø 8 mm)
8	upper substrate (acrylic)	c	leakage hole (Ø 2,5 mm)
9	bolt for connecting upper substrate	d	injection hole (Ø 10 mm)
10	mortar substrate	e	see Figure A.4
11	steel plate for fixing mortar substrate	f	injection hole (Ø 20 mm)
12	bolt for fixing with chamber (Ø 10 mm)	g	leakage hole (Ø 2,5 mm)

Figure A.3 — Basic parts planar of test specimen

A.2.5 Others.

A.2.5.1 Injector suitable for the application of the tested repair material into the concrete specimen.

A.2.5.2 Water container.

A.2.5.3 Masking tape, silicone sealant and/or additional sealing materials.

A.3 Preparation

A.3.1 Test specimen assembly part 1

- 1) Insert the inlet bar and the pin plate on the steel plate. Next, pour the mortar (the mortar substrate part) in the mould inside the steel plate (see steps 1, 2 and 3 in [Figure A.4](#)).
- 2) Cure the mortar substrate part plate for 72 hours at 20 ± 3 °C and >65 % RH, and remove the hole plate, pin plate and inlet bar (see step 4 in [Figure A.4](#)).
- 3) Place the entire specimen at rest for more than 168 hours at 20 ± 3 °C and >65 % RH (see step 4 in [Figure A.4](#)).




Figure A.4 — Test specimen assembly part 1

A.4 Test specimen assembly part 2

- 1) Attach the non-woven fabric for filtering repair material particulates on the bottom of the steel plate, and fix it in place with the acrylic plate (see steps 1, 2 and 3 in [Figure A.5](#)).
- 2) Place the upper acrylic substrate part on the bolts so that it lies horizontally over the steel plate, parallel to the placement of the mortar substrate part (see step 4 in [Figure A.5](#)).
- 3) Place the acrylic band around the two substrate parts to cover the space openings on the side to prevent leakage during repair material injection. Apply silicone sealing if needed to close off the seams of the acrylic band for reinforced sealing (see step 4 in [Figure A.5](#)).