



Technical Specification

ISO/TS 20953

Footwear — Performance requirements for components for footwear — Lining and insoles

*Chaussures — Exigences de performance pour les composants des
chaussures — Doublures et premières de propreté*

**First edition
2024-11**

STANDARDSISO.COM : Click to view the full PDF of ISO/TS 20953:2024

STANDARDSISO.COM : Click to view the full PDF of ISO/TS 20953:2024



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Classification	2
5 Requirements	2
5.1 General.....	2
5.2 Essential and additional performance requirements for lining.....	2
5.3 Essential and additional performance requirements for insock.....	4
6 Marking and labelling	6

STANDARDSISO.COM : Click to view the full PDF of ISO/TS 20953:2024

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 216, *Footwear*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Footwear — Performance requirements for components for footwear — Lining and insoles

1 Scope

This document establishes the performance requirements for lining and insole components for footwear, irrespective of the material, in order to assess the suitability for the end use and/or fitness for purpose. It also establishes the test methods to be used to evaluate compliance with these requirements.

This document applies to lining and insoles for all kinds of footwear as defined in [Clause 4](#).

This document can be used as a reference by the manufacturer and the supplier.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 17694, *Footwear — Test methods for uppers and lining — Flex resistance*

ISO 17696, *Footwear — Test methods for uppers, linings and insoles — Tear strength*

ISO 17697, *Footwear — Test methods for uppers, lining and insoles — Seam strength*

ISO 17699, *Footwear — Test methods for uppers and lining — Water vapour permeability and absorption*

ISO 17700, *Footwear — Test methods for upper components and insoles — Colour fastness to rubbing and bleeding*

ISO 17704, *Footwear — Test methods for uppers, linings and insoles — Abrasion resistance*

ISO 17709, *Footwear — Sampling location, preparation and duration of conditioning of samples and test pieces*

ISO 19952, *Footwear — Vocabulary*

ISO 22649, *Footwear — Test methods for insoles and insoles — Water absorption and desorption*

ISO 22652, *Footwear — Test methods for insoles, lining and insoles — Perspiration resistance*

ISO 80000-1, *Quantities and units — Part 1: General*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 19952 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Classification

The footwear shall be classified according to [Table 1](#).

Table 1 — Classification

Class	Exposure	Shoe type
A	slight	infant shoes, slippers, indoor shoes, fashion shoes
B	medium	casual shoes (adult and children shoes)
C	high	children school shoes, adult work shoes (not PPE) and general sport shoes
D	heavy	heavy work shoes (not PPE), trekking, hiking or similar purpose sports shoes

5 Requirements

5.1 General

This document establishes two different types of performance requirements.

The essential requirements shall all be fulfilled. Additional requirements can be agreed upon by the component supplier and the footwear manufacturer as indicated in [Table 2](#) or [Table 3](#).

The results of each determination, as well as the average values, shall be rounded off in accordance with ISO 80000-1.

When taken from finished footwear, samples shall be prepared in accordance with ISO 17709.

5.2 Essential and additional performance requirements for lining

The essential requirements in [Table 2](#) shall be fulfilled in all cases.

Table 2 — Test methods and requirements for lining

Test method		Test name	Requirements			
			Class A	Class B	Class C	Class D
Essential requirements	ISO 17696	Tear strength	Lining: ≥ 10 N	Lining: ≥ 12 N	Lining: ≥ 15 N	Lining: ≥ 30 N
	ISO 17697 (method A)	Seam strength	≥ 2,0 N/mm	≥ 2,5 N/mm	≥ 3,0 N/mm	≥ 5,0 N/mm
	ISO 17700 (method A)	Colour fastness to rubbing	Reinforcing lining: ≥ 20 N (if it applies) Staining ≥ 3 (grey scale) after: — 150 cycles dry — 50 cycles wet or 20 cycles with perspiration solution			
	ISO 17704	Abrasion resistance	No holes ^a after: — 25 000 cycles dry — 6 400 cycles (counter lining) wet; 3 200 cycles (vamp and quarter lining) wet	No holes ^a after: — 30 000 cycles dry — 12 800 cycles (counter lining) wet; 6 400 cycles (vamp and quarter lining) wet	No holes ^a after: — 50 000 cycles dry — 25 600 cycles (counter lining) wet; 12 800 cycles (vamp and quarter lining) wet	
	ISO 17699	Water vapour permeability	WVP ≥ 2,0 mg/cm ² /h			
Additional requirements	ISO 22652	Perspiration resistance	After 3 cycles the component shall not develop any cracks when bent, and shall keep ≥ 80 % tear resistance (testing not necessary to certain lining materials)		After 5 cycles the component shall not develop any cracks when bent, and shall keep ≥ 80 % tear resistance (testing not necessary to certain lining materials)	
	ISO 17694	Flex resistance	Dry: 15 000 cycles without visible damage (only for coated material)			
A hole should only be considered as a hole when it extends through the full thickness of the wearing surface.						

5.3 Essential and additional performance requirements for insock

The essential requirements in [Table 3](#) shall be fulfilled in all cases.

STANDARDSISO.COM : Click to view the full PDF of ISO/TS 20953:2024

Table 3 — Test methods and requirements for insock

Test method		Test name	Requirements			
			Class A	Class B	Class C	Class D
Essential requirements	ISO 17700 (method A)	Colour fastness to rubbing	Staining ≥ 3 (grey scale) after: — 150 cycles dry — 50 cycles wet or 20 cycles with perspiration solution			
	ISO 17704	Abrasion resistance	No holes ^a in material in contact with foot after: — 12 800 cycles dry — 3 200 cycles wet	No holes ^a in material in contact with foot after: — 12 800 cycles dry — 6 400 cycles wet	No holes ^a in material in contact with foot after: — 25 600 cycles dry — 12 800 cycles wet	
	ISO 22649 (method B)	Water absorption and desorption	Only for insocks with thickness more than 3 mm: — Absorption: ≥ 60 mg/cm ² — Desorption: ≥ 60 %		Only for insocks with thickness more than 3 mm: — Absorption: ≥ 70 mg/cm ² — Desorption: ≥ 80 %	
	ISO 22652	Perspiration resistance	After 3 cycles the component shall not develop any cracks when bent, and shall keep ≥ 80 % tear resistance (testing not necessary to certain lining materials)			
Additional requirements						
^a A hole should only be considered as a hole when it extends through the full thickness of the wearing surface.						