

H-13-15

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE AMS-1531REV
B

Submitted for recognition as an American National Standard

Issued 1978-01-15
Revised 1990-07-01

Superseding AMS-1531A

CLEANER FOR AIRCRAFT EXTERIOR SURFACES Wipe-On, Wipe-Off, Containing Suspended Abrasive Solids

1. SCOPE:

- 1.1 Form: This specification covers a water-soluble cleaner containing suspended abrasive solids in the form of a ready-to-use liquid.
- 1.2 Application: Primarily for removing resistant soils from exhaust areas of exterior metal and painted surfaces of aircraft by a wipe-on, wipe-off procedure not requiring a water rinsing operation. NOT recommended for use on stretched or cast acrylic plastic.
- 1.3 Safety - Hazardous Materials: While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.
2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.
- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

SAE AMS-1531 Revision B**2.1.1 Aerospace Material Specifications:**

- AMS-2475 - Protective Treatments, Magnesium Alloys
- AMS-2825 - Material Safety Data Sheets
- AMS-4049 - Aluminum Alloy Sheet and Plate, Alclad, 5.6Zn - 2.5Mg -
1.6Cu - 0.23Cr (Alclad 7075; -T6 Sheet, -T651 Plate),
Solution and Precipitation Heat Treated
- AMS-4376 - Magnesium Alloy Plate, 3.0Al - 1.0Zn (AZ31B-H26), Cold Rolled
and Partially Annealed
- AMS-4911 - Titanium Alloy Sheet, Strip, and Plate, 6Al - 4V, Annealed
- AMS-5045 - Steel Sheet and Strip, 0.25 max Carbon, Hard Temper

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM D 56 - Flash Point by Tag Closed Tester
- ASTM D 1404 - Estimation of Deleterious Particles in Lubricating Grease
- ASTM F 483 - Total Immersion Corrosion Test for Aircraft Maintenance
Chemicals
- ASTM F 484 - Stress Cracking of Acrylic Plastics in Contact with Liquid or
Semi-Liquid Compounds
- ASTM F 485 - Effects of Cleaners on Unpainted Aircraft Surfaces
- ASTM F 502 - Effects of Cleaning and Chemical Maintenance Materials on
Painted Aircraft Surfaces
- ASTM F 519 - Mechanical Hydrogen Embrittlement Testing of Plating Processes
and Aircraft Maintenance Chemicals
- ASTM F 1104 - Preparing Aircraft Cleaning Compounds, Liquid Type, Water Base,
for Storage Stability Testing
- ASTM F 1110 - Sandwich Corrosion Test
- ASTM F 1111 - Corrosion of Low Embrittling Cadmium Plate by Aircraft
Maintenance Chemicals

2.3 U.S. Government Publications: Available from Standardization Documents Order Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.**2.3.1 Military Specifications:**

- MIL-C-23377 - Primer Coating, Epoxy Polyamide, Chemical and Solvent
Resistant
- MIL-P-25690 - Plastic, Sheets and Parts, Modified Acrylic Base,
Monolithic, Crack Propagation Resistant
- MIL-C-83286 - Coating, Urethane, Aliphatic Isocyanate, for Aerospace
Applications

2.3.2 Military Standards:

- MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

- 3.1 **Material:** Shall consist of a mixture of selected solvents, mild abrasives,
Ø detergents, soaps, and water, either with or without thickening agents, to
produce a product meeting the requirements of 3.2.

SAE AMS-1531 Revision B

3.2 Properties: The cleaner shall conform to the following requirements; tests shall be performed in accordance with specified test methods on the product as-received in concentrated form:

3.2.1 Corrosion of Metal Surfaces:

3.2.1.1 Sandwich Corrosion: Specimens, after test, shall show a rating not worse than 1, determined in accordance with ASTM F 1110.

3.2.1.2 Total Immersion Corrosion: The product shall neither show evidence of corrosion nor cause a weight change of any test panel greater than the following, determined in accordance with ASTM F 483:

Panel	Weight Change mg/cm ² per 24 hours
AMS-4049 Aluminum Alloy	0.3
AMS-4376 Magnesium Alloy, Dichromate Treated as in AMS-2475	0.2
AMS-4911 Titanium Alloy	0.1
AMS-5045 Carbon Steel	0.8

3.2.1.3 Low-Embrittling Cadmium Plate: Panels coated with low-embrittling cadmium plate shall not show a weight change greater than 0.3 mg/cm² per 24 hours, determined in accordance with ASTM F 1111.

3.2.2 Hydrogen Embrittlement: The product shall be non-embrittling, determined in accordance with ASTM F 519, Type 1a, 1c, or 2a.

3.2.3 Flash Point: Shall be not lower than 60°C (140°F), determined in accordance with ASTM D 56.

3.2.4 Effect on Plastics: The product shall not craze, stain, or discolor MIL-P-25690 stretched acrylic plastic, determined in accordance with ASTM F 484.

3.2.5 Effect on Painted Surfaces: The product shall neither decrease the hardness of the paint film by more than two pencil hardness levels nor shall it produce any streaking, discoloration, or blistering of the paint film, determined in accordance with ASTM F 502.

3.2.6 Effect on Unpainted Surfaces: The product, tested in accordance with ASTM F 485, shall neither produce streaking nor leave any stains requiring polishing to remove.

3.2.7 Abrasive Effects: The cleaner shall not scratch glass, paint, or aluminum alloy surfaces, determined in accordance with ASTM D 1404 except that the test specimens shall be glass, AMS-4049 aluminum alloy, and AMS-4049 aluminum alloy coated with MIL-C-23377 epoxy primer and MIL-C-83286 urethane coating. The cleaner shall be applied to the specimens in the as-received concentrated form. Only arc-type scratches greater than 1/16 inch (1.6 mm) from the edge of any specimen shall be considered.

SAE AMS-1531 Revision B

3.2.8 Storage Stability: The product, tested in accordance with ASTM F 1104, shall be restorable to its original appearance by vigorous shaking and shall conform to all other technical requirements of this specification after the storage stability period.

3.2.9 Performance: The cleaner, when used in accordance with manufacturer's recommendations, shall remove normally accumulated soils from the exterior surfaces of aircraft without leaving any visible residue on any surface tested.

3.3 Quality: The cleaner, as received by purchaser, shall be homogenous, uniform in color, and free from skins and lumps and from foreign materials detrimental to usage of the cleaner.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the cleaner shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the cleaner conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for total immersion corrosion (3.2.1.2), effect on painted surfaces (3.2.5), effect on unpainted surfaces (3.2.6), and quality (3.3) are acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests for sandwich corrosion (3.2.1.1), low-embrittling cadmium plate (3.2.1.3), hydrogen embrittlement (3.2.2), flash point (3.2.3), effect on plastics (3.2.4), abrasive effects (3.2.7), storage stability (3.2.8), and performance (3.2.9) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of the cleaner to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing: Sufficient cleaner shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three. A lot shall be all cleaner produced in a single production run from the same batches of raw materials under the same fixed conditions and presented for vendor's inspection at one time.