

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE AMS 1730A

Issued 10-15-79

Revised 1-1-86

Superseding AMS 1730

UREA COMPOUND, SHOTTED

1. SCOPE:

1.1 Form: This specification covers a urea compound in the form of a solid.

1.2 Application: Primarily for use in deicing airport ramps, walkways, and other ground surfaces as required.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace Recommended Practices shall apply. The applicable issue of other documents shall be as specified in AMS 2350 except that the issue of APHA and AOAC publications in effect on date of invitation to bid or request for proposal shall apply.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2825 - Material Safety Data Sheets

AMS 4049 - Aluminum Alloy Sheet and Plate, Alclad, 5.6Zn - 2.5Mg - 1.6Cu - 0.23Cr (Alclad 7075; -T6 Sheet, - T651 Plate)

2.1.2 Aerospace Recommended Practices:

ARP 1511 - Corrosion of Low-Embrittling Cadmium Plate by Aircraft Maintenance Chemicals

ARP 1512 - Corrosion of Aluminum Alloys by Aircraft Maintenance Chemicals, Sandwich Test

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM D1119 - Ash Content of Engine Antifreezes, Antirusts, and Coolants
- ASTM D1193 - Reagent Water
- ASTM D1353 - Nonvolatile Matter in Volatile Solvents for Use in Paint, Varnish, Lacquer, and Related Products
- ASTM D1568 - Sampling and Chemical Analysis of Alkylbenzene Sulfonates
- ASTM E324 - Relative Initial and Final Melting Points and the Melting Range of Organic Chemicals
- ASTM F483 - Total Immersion Corrosion Test for Aircraft Maintenance Chemicals
- ASTM F484 - Stress Cracking of Acrylic Plastics in Contact with Liquid or Semi-Liquid Compounds
- ASTM F502 - Effects of Cleaning and Chemical Maintenance Materials on Painted Aircraft Surfaces
- ASTM F503 - Preparing Aircraft Cleaning Compounds, Liquid Type, for Storage Stability Testing
- ASTM F519 - Mechanical Hydrogen Embrittlement Testing of Plating Processes and Aircraft Maintenance Chemicals

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

MIL-P-83310 - Plastic Sheet, Polycarbonate, Transparent

2.3.2 Military Standards:

- MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
- MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

2.4 APHA Publications: Available from American Public Health Association, 1015 Eighteenth Street, N.W., Washington DC 20036.

APHA Standard Methods for Examination of Water and Wastewater

2.5 AOAC Publications: Available from Association of Official Agricultural Chemists, P.O. Box 540, Benjamin Franklin Station, Washington, DC 20004.

Official Methods of Analysis of the Association of Official Agricultural Chemists

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall be a uniform compound of shotted urea and shall comply with the following chemical requirements, determined in accordance with specified test methods from APHA Standard Methods for Examination of Water and Wastewater:

		Method No.
Free Ammonia (NH ₃), max	300 ppm	132
Chlorides	None	112A
Iron, max	2 ppm	124A, B, or C
Sulfides	None	157
Sulfates (SO ₄)	None	156C
Nitrogen, min	46%	135

- 3.1.1 Moisture: Shall be not more than 0.40%, determined in accordance with ASTM D1568.

- 3.2.1 Biuret: Shall be not more than 2.1%, determined in accordance with Official Methods of the Association of Official Agricultural Chemists, Chapter 2, excluding ion exchange column. Prepare a standard curve using 5 mL, 15 mL, and 25 mL quantities and using a 2-g sample.

- 3.1.3 Ash: Shall be not higher than 0.1% by weight, determined in accordance with ASTM D1119.

- 3.2 Properties: Urea compound shall conform to the following requirements; tests shall be performed in accordance with specified test methods on the product supplied in concentrated form and at use dilution as specified:

- 3.2.1 On Concentrated Urea Compound:

- 3.2.1.1 Temperature Stability: Urea compound shall show no chemical or physical deterioration, including evidence of discoloration or other change denoting loss of stability, after being exposed for 120 hr $\pm$ 1 at 2°C $\pm$ 3 (35°F $\pm$ 5).

- 3.2.1.2 Effect on Painted Surfaces: Urea compound shall neither decrease the hardness of the paint film by more than two pencil hardness levels nor shall it produce any streaking, discoloration, or blistering of the paint film, determined in accordance with ASTM F502.

- 3.2.1.3 Storage Stability: Urea compound shall be stable in storage for not less than 12 months at room temperature and shall not deliquesce or otherwise deteriorate when stored in shipping container or use package, determined in accordance with ASTM F503.

- 3.2.1.4 Nonvolatile Matter: Shall be determined in accordance with ASTM D1353 and the results reported.

- 3.2.1.5 Melting Point: Shall be not lower than 132°C (270°F) and not higher than 133°C (272°F), determined in accordance with ASTM E324.

3.2.2 On Diluted Urea Compound: Shall be as follows, determined on a 25% ASTM
Ø D1193, Type IV, water solution of the urea:

3.2.2.1 Residue: Urea solution shall leave no residue or stains on AMS 4049
aluminum alloy, determined as in 3.2.2.1.1.

3.2.2.1.1 Two 2 x 6 in. (50 x 150 mm) panels of AMS 4049 aluminum alloy shall be
cleaned with acetone and immersed in the urea solution so as to cover
approximately one-half of the panel. After the urea solution has been
applied, the panels shall be placed at 45 deg + 5 from the horizontal
in an oven maintained at 38°C + 1 (100°F + 2) for 30 min. + 1, removed
from the oven, rinsed with room temperature methyl ethyl ketone,
allowed to dry, and the treated and untreated areas of the panels
visually examined and compared for the presence of residue and stains.

3.2.2.2 Corrosion of Metal Surfaces:

3.2.2.2.1 Sandwich Corrosion: Two 2 x 6 in. (50 x 150 mm) panels of AMS 4049
aluminum alloy, after test, shall show a rating not worse than 1,
determined in accordance with ARP 1512.

3.2.2.2.2 Total Immersion Corrosion: Urea solution shall neither show evidence
of pitting or corrosion of the panels nor cause a weight change of any
test panel of AMS 4049 aluminum alloy greater than 0.3 mg/cm² per 24
hr, determined in accordance with ASTM F483.

3.2.2.2.3 Low-Embrittling Cadmium Plate: Test panels coated with
low-embrittling cadmium plate shall not show a weight change greater
than 0.3 mg/cm² per 24 hr, determined in accordance with ARP 1511.

3.2.2.3 Hydrogen Embrittlement: Urea solution shall be non-embrittling,
determined in accordance with ASTM F519, Types 1a, 1c, or 2a.

3.2.2.4 Effect on Transparent Plastics: Urea solution shall not craze, stain,
Ø or discolor Type C acrylic plastic, determined in accordance with ASTM
F484. The urea solution shall not craze, stain, or discolor MIL-P-83310
polycarbonate plastic or polysulfone plastic, determined in accordance
with test procedures specified in ASTM F484 on specimens stressed to an
outer fiber stress of 3000 psi (20 MPa) for 30 min. + 2.

3.3 Quality: Urea compound, as received by purchaser, shall be uniform,
uncoated, and free from foreign materials detrimental to usage of the urea
compound.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of urea compound shall supply all
Ø samples for vendor's tests and shall be responsible for performing all
required tests. Results of such tests shall be reported to the purchaser as
required by 4.5. Purchaser reserves the right to sample and to perform any
confirmatory testing deemed necessary to ensure that the urea compound
conforms to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), hydrogen embrittlement (3.2.2.3), and effect on transparent plastics (3.2.2.4) are classified as acceptance tests and shall be performed on each lot.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for temperature stability (3.2.1.1), effect on painted surfaces (3.2.1.2), melting point (3.2.1.5), residue (3.2.2.1), and corrosion of metal surfaces (3.2.2.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in ingredients, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction tests material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

- 4.3 Sampling: Shall be in accordance with all applicable requirements of ASTM D1568 and MIL-STD-105, Level S-2; a lot shall be all urea compound produced in one continuous manufacturing operation from the same lots of raw materials and presented for vendor's inspection at one time.

- 4.3.1 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3 and the report of 4.5 shall state that such plan was used.

4.4 Approval:

- 4.4.1 Sample urea compound shall be approved by purchaser before urea for production use is supplied, unless such approval be waived by purchaser. Results of tests on production urea shall be essentially equivalent to those on the approved sample.
- 4.4.2 Vendor shall use ingredients, manufacturing procedures, and methods of inspection on production urea which are essentially the same as those used on the approved sample urea. If necessary to make any change in ingredients or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material, processing, or both and, when requested, sample urea. Production urea made by the revised procedure shall not be shipped prior to receipt of reapproval.