

NOTICE OF
ADOPTIONAMS 2249D
NOTICE 1
12 May 1992
SUPERSEDING
AMS 2249C
1 November 1985

ADOPTION NOTICE

CHEMICAL CHECK ANALYSIS LIMITS TITANIUM AND TITANIUM ALLOYS

The above non-Government document was adopted on 12 May 1992 and is approved for use by the DoD. Copies of the document should be ordered from Standardization Documents Order Desk, Bldg 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094 for issue to DoD activities only. All others desiring copies must obtain them from SAE, 400 Commonwealth Drive, Warrendale, PA 15096, or from some other authorized distribution.

RELEASING NON-GOVERNMENT STANDARDS BODY: SAE

SAE APPROVAL DATE: 1 April 1992

Custodians:

Army - MR
Navy - AS
Air Force - 11

Military Coordinating Activity:

Army - MR
Project 95GP-0388

DISTRIBUTION STATEMENT A Approved for public release; distribution unlimited. FSC 95GP

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE

AMS 2249D

Issued 15 JAN 1961
Revised 1 APR 1992
Superseding AMS 2249C

CHEMICAL CHECK ANALYSIS LIMITS Titanium and Titanium Alloys

1. SCOPE:

This specification covers standard chemical check analysis limits as established by AMS usage. The chemical check analysis limits shown herein shall apply when this specification is referenced in material specifications for titanium and titanium alloys. Check analysis limits for elements or for ranges of elements not listed herein shall be as agreed upon by purchaser and vendor.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The applicable issue of referenced publications shall be the issue in effect on the date of the purchase order.

2.1 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM E 59 Sampling Steel and Iron for Determination of Chemical Composition
ASTM E 120 Chemical Analysis of Titanium and Titanium Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition: (R)

Referee methods of analysis shall be by wet chemical methods in accordance with ASTM E 120, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 2249D

SAE

AMS 2249D

3.2 Definitions:

- 3.2.1 Check Analysis: An analysis made by purchaser or vendor of the metal after it has been worked into semi-finished or finished forms or fabricated into parts, and is either for the purpose of verifying the composition of a heat or lot or to determine variations in the composition within the heat. Acceptance or rejection of a heat or lot of material or batch of parts may be made by the purchaser on the basis of this check analysis. In the analysis of finished parts, these values do not apply to elements whose percentage can be varied by fabricating techniques employed (for example oxygen, nitrogen, hydrogen) unless the sample is sufficiently large to produce a reliable result.
- 3.2.2 Variation Limit, Under Minimum or Over Maximum: Given in 3.3 is the amount an individual determination for a specified element may vary under or over the specified composition limit. In no case shall the several determinations of any element in a heat, using the same analytical procedure, vary both above and below the specified range. These variations are not permitted for ingot analyses made by the producer.
- 3.2.3 Remainder: Shows the basis element from which the alloy is made and is assumed to be present in an amount approximately equal to the difference between 100% and the sum percentage of the alloying elements and listed impurities. Analysis for this element need not be made nor need a percentage figure be reported.
- 3.2.4 Residual Elements, Each, Maximum: The maximum amount of an individual element not mentioned specifically in the tabulated composition that may be present. Producer normally will analyze only for impurities which are possible to be present because of raw materials or manufacturing processes and which may affect the product significantly. Others will analyze for impurities as they deem necessary.
- 3.2.5 Residual Elements, Total, Maximum: The sum percentage of the residual elements (See 3.2.4) found. It is not inferred by this statement that an analysis need be made for each element of the periodic table not mentioned specifically in the tabulated composition.
- 3.2.6 Heat: All metal which, during the final melting operation, is melted in the same furnace crucible and solidified in the same ingot mold.
- 3.2.7 Lot: All product of the same size processed at the same time from the same heat.

AMS 2249D

SAE

AMS 2249D

3.3 Check Analysis Limits:

Shall be as shown in Table 1.

TABLE 1 - Check Analysis Limits

Element	Limits or Maximum of Specified Range, %		Variation Under Min or Over Max
Carbon	Up to	0.20, incl	0.02
	Over 0.20 to	0.50, incl	0.04
	Over 0.50		0.06
Manganese	Up to	0.30, incl	0.10
	Over 0.30 to	6.00, incl	0.20
	Over 6.00 to	9.00, incl	0.25
Chromium	Up to	1.00, incl	0.05
	Over 1.00 to	4.00, incl	0.20
	Over 4.00		0.25
Molybdenum (R)	Up to	0.50, incl	0.04
	Over 0.50 to	1.00, incl	0.10
	Over 1.00 to	10.00, incl	0.20
	Over 10.00 to	30.00, incl	0.25
Aluminum	Up to	1.00, incl	0.12
	Over 1.00 to	10.00, incl	0.40
	Over 10.00 to	35.00, incl	0.50
Hydrogen	Up to	0.020 (200 ppm), incl	0.0020 (20 ppm)
	Over 0.020 to	0.050 (200 to 500 ppm), incl	0.005 (50 ppm)
	Over 0.050	(500 ppm)	0.010 (100 ppm)
Nitrogen	Up to	0.10 (1000 ppm), incl	0.02 (200 ppm)
Oxygen	Up to	0.20 (2000 ppm), incl	0.02 (200 ppm)
	Over 0.20	(2000 ppm)	0.03 (300 ppm)
Iron	Up to	0.25, incl	0.10
	Over 0.25 to	0.50, incl	0.15
	Over 0.50 to	5.00, incl	0.20
	Over 5.00		0.25
Vanadium	Up to	0.50, incl	0.05
	Over 0.50 to	5.00, incl	0.15
	Over 5.00 to	6.00, incl	0.20
	Over 6.00 to	10.00, incl	0.30
	Over 10.00 to	20.00, incl	0.40
Tin	Up to	3.00, incl	0.15
	Over 3.00 to	6.00, incl	0.25
	Over 6.00 to	12.00, incl	0.40