

Control of Forgings Requiring First Article Approval

RATIONALE

AMS2375D has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE

1.1 Purpose

This specification covers procedures for obtaining first-article (preproduction) approval of forgings and the controls to be exercised in producing subsequent production forgings.

1.2 Application

This procedure has been used typically for forgings which require preproduction approval and where assurance is required that production lots are of essentially the same metallurgical quality and are produced by the same basic procedures as the forging originally qualified.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 ASTM Publications

Available from ASTM, International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E 3 **Preparation of Metallographic Specimens**

3. TECHNICAL REQUIREMENTS

3.1 Forging Stock

3.1.1 The forging vendor shall determine that the forging stock conforms to the applicable material specification and will yield acceptable forgings. Tests which are characteristic of a heat or lot, and that are conducted by the forging stock vendor, need not be repeated by the forging vendor provided the results of such tests have been supplied by the forging stock vendor.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: **Tel:** 877-606-7323 (inside USA and Canada)
 Tel: +1 724-776-4970 (outside USA)
 Fax: 724-776-0790
 Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS2375D>**

3.1.2 When specified, forging stock shall be procured from sources approved by purchaser of the forgings.

3.2 Preproduction Forgings

3.2.1 Procedure

The forging vendor shall produce and heat treat to final condition one or more preproduction forgings and shall test a forging or sections thereof to determine conformance to all requirements of the material specification, the drawing, and any additional requirements specified by purchaser. The preproduction forgings shall be made by the same practices to be used on production forgings and, unless otherwise specified, may be produced as part of the initial production run. A duplicate preproduction forging or the remaining section of such forgings shall be submitted to purchaser for confirmatory testing, when requested.

3.2.1.1 When forgings are to be supplied in other than the final heat treated condition, the test forging(s) shall be heat treated to the final heat treated condition of the part. If the as-forged section size is too large to achieve proper heat treatment response, the forging, or a section thereof, shall be machined to a configuration of the same equivalent round as that of the heaviest section of the heat treat configuration.

3.2.1.1.1 If the final heat treated condition of the forgings requires a tensile strength of 200 ksi (1379 MPa) or higher, and the forgings are supplied in a different condition, the vendor may excise oversize test coupons from such forgings. Such coupons shall be given the final heat treatment prior to machining to specimen size for testing.

3.2.2 Specimen Locations

The location(s) of coupons that are to be taken for mechanical property tests and the sections for grain flow examination shall be as specified by purchaser. The forging vendor shall perform the required tests on specimens from these locations. If locations are not specified, the forging vendor shall select representative areas for testing and, when required, shall obtain concurrence of purchaser. Mechanical property test specimens shall be taken in the transverse direction whenever practicable unless only longitudinal properties are specified in the material specification.

3.2.3 Properties

3.2.3.1 Grain Flow

A representative forging shall be sectioned as indicated on the drawing and the sections suitably etched to show the grain flow. Photographs showing the grain flow pattern shall be made of each section and the photographs shall be identified to indicate the corresponding sections in the forging. The grain flow shall conform to the requirements of the drawing and good forging practice consistent with the part shape, without reentrant flow lines. When the specified alloy is not conducive to good grain flow determination, a substitute alloy or melting practice showing good grain flow and having equivalent forgability shall be substituted and so indicated in the test report.

3.2.3.2 Hardness

Hardness surveys shall be made across the heaviest section of test forgings, unless otherwise specified.

3.2.3.3 Microstructure

Sections shall be taken from the fully heat-treated forging at the center of the heaviest usable section and at the surface of the heaviest and thinnest sections and prepared for metallographic examination in accordance with ASTM E 3. There shall not be any detrimental microstructural abnormalities related to improper forging or heat treating practice or to forging stock quality. Photographs of the microstructures shall be submitted to purchaser and any abnormal microstructural conditions identified.

3.2.3.4 Mechanical Properties

Test specimens from the representative forging(s) shall meet the specified mechanical properties for the part in the final heat treated condition.

3.3 Process Control Factors

Process control factors (See 4.4.2.1), established for producing forgings of each part number, shall be submitted with the results of tests on the preproduction forging(s); when permitted by purchaser, the process control factors need not be submitted with the test results but shall be kept on file for review by purchaser.

3.4 Production Forgings

Shall be produced using the same operations, practices, and process control factors used on the approved preproduction forging(s) (See 4.2.2.1.2).

3.4.1 Production forgings shall not be shipped until the forging vendor has received written approval of the preproduction forging(s), unless preshipment approval is waived by purchaser.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of forgings shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the forgings conform to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Tests of forging stock and forgings to determine conformance to applicable requirements of the material specification (3.2.1) and to any additional requirements specified by purchaser are acceptance tests and shall be performed on each heat or lot, as applicable. Such tests of forging stock shall be performed prior to use of a new heat or lot for production forgings.

4.2.2 Preproduction Tests

Tests of preproduction forgings to determine conformance to all applicable technical requirements of the material specification, to requirements for grain flow (3.2.3.1), hardness (3.2.3.2), microstructure (3.2.3.3), and mechanical properties (3.2.3.4), and to any additional requirements specified by purchaser are preproduction tests and shall be conducted under the following circumstances:

4.2.2.1 The first production of a new forging.

4.2.2.1.1 At any time a change is made in forging design or in process control factors (4.4.2).

4.2.2.1.2 Forger shall obtain purchaser's concurrence on changes that are deemed not to affect preproduction test results.

4.3 Sampling and Testing

Shall be as follows; a lot shall be all forgings of the same part number or configuration, opposite hands being considered one configuration, produced from the same heat of forging stock, heated and forged in the same manner, and heat treated in a continuous furnace or in a series of batch-type furnace operations with no change in furnace settings or interruption of power.

4.3.1 For Acceptance Tests

As specified on forging drawing, material specification, or quality assurance specification. For forgings supplied in the final heat treat condition, one forging from each lot shall be subjected to destructive testing. On forgings that contain a test prolongation, each prolongation shall be tested unless a sampling plan is agreed upon by purchaser and vendor. Each prolongation, and the forging it represents, shall be given a serial number for identification.

4.3.2 For Preproduction Tests

As specified in Section 3, tests shall be performed on the first production of a new forging by a vendor and following any change in configuration or forging design.

4.4 Approval

4.4.1 Preproduction forgings and the forging procedure shall be approved by purchaser before production forgings are supplied, unless preproduction approval is waived by purchaser. Neither the approval of preproduction forgings and procedures nor the waiver of preproduction approval shall relieve the forging vendor of responsibility for continued conformance to all requirements.

4.4.2 The forging vendor shall establish for each part number or configuration parameters for process control factors that will produce forgings conforming to the requirements of this specification and the material specification. These control factors shall constitute the approved manufacturing procedures and shall be used for production forgings. If necessary to make any change in parameters for process control factors, the forging vendor shall submit for reapproval a statement of the proposed changes and, when requested, perform preproduction tests of revised forgings. Production forgings incorporating the revised operations shall not be shipped prior to receipt of reapproval unless prior approval is waived by purchaser.

4.4.2.1 Process control factors for producing forgings include, but are not limited to, the following:

Type (ingot, bloom, billet, or bar), nominal size (cross-sectional area), shape, and nominal multiple-weight of forging stock; rounds and round-corner-squares of the same nominal cross-sectional area are considered the same shape

Inspection and qualification of forging stock

Processing sequence or number of operations that would result in different cross-sectional structure, grain flow, or working of the metal

Type of forging equipment (press, hammer, ring roll, etc.)

Description of die configuration, dimensions, and forging pressure

Thermal parameters, including heating of stock for forging, annealing, and heat treatment of forgings

Stress relief procedures, when applicable

Protective atmosphere and/or coatings

Cleaning operations (e.g., chemical descaling, blasting)

Inspection procedures

4.4.2.1.1 Any of the above process control factors for which parameters are considered proprietary by the vendor may be assigned a code designation. Each variation in such factors shall be assigned a modified code designation. The vendor shall maintain complete records of all proprietary processes and factors.

4.5 Records

4.5.1 Maintenance of Facilities

Each forging vendor shall keep records demonstrating that the facilities used to produce, control, measure, and test forging stock and forgings during manufacture and inspection are properly maintained and are checked for accuracy at stated intervals against acceptable standards for accuracy. Records shall be maintained on file for not less than seven years, unless otherwise specified by purchaser.

4.5.2 Process Instructions

For each forging part number or configuration, opposite hands being considered a single configuration, the forging vendor shall prepare and maintain documented instructions defining the processing methods and routing in manufacturing and inspection cycles.