

|                                                                                                                                            |                                                        |                                                                    |                      |
|--------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------|--------------------------------------------------------------------|----------------------|
|  <p><b>SAE Aerospace</b><br/>An SAE International Group</p> | <p><b>AEROSPACE<br/>MATERIAL<br/>SPECIFICATION</b></p> | <p><b>SAE AMS2434</b></p>                                          | <p><b>REV. D</b></p> |
|                                                                                                                                            |                                                        | <p>Issued 1998-07<br/>Revised 2011-09<br/>Superseding AMS2434C</p> |                      |
| <p>Plating, Tin-Zinc Alloy</p>                                                                                                             |                                                        |                                                                    |                      |

## RATIONALE

AMS2434D results from a Five Year Review and update of this specification.

## NOTICE

ORDERING INFORMATION: The following information shall be provided to the plating processor by the purchaser.

1) Purchase order shall specify not less than the following:

- AMS2434D and plating Type. See 1.3.
- Plating thickness desired. See 3.4.1.
- Basis metal to be plated.
- Copper underplating, if required for soft soldering. See 8.7.
- Tensile strength or hardness of the basis metal
- Pre-plate stress relief to be performed by plating processor (time and temperature) if different from 3.1.2.
- Special features, geometry or processing present on parts that requires special attention by the plating processor
- Hydrogen embrittlement relief to be performed by plating processor (parameters or reference document) if different from 3.3.
- Minimum thickness on internal surfaces, if required. See 3.4.1.1.
- Solderability, if required. See 3.4.6.
- Optional: Periodic testing frequency (4.2.2) and sample quantity (4.3.2).
- Quantity of pieces to be plated.

2) Parts manufacturing operations such as heat treating, forming, joining and media finishing can affect the condition of the substrate for plating, or if performed after plating, could adversely affect the plated part. The sequencing of these types of operations should be specified by the cognizant engineering organization or purchaser and is not controlled by this specification.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions. Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

**TO PLACE A DOCUMENT ORDER:**  
 Tel: 877-606-7323 (inside USA and Canada)  
 Tel: +1 724-776-4970 (outside USA)  
 Fax: 724-776-0790  
 Email: CustomerService@sae.org  
 http://www.sae.org

**SAE values your input. To provide feedback  
on this Technical Report, please visit**  
<http://www.sae.org/technical/standards/AMS2434D>

**SAE WEB ADDRESS:**

## 1. SCOPE

### 1.1 Purpose

This specification covers the requirements for the electrodeposited tin-zinc alloy plating.

### 1.2 Application

This plating has been used typically as a corrosion resistant plating where cadmium cannot be used, as a replacement for tin plating where tin whisker growth is a concern, a coating for fasteners where thread lubricity is desirable, and for parts which are to be joined using tin-lead solders, but usage is not limited to such applications.

### 1.3 Classification

Plating covered by this specification is classified as follows:

Type 1 - As plated

Type 2 - With supplementary surface treatment

### 1.4 Safety - Hazardous Materials

While the materials, methods, applications and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards that may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take the necessary precautionary measures to ensure the health and safety of all personnel involved.

## 2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

### 2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), [www.sae.org](http://www.sae.org).

AMS2418 Plating, Copper

AMS4751 Tin - Lead Eutectic 63Sn - 37Pb

AS2390 Chemical Process Test Specimen Material

### 2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, [www.astm.org](http://www.astm.org).

ASTM B 117 Operating Salt Spray (Fog) Testing Apparatus

ASTM B 253 Preparation of Aluminum Alloys for Electroplating

ASTM B 487 Measurement of Metal and Oxide Coating Thicknesses by Microscopic Examination of a Cross-Section

- ASTM B 499 Measurement of Coating Thickness by the Magnetic Method, Nonmagnetic Coatings on Magnetic Basis Metals
- ASTM B 504 Measurement of Thickness of Metallic Coatings by the Coulometric Method
- ASTM B 567 Measurement of Coating Thickness by the Beta Backscatter Method
- ASTM B 568 Measurement of Coating Thickness by X-Ray Spectrometry
- ASTM B 571 Adhesion of Metallic Coatings
- ASTM F 519 Mechanical Hydrogen Embrittlement Testing of Plating Processes and Aircraft Maintenance Chemicals

### 3. TECHNICAL REQUIREMENTS

#### 3.1 Preparation

3.1.1 Unless otherwise specified, parts shall be within drawing dimensions before plating, except as specified in 3.1.1.1.

3.1.1.1 All engine and propeller utility parts having numbers with prefix AN, AS, or MS, required to be plated in accordance with this specification, shall be made to such dimensions that parts will be within drawing limits after plating. Undercutting before plating shall not be permitted unless authorized by purchaser.

#### 3.1.2 Stress Relief Treatment

All steel parts having a hardness of 40 HRC and above and that are machined, ground, cold formed or cold straightened shall be cleaned to remove surface contamination and thermally stress relieved before plating for relief of residual tensile stresses. Temperatures to which parts are heated shall be such that maximum stress relief is obtained without reducing hardness of parts below drawing limits, but, unless otherwise specified, not less than 275 °F (135 °C) for not less than 5 hours for parts having hardness of 55 HRC or higher or not less than 375 °F (191 °C) for not less than 4 hours for other parts. Residual tensile stresses have been found to be damaging during electrofinishing.

3.1.3 The plating shall be applied over a surface free from water breaks. The cleaning procedure shall not produce pitting or intergranular attack of the basis metal and shall preserve dimensional requirements.

3.1.4 Except for barrel plating, electrical contact points shall be as follows. For parts which are to be plated all over, locations shall be acceptable to purchaser. For parts which are not to be plated all over, locations shall be in areas on which plating is not required.

3.1.5 Aluminum alloys shall be zincate or stannate treated in accordance with ASTM B 253 or other method acceptable to the cognizant engineering organization prior to plating

#### 3.2 Procedure

3.2.1 Except as noted or otherwise specified, tin-zinc shall be electrodeposited directly on the basis metal from a suitable tin-zinc solution. Unless otherwise specified, a wet or dry abrasive cleaning that does not change dimensions of the part may be used to assist adhesion of the plate. See 8.7 if soft soldering is required.

3.2.1.1 Nickel or cobalt alloys and corrosion resistant steels may be given a nickel strike prior to tin-zinc plating.

3.2.2 Spotting-in and double plating are not permitted.

### 3.3 Post Treatment

- 3.3.1 Parts shall be given a hydrogen embrittlement relief or adhesion enhancement treatment in a circulating air furnace in accordance with Table 1. Treatment shall begin within four hours of the completion of the plating operation.

TABLE 1 - POST PLATING BAKING CONDITIONS

| Material                                      | Temperature               | Time, Hours<br>Minimum |
|-----------------------------------------------|---------------------------|------------------------|
| Carburized parts                              | 275 °F ± 25 (135 °C ± 14) | 23                     |
| Other steels over 55 HRC                      | 275 °F ± 25 (135 °C ± 14) | 23                     |
| Steel parts 40 HRC and higher                 | 340 °F ± 25 (171 °C ± 14) | 12                     |
| Threaded fasteners 31 HRC and higher          | 340 °F ± 25 (171 °C ± 14) | 12                     |
| PH steels and aged below 1000 °F (538 °C)     | 340 °F ± 25 (171 °C ± 14) | 12                     |
| Adhesion enhancement, Aluminum                | 225 °F ± 25 (107 °C ± 14) | 1                      |
| Alloy parts (See 8.7)                         |                           |                        |
| Adhesion enhancement, other alloys (optional) | 225 °F ± 25 (107 °C ± 14) | 1                      |

- 3.3.2 Type 2 parts, which require hydrogen embrittlement relief in accordance with Table 1, shall be chemical conversion coated after baking and surface reactivation. The chemical conversion coating process, which retards the formation of white corrosion product sufficiently to meet the requirements of 3.4.4.2, shall be acceptable to the purchaser. Waxes, oils or other water repellent systems shall not be used for this purpose.

### 3.4 Properties

#### 3.4.1 Thickness

Thickness of the plated deposit shall be as specified on the engineering drawing, determined in accordance with any of the following methods as applicable: ASTM B 487, ASTM B 499, ASTM B 504, ASTM B 567, ASTM B 568 or other method acceptable to purchaser.

- 3.4.1.1 All surfaces of the part, except those which cannot be touched by a sphere 0.75 inch (19 mm) in diameter, shall be plated to the specified thickness. Unless otherwise specified, surfaces such as holes, recesses, threads and other areas where a controlled deposit cannot be obtained under normal plating conditions, may be under the specified limit provided they show visual plating coverage.

- 3.4.1.2 Where a tin-zinc flash plate is specified, plate thickness shall be approximately 0.0001 inch (2.5 µm).

#### 3.4.2 Composition

The plated deposit shall have a composition of 70 to 90% tin and 10 to 30% zinc, as determined by a method acceptable to the cognizant engineering organization. See 8.8. In case of dispute, one or more of the parts may be stripped of coating, and the resultant solution analyzed by conventional wet chemical methods for relative proportions of tin and zinc.

#### 3.4.3 Adhesion

Adhesion shall meet the requirements of the heat quench method described in ASTM B 571 for tin plating.

#### 3.4.4 Corrosion Resistance

##### 3.4.4.1 Type 1

Parts or specimens having a plate thickness of 0.0003 to 0.0005 inch (8 to 13 µm) shall not show basis metal corrosion after 96 hours of continuous salt spray test, conducted in accordance with ASTM B 117.

#### 3.4.4.2 Type 2

Parts or specimens having a plate thickness of 0.0003 to 0.0005 inch (8 to 13  $\mu\text{m}$ ) shall show neither white corrosion product after 96 hours of continuous salt spray test nor basis metal corrosion after 500 hours of continuous salt spray test conducted in accordance with ASTM B 117. The presence of white corrosion product within 0.25 inch (6.4 mm) from the edges of the specimen shall not constitute failure.

#### 3.4.5 Hydrogen Embrittlement

The plating process shall not cause embrittlement in ferrous parts when tested in accordance with 4.3.3.3.

#### 3.4.6 Solderability

When specified, Type 1 deposits shall demonstrate acceptable solderability using AMS4751 tin-lead solder and mildly reactive rosin (RMA) flux. The solder shall flow uniformly and shall show no evidence of dewetted areas.

#### 3.5 Quality

Plating shall be smooth, continuous, free of delamination within the plating, uniform in appearance, and free of imperfections detrimental to usage of the plating. Plating shall be visually free from frosty areas, pinholes, porosity, blisters, nodules, and pits. Slight discoloration or staining is permitted.

### 4. QUALITY ASSURANCE PROVISIONS

#### 4.1 Responsibility for Inspection

The processor shall supply all specimens for processor's tests and shall be responsible for the performance of all required tests. Parts, if required for tests, shall be supplied by purchaser. The cognizant engineering organization reserves the right to sample and to perform any confirmatory tests deemed necessary to ensure that processing conforms to specified requirements.

#### 4.2 Classification of Tests

##### 4.2.1 Acceptance Tests

Thickness (3.4.1), adhesion (3.4.3), solderability, when specified, (3.4.6) and quality (3.5) are acceptance tests and shall be performed on parts, or specimens representing parts when permitted herein from each lot. See 4.3.3.

##### 4.2.2 Periodic Tests

Composition (3.4.2) and corrosion resistance (3.4.4) are periodic tests and shall be performed at least monthly unless frequency of testing is specified by the cognizant engineering organization. Tests of cleaning and plating solutions are periodic tests and shall be performed at a frequency established by the processor unless frequency is specified by the cognizant engineering organization. See 8.6 and 4.4.3.

Hydrogen embrittlement (3.4.5) is a periodic test and shall be performed in accordance with 4.3.3.3 at least once in each month that steel parts 36 HRC and over are plated unless frequency of testing is specified by the cognizant engineering organization.

##### 4.2.3 Preproduction Tests

All property verification test (3.4) are preproduction tests and shall be performed prior to or on the initial shipment of plated parts to a purchaser and when the cognizant engineering organization requires confirmatory testing to be required.

### 4.3 Sampling for Testing

#### 4.3.1 Acceptance Tests

Test samples shall be randomly selected from all parts in the lot. A lot shall be all parts of the same part number, processed in a continuous series of operations (3.1 through 3.3), in not longer than 8 consecutive hours, and presented for processor's inspection at one time. Unless the cognizant engineering organization provides a sampling plan, the minimum number of samples shall be as shown in Table 2.

TABLE 2 - SAMPLING FOR ACCEPTANCE TESTS

| Number of Parts in Lot | Quality | Thickness, Adhesion and Solderability, when specified |
|------------------------|---------|-------------------------------------------------------|
| Up to 7                | all     | 3 or all*                                             |
| 8 to 15                | 7       | 4                                                     |
| 16 to 40               | 10      | 4                                                     |
| 41 to 110              | 15      | 5                                                     |
| 111 to 300             | 25      | 6                                                     |
| 301 to 500             | 35      | 7                                                     |
| 501 to 700             | 50      | 8                                                     |
| 701 to 1200            | 125     | 15                                                    |

\*Whichever is less

#### 4.3.2 Periodic Tests

Sample quantity shall be four for corrosion resistance. For hydrogen embrittlement, sample size shall be as specified in ASTM F 519 unless otherwise specified by the cognizant engineering organization. See 4.3.3.3. Sample quantity for other periodic tests shall be at the discretion of the processor unless otherwise specified by the cognizant engineering organization or herein.

#### 4.3.3 Sample Configuration

Nondestructive testing shall be performed wherever practical. Except as noted, actual parts shall be selected as samples for tests. When representative specimens are used for acceptance testing, values so obtained shall be correlated with those of parts since properties, such as thickness, may differ between parts and representative test specimens.

4.3.3.1 Representative test specimens may be used in lieu of parts under any one of the following circumstances: The plated parts are of such configuration or size as to be not readily adaptable to specified tests, nondestructive testing is not practical on actual parts, or it is not economically acceptable to perform destructive tests on actual parts. Except as specified below, representative test specimens shall be made of the same generic class of alloy as the parts, established in accordance with AS2390, distributed within the lot, cleaned, plated, and post treated with the parts represented.

#### 4.3.3.2 Corrosion Test Specimens

When ferrous alloy parts are processed within the test month, representative test specimens shall be low carbon or low alloy steel 0.025 inch (0.63 mm) minimum thickness and not less than 4 x 6 inches (102 x 152 mm) or bars approximately 0.5 inch (13 mm) in diameter and 4 inches (102 mm) long having a surface roughness not to exceed 40 microinches (1  $\mu$ m) AA. Representative test specimens for aluminum alloy parts (same specimen size as for steel) made of either 2024-T3 or the same generic class of alloy as the parts processed within the test period when aluminum alloy parts are plated. Representative test specimens, made of the predominant generic class of alloy as the parts and plated within the test period may be used when acceptable to the cognizant engineering organization. Alternative alloy or configuration may be used when acceptable to the cognizant engineering organization. Plating thickness shall be 0.0005 inch (13  $\mu$ m) maximum.

- 4.3.3.3 Hydrogen embrittlement testing shall be in accordance with the requirements of ASTM F 519 Type 1a.1 using round notched bars, unless a different specimen is specified by the cognizant engineering organization, stressed in tension under constant load. For test purposes, plating thickness shall be  $0.0005 \text{ inch} \pm 0.0002$  ( $51 \mu\text{m} \pm 5$ ) measured on the smooth section of the specimen, but with visual evidence of plating in the root of the notch.

#### 4.4 Approval

- 4.4.1 The process and control factors, or a preproduction part, or both, whichever is specified, shall be approved by the cognizant engineering organization before production parts are supplied.
- 4.4.2 If the processor makes a significant change to any material, process, or control factor from that which was used for process approval, all preproduction tests shall be performed and the results submitted to the cognizant engineering organization for process reapproval unless the change is approved by the cognizant engineering organization. A significant change is one which, in the judgment of the cognizant engineering organization, could affect the properties or performance of the parts.
- 4.4.3 Control factors shall include, but not be limited to the following:

##### Surface preparation

Strike bath composition limits when used  
Current or voltage limits of the strike bath when used  
Temperature limits of the strike bath, when used  
Plating bath composition limits and controls  
Plating bath temperature limits  
Plating bath current/voltage limits  
Methods for measuring plating thickness and adhesion  
Method to assure plating composition  
Conversion coating method and chemical composition limits when used  
Stripping procedures, when applicable  
Method for surface reactivation after plating and before conversion coating (3.3.2)  
Periodic test plan for cleaning and processing solutions. See 8.6.

#### 4.5 Reports

The processor of plated parts shall furnish with each shipment a report stating that the parts have been processed and tested in accordance with the specified requirements and that they conform to acceptance test requirements. This report shall include the purchase order, lot number, AMS2434D, part number and quantity.

#### 4.6 Resampling and Retesting

- 4.6.1 If any acceptance test fails to meet the specified test requirements, the parts in the lot may be stripped, pretreated, plated and post treated as defined herein, and retested. Alternatively, all parts in the lot may be inspected for the non-conforming attribute, and the non conforming parts may be stripped, pretreated, plated and post treated as defined herein, and retested.
- 4.6.1.1 When stripping is performed, the method shall be acceptable to the cognizant engineering organization and shall not roughen, pit, or embrittle the basis metal or adversely affect part dimensions. When parts have been stripped and replated, the purchaser shall be informed.
- 4.6.2 If any periodic test fails to meet the specified test requirements, the process is nonconforming. No additional parts shall be plated until the process is corrected and new specimens are plated and tested. Results of all tests shall be recorded, and, when requested, reported. Purchaser shall be notified of all parts plated since the last acceptable test.