



AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

AMS 2476A

Superseding AMS 2476

Issued 9-15-57

Revised 4-15-67

ELECTROLYTIC TREATMENT FOR MAGNESIUM BASE ALLOYS Alkaline Type, Full Coat

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** To increase corrosion resistance, to provide surfaces which will ensure maximum paint adherence, and to impart maximum abrasion resistance. This process is applicable to all cast and wrought magnesium alloys, after proper allowance has been made for dimensional change, but should not be used on parts which will be flexed in service. For maximum corrosion protection, resin sealing or painting over the coating is required.
3. **PREPARATION:** Parts to be treated shall be cleaned as necessary to leave the surfaces free from grease, oil, soap, alkali, and other contaminants.
4. **SOLUTIONS:** The electrolyte shall be an aqueous solution of the following composition in oz per gal, or its equivalent:

Potassium Hydroxide (KOH)	16.0 - 18.0
Aluminum Hydroxide (dried gel) $(Al(OH)_3)$	4.0 - 5.0
Potassium Fluoride (KF)	4.0 - 5.0
Tri-sodium Phosphate $(Na_3PO_4 \cdot 12H_2O)$	4.0 - 5.0
Potassium Manganate $(97\% K_2MnO_4)$	2.0 - 3.0

The temperature of the solution shall be maintained within the range of 70 - 95 F (21.1 - 35 C).

5. **PROCEDURE:**
 - 5.1 Parts shall be suspended on both electrodes so that the surface areas of the parts on each electrode are approximately equal.
 - 5.2 Parts shall be firmly attached to the racks; contact areas shall be kept to minimum size and, when practicable, shall be on surfaces not required to be coated. When parts are to be coated all over, electrical contact shall be on areas indicated on the drawing.
 - 5.3 The parts shall, insofar as practicable, be hung so that no escaping gas can be entrapped during processing.
 - 5.4 An alternating current shall be applied and the voltage raised as rapidly as possible, maintaining a current density of 15 - 30 amp per sq ft, based on the total area of exposed immersed metal. Completion is indicated by a minimum of 85 v across the work and a uniform brown color free from definite light areas when examined wet after rinsing in cold water. After treatment, parts shall be rinsed in cold water.
 - 5.5 Unless otherwise specified, all parts, immediately following treatment as in 5.4, shall be immersed in the following aqueous solution at room temperature for 40 - 50 sec, after which parts shall be thoroughly drained and allowed to dry without rinsing.

Sodium Dichromate $(Na_2Cr_2O_7 \cdot 2H_2O)$ 2.5 - 3.0 oz per gal

Ammonium Bifluoride (NH_4HF_2) 13.0 - 13.5 oz per gal

E. Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."