

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE AMS 2503D

Issued 10-15-40
Revised 7-1-86

Superseding AMS 2503C

BLACK FINISHING Low Baking Enamel

1. SCOPE:

1.1 Form: This specification covers the engineering requirements for finishing aircraft parts and assemblies with a black enamel.

1.2 Application: Primarily for parts and assemblies operating in service up to 350°F (175°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2400 - Cadmium Plating

AMS 2470 - Anodic Treatment of Aluminum Alloys, Chromic Acid Process

AMS 2471 - Anodic Treatment of Aluminum Alloys, Sulfuric Acid Process, Undyed Coating

AMS 2475 - Protective Treatments, Magnesium Alloys

AMS 2480 - Phosphate Treatment, Paint Base

AMS 3110 - Primer, Zinc Chromate

AMS 3120 - Enamel, Glyceryl Phthalate, Black Baking

2.2 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.2.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

3. TECHNICAL REQUIREMENTS:

3.1 Preparation: Parts and assemblies, before being painted, shall be prepared as follows; elapsed time between preparatory treatments and priming shall be as short as practicable:

3.1.1 Aluminum and Aluminum Alloys: Both wrought and cast parts shall be anodized in accordance with AMS 2470 or AMS 2471.

3.1.1.1 Aluminum Assemblies: Aluminum alloy parts which with parts made of other materials constitute assemblies shall be anodized in accordance with AMS 2470 or AMS 2471 before assembling with such other parts. Anodizing in accordance with AMS 2470 should be used on assemblies in which sulfuric acid could be trapped. Assemblies with parts made of other metals may be anodized if such other parts are insulated.

3.1.2 Magnesium Alloys: Both wrought and cast parts shall be treated in accordance with AMS 2475. Machining of external surfaces shall be completed prior to such treatment.

3.1.3 Steel: Cadmium plated parts shall be thoroughly neutralized in accordance with AMS 2400. Unplated parts shall be cleaned free from oil, grease, dirt, and rust and then treated in accordance with AMS 2480.

3.2 Procedure:

3.2.1 Priming: One coat of AMS 3110 zinc chromate primer shall be applied to all surfaces of metallic parts requiring enameling, except as follows:

3.2.1.1 Anodized rivets shall not be primed as details.

3.2.1.2 Two coats of primer shall be applied to magnesium alloy parts.

3.2.2 Cleaning: When there are intervening operations between priming and enameling, such as assembling or additional machining, the parts shall be thoroughly cleaned by spraying with clean naphtha, or other solvent of low volatility, and given another coat of AMS 3110 zinc chromate primer before the first coat of enamel is applied.

3.2.3 Baking: Each coat of primer shall be baked at 250° - 300°F (120° - 150°C) unless baking at a lower temperature or air drying is permitted by purchaser.

3.2.4 Enameling: The following requirements apply to all metallic surfaces which are exposed after parts are assembled in the power plant or aircraft. Magnesium alloy parts used as covers but not in contact with oil shall be enameled on both inside and outside surfaces except on contacting machined surfaces. Enameling of spot faces is optional.

3.2.4.1 Three coats of AMS 3120 black enamel shall be applied to magnesium alloy parts for use on other than aircraft power plants.

3.2.4.2 Two coats of AMS 3120 black enamel shall be applied to magnesium alloy parts for use on aircraft power plants and to parts of all other metals for all applications.

3.2.4.3 Each coat of enamel shall be thoroughly baked at not higher than 300°F (150°C) or preliminary coats may be air-dried dust-free and the final coat baked firm and hard at not higher than 300°F (150°C).

3.2.4.4 Enameling is not required on nonmetallic materials and associated metal parts, on threaded sections, or on removable steel parts.

3.3 Quality: Finish on parts, as received by purchaser, shall be smooth, uniform in color and gloss, and free from pinholes, sags, runs, heavy edges, foreign materials, and other imperfections detrimental to appearance or performance of the coating.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The finishing vendor shall be responsible for performing all required inspections. Purchaser reserves the right to sample and to perform any confirmatory inspection deemed necessary to ensure that finishing conforms to the requirements of this specification.

4.2 Classification of Inspections: Inspection to determine conformance to requirements for quality (3.3) and for coverage in accordance with drawing requirements or other instructions are classified as acceptance inspections.

4.3 Sampling: Each part or assembly shall be examined.

4.4 Reports: The vendor of painted parts shall furnish with each shipment a report stating that the parts have been processed and inspected in accordance with the requirements of this specification and that they conform. This report shall include the purchase order number, AMS 2503D, part number, and quantity.

5. PREPARATION FOR DELIVERY:

5.1 Packaging:

5.1.1 Finished parts shall be packaged in such a manner as will ensure that the parts, during shipment and storage, will be protected against damage through handling and from exposure to weather or any other normal hazard.

5.1.2 Finished parts shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the finished parts to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.