

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 2672A

Issued 11-1-49

Revised 6-15-52

ALUMINUM BRAZING

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Joining aluminum and selected aluminum alloys.
3. PROCESS REQUIREMENTS:
 - 3.1 Surface Condition: Surfaces to be joined shall be cleaned by suitable means prior to assembly.
 - 3.2 Fluxing: Unless otherwise specified, flux conforming to AMS 3412 shall be applied so that surfaces to be joined are sufficiently coated to ensure the specified bond between the parts after brazing.
 - 3.3 Assembly: Parts to be joined shall be assembled so that clearances between mating surfaces are within tolerances specified on drawing. Assembly should be supported so that the parts will be in proper alignment after brazing.
 - 3.4 Brazing Material: Unless otherwise specified, aluminum brazing alloy shall conform to AMS 4184 or AMS 4185. AMS 4184 is preferred for torch brazing; AMS 4185 is preferred for furnace and dip brazing. Sufficient brazing alloy shall be placed within, or in close proximity to, the joint, except in the case of dip brazing.
 - 3.5 Joining: Unless otherwise specified, heating and joining may be effected by any of the following methods: furnace, torch, or molten flux. Parts shall be heated until brazing alloy melts and joints are formed. Further heating shall be kept to a minimum. The temperature to which parts are heated for brazing shall be controlled so that incipient melting of the parts does not occur.
 - 3.6 Cooling: After brazing, assemblies shall be cooled in such manner as to prevent cracks and minimize internal stress, distortion and oxidation. If solution heat treatment is to be done in conjunction with brazing, cooling procedures may be revised accordingly.
 - 3.7 Flux Removal: After brazing and cooling, flux shall be removed from the parts by a method not injurious to the specified surface finish.
4. QUALITY:
 - 4.1 Exterior examination of joints shall show a generous fillet of brazing alloy at the end of the joint at which the brazing alloy was introduced, and, when practical, complete penetration of brazing alloy in the joint.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Protective users of the report are responsible for protecting themselves against liability for infringement of patents."