

OIL, LUBRICATING, LOW TEMPERATURE
For -55°C (-65°F) Service

1. SCOPE:

1.1 Form: This specification covers a petroleum-base lubricating oil.

1.2 Application: Primarily for general purpose, low-temperature lubrication applications where low evaporation and rust-preventive characteristics are desired.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 2760 - Heat Treatment, Carbon, Low-Alloy, and Specialty Steels

AMS 2825 - Material Safety Data Sheets

AMS 4037 - Aluminum Alloy Sheet and Plate, 4.4Cu - 1.5Mg - 0.60Mn
(2024; -T3 Flat Sheet, -T351 Plate)

AMS 4377 - Magnesium Alloy Sheet and Plate, 3.0Al - 1.0Zn (AZ31B-H24)

AMS 4500 - Copper Sheet, Strip, and Plate, Soft Annealed (CDA 110)

AMS 4507 - Brass Sheet, Strip, and Plate, 70Cu - 30Zn (CDA26000), Half
Hard

AMS 5040 - Steel Sheet and Strip, 0.15 max Carbon, Deep Forming Grade

AMS 6440 - Steel Bars, Forgings, and Tubing, 1.45Cr (0.98-1.10C)
(SAE 52100), For Bearing Applications

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

- ASTM D91 - Precipitation Number of Lubricating Oils
- ASTM D92 - Flash and Fire Points by Cleveland Open Cup
- ASTM D97 - Pour Point of Petroleum Oils
- ASTM D130 - Detection of Copper Corrosion from Petroleum Products by the Copper Strip Tarnish Test
- ASTM D445 - Kinematic Viscosity of Transparent and Opaque Liquids (and the Calculation of Dynamic Viscosity)
- ASTM D664 - Neutralization Number by Potentiometric Titration
- ASTM D972 - Evaporation Loss of Lubricating Greases and Oils
- ASTM D1500 - ASTM Color of Petroleum Products (ASTM Color Scale)
- ASTM D1748 - Rust Protection by Metal Preservatives in the Humidity Cabinet

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-290 - Packaging of Petroleum and Related Products

2.4 ANSI Publications: Available from American National Standards Institute, Inc., 1430 Broadway, New York, NY 10018.

ANSI B46.1 - Surface Texture

3. TECHNICAL REQUIREMENTS:

- 3.1 Material: The oil shall be a fraction of refined crude petroleum, containing additives imparting corrosion protective and oxidation resisting properties, meeting the requirements of 3.2.
- 3.2 Properties: The oil shall conform to the following requirements, determined in accordance with specified test methods insofar as practicable:
- 3.2.1 Color and Appearance: The oil shall be clear, transparent, and uniform in appearance and not darker than No. 5 (ASTM Color Scale), determined in accordance with ASTM D1500.
- 3.2.2 Kinematic Viscosity: Shall conform to the following values, determined in accordance with ASTM D445:

Temperature $\pm 1^{\circ}\text{C}$ ($\pm 2^{\circ}\text{F}$)	Value, cSt (mm^2/s)
38°C (100°F)	10 max
-40°C (-40°F)	4000 max

- 3.2.3 Flash Point: The flash point of the preproduction samples shall be not lower than 130°C (265°F), determined in accordance with ASTM D92. Tests on subsequent lots for acceptance testing shall not differ from the preproduction flash point value by more than $\pm 6^{\circ}\text{C}$ ($\pm 10^{\circ}\text{F}$).
- 3.2.4 Pour Point: Shall be -57°C (-70°F) or below, determined in accordance with ASTM D97.
- 3.2.5 Precipitation Number: Shall be 0.00, determined in accordance with ASTM D91.
- 3.2.6 Corrosion: Shall be not greater than Class 1, determined in accordance with ASTM D130 at $100^{\circ}\text{C} \pm 1$ ($212^{\circ}\text{F} \pm 2$) for 3 hr ± 0.1 .
- 3.2.7 Evaporation: Weight loss shall not exceed 22%, determined in accordance with ASTM D972.
- 3.2.8 Humidity Resistance: Not more than one panel out of five, covered with a film of the lubricating oil and subjected to humidity testing in accordance with ASTM D1748 for 100 hr ± 0.25 , using the same steel and thickness of test panel as in 4.5.1.2, shall exhibit either a dot of rust larger than 2 mm in diameter or two or more dots of rust larger than 1 mm in diameter on the significant area of the panel.
- 3.2.9 Corrosion and Oxidation Stability: The oil shall comply with the following requirements, determined in accordance with 4.5.1:
- 3.2.9.1 Corrosion: The change in weight of metal test specimens shall not exceed $\pm 0.2 \text{ mg/cm}^2$ of surface for each specimen. There shall be no pitting, etching, or visible corrosion on the surfaces of any of the metals when examined at approximately 20X magnification. Slight discoloration of surfaces of the copper and cadmium specimens will be permitted.
- 3.2.9.2 Viscosity Change Due to Oxidation: The viscosity of the oil shall be within -5 to $+20\%$ of the original viscosity, determined in accordance with ASTM D445 at $38^{\circ}\text{C} \pm 1$ ($100^{\circ}\text{F} \pm 2$).
- 3.2.9.3 Neutrality Number Change Due to Oxidation: After the oxidation-corrosion test, the increase in the acid number shall be not greater than 0.20 and there shall be no evidence of separation of insoluble materials or gumming of the oil.
- 3.2.10 Low-Temperature Stability: There shall be no indication of low temperature instability evidenced by gelling or separation of solid or liquid phases in the oil after completion of the test in 4.5.2. The presence of cloudiness which does not settle out is acceptable.
- 3.2.11 Corrosivity Test: Two of the three test assemblies shall show no signs of corrosion or pitting, and the third disc shall exhibit not more than three spots of corrosion within the area covered by the brass clip, determined in accordance with 4.5.3.

3.3 Quality: Oil, as received by purchaser, shall be free of undissolved water, sediment, suspended matter, and other foreign materials detrimental to usage of the oil.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of oil shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the oil conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each lot:

Requirement	Paragraph Reference
Color	3.2.1
Kinematic Viscosity	3.2.2
Flash Point	3.2.3
Pour Point	3.2.4
Precipitation Number	3.2.5
Corrosion, Copper Strip	3.2.6
Evaporation	3.2.7
Corrosion and Oxidation Stability	3.2.9

4.2.2 Preproduction Test: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of oil to a purchaser, when a change in material or processing, or both, requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test oil shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Sufficient oil shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1 A lot shall be all oil produced in a single production run from the same batches of raw materials under the same fixed conditions and presented for vendor's inspection at one time and shall not exceed 10,000 gal (38,000 L). A lot may be packaged in smaller quantities and delivered under the basic lot approval provided the lot identification is maintained.

- 4.3.2 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3 and the report of 4.6.1 shall state that such plan was used.

4.4 Approval:

- 4.4.1 Sample oil shall be approved by purchaser before oil for production use is supplied, unless such approval be waived by purchaser. Results of tests on production oil shall be essentially equivalent to those on the approved sample.
- 4.4.2 Vendor shall use ingredients, manufacturing procedures, and methods of inspection on production oil which are essentially the same as those used on the approved sample oil. If necessary to make any change in ingredients or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in ingredients or processing, or both, and, when requested, sample oil. Production oil made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Test Methods:

4.5.1 Corrosiveness and Oxidation Stability:

- 4.5.1.1 Test Apparatus: Pyrex test tube of standard-wall with 50 mm $\pm$ 3 OD and 500 mm $\pm$ 10 long, with open end formed as a male ground-glass joint. Allihn type condenser of Pyrex; 40 mm, min, OD by 300 mm $\pm$ 20 long jacket, with the lower end formed as a female ground-glass joint to mate with the test tube. Air tube of Pyrex, standard wall, 6 to 8 mm OD and length at least 50 mm longer than the combined length of the assembled test tube and condenser described above. The tube shall have one end drawn to an outside diameter of 0.063 in. $\pm$ 0.016 (1.6 mm $\pm$ 0.4). Constant temperature bath capable of maintaining a temperature of 150°C $\pm$ 1 (300°F $\pm$ 2).
- 4.5.1.2 Preparation of Specimens: Metal specimens, 1 each, nominally 0.032 in. (0.80 mm) thick by 1 in. (25 mm) square, with two holes (Fig. 1) cut from the following materials: AMS 4500 copper, AMS 4037 aluminum alloy, AMS 4377 magnesium alloy, AMS 5040 low carbon steel, and cadmium anode material. Remove burrs from the edges of the specimens and from around drilled holes. Remove surface defects from both surfaces and all edges using progressively finer grades of abrasive paper. After this operation, all subsequent handling of the specimens shall be carried out with clean filter paper or tongs. Use a 240 grit (60 μ m) silicon carbide paper for the final sanding operation, making sure all marks produced by previous abrasive papers are removed. Clean the specimens and store separately immersed in acetone. Remove the specimens from the acetone and polish both flat surfaces and edges, using 150 mesh (100 μ m) silicon carbide grains applied with an acetone moistened pad. Wipe the

4.5.1.2 (Cont'd.):

specimens with clean absorbent cotton pads, changing pads until the pad no longer exhibits a soil when the specimen is wiped. Wash the specimens in warm (approximately 55°C (130°F)) 1,1,1-trichloroethane and allow them to air dry. Weigh and record the weight of each specimen to an accuracy of 0.1 milligram.

- 4.5.1.3 Test Procedure: Determine the neutralization number of the oil sample being evaluated in accordance with ASTM D664. Determine the viscosity of the oil in accordance with ASTM D445 at 38°C + 1 (100°F + 2). Arrange the prepared metal specimens in a wooden or plastic fixture in the pattern shown in Fig. 1, making sure the magnesium and copper specimens do not touch. Tie the squares together using a clean light-weight cotton or nylon cord. Wear latex surgical gloves or nylon gloves when handling the cord and tying the knots. Using forceps, place the assembled specimens in the bottom of the test tube with the squares positioned vertically (so the air tube can be inserted to the bottom of the test tube). Weigh the test tube with metal specimens and the air tube together to the nearest 0.1 gram. Add 100 mL + 1 of the sample oil to the test tube containing the metal specimens, reweigh the air tube, test tube, and contents together to the nearest 0.1 g and determine the weight of the oil sample added. Assemble the test tube and condenser and mount the assembly so that 300 mm + 50 of the test tube is submerged in the constant temperature bath previously stabilized at 150°C + 1 (300°F + 2). Start the flow of cooling water through the condenser jacket. Insert the air tube, orifice end down, through the condenser and into the oil sample, and support it so the orifice is within 0.125 in. (3 mm) of the bottom of the test tube. Connect the air tube to a supply of low pressure, filtered, dry air, and adjust the flow through the tube to 5 L/hr + 0.5. Continue the test for 68 hr + 1. At the end of the test period, stop the flow of air, remove the air tube, and separate the condenser from the test tube containing the specimens. Remove the test tube from the constant temperature bath, allow to cool to room temperature, and wipe the outside with a cloth dampened with 1,1,1-trichloroethane. Reweigh the air tube, test tube, and contents to the nearest 0.1 g, determine the weight of sample remaining, and compute the percentage of weight loss resulting from evaporation of the sample. If the weight loss exceeds 8%, the seal is inadequate and the cause of leak shall be determined and the test repeated using a new oil sample and fresh metal specimens. If the oil sample has lost less than 8% of its initial weight, proceed to remove the metal specimens using forceps. Retain the oil sample for additional testing and visual examination. Remove the cords holding the specimens together and wash the metal specimens individually in warm (approximately 55°C (130°F)) 1,1,1-trichloroethane. Repeat the operation using fresh solvent and scrubbing the surface of the metal specimens with a stiff, short bristled brush until the solvent shows no discoloration. Allow the squares to dry. Reweigh the metal specimens to the nearest 0.1 mg and compute the weight change for each specimen. Visually inspect the

4.5.1.3 (Cont'd.):

metal specimens at 20X magnification and report the presence of pitting or etching and specifically note the color of any stains visible on the surface of the copper specimen. Determine the neutralization number of the residual oil sample in accordance with ASTM D664 and determine the viscosity in accordance with ASTM D445 at $38^{\circ}\text{C} \pm 1$ ($100^{\circ}\text{F} \pm 2$).

4.5.2 Low-Temperature Stability: Place approximately 100 mL of the lubricating oil in a glass-stoppered flask and hold at $-55^{\circ}\text{C} \pm 3$ ($-65^{\circ}\text{F} \pm 5$) for 72 hr ± 0.5 . At the end of the test, examine the oil for evidence of gelling, separation of ingredients, or crystal formation in the oil.

4.5.3 Corrosivity Test:4.5.3.1 Preparation of Specimens:

4.5.3.1.1 Steel Discs: Cut three discs approximately 0.5 in. (12.5 mm) thick from a 1-in. (25-mm) diameter bar of AMS 6440 alloy steel. Heat treat the discs in accordance with AMS 2760 to a hardness not lower than 62 HRC. Wet grind one of the flat surfaces to a surface texture not rougher than 20 microin (0.5 μm), determined in accordance with ANSI B46.1. Remove grinding coolant by washing the discs in clean methanol. Finish the ground surface by using successively finer grades of metallographic polishing papers 1/0, 2/0, 3/0, and finally 4/0 (80 grit (200 μm), 100 grit (150 μm), 125 grit (125 μm), 150 grit (100 μm)). Scratches produced by each polishing paper shall be removed by the next finer grade. Finished discs shall have no scratches more coarse than those produced by the 4/0 (150 grit (100 μm)) polishing paper. Polishing papers incorporating iron oxide as a polishing medium shall not be used. Wipe the discs clean using sterile cotton and examine under 10X magnification. Discs which evidence any corrosion shall not be used. Store the completed discs in a desiccator containing silica gel until ready for use.

4.5.3.1.2 Brass Clips: Three clips shall be fabricated from 0.0225 in. (0.570 mm) AMS 4507 brass sheet as illustrated in Fig. 2. Remove any oil by vapor degreasing and etch the clips by immersing in the following solution for approximately 20 sec at room temperature:

450 mL water
225 mL nitric acid, concentrated
300 mL sulfuric acid, concentrated
8 mL hydrochloric acid, concentrated

AMS 3054

4.5.3.1.2.1 Observe normal precautions in mixing concentrated sulfuric acid and water. Pour the acid into the water slowly, stirring to prevent excessive local heating. After etching, wash the clips in flowing water to ensure removal of the etchant. Rinse in acetone and dry thoroughly. After drying, store the clips in a desiccator containing silica gel until ready for use.

4.5.3.2 Test Procedure: Remove the discs and clips from the desiccator and coat the discs with the test oil by dipping a glass stirring rod in the oil and then allowing it to drop from the rod onto the polished surface of the discs. The oil shall be spread to ensure complete coverage of the discs' surfaces. Place the brass clips over the coated surfaces of the discs and put the assembled specimens in a test chamber which is maintained at $26^{\circ}\text{C} + 1$ ($80^{\circ}\text{F} + 2$) and $50\% + 3$ relative humidity. Continue the test for not less than 10 days. Remove the specimens from the chamber on completion of the test, and outline the area covered by the brass clips using the clip as a template. Remove the clips and carefully wipe the oil from the test surface of the discs. Examine the area outlined on the test surface for corrosion or pitting under 10X magnification.

4.6 Reports:

4.6.1 The vendor of oil shall furnish with each shipment three copies of a report showing the results of tests on each lot to determine conformance to the acceptance test requirements and stating that the oil conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 3054, formula number, lot number, and quantity.

4.6.2 A material safety data sheet conforming to AMS 2825 or equivalent shall be supplied to each purchaser prior to, or concurrent with, the report of preproduction test results or, if preproduction testing be waived by purchaser, concurrent with the first shipment of oil for production use. Each request for modification of formulation shall be accompanied by a revised data sheet for the proposed formulation.

4.7 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the oil may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the oil represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Packaging and Identification:

5.1.1 The oil shall be packaged in airtight containers of such size and design as to keep ullage to a minimum.

- 5.1.2 Each container of oil shall be identified by an attached label, using characters of such size as to be legible and which will not be obliterated by normal handling. Each label shall show not less than the following information:

OIL, LUBRICATING, LOW TEMPERATURE, FOR -55°C (-65°F) SERVICE
AMS 3054

MANUFACTURER'S MATERIAL DESIGNATION _____

PURCHASE ORDER NUMBER _____

LOT (OR BATCH) NUMBER _____

QUANTITY _____

APPROPRIATE WARNINGS OR PRECAUTIONARY NOTICES _____

- 5.1.3 The oil shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the oil to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.
- 5.1.4 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-290, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.1.1 and 5.1.3 will be acceptable if it meets the requirements of Level C.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Oil not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.

8. NOTES:

- 8.1 Dimensions and properties, other than temperatures, in inch/pound units are standard; dimensions and properties in SI units are shown as the approximate equivalents of the inch/pound units and are presented only for informational purposes.

- 8.2 For direct U.S. Military procurement, purchase documents should specify not less than the following:

Title, number, and date of this specification

Type and size of containers desired

Quantity of oil desired

Applicable level of packaging (See 5.1.4)

8.3 Similar Specifications:

- 8.3.1 This specification is the equivalent of MIL-L-7870A, dated 10 August 1953.