

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard



AMS 3157C

Issued JAN 1964

Revised MAY 1996

Superseding AMS 3157B

OIL FLUORESCENT PENETRANT High Fluorescence, Solvent Soluble

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of May 1996. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the "B" revision of the subject specification.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "K"

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1996 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

OIL, FLUORESCENT PENETRANT
High Fluorescence, Solvent Soluble

REAFFIRMED

APR -- 1994

1. SCOPE:

1.1 Form: This specification covers a petroleum-base material in the form of a high-fluorescence, solvent-soluble solution.

1.2 Application: Primarily for use in fluorescent penetrant inspection of parts and assemblies for detection of surface discontinuities and imperfections, particularly when a darkness booth is not available for use in the examination.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

AMS 2350 - Standards and Test Methods

AMS 3160 - Solvent, Petroleum

AMS 4045 - Aluminum Alloy Sheet and Plate, 5.6Zn - 2.5Mg - 1.6Cu - 0.26Cr (7075; -T6 Sheet; -T651 Plate)

AMS 4375 - Magnesium Alloy Sheet and Plate, 3.0Al - 1.0Zn (AZ31B-0)

AMS 6350 - Steel Sheet, Strip, and Plate, 0.95Cr - 0.20Mo (0.28 - 0.33C) (SAE 4130)

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D56 - Flash Point by Tag Closed Tester

ASTM D91 - Precipitation Number of Lubricating Oils

ASTM D95 - Water in Petroleum Products and Bituminous Materials by Distillation

ASTM D130 - Detection of Copper Corrosion from Petroleum Products by the Copper Strip Tarnish Test

ASTM D287 - API Gravity of Crude Petroleum and Petroleum Products (Hydrometer Method)

ASTM D445 - Kinematic Viscosity of Transparent and Opaque Liquids (and the Calculation of Dynamic Viscosity)

ASTM D482 - Ash from Petroleum Products

2.3 U. S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS

3.1 Material: Shall be composed of suitable oil or oil-like components together with a dye or other additives necessary to provide a stable, hydrocarbon-solvent-soluble, highly penetrating, fluorescent solution having the properties specified in 3.2.

3.2 Properties: Penetrant shall conform to the following requirements; tests shall be performed on the penetrant supplied and in accordance with specified test methods:

3.2.1 Flash Point: Shall be not lower than 150° F (65° C), determined in accordance with ASTM D56.

3.2.2 Water Content: Shall be not greater than 0.2%, determined in accordance with ASTM D95.

3.2.3 After initial approval of vendor's product as in 4.4.1., subsequent shipments shall not deviate from the qualification values for the following characteristics in excess of the percentages indicated:

3.2.3.1 Gravity, deg API	±5%	ASTM D287
--------------------------	-----	-----------

3.2.3.2 Viscosity, Kinematic at 100° F (37.8° C), Centistokes	±10%	ASTM D445
--	------	-----------

3.2.3.3 Ash, % max	±5%	ASTM D482
--------------------	-----	-----------

3.2.3.4 Precipitation Number, max	±10%	ASTM D91
-----------------------------------	------	----------

3.2.4 Toxicity: The oil shall contain materials of not more than low toxicity. The penetrant shall not cause discomfort or injury to persons using the oil under normal operating conditions.

3.2.5 Solvent Solubility: Shall be such that the droplets produced when 1 or 2 drops of the penetrant are dropped into a beaker of AMS 3160 petroleum solvent at room temperature shall disperse immediately, leaving only a smoky appearance in the solvent.

3.2.6 Fluorescent Brightness: Shall be not less than 85% of that found in the original product on which source approval was granted, determined in accordance with 4.5.1. Other test methods may be used when agreed upon by purchaser and vendor.

3.2.7 Fluorescent Stability: The fluorescent stability of the exposed specimens shall be not less than 90% of the same unexposed specimens, determined in accordance with 4.5.2.

3.2.8 Corrosiveness: Specimens of AMS 4045 aluminum alloy, AMS 4375 magnesium alloy, and AMS 6350 steel shall reveal no evidence of etching, pitting, or corrosion products after being exposed to a sample of the penetrant solution at 122°F ± 2 (50° C ± 1) in accordance with the test procedure of ASTM D130. Tarnishing shall be no greater than that found by conducting similar tests using tap water.

3.2.9 Storage Life: A closed, filled container of each penetrant submitted for qualification shall meet the requirements of 3.2.1 through 3.2.8 after being stored at 60° - 100° F (16° - 38° C) for one year.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the penetrant shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform such confirmatory testing as he deems necessary to ensure that the penetrant conforms to the requirements of this specification,

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to all technical requirements of this specification, except storage life (3.2.9), are classified as acceptance tests and shall be performed on each lot.

- 4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the initial shipment of the penetrant to a purchaser, when a change in material or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Sufficient penetrant shall be taken at random from each lot to perform all required tests in triplicate; a lot shall be all penetrant produced in a single production run from the same batches of raw materials under the same fixed conditions and presented for vendor's inspection at one time. A lot may be packaged in smaller quantities and delivered separately under the basic lot approval as long as lot identity is maintained,
- 4.4 Approval:
- 4.4.1 Sample penetrant shall be approved by purchaser before penetrant for production use is supplied, unless such approval be waived. Results of tests on production penetrant shall be essentially equivalent to those on the approved sample.
- 4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production penetrant which are essentially the same as those used on the approved sample penetrant. If any change is necessary in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material and processing and, when requested, sample penetrant. Production penetrant made by the revised procedure shall not be shipped prior to receipt of reapproval.
- 4.5 Test Methods:
- 4.5.1 Fluorescent Brightness:
- 4.5.1.1 Test Apparatus: Shall be a photoelectric photofluorometer, Coleman #12C or equivalent, equipped with a Coleman B-1-S primary filter (Corning 5874 glass) which has been sandblasted on the side toward the sample, a Corning CS-3-132 secondary filter, and reflectance sample holder or equivalent.
- 4.5.1.2 Preparation of Specimens: Small amounts of an approved reference penetrant and the penetrant to be tested shall be diluted with a non-fluorescent volatile solvent, such as methylene chloride, in separate containers, in the ratio of one part sample to nine parts solvent. Both penetrants shall be soluble in the same solvent. The solutions shall be agitated and poured into separate wide-mouthed containers. Immediately after the solutions have been poured into the test containers, test paper specimens, Munktel's No. 5 or equivalent, cut to fit the sample holder for the photofluorometer, shall be dipped into each solution, withdrawn, and held in a fixture to air dry. When the samples are dry, they shall be placed for 5 min. $\pm$ 0.5 in a preheated oven at 225° F $\pm$ 5 (107° C $\pm$ 3). Six paper specimens shall be prepared for the reference sample and five for the test material.
- 4.5.1.3 Test Procedure: