



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
485 LEXINGTON AVENUE, NEW YORK, N. Y. 10017

AMS 3193

Issued 5-1-68
Revised

SILICONE RUBBER SPONGE Closed Cell, Medium, Extreme Low Temperature

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **FORM:** Sheet, strip, molded shapes, and extrusions.
3. **APPLICATION:** Primarily for general applications requiring the use of closed cell medium sponge rubber that will be flexible from -112 to +205 C (-170 to +401 F). Compression set may be high at the higher temperatures.
4. **TECHNICAL REQUIREMENTS:**
 - 4.1 **General:**
 - 4.1.1 **Finish:** Unless otherwise specified, the top and bottom surfaces of sheet and strip and the exterior surfaces of molded parts and extrusions (except ends) shall have a natural finish.
 - 4.2 **Properties:** The product shall conform to the following requirements. Tests shall be performed on the product supplied and in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable.
 - 4.2.1 **As Received:**

4.2.1.1 Compression - Deflection, psi	6 - 14	ASTM D1056
		Temperature: 20 - 30 C (68 - 86 F)
4.2.1.2 Density, lb per cu in., max	0.020	
4.2.2 Compression Set:		ASTM D1056
		Temperature: 100 C $\pm$ 1 (212 F $\pm$ 1.8)
4.2.2.1 Per cent of original deflection, max	60	Time: 22 hr
4.2.2.2 Per cent of original thickness, max	30	
4.2.3 Low Temperature Brittleness:	Pass	ASTM D736 (See Note 1)
		Temperature: -90 C $\pm$ 3 (-130 F $\pm$ 5.4)
		Time: 5 hr
- Note 1. To be specified only until satisfactory replacement test and values are established.
5. **QUALITY:** The product shall be uniform in quality and condition, clean, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.
6. **TOLERANCES:** Unless otherwise specified, the following tolerances shall apply; measurements shall be made in accordance with the issue of ASTM D1056 listed in the latest issue of AMS 2350.

SAE Technical Board rules provide that: "All technical reports, including standards, specifications, and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standards or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."