

AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

AMS 3201F

Issued 12-1-42
Revised 2-15-65

SYNTHETIC RUBBER Dry Heat Resistant 35 - 45

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **FORM:** Sheet, strip, tubing, molded shapes, extrusions, or as ordered.
3. **APPLICATION:** Primarily for packings, bushings, grommets, and seals where resistance to dry heat is of prime importance.
4. **TECHNICAL REQUIREMENTS:**
 - 4.1 **General:**
 - 4.1.1 **Condition:** Unless otherwise specified, a suitably cured product shall be furnished.
 - 4.1.2 **Weathering:** When specified, the product shall have weather resistance acceptable to the purchaser as determined by a procedure agreed upon by purchaser and vendor.
 - 4.1.3 **Corrosion:** The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.
 - 4.2 **Properties:** The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable. When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample shall be supplied upon request. This strip shall be prepared from 1 in. $\pm$ 1/16 OD by 0.075 in. $\pm$ 0.008 thick wall tubing which shall be mechanically split and flattened into a strip while being extruded and then cured in the same manner as production material.
 - 4.2.1 **As Received:**

Ø 4.2.1.1 Hardness, Durometer "A" or equiv.	40 $\pm$ 5	ASTM D676
4.2.1.2 Tensile Strength, psi, min		ASTM D412, Die B or C
4.2.1.2.1 For parts other than extrusions	1000	
4.2.1.2.2 For extruded parts	800	
4.2.1.3 Elongation, %, min	300	ASTM D412, Die B or C
 - 4.2.2 **Processing Oil Resistance:**

(Immediate Deterioriated Properties)		ASTM D471
		Medium: ASTM Oil No. 3
		Temperature: 100 C $\pm$ 1
		(212 F $\pm$ 1.8)
		Time: 70 hr
 - 4.2.2.1 Hardness Change, Durometer "A" or equiv. -15 to +10 | | - 4.2.2.2 Tensile Strength Change, %, max (based on area before immersion) -50 | |

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no obligation to conform to or be guided by any technical report. In formulating and applying technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

4.2.2.3	Elongation Change, %, max	-40	
4.2.2.4	Volume Change, %	-10 to +50	
4.2.2.5	Decomposition	None	
4.2.2.6	Surface Tackiness	None	
Ø 4.2.3	<u>Dry Heat Resistance:</u>		ASTM D865
4.2.3.1	Hardness Change, Durometer "A" or equiv.	0 to +20	Temperature: 150 C $\pm$ 3 (302 F $\pm$ 5.4) Time: 70 hr
4.2.3.2	Tensile Strength Change, %, max		
4.2.3.2.1	For parts other than extrusions	-60	
4.2.3.2.2	For extruded parts	-70	
4.2.3.3	Elongation Change, %, max		
4.2.3.3.1	For parts other than extrusions	-70	
4.2.3.3.2	For extruded parts	-85	
4.2.3.4	Bend (flat)	No cracking or checking	
Ø 4.2.4	<u>Compression Set:</u>		ASTM D395, Method B
4.2.4.1	Per cent of original deflection, max	75	Temperature: 100 C $\pm$ 1 (212 F $\pm$ 1.8) Time: 70 hr
Ø 4.2.4.2	Per cent of original thickness, max	19	
4.2.5	<u>Low Temperature Brittleness:</u>	Pass	ASTM D736 (See Note 1) Temperature: -40 C $\pm$ 1 (-40 F $\pm$ 1.8) Time: 5 hr

Note 1. To be specified only until satisfactory replacement test and values are established.

5. QUALITY: The product shall be uniform in quality and condition, clean, smooth, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

6. TOLERANCES: Unless otherwise specified, the following tolerances apply:

6.1 Sheet and Strip:

Nominal Thickness Inches	Tolerance, Inch Plus and Minus
Up to 1/8, incl	1/64
Over 1/8 to 1/2, incl	1/32
Over 1/2	3/64