



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.

TWO PENNSYLVANIA PLAZA, NEW YORK, N. Y. 10001

AMS 3232J

Superseding AMS 3232H

Issued 3-13-40

Revised 11-1-69

ASBESTOS AND SYNTHETIC RUBBER SHEET Hot Oil Resistant

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for gaskets, sealing between metal surfaces, in contact with fuels or with lubricating oil at temperatures up to 150 C (302 F).
3. **MATERIAL AND FABRICATION:** Material shall be made from selected long fibre asbestos and heat resisting synthetic rubber compounds bonded and felted together under pressure into a pliable, resilient product.
4. **TECHNICAL REQUIREMENTS:**
 - 4.1 **General:**
 - 4.1.1 **Color:** Shall be black or light gray, unless otherwise permitted. A deep tan or brown discoloration of light gray products will not be permitted.
 - 4.1.2 **Weathering:** When specified, the product shall have weather resistance acceptable to the purchaser as determined by a procedure agreed upon by purchaser and vendor.
 - 4.1.3 **Delamination:** The product shall not delaminate, due to sticking, when removed from an assembly.
 - 4.1.4 **Corrosion:** The product shall not cause objectionable corrosion of aluminum, magnesium, steel, and copper alloys.
 - 4.2 **Properties:** The product shall conform to the following requirements; tests shall be performed on the product supplied and, except as otherwise noted, in accordance with the issue of ASTM F39 listed in the latest issue of AMS 2350, insofar as practicable. Only specimens for tensile tests of the product as received shall be conditioned. Method A shall be used for all immersion tests.
 - 4.2.1 **As Received:**

4.2.1.1 Tensile Strength, psi, min	
Parallel to Direction of Rolling	4000
Perpendicular to Direction of Rolling	2000
4.2.1.2 Compressibility, %	5 to 20
4.2.1.3 Chloride Content as Cl, %, max	0.35 See Note 1
 - 4.2.2 **Non-Aromatic Fuel Resistance:**

(Immediate Deteriorated Properties)	Medium: ASTM Ref. Fuel A
	Temperature: 20 - 30 C
	(68 - 86 F)
4.2.2.1 Thickness Change, % max	0 to +10 Time: 5 hr
4.2.2.2 Thickness Change on Drying (after 5 hr non-aromatic fuel immersion) at 70 C $\pm$ 1 (158 F $\pm$ 1.8) for 48 hr, %, max	-5

4.2.2.3	Compressibility, %, max	25	
4.2.2.4	Disintegration	None	
4.2.3	<u>Lubricating Oil Resistance:</u> (Immediate Deteriorated Properties)		Medium: ASTM Oil No. 1 Temperature: $150\text{ C} \pm 3$ ($302\text{ F} \pm 5.4$)
4.2.3.1	Tensile Strength Change, %, max	-20	Time: 5 hr
4.2.3.2	Thickness Change, %	0 to +10	
4.2.3.3	Compressibility, %, max	20	
4.2.3.4	Bend 180 deg around diameter equal to 12T for thicknesses 1/16 in. and under or 16T for thicknesses over 1/16 in.	No cracks	
4.2.4	<u>Dry Heat Resistance:</u>		Temperature: $100\text{ C} \pm 1$ ($212\text{ F} \pm 1.8$)
4.2.4.1	Compressibility, %	5 to 20	Time: 16 hr
4.2.4.2	Bend 180 deg around diameter equal to 12T for thicknesses 1/16 in. and under or 16T for thicknesses over 1/16 in.	No cracks	

Note 1. Weigh out a 5 g sample, cut in 1/8 in. squares. Place in Erlenmeyer flask of suitable size. Add 150 ml of distilled water, boil for 1 hr, and filter. Wash flask and sample with distilled water. Cool filtrate and washings to room temperature and dilute to 200 milliliters. Titrate with 0.1 N silver nitrate solution, either potentiometrically or using potassium chromate as the indicator. Run a blank determination on distilled water. Subtract the value for the blank from that for the sample. Calculate per cent chlorine in the sample.

5. **QUALITY:** The product shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

6. **TOLERANCES:** Unless otherwise specified, the following tolerances apply:

Nominal Thickness Inch	<u>Thickness Tolerance, Inch</u>	
	Plus	Minus
Up to 1/64, incl	0.005	0.002
Over 1/64 to 1/16, excl	0.005	0.005
1/16 and over	0.008	0.008

7. REPORTS:

- 7.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report showing the results of tests made on the product to determine conformance to the requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, vendor's material designation, thickness, size, and quantity.
- 7.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, supplier's material designation, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.