

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL
400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 3237E

Submitted for recognition as an American National Standard

Issued 15 FEB 1953
Revised 1 APR 1991

Superseding AMS 3237D

BUTYL (IIR) RUBBER Phosphate Ester Resistant 35 - 45

1. SCOPE:

1.1 Form: This specification covers a butyl (IIR) rubber in the form of sheet, strip, extrusions, and molded shapes.

1.2 Application: Primarily for parts, such as diaphragms, gaskets, grommets, and seals, requiring resistance to phosphate esters or low permeability to gases. Not suitable for use in contact with petroleum-base fluids due to excessive swell.

1.3 Safety - Hazardous Materials: While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS 2279 - Tolerances, Rubber Products
MAM 2279 - Tolerances, Metric, Rubber Products
AMS 2810 - Identification and Packaging, Elastomeric Products

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 3237E

SAE

AMS 3237E

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM D 297 - Rubber Products - Chemical Analysis
- ASTM D 395 - Rubber Property - Compression Set
- ASTM D 412 - Rubber Properties in Tension
- ASTM D 471 - Rubber Property - Effect of Liquids
- ASTM D 518 - Rubber Deterioration - Surface Cracking
- ASTM D 573 - Rubber - Deterioration in an Air Oven
- ASTM D 624 - Rubber Property - Tear Resistance
- ASTM D 797 - Rubber Property - Young's Modulus at Normal and Subnormal Temperatures
- ASTM D 1149 - Rubber Deterioration - Surface Ozone Cracking in a Chamber (Flat Specimens)
- ASTM D 2137 - Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
- ASTM D 2240 - Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS:

- 3.1 Material: Shall be a compound, based on a butyl (IIR) elastomer, suitably cured to produce a product meeting the requirements of 3.2.
- 3.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

3.2.1 As Received:

- | | | | |
|---------|--|--------------------------------|--|
| 3.2.1.1 | Hardness, Durometer "A" or equivalent | 40 $\pm$ 5 | ASTM D 2240 |
| 3.2.1.2 | Tensile Strength, minimum | 1100 psi (7.59 MPa) | ASTM D 412, Die B or C |
| 3.2.1.3 | Elongation, minimum | 550% | ASTM D 412, Die B or C |
| 3.2.1.4 | Tear Resistance pounds/inch (kg/m), minimum | 80% of Preproduction Value | ASTM D 624, Die B |
| 3.2.1.5 | Specific Gravity | Preproduction Value $\pm$ 0.03 | ASTM D 297 |
| 3.2.2 | <u>Phosphate Ester Resistance:</u> (Immediate Deteriorated Properties) | | ASTM D 471 |
| | | | Medium: Tri-n-butyl phosphate |
| 3.2.2.1 | Hardness Change, Durometer "A" or equivalent | 0 to -20 | Temperature: 100°C $\pm$ 1 (212°F $\pm$ 2) |
| | | | Time: 70 hours $\pm$ 0.5 |

AMS 3237E

SAE

AMS 3237E

- 3.2.2.2 Tensile Strength Change, maximum -40%
- 3.2.2.3 Elongation Change, maximum -20%
- 3.2.2.4 Volume Change 0 to +35%
- 3.2.3 Dry Heat Resistance: ASTM D 573
 Temperature: $100^{\circ}\text{C} \pm 1$
 ($212^{\circ}\text{F} \pm 2$)
 Time: 70 hours ± 0.5
- 3.2.3.1 Hardness Change, Durometer "A" or equivalent 0 to +15
- 3.2.3.2 Tensile Strength Change, maximum -25%
- 3.2.3.3 Elongation Change, maximum -50%
- 3.2.4 Compression Set: ASTM D 395, Method B
 Temperature: $100^{\circ}\text{C} \pm 1$
 ($212^{\circ}\text{F} \pm 2$)
 Time: 70 hours ± 0.5
- 3.2.4.1 Percent of Original Deflection, maximum 85
- 3.2.5 Low Temperature Resistance:
- 3.2.5.1 Brittleness Pass ASTM D 2137, Method A
 Temperature: $-35^{\circ}\text{C} \pm 1$
 ($-31^{\circ}\text{F} \pm 2$)
 Time: 10 minutes ± 0.5
- 3.2.5.2 Young's Modulus, maximum (See 8.2) 10 ksi (68.9 MPa) ASTM D 797
 Temperature: $-40^{\circ}\text{C} \pm 1$
 ($-40^{\circ}\text{F} \pm 2$)
- 3.2.6 Weathering: The product shall show no evidence of cracking when tested in accordance with ASTM D 1149 for seven days at $41^{\circ}\text{C} \pm 1$ ($106^{\circ}\text{F} \pm 2$). Test specimens shall be prepared and mounted in accordance with ASTM D 518, Method B.
- 3.2.7 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.
- 3.3 Quality: The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign materials as commercially practicable, and free from imperfections detrimental to usage of the product.
- 3.4 Tolerances: Shall conform to all applicable requirements of AMS 2279 and
 Ø MAM 2279.

AMS 3237E

SAE

AMS 3237E

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all
 0 samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for the following requirements are acceptance tests and shall be performed on each lot:

Requirement	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Volume Change in phosphate ester	3.2.2.4
Compression Set	3.2.4

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing: Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 If specimens cannot be prepared from the product, ASTM test specimens
 0 prepared from the same batch and state of cure shall be used. When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample from the same production lot shall be supplied upon request. This strip shall be prepared from tubing 1.000 inch $\pm$ 0.063 (25.40 mm $\pm$ 1.60) in OD by 0.075 inch $\pm$ 0.008 (1.90 mm $\pm$ 0.20) in wall thickness, mechanically slit and flattened into a strip while being extruded, and cured in the same manner as production product. When the product is a molded shape from which test specimens cannot be cut, a slab 6 inches (152 mm) square by 0.075 inch $\pm$ 0.008 (1.90 mm $\pm$ 0.20) thick molded from the same batch of compound shall be supplied upon request.