

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 3243E

Issued 15 JAN 1957
Revised 1 APR 1991

Submitted for recognition as an American National Standard

Superseding AMS 3243D

CHLOROPRENE (CR) RUBBER Flame Resistant 55 - 65

1. SCOPE:

- 1.1 Form: This specification covers a chloroprene (CR) rubber in the form of sheet, strip, tubing, extrusions, and molded shapes.
- 1.2 Application: Primarily for parts, such as grommets, seals, and line supports, on the firewall of aircraft or wherever flame resistance is of prime importance.
- 1.3 Safety - Hazardous Materials: While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS 2279 - Tolerances, Rubber Products
MAM 2279 - Tolerances, Metric, Rubber Products
AMS 2810 - Identification and Packaging, Elastomeric Products

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 3243E

SAE

AMS 3243E

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM D 297 - Rubber Products - Chemical Analysis
 ASTM D 395 - Rubber Property - Compression Set
 ASTM D 412 - Rubber Properties in Tension
 ASTM D 471 - Rubber Property - Effect of Liquids
 ASTM D 573 - Rubber - Deterioration in an Air Oven
 ASTM D 624 - Rubber Property - Tear Resistance
 ASTM D 635 - Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position
 ASTM D 2137 - Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
 ASTM D 2240 - Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS:

3.1 Material: Shall be a compound, based on a chloroprene (CR) elastomer, suitably cured to produce a product meeting the requirements of 3.2.

3.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

3.2.1 As Received:

3.2.1.1	Hardness, Durometer "A" or equivalent	60 $\pm$ 5	ASTM D 2240
3.2.1.2	Tensile Strength, minimum	900 psi (6.2 MPa)	ASTM D 412, Die B or C
3.2.1.3	Elongation, minimum	200%	ASTM D 412, Die B or C
3.2.1.4	Tear Resistance, minimum	70 pounds force per inch (12.5 kN/m)	ASTM D 624, Die B
3.2.1.5	Specific Gravity	Preproduction Value $\pm$ 0.02	ASTM D 297
3.2.2	<u>Petroleum Hydraulic Oil Resistance:</u> (Immediate Deteriorated Properties)		ASTM D 471 Medium: ASTM Oil No. 3 Temperature: 100°C $\pm$ 1 (212°F $\pm$ 2) Time: 22 hours $\pm$ 0.5
3.2.2.1	Tensile Strength Change, maximum	-60%	
3.2.2.2	Elongation Change, maximum	-60%	
3.2.2.3	Volume Change	+40 to +100%	

AMS 3243E	SAE	AMS 3243E
3.2.2.4 Decomposition	None	
3.2.2.5 Surface Tackiness	None	
3.2.3 <u>Aromatic Fuel Resistance:</u> (Immediate Deteriorated Properties)		ASTM D 471 Medium: ASTM Ref. Fuel B Temperature: 20° - 30°C (68° - 86°F) Time: 22 hours ± 0.5
3.2.3.1 Tensile Strength Change, maximum	-75%	
3.2.3.2 Elongation Change, maximum	-50%	
3.2.3.3 Volume Change	0 to +80%	
3.2.3.4 Decomposition	None	
3.2.3.5 Surface Tackiness	None	
3.2.4 <u>Dry Heat Resistance:</u>		ASTM D 573 Temperature: 125°C ± 2 (257°F ± 4) Time: 70 hours ± 0.5
3.2.4.1 Hardness Change, Durometer "A" or equivalent	0 to +20	
3.2.4.2 Tensile Strength Change, maximum	-30%	
3.2.4.3 Elongation Change, maximum	-50%	
3.2.5 <u>Compression Set:</u>		ASTM D 395, Method B Temperature: 100°C ± 1 (212°F ± 2) Time: 70 hours ± 0.5
3.2.5.1 Percent of Original Deflection, maximum	50	
3.2.6 <u>Low-Temperature Resistance:</u>		ASTM D 2137, Method A Temperature: -35°C ± 1 (-31°F ± 2)
3.2.6.1 Brittleness	Pass	
3.2.7 <u>Flame Resistance See (8.2):</u> Flameout time, maximum	10 seconds	4.5.1
3.2.8 <u>Weathering:</u> When specified, the product shall have weather resistance acceptable to purchaser, determined by a procedure agreed upon by purchaser and vendor.		
3.2.9 <u>Corrosion:</u> The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.		

AMS 3243E

SAE

AMS 3243E

3.3 Quality: The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign material as commercially practicable, and free from imperfections detrimental to usage of the product.

3.4 Tolerances: Shall conform to all applicable requirements of AMS 2279 or
 Ø MAM 2279.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all
 Ø samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for the following requirements are acceptance tests and shall be performed on each lot:

Requirement	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity	3.2.1.5
Volume Change in Oil	3.2.2.3
Flame Resistance	3.2.7

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of a product to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing: Shall be as follows:
 Ø

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.