

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 3315

Issued 11-1-49

Revised

SILICONE RUBBER SHEET - GLASS FABRIC REINFORCED

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. FORM: Calendered sheet, or as ordered.
3. APPLICATION: Primarily intended for gasketing or sealing purposes requiring a thin, resilient, non-porous sheet material suitable for operating at temperatures from -65 to +400 F. The material is resistant to deterioration by weathering and engine oil and remains flexible over the temperature range noted. This material is not normally suitable for use in contact with fuels due to excessive swelling.
4. MATERIAL AND FABRICATION: Sheet shall consist of a single ply of woven glass fabric impregnated and coated on both sides with a silicone rubber compound.
5. TECHNICAL REQUIREMENTS:
 - 5.1 General:
 - 5.1.1 Condition: Unless otherwise specified, a suitably cured product shall be furnished.
 - 5.1.2 Weathering: When specified, the product shall have weather resistance acceptable to the purchaser as determined by a procedure agreed upon by purchaser and vendor.
 - 5.1.3 Corrosion: The product shall not have a corrosive or other deleterious effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.
 - 5.1.4 Coating: Shall be substantially uniform in thickness on both sides of the fabric.
 - 5.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with listed ASTM Methods insofar as practicable:

Property	Value	Test Method
5.2.1 <u>As Received</u> :		ASTM D751-46T
5.2.1.1 Breaking Strength lb per in., min Nominal Thickness, in.		Cut Strip Method
	0.010	70
	0.017	200
	0.032	400

7C of the SAE Technical Board rules provides that: "All technical reports, including standards, developed by the Society of Automotive Engineers, Inc. are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to them, to be guided by any technical report, in formulating and approving technical reports, or to be responsible for protecting themselves against infringement of patents."

<u>Property</u>	<u>Value</u>	<u>Test Method</u>
5.2.1.2 Thread Count, per in., min Nominal Thickness, in.	Warp Fill	
0.010	60 64	
0.017	42 32	
0.032	20 16	
5.2.1.3 Hydrostatic Pressure Resistance	No leaks	Method B Pressure 20 psi Time 1 hr
5.2.1.4 Adhesion, lb per in. width, min	2.0	
Note: If it is impossible to strip adhesion test specimens so as to make the test properly, the sheet may be considered satisfactory.		
5.2.2 <u>Lubricating Oil Resistance:</u>		ASTM D471-46T
(Immediate Deteriorated Properties)		
Volume Change (Method A), %	0 to + 10	Medium: ASTM Oil No. 1
Decomposition	None	Temperature: 350 F+ 2
Surface Tackiness	None	Time: 70 hr -
5.2.3 <u>Dry Heat Resistance:</u>		ASTM D865-48T
Bend (flat)	No cracking or checking	Temperature: 450 F+ 5 Time: 24 hr -
5.2.4 <u>Low Temperature Brittleness:</u>		ASTM D736-46T
Flex	Pass	Temperature: -70 F+2
Delamination	None	Time: 5 hr -
6. <u>QUALITY:</u> The product shall be uniform in quality and condition, clean, smooth, and free from chalky spots, delamination, foreign materials and defects detrimental to fabrication, appearance, or performance of parts.		
7. <u>SIZES AND TOLERANCES:</u> Unless otherwise specified, coated fabric shall be supplied in nominal thicknesses and widths, and to the tolerances, given below:		
Nominal Size, inches	Tolerance, inch	
<u>Thickness</u> <u>Width</u>	<u>Thickness</u>	<u>Width</u>
	plus and minus	plus and minus
0.010	0.001	1.0
0.017	0.002	1.0
0.032	0.008	1.0