

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 3320B

Issued 11-1-49
Revised 12-1-53

SILICONE RUBBER SHEET, GLASS FABRIC REINFORCED Heat and Weather Resistant (60-80)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Molded sheet, or as ordered.
3. APPLICATION: Primarily for gaskets or seals requiring a resilient, nonporous sheet material suitable for operating at temperatures from -65 to +400 F. The material is resistant to deterioration by weathering and engine oil and remains flexible over the temperature range noted. This material is not normally suitable for use in contact with gasoline or aromatic fuels and low aniline point petroleum base fluids due to excessive swelling of the elastomer.
4. MATERIAL AND FABRICATION: Sheet shall consist of a single ply of woven glass fabric (Types 162, 164 or 184) impregnated and bonded between two layers of silicone rubber of essentially equal thickness, molded to an overall thickness of 0.062 to 0.125 in. as ordered.
5. TECHNICAL REQUIREMENTS:
 - 5.1 General:
 - 5.1.1 Condition: Unless otherwise specified, a suitably cured product shall be furnished.
 - 5.1.2 Weathering: When specified, the product shall have weather resistance acceptable to the purchaser as determined by a procedure agreed upon by purchaser and vendor.
 - 5.1.3 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.
 - 5.2 Properties: The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with listed ASTM Methods, insofar as practicable:
 - 5.2.1 As Received:

5.2.1.1 Hardness, Durometer "A" or equiv.	70 $\pm$ 10	See note 1
5.2.1.2 Breaking Strength, lb per in., min	300	ASTM D39-39 Cut Strip Method
5.2.1.3 Edge Leakage at 10 psi	None	See note 2

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone in the industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by the technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

5.2.2 Lubricating Oil Resistance:
(Immediate Deteriorated Properties)

ASTM D471-52T

Medium: ASTM Oil No. 1

Temperature: 350 F + 2

Time: 70 hr

**5.2.2.1 Hardness Change, Durometer "A"
or equiv.**

-15 to +5

5.2.2.2 Volume Change (Method A), %

0 to +10

5.2.2.3 Decomposition

None

5.2.2.4 Surface Tackiness

None

5.2.3 Dry Heat Resistance:**5.2.3.1 Gasket Test****5.2.3.1.1 Decomposition or Softening**

None

See note 3

5.2.3.1.2 Surface Tackiness

None

Temperature: 450 F ± 2
Time: 2 hr**5.2.3.2 Hardness Change, Durometer "A"
or equiv.**

-5 to +10

ASTM D573-52

Temperature: 450 F + 2

Time: 24 hr

5.2.3.3 Bend

No cracking

Bend 180 deg over rod
whose diameter is equal to
thickness of material.**5.2.4 Compression Set:**

ASTM D395-49T Method B

5.2.4.1 Percent of Original Deflection, max

72

Temperature: 350 F ± 2

Time: 22 hr

5.2.4.2 Percent of Original Thickness, max

18

Compressed to 75% of original
thickness.**5.2.5 Low Temperature Brittleness:**

ASTM D736-46T (See note 4)

5.2.5.1 Flex

Pass

Temperature: -70 F ± 2

Time: 5 hr

5.2.5.2 Delamination

None

Note 1. Hardness requirement applies to sheet specimens stacked to
1/4 in. thick.

Note 2. A circular gasket specimen shall be prepared, having ID not less than 2 in. and 1-in. wide faces. The gasket shall be clamped between suitable flanges, using #10-32 bolts (0.189 in. dia) spaced approximately 1 in. on centers for clamping; nuts shall be tightened to 40 in-lb torque. Air at an edge pressure of 10 psi shall be applied to the ID of the gasket with the assembly immersed in, or coated with, soap solution, for not less than 1 min. at room temperature. There shall be no leakage through the fabric layer.

Note 3. A gasket specimen at least 1 sq in. in surface area shall be clamped finger tight between aluminum plates and conditioned at the temperature and time specified. Examination shall be immediately upon removal from the oven and cooling to room temperature.

Note 4. To be used only until satisfactory replacement test and values are established.

6. QUALITY: The product shall be uniform in quality and condition, clean, smooth, and free from chalky spots, delamination, foreign materials and defects detrimental to fabrication, appearance, or performance of parts.
7. TOLERANCES: Unless otherwise specified, the following tolerances apply to molded sheet:

Nominal Thickness Inch	Tolerance, Inch Plus and Minus
0.062 to 0.125, incl	0.015

8. REPORTS:

- 8.1 Unless otherwise specified, the vendor the product shall furnish with each shipment three copies of a report stating that the product meets the requirements of this specification. This report shall include the purchase order number, material specification number, vendor's compound number, form or part number, and quantity.
- 8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.
9. IDENTIFICATION: Unless otherwise specified, all material shall be identified and marked in accordance with the latest issue of AMS 2810.