

AEROSPACE MATERIAL SPECIFICATION



AMS 3335D

Issued MAR 1955
Revised JAN 1983
Noncurrent MAY 1990
Reaf. Noncur. APR 2001

Superseding AMS 3335C

Silicone Rubber
Extreme Low-Temperature Resistant
45 - 55

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of May 1990. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available.

SAENORM.COM : Click to view the full PDF of AMS 3335D

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2001 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

1. SCOPE:

1.1 Form:

This specification covers an extreme-low-temperature-resistant silicone rubber in the form of sheet, strip, tubing, extrusions, and molded shapes.

1.2 Application:

Primarily for rubber-like parts required to operate or seal from -75° to +120°C (-105° to +250°F), compounded especially for operation at extreme low temperatures. Silicone elastomer is resistant to deterioration by weathering and by high-aniline-point petroleum-base oils and remains flexible over the temperature range noted. This material is not normally suitable for use in contact with low-aniline-point petroleum-base fluids, including fuels, due to excessive swelling.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 Standards and Test Methods

AMS 2810 Identification and Packaging, Elastomeric Products

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D297 Rubber Products - Chemical Analysis

ASTM D395 Rubber Property - Compression Set

ASTM D412 Rubber Properties in Tension

ASTM D471 Rubber Property - Effect of Liquids

ASTM D518 Rubber Deterioration - Surface Cracking

ASTM D573 Rubber Deterioration in an Air Oven

ASTM D624 Rubber Property - Tear Resistance

ASTM D797 Rubber Property - Young's Modulus at Normal and Subnormal Temperatures

ASTM D1149 Rubber Deterioration - Surface Ozone Cracking in a Chamber (Flat Specimens)

ASTM D2137 Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics

ASTM D2240 Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Shall be a compound based on a silicone rubber, suitably cured to produce a product meeting the requirements of 3.2.

3.2 Properties:

The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable.

3.2.1 As Received:

3.2.1.1	Hardness, Durometer "A" or equiv.	50 ± 5	ASTM D2240
---------	--------------------------------------	--------	------------

3.2.1.2	Tensile Strength, min	600 psi (4.15 MPa)	ASTM D412, Die B or C
---------	-----------------------	-----------------------	--------------------------

3.2.1.3	Elongation, min	175%	ASTM D412, Die B or C
---------	-----------------	------	--------------------------

3.2.1.4	Tear Resistance, min	45 lb per in. (7.90 kN/m)	ASTM D624, Die B
---------	----------------------	------------------------------	---------------------

3.2.1.5	Specific Gravity	Preproduction Value ± 0.03	ASTM D297
---------	------------------	-------------------------------	-----------

3.2.2	Petroleum Lubricating Oil Resistance:	ASTM D471 Medium:	ASTM Oil No. 1
-------	---------------------------------------	----------------------	----------------

3.2.2.1	Hardness Change, Durometer "A" or equiv.	-10 to +5	Temperature: 100°C ± 1 (212°F ± 2)
			Time: 70 hr ± 0.5

3.2.2.2	Tensile Strength Change, max	-30%
---------	---------------------------------	------

3.2.2.3	Elongation Change, max	-15%
---------	------------------------	------

3.2.2.4	Volume Change	0 to +10%
---------	---------------	-----------

3.2.2.5	Decomposition	None
---------	---------------	------

3.2.2.6	Surface Tackiness	None
---------	-------------------	------

AMS 3335D**SAE****AMS 3335D****3.2.3 Dry Heat Resistance:**

ASTM D573

Temperature: 100°C ± 1

3.2.3.1 Hardness Change, Durometer "A" or equiv. -0 to +5(212°F ± 2)
Time: 22 hr ± 0.5**3.2.3.2 Tensile Strength Change, max** -10%**3.2.3.3 Elongation Change, max** -15%**3.2.3.4 Bend (flat)** No cracking or checking**3.2.4 Compression Set:**

ASTM D395, Method B

Temperature: 100°C ± 1

3.2.4.1 Percent of Original Deflection, max 30(212°F ± 2)
Time: 22 hr ± 0.5**3.2.5 Low-Temperature Resistance:****3.2.5.1 Brittleness** Pass

ASTM D2137, Method A

Temperature: -80°C ± 3
(-112°F ± 5)**3.2.5.2 Young's Modulus, max (See 8.2)** 10,000 psi
(69.0 MPa)ASTM D797
Temperature: -75°C ± 3
(-103°F ± 5)
Time: 5 hr ± 0.2

3.2.6 Weathering: The product, unless otherwise specified, shall show no evidence of cracking when tested in accordance with ASTM D1149 for 7 days at 40°C ± 1 (104°F ± 2). Test specimens shall be prepared and mounted in accordance with ASTM D518, Method B.

3.2.7 Corrosion: The rubber, unless otherwise specified, shall not have a corrosive effect on other materials, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.

3.3 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign material as commercially practicable, and free from imperfections detrimental to usage of the product.

3.4 Tolerances:

Unless otherwise specified, the following tolerances shall apply:

3.4.1 Sheet and Strip:

TABLE I

Nominal Thickness (T) Inches	Tolerance, Inch Plus and Minus Fixed	Tolerance, Inch Plus and Minus Closure (See 3.4.1.1)
Up to 0.400, incl	0.008	0.013
Over 0.400 to 0.630, incl	0.010	0.016
Over 0.630 to 1.000, incl	0.013	0.020
Over 1.000 to 1.600, incl	0.016	0.025
Over 1.600 to 2.500, incl	0.020	0.032
Over 2.500 to 4.000, incl	0.025	0.040
Over 4.000 to 6.300, excl	0.032	0.050
6.300 and over	0.005T	

TABLE I (SI)

Nominal Thickness (T) Millimetres	Tolerance, Millimetres Plus and Minus Fixed	Tolerance, Millimetres Plus and Minus Closure (See 3.4.1.1)
Up to 10.00, incl	0.20	0.32
Over 10.00 to 16.00, incl	0.25	0.40
Over 16.00 to 25.00, incl	0.32	0.50
Over 25.00 to 40.00, incl	0.40	0.63
Over 40.00 to 63.00, incl	0.50	0.80
Over 63.00 to 100.00, incl	0.63	1.00
Over 100.00 to 160.00, excl	0.80	1.25
160 and over	0.005T	

3.4.1.1 Closure dimensions are across mold parting line.

3.4.2 Tubing Diameter and Wall Thickness:

TABLE II

Nominal OD or ID (D) (not both) and Wall Thickness Inches	Tolerance, Inch Plus and Minus	Ovality, % (See 3.4.2.2)
Up to 0.100, incl (See 3.4.2.1)	0.016	10
Over 0.100 to 0.160, incl	0.020	15
Over 0.160 to 0.250, incl	0.025	15
Over 0.250 to 0.400, incl	0.030	15
Over 0.400 to 0.630, incl	0.040	15
Over 0.630 to 1.000, incl	0.050	15
Over 1.000	0.0450xD	15

TABLE II (SI)

Nominal OD or ID (D) (not both) and Wall Thickness Millimetres	Tolerance, Millimetre Plus and Minus	Ovality (See 3.4.2.2)
Up to 2.50, incl (See 3.4.3.1)	0.40	10
Over 2.50 to 4.00, incl	0.50	15
Over 4.00 to 6.30, incl	0.63	15
Over 6.30 to 10.00, incl	0.80	15
Over 10.00 to 16.00, incl	1.00	15
Over 16.00 to 25.00, incl	1.25	15
Over 25.00	0.0450xD	

3.4.2.1 In general, cross-section dimensions less than 0.040 in. (1.00 mm) are impractical to extrude.

3.4.2.2 Ovality applies to tubing ordered in straight lengths with wall thickness of 0.063 in. (1.60 mm) and over, and shall be computed from the difference between the minor and major axis diameter measurements, taken at the same transverse plane of the tube, expressed as a percentage of the nominal diameter.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each lot:

Requirement	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity	3.2.1.5
Compression Set	3.2.4
Brittleness	3.2.5.1

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of tests for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three. When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample shall be supplied upon request. This strip shall be prepared from tubing 1 in. ± 0.063 (25 mm ± 1.60) in OD by 0.080 in. ± 0.008 (2.00 mm ± 0.20) in wall thickness, mechanically split and flattened into a strip while being extruded, and cured in the same manner as production material. When the product is a molded shape from which test specimens cannot be cut, a slab 6 x 6 x 0.075 in. (150 x 150 x 2 mm) molded from the same batch of compound shall be supplied upon request.

4.3.1.1 A lot shall be all product from the same batch of compound processed in one continuous run and presented for vendor's inspection at one time. An inspection lot shall not exceed 500 lb (225 kg).

4.3.1.2 A batch shall be the quantity of compound run through a mill or mixer at one time.

4.3.1.3 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6.1 shall state that such plan was used.