

AEROSPACE MATERIAL SPECIFICATION



AMS3335

REV. E

Issued	1955-03
Revised	1983-01
Noncurrent	1990-05
Reaf. Noncur.	2001-04
Stabilized	2011-11

Superseding AMS3335D

Silicone Rubber
Extreme Low-Temperature Resistant
45 - 55

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE CE, Elastomers Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of AMS3335E

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2011 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3335E>**

1. SCOPE:

1.1 Form:

This specification covers an extreme-low-temperature-resistant silicone rubber in the form of sheet, strip, tubing, extrusions, and molded shapes.

1.2 Application:

Primarily for rubber-like parts required to operate or seal from -75° to +120°C (-105° to +250°F), compounded especially for operation at extreme low temperatures. Silicone elastomer is resistant to deterioration by weathering and by high-aniline-point petroleum-base oils and remains flexible over the temperature range noted. This material is not normally suitable for use in contact with low-aniline-point petroleum-base fluids, including fuels, due to excessive swelling.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 Standards and Test Methods
AMS 2810 Identification and Packaging, Elastomeric Products

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D297	Rubber Products - Chemical Analysis
ASTM D395	Rubber Property - Compression Set
ASTM D412	Rubber Properties in Tension
ASTM D471	Rubber Property - Effect of Liquids
ASTM D518	Rubber Deterioration - Surface Cracking
ASTM D573	Rubber Deterioration in an Air Oven
ASTM D624	Rubber Property - Tear Resistance
ASTM D797	Rubber Property - Young's Modulus at Normal and Subnormal Temperatures
ASTM D1149	Rubber Deterioration - Surface Ozone Cracking in a Chamber (Flat Specimens)
ASTM D2137	Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
ASTM D2240	Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Shall be a compound based on a silicone rubber, suitably cured to produce a product meeting the requirements of 3.2.

3.2 Properties:

The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

3.2.1 As Received:

3.2.1.1	Hardness, Durometer "A" or equiv.	50 ± 5	ASTM D2240	
3.2.1.2	Tensile Strength, min	600 psi (4.15 MPa)	ASTM D412, Die B or C	
3.2.1.3	Elongation, min	175%	ASTM D412, Die B or C	
3.2.1.4	Tear Resistance, min	45 lb per in. (7.90 kN/m)	ASTM D624, Die B	
3.2.1.5	Specific Gravity	Preproduction Value ± 0.03	ASTM D297	
3.2.2	Petroleum Lubricating Oil Resistance:		ASTM D471 Medium:	ASTM Oil No. 1
3.2.2.1	Hardness Change, Durometer "A" or equiv.	-10 to +5	Temperature:	100°C ± 1 (212°F ± 2)
			Time:	70 hr ± 0.5
3.2.2.2	Tensile Strength Change, max	-30%		
3.2.2.3	Elongation Change, max	-15%		
3.2.2.4	Volume Change	0 to +10%		
3.2.2.5	Decomposition	None		
3.2.2.6	Surface Tackiness	None		

3.2.3	Dry Heat Resistance:		ASTM D573	
			Temperature:	100°C ± 1
3.2.3.1	Hardness Change, Durometer "A" or equiv.	-0 to +5		(212°F ± 2)
			Time:	22 hr ± 0.5
3.2.3.2	Tensile Strength Change, max	-10%		
3.2.3.3	Elongation Change, max	-15%		
3.2.3.4	Bend (flat)	No cracking or checking		
3.2.4	Compression Set:		ASTM D395, Method B	
			Temperature:	100°C ± 1
3.2.4.1	Percent of Original Deflection, max	30		(212°F ± 2)
			Time:	22 hr ± 0.5
3.2.5	Low-Temperature Resistance:			
3.2.5.1	Brittleness	Pass	ASTM D2137, Method A	
			Temperature:	-80°C ± 3 (-112°F ± 5)
3.2.5.2	Young's Modulus, max (See 8.2)	10,000 psi (69.0 MPa)	ASTM D797	
			Temperature:	-75°C ± 3 (-103°F ± 5)
			Time:	5 hr ± 0.2
3.2.6	Weathering: The product, unless otherwise specified, shall show no evidence of cracking when tested in accordance with ASTM D1149 for 7 days at 40°C ± 1 (104°F ± 2). Test specimens shall be prepared and mounted in accordance with ASTM D518, Method B.			
3.2.7	Corrosion: The rubber, unless otherwise specified, shall not have a corrosive effect on other materials, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.			
3.3	Quality:			

The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign material as commercially practicable, and free from imperfections detrimental to usage of the product.

3.4 Tolerances:

Unless otherwise specified, the following tolerances shall apply:

3.4.1 Sheet and Strip:

TABLE I

Nominal Thickness (T) Inches	Tolerance, Inch Plus and Minus Fixed	Tolerance, Inch Plus and Minus Closure (See 3.4.1.1)
Up to 0.400, incl	0.008	0.013
Over 0.400 to 0.630, incl	0.010	0.016
Over 0.630 to 1.000, incl	0.013	0.020
Over 1.000 to 1.600, incl	0.016	0.025
Over 1.600 to 2.500, incl	0.020	0.032
Over 2.500 to 4.000, incl	0.025	0.040
Over 4.000 to 6.300, excl	0.032	0.050
6.300 and over	0.005T	

TABLE I (SI)

Nominal Thickness (T) Millimetres	Tolerance, Millimetres Plus and Minus Fixed	Tolerance, Millimetres Plus and Minus Closure (See 3.4.1.1)
Up to 10.00, incl	0.20	0.32
Over 10.00 to 16.00, incl	0.25	0.40
Over 16.00 to 25.00, incl	0.32	0.50
Over 25.00 to 40.00, incl	0.40	0.63
Over 40.00 to 63.00, incl	0.50	0.80
Over 63.00 to 100.00, incl	0.63	1.00
Over 100.00 to 160.00, excl	0.80	1.25
160 and over	0.005T	

3.4.1.1 Closure dimensions are across mold parting line.

3.4.2 Tubing Diameter and Wall Thickness:

TABLE II

Nominal OD or ID (D) (not both) and Wall Thickness Inches	Tolerance, Inch Plus and Minus	Ovality, % (See 3.4.2.2)
Up to 0.100, incl (See 3.4.2.1)	0.016	10
Over 0.100 to 0.160, incl	0.020	15
Over 0.160 to 0.250, incl	0.025	15
Over 0.250 to 0.400, incl	0.030	15
Over 0.400 to 0.630, incl	0.040	15
Over 0.630 to 1.000, incl	0.050	15
Over 1.000	0.0450xD	15

TABLE II (SI)

Nominal OD or ID (D) (not both) and Wall Thickness Millimetres	Tolerance, Millimetre Plus and Minus	Ovality (See 3.4.2.2)
Up to 2.50, incl (See 3.4.3.1)	0.40	10
Over 2.50 to 4.00, incl	0.50	15
Over 4.00 to 6.30, incl	0.63	15
Over 6.30 to 10.00, incl	0.80	15
Over 10.00 to 16.00, incl	1.00	15
Over 16.00 to 25.00, incl	1.25	15
Over 25.00	0.0450xD	

3.4.2.1 In general, cross-section dimensions less than 0.040 in. (1.00 mm) are impractical to extrude.

3.4.2.2 Ovality applies to tubing ordered in straight lengths with wall thickness of 0.063 in. (1.60 mm) and over, and shall be computed from the difference between the minor and major axis diameter measurements, taken at the same transverse plane of the tube, expressed as a percentage of the nominal diameter.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to the following requirements are classified as acceptance tests and shall be performed on each lot:

Requirement	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity	3.2.1.5
Compression Set	3.2.4
Brittleness	3.2.5.1

- 4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

- 4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

- 4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of tests for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three. When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample shall be supplied upon request. This strip shall be prepared from tubing 1 in. ± 0.063 (25 mm ± 1.60) in OD by 0.080 in. ± 0.008 (2.00 mm ± 0.20) in wall thickness, mechanically split and flattened into a strip while being extruded, and cured in the same manner as production material. When the product is a molded shape from which test specimens cannot be cut, a slab 6 x 6 x 0.075 in. (150 x 150 x 2 mm) molded from the same batch of compound shall be supplied upon request.

- 4.3.1.1 A lot shall be all product from the same batch of compound processed in one continuous run and presented for vendor's inspection at one time. An inspection lot shall not exceed 500 lb (225 kg).

- 4.3.1.2 A batch shall be the quantity of compound run through a mill or mixer at one time.

- 4.3.1.3 When a statistical sampling plan and acceptance quality level (AQL) have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6.1 shall state that such plan was used.