



AEROSPACE MATERIAL SPECIFICATION

AMS3356**REV. F**

Issued	1956-07
Revised	1991-04
Reaffirmed	2003-11
Stabilized	2014-05

Superseding AMS3356E

Silicone (VMQ) Rubber
Lubricating Oil and Compression Set Resistant, Electrical Grade
55 - 65

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by the AMS CE Elastomers Committee and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of AMS3356F

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2014 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3356F>**

1. SCOPE:

1.1 Form:

This specification covers a silicone (VMQ) rubber in the form of sheet, strip, tubing, extrusions, and molded shapes.

1.2 Application:

Primarily for parts required to operate or seal from -55° to +230°C (-67° to +446°F), compounded especially for aircraft piston engine oil resistance, low compression set, and controlled dielectric strength. Silicone elastomer is resistant to deterioration by weathering and by high-aniline-point petroleum-base oils and remains flexible over the temperature range noted. This elastomer is not normally suitable for use in contact with gasoline or aromatic fuels and low-aniline-point petroleum-base fluids due to excessive swelling of the elastomer.

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS 2279	Tolerances, Rubber Products
MAM 2279	Tolerances, Metric, Rubber Products
AMS 2810	Identification and Packaging, Elastomeric Products

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM D 149	Dielectric Breakdown Voltage and Dielectric Strength of Electrical Insulating Materials at Commercial Power Frequencies
ASTM D 297	Rubber Products - Chemical Analysis
ASTM D 395	Rubber Property - Compression Set
ASTM D 412	Rubber Properties in Tension
ASTM D 471	Rubber Property - Effect of Liquids
ASTM D 573	Rubber - Deterioration in an Air Oven
ASTM D 624	Rubber Property - Tear Resistance
ASTM D 797	Rubber Property - Young's Modulus at Normal and Subnormal Temperatures
ASTM D 2137	Rubber Property - Brittleness Point of Flexible Polymers and Coated Fabrics
ASTM D 2240	Rubber Property - Durometer Hardness

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Shall be a compound, based on a silicone (VMQ) rubber, suitably cured to produce a product meeting the requirements of 3.2.

3.2 Properties:

The product shall conform to the following requirements; tests shall be performed on the product supplied and in accordance with specified ASTM methods, insofar as practicable:

3.2.1 As Received:

3.2.1.1 Hardness, Durometer "A" or equivalent	60 ± 5	ASTM D 2240
--	--------	-------------

3.2.1.2	Tensile Strength, minimum	800 psi (5.52 MPa)	ASTM D 412, Die B or C
3.2.1.3	Elongation, minimum	200%	ASTM D 412, Die B or C
3.2.1.4	Tensile Stress at 50% Elongation, maximum	250 psi (1.72 MPa)	ASTM D 412, Die B or C
3.2.1.5	Tear Strength, minimum	50 pounds force per inch (8.76 kN/m)	ASTM D 624, Die B
3.2.1.6	Dielectric Strength, Short Time Test, minimum Specimen Thickness: 0.070 - 0.080 inch (1.78 - 2.03 mm)	350 Volts per mil (13,800 V/mm)	ASTM D 149
3.2.1.7	Specific Gravity	Preproduction Value ± 0.03	ASTM D 297
3.2.2	Petroleum Lubricating-Oil Resistance: (Immediate Deteriorated Properties)		ASTM D 471 Medium: ASTM Oil No. 1 Temperature: $175^{\circ}\text{C} \pm 3$ ($347^{\circ}\text{F} \pm 5$) Time: 70 hours ± 0.5
3.2.2.1	Hardness Change, Durometer "A" or equivalent	-15 to +5	
3.2.2.2	Tensile Strength Change, maximum	-20%	
3.2.2.3	Elongation Change, maximum	-15%	
3.2.2.4	Volume Change, maximum	0 to +15%	
3.2.2.5	Decomposition	None	
3.2.2.6	Surface Tackiness	None	

3.2.3	Water Resistance: (Immediate Deteriorated Distilled Water Properties)		ASTM D 471 Medium: Temperature: 20° - 30°C (68° - 86°C) Time: 46 hours ± 0.5
3.2.3.1	Volume Change, maximum ± 0.5	0 to +5%	
3.2.3.2	Dielectric Strength Change, maximum	-15%	
3.2.4	Dry Heat Resistance:		ASTM D 573 Temperature: 225°C ± 3 (437°F ± 5) Time: 22 hours ± 0.5
3.2.4.1	Hardness Change, Durometer "A" or equivalent	0 to +10	
3.2.4.2	Tensile Strength Change, maximum	-15%	
3.2.4.3	Elongation Change, maximum	-25%	
3.2.5	Compression Set:		ASTM D 395, Method B Temperature: 175°C ± 3 (347°F ± 5) Time: 22 hours ± 0.5
3.2.5.1	Percent of Original Deflection, maximum	30	
3.2.6	Low-Temperature Resistance:		
3.2.6.1	Brittleness	Pass	ASTM D 2137, Method A Temperature: -65°C ± 3 (-85°F ± 5)
3.2.6.2	Young's Modulus, maximum (See 8.2)	10,000 psi (68.9 MPa)	ASTM D 797 Temperature: -50°C ± 3 (-58°F ± 5) Time: 5 hours ± 0.2
3.2.7	Weathering: The product shall have weather resistance acceptable to purchaser, determined by a procedure agreed upon by purchaser and vendor.		
3.2.8	Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service, determined by a procedure agreed upon by purchaser and vendor. Discoloration of metal shall not be considered objectionable.		

3.3 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, smooth, as free from foreign materials as commercially practicable, and free from imperfections detrimental to usage of the product.

3.4 Tolerances:

Shall conform to all applicable requirements of AMS 2279 or MAM 2279.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

φ

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for the following requirements are acceptance tests and shall be performed on each lot.

Requirement	Paragraph Reference
Hardness, as received	3.2.1.1
Tensile Strength, as received	3.2.1.2
Elongation, as received	3.2.1.3
Specific Gravity	3.2.1.7
Petroleum Lubricating Oil Resistance	3.2.2
Compression Set	3.2.5

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the initial shipment of the product to a purchaser, when a change in ingredients and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:

φ

Shall be as follows:

4.3.1 For Acceptance Tests: Sufficient product shall be taken at random from each lot to perform all required tests. The number of determinations for each requirement shall be as specified in the applicable test procedure or, if not specified therein, not less than three.

4.3.1.1 φ If specimens cannot be prepared from the product, ASTM test specimens prepared from the same batch and state of cure shall be used. When the product supplied is an extrusion of such shape that suitable test specimens cannot be cut from the product, a separate flat strip test sample from the same production lot shall be supplied upon request. This strip shall be prepared from tubing 1.000 inch $\pm$ 0.063 (25.40 mm $\pm$ 1.60) in OD by 0.075 inch $\pm$ 0.008 (1.90 mm $\pm$ 0.20) in wall thickness, mechanically slit and flattened into a strip while being extruded, and cured in the same manner as production product. When the product is a molded shape from which test specimens cannot be cut, a slab 6 inches (152 mm) square by 0.075 inch $\pm$ 0.008 (1.90 mm $\pm$ 0.020) thick molded from the same batch of compound shall be supplied upon request.

4.3.1.2 A lot shall be all product from the same batch of compound processed in one continuous run and presented for vendor's inspection at one time. An inspection lot shall not exceed 500 pounds (227 kg) and may be packaged in smaller quantities and delivered under the basic lot approval provided lot identification is maintained.

4.3.1.3 A batch shall be the quantity of compound run through a mill or mixer at one time.

4.3.1.4 φ When a statistical sampling plan has been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.5 shall state that such plan was used.

4.3.2 For Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval:

4.4.1 Sample product shall be approved by purchaser before product for production use is supplied, unless such approval be waived by purchaser. Results of tests on production product shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production product which are essentially the same as those used on the approved sample product. If necessary to make any change in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in ingredients and/or processing and, when requested, sample product. Production product made by the revised procedure shall not be shipped prior to receipt of reapproval.