

AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N.Y. 10017

AMS 3364A

Issued 1-31-64

Revised 2-15-65

SILICONE RUBBER COMPOUND

Room Temperature Vulcanizing, 50,000 Centipoises Viscosity, Short Pot Life
Durometer 35 - 55

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **FORM:** Liquid compound, to which a separate catalyst is added for curing.
3. **APPLICATION:** Primarily for potting or encasement of electrical and electronic components with an elastomeric medium, or for production of mechanical rubber parts in low pressure tooling. Elastomeric properties are retained in operation at temperatures from -55 to +230 C (-67 to +446 F). For mechanical applications where compression set resistance is important, elevated temperature post curing of parts may be required.
4. **TECHNICAL REQUIREMENTS:**
 - 4.1 **General:**
 - 4.1.1 **Curing:** When mixed with catalyst in accordance with manufacturer's recommendations and cured at room temperature, the compound shall polymerize to a uniform elastomeric material. A number of different catalysts may be found applicable by the user in order to vary pot life and cure time to meet specific production conditions. However, for purposes of qualification to this specification and for inspection control, a standard catalyst type and quantity, as supplied or recommended by the manufacturer of the base compound, shall be used.
 - 4.1.2 **Viscosity:** Viscosity of compound as received shall be 35,000 - 70,000 centipoises measured on a Brookfield Viscometer at $25\text{ C} \pm 1$ ($77\text{ F} \pm 1.8$). In measuring viscosity, the viscometer spindle and speed used shall be consistent with the viscosity of the material being tested, in accordance with directions supplied by the manufacturer of the instrument.
 - 4.1.3 **Pot Life:** Compound mixed with the recommended catalyst addition (See 4.1.1) and maintained at a temperature not higher than 30 C (86 F) shall have a pot life of 5 - 15 minutes. Pot life shall be determined as follows: Weigh a $10\text{ g} \pm 0.10$ sample of the compound into a cup or dish 2 - 2.5 in. in diameter. Add the recommended type and amount of catalyst (See 4.1.1) and mix thoroughly with a small spatula for $60\text{ sec} \pm 10$. Dip the spatula into the catalyzed compound and pull out strings of material. Repeat the pulling out procedure at intervals until the strings break or pull back before stretching more than 1/8 inch. Pot life shall be recorded as the time interval between completion of the mixing cycle and first breaking of strings pulled 1/8 inch.
 - 4.1.4 **Shrinkage:** Compound mixed with the recommended catalyst addition (See 4.1.1) and free of air shall be capable of not shrinking more than 1% in any direction when cured for 16 hr in a mold followed by 24 hr in open air. Test specimen shall be a standard test slab approximately 6 in. x 6 in. and 0.075 in. ± 0.005 thick. Curing temperature shall be $25\text{ C} \pm 2$ ($77\text{ F} \pm 3.6$).
 - 4.1.5 **Corrosion:** The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports, specifications, and standards developed by the Society of Automotive Engineers, Inc. are the property of the Society and are to be used by anyone engaged in industry or trade is entirely voluntary. There is no obligation on the part of the user to conform to or be guided by any technical report, in formulating and a patent which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

- 4.2 **Properties:** The compound, when mixed with the recommended catalyst addition (See 4.1.1) and cured, shall conform to the requirements of 4.2.1, and shall be capable of meeting the requirements of 4.2.2, 4.2.3, and 4.2.4. Tests shall be performed in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable, on standard test slabs prepared in accordance with 4.1.4. Test results from specimens found to contain air bubbles at the point of break may be discarded and new specimens selected for test. Air bubbles may be minimized by subjecting the catalyzed compound to low pressures or centrifuging before curing.

4.2.1 **As Cured:**

4.2.1.1	Hardness, Durometer "A" or equiv.	35 - 55	ASTM D676
4.2.1.2	Tensile Strength, psi, min	300	ASTM D412, Die B or C
4.2.1.3	Elongation, %, min	100	ASTM D412, Die B or C
4.2.1.4	Dielectric Strength, v per mil, min	300	ASTM D149 Electrode Dia: 2 in. Rate of Rise: 500 v per sec

Ø 4.2.2 **Dry Heat Resistance:**

4.2.2.1	Hardness Change, Durometer "A" or equiv.	0 to -15	ASTM D573 Temperature: 225 C ± 3 (437 F ± 5.4) Time: 24 hr
4.2.2.2	Tensile Strength Change, %, max	-30	
4.2.2.3	Elongation Change, %, max	-10	

4.2.3 **Compression Set:**

4.2.3.1	Per cent of original deflection, max	35	ASTM D395, Method B Temperature: 100 C ± 1 (212 F ± 1.8) Time: 22 hr
Ø 4.2.3.2	Per cent of original thickness, max	9	

4.2.4 **Low Temperature Brittleness:**

Pass	ASTM D746, Procedure B Temperature: -55 C ± 3 (-67 F ± 5.4) Time: 10 min.
------	--

5. **QUALITY:** The product shall be uniform in quality and condition, clean, homogeneous, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

6. **REPORTS:**

- 6.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the requirements of this specification. This report shall include the purchase order number, material specification number, vendor's compound number, part number, and quantity.