

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 3365

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 1-15-61
Revised

SILICONE RUBBER COMPOUND

Room Temperature Vulcanizing, 35,000 Centipoises Viscosity
(Durometer 40 - 55)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. FORM: Liquid compound, to which a separate catalyst is added for curing.
3. APPLICATION: Primarily for potting or encasement of electrical and electronic components with an elastomeric medium, or for production of mechanical rubber parts in low pressure tooling. Elastomeric properties are retained in operation at temperatures from -65 to +450 F. For mechanical applications where compression set resistance is important, elevated temperature post-curing of parts may be required.
4. TECHNICAL REQUIREMENTS:
 - 4.1 General:
 - 4.1.1 Curing: When mixed with catalyst in accordance with manufacturer's recommendations and cured at room temperature, the compound shall polymerize to a uniform elastomeric material. A number of different catalysts may be found applicable by the user in order to vary pot life and cure time to meet specific production conditions. However, for purposes of qualification against this specification and for inspection control, a standard catalyst type and quantity, as supplied or recommended by the manufacturer of the base compound, shall be used.
 - 4.1.2 Viscosity: Viscosity of compound as received shall be 20,000 - 50,000 centipoises measured on a Brookfield Viscometer at 75 F $\pm$ 5. In measuring viscosity, the Viscometer spindle and speed used shall be consistent with the viscosity of the material being tested, in accordance with directions supplied by the manufacturer of the instrument.
 - 4.1.3 Pot Life: Compound mixed with the recommended catalyst addition (see 4.1.1) and maintained at a temperature not higher than 85 F shall have a pot life of not less than 30 minutes. Pot life shall be determined as follows: Weigh a 10 g $\pm$ 0.10 sample of the compound into a cup or dish 2 to 2.5 in. in diameter. Add the recommended type and amount of catalyst (see 4.1.1) and mix thoroughly with a small spatula for 60 sec $\pm$ 10. Dip the spatula into the catalyzed compound and pull out strings of material. Repeat the pulling-out procedure at intervals until the strings break or pull back before stretching more than 1/8 inch. Pot life shall be recorded as the time interval between completion of the mixing cycle and first breaking of strings pulled 1/8 inch.
 - 4.1.4 Shrinkage: Compound mixed with the recommended catalyst addition (see 4.1.1) and free of air shall shrink not more than 1% in any direction when cured for 16 hr in a mold followed by 24 hr in open air. Test specimen shall be a standard test slab approximately 6 x 6 in. and 0.075 in. $\pm$.005 thick. Curing temperature shall be 75 F $\pm$ 5.

4.1.5 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.

4.2 Properties: The compound, when mixed with the recommended catalyst addition (see 4.1.1) and cured, shall conform to the following requirements. Tests shall be performed in accordance with listed ASTM methods, insofar as practicable, on standard test slabs prepared in accordance with 4.1.4. Test results from specimens found to contain air bubbles at the point of break shall be discarded and new specimens selected for test.

4.2.1 As Cured:

4.2.1.1 Hardness, Durometer "A" or equiv. 40 - 55

4.2.1.2 Tensile Strength, psi, min 350 ASTM D412-51T, Die B or C

4.2.1.3 Elongation, %, min 100 ASTM D412-51T, Die B or C

4.2.1.4 Dielectric Strength, v per mil, min 300 ASTM D149-59
Electrode Diameter: 2 in.
Rate of Rise: 500 v per min.

4.2.2 Dry Heat Resistance:

4.2.2.1 Hardness Change, Durometer "A" or equiv. -5 to +10

ASTM D573-53
Temperature: 450 F $\pm$ 5
Time: 70 hr

4.2.2.2 Tensile Strength Change, %, max -35

4.2.2.3 Elongation Change, %, max -25

4.2.3 Compression Set:
(See Note 1)

ASTM D395-55, Method B
Temperature: 300 F $\pm$ 5
Time: 70 hr

4.2.3.1 Per cent of original deflection, max 30

Compressed to 70% of original thickness

4.2.3.2 Per cent of original thickness, max 9

4.2.4 Low Temperature Resistance:

4.2.4.1 Brittleness Pass

ASTM D746-57T, Procedure B
Temperature: -70 F $\pm$ 2
Time: 10 min.

Note 1. Specimens shall receive an additional cure of 24 hr at 450 F $\pm$ 5 in a circulating air oven before testing.

5. QUALITY: The product shall be uniform in quality and condition, clean, homogeneous, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.