

AEROSPACE MATERIAL SPECIFICATION



AMS3366

REV. C

Issued 1961-01
Revised 1989-10
Stabilized 2012-01

Superseding AMS3366B

Silicone Rubber Compound
Room Temperature Vulcanizing, 55,000 Centipoise Viscosity
Durometer 55 - 70

RATIONALE

This document has been determined to contain basic and stable technology which is not dynamic in nature.

STABILIZED NOTICE

This document has been declared "Stabilized" by SAE G-9, Aerospace Sealing Committee, and will no longer be subjected to periodic reviews for currency. Users are responsible for verifying references and continued suitability of technical requirements. Newer technology may exist.

SAENORM.COM : Click to view the full PDF of AMS3366C

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS3366C>**

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Liquid compound, to which a separate catalyst is added for curing.
3. APPLICATION: Primarily for potting or encasement of electrical and electronic components with an elastomeric medium, or for production of mechanical rubber parts in low pressure tooling. Elastomeric properties are retained in operation at temperatures from -55 to +230 C (-67 to + 446 F). For mechanical applications where compression set resistance is important, elevated temperature post-curing of parts may be required.
4. TECHNICAL REQUIREMENTS:
 - 4.1 General:
 - 4.1.1 Curing: When mixed with catalyst in accordance with manufacturer's recommendations and cured at room temperature, the compound shall polymerize to a uniform elastomeric material. A number of different catalysts may be found applicable by the user in order to vary pot life and cure time to meet specific production conditions. However, for purposes of qualification to this specification and for inspection control, a standard catalyst type and quantity, as supplied or recommended by the manufacturer of the base compound, shall be used.
 - 4.1.2 Viscosity: Viscosity of compound as received shall be 40,000 - 75,000 centipoises when measured on a Brookfield Viscometer at $25\text{ C} \pm 1$ ($77\text{ F} \pm 1.8$). In measuring viscosity, the viscometer spindle and speed used shall be consistent with the viscosity of the material being tested, in accordance with directions supplied by the manufacturer of the instrument.
 - 4.1.3 Pot Life: Compound mixed with the recommended catalyst addition (See 4.1.1) and maintained at a temperature not higher than 30 C (86 F) shall have a pot life of 2 - 5 hours. Pot life shall be determined as follows: Weigh a 10 ± 0.10 sample of the compound into a dish or cup 2 - 2.5 in. in diameter. Add the recommended type and amount of catalyst (See 4.1.1) and mix thoroughly with a small spatula for $60\text{ sec} \pm 10$. Dip the spatula into the catalyzed compound and pull out strings of material. Repeat the pulling-out procedure at intervals until the strings break or pull back before stretching more than 1/8 inch. Pot life shall be recorded as the time interval between completion of the mixing cycle and first breaking of strings pulled 1/8 inch.
 - 4.1.4 Shrinkage: Compound mixed with the recommended catalyst addition (See 4.1.1) and free of air shall be capable of not shrinking more than 1% in any direction when cured for 24 hr in a mold followed by 48 hr in open air. Test specimen shall be a standard slab approximately 6 in. x 6 in. and $0.075\text{ in.} \pm 0.005$ thick. Curing temperature shall be $25\text{ C} \pm 2$ ($77\text{ F} \pm 3.6$).
 - 4.1.5 Corrosion: The product shall not have a corrosive effect on other materials when exposed to conditions normally encountered in service. Discoloration of metal shall not be considered objectionable.

- 4.2 Properties: The compound, when mixed with the recommended catalyst addition (See 4.1.1) and cured, shall conform to the requirements of 4.2.1 and shall be capable of meeting the requirements of 4.2.2, 4.2.3, and 4.2.4. Tests shall be performed in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable, on standard test slabs prepared in accordance with 4.1.4. Test results from specimens found to contain air bubbles at the point of break may be discarded and new specimens selected for test. Air bubbles may be minimized by subjecting the catalyzed compound to low pressures or centrifuging before curing.

4.2.1 As Cured:

4.2.1.1	Hardness, Durometer " A" or equiv.	55 - 70	ASTM D676
4.2.1.2	Tensile Strength, psi, min	450	ASTM D412, Die B or C
4.2.1.3	Elongation, %, min	70	ASTM D412, Die B or C
4.2.1.4	Dielectric Strength, v per mil, min	300	ASTM D149 Electrode Dia: 2 in. Rate of Rise: 500 v per sec
4.2.2	<u>Dry Heat Resistance:</u>		ASTM D573
4.2.2.1	Hardness Change, Durometer "A" or equiv.	-10 to +10	Temperature: 225 C $\pm$ 3 (437 F $\pm$ 5.4) Time: 24 hr
4.2.2.1.1	Hardness, Absolute, min, Durometer "A" or equiv.	50	
4.2.2.2	Tensile Strength Change, %, max	-35	
4.2.2.3	Elongation Change, %, max	-25	
4.2.3	<u>Compression Set:</u>		ASTM D395, Method B
4.2.3.1	Per cent of original deflection, max	60	Temperature: 100 C $\pm$ 1 (212 F $\pm$ 1.8) Time: 22 hr
4.2.3.2	Per cent of original thickness, max	15	
4.2.4	<u>Low Temperature Brittleness:</u>	Pass	ASTM D746, Procedure B Temperature: -55 C $\pm$ 3 (-67 F $\pm$ 5.4) Time: 10 min.

5. QUALITY: The product shall be uniform in quality and condition, clean, homogeneous, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.

6. REPORTS:

- 6.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the requirements of this specification. This report shall include the purchase order number, material specification number, vendor's compound number, part number, and quantity.