



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc. SPECIFICATION

400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS3623A

Superseding AMS 3623

Issued 11-1-68

Revised 6-15-75

ELASTOMERIC TUBING, ELECTRICAL INSULATION Irradiated Polychloroprene, Flexible, Heat-Shrinkable 1.750 to 1 Shrink Ratio

1. SCOPE:

- 1.1 Form: This specification covers an irradiated, thermally-stabilized, flame-resistant, modified-polychloroprene rubber in the form of flexible, heat-shrinkable tubing.
- 1.2 Application: Primarily for use as a flexible, electrical insulation tubing whose diameter can be reduced to a predetermined size by heating to temperatures higher than 135°C (275°F). This material is stable under the following conditions:

-70°C (-94°F) to 105°C (221°F) Continuous
-70°C (-94°F) to 200°C (392°F) 4 hr

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, Pennsylvania 15096.

- 2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

ASTM D149 - Dielectric Breakdown Voltage and Dielectric Strength of Electrical Insulating Materials at Commercial Power Frequencies

ASTM D257 - D-C Resistance or Conductance of Insulating Materials

ASTM D412 - Tension Testing of Vulcanized Rubber

ASTM D570 - Water Absorption of Plastics

ASTM D573 - Accelerated Aging of Vulcanized Rubber by the Oven Method

ASTM D792 - Specific Gravity and Density of Plastics by Displacement

ASTM D876 - Testing Nonrigid Vinyl Chloride Polymer Tubing

ASTM D2240 - Indentation Hardness of Rubber and Plastics by Means of a Durometer

ASTM D2671 - Testing Heat-Shrinkable Tubing

ASTM G21 - Resistance of Synthetic Polymeric Materials to Fungi

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120.

SAE Technical Board rules provide that: "All technical reports, including standards approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or specification, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

2.3.1 Military Specifications:

- MIL-H-5606 - Hydraulic Fluid, Petroleum Base, Aircraft, Missiles and Ordnance
 MIL-T-5624 - Turbine Fuel, Aviation, Grades JP-4 and JP-5
 MIL-L-7808 - Lubricating Oil, Aircraft Turbine Engine, Synthetic Base
 MIL-A-8243 - Anti-icing and Deicing-Defrosting Fluid

3. TECHNICAL REQUIREMENTS:

3.1 Composition: The material shall be an irradiated, thermally-stabilized, flame-resistant, modified-polychloroprene rubber.

3.2 Color: Shall be black.

3.3 Properties: The product shall conform to the following requirements; tests shall be conducted in accordance with the specified methods, insofar as practicable. Unless otherwise specified, tubing shall be tested after being shrunk by heating for not less than 10 min. in a mechanical convection oven which is at $175^{\circ}\text{C} \pm 5$ ($347^{\circ}\text{F} \pm 9$), with an air velocity of 100 - 200 ft per min. (508 - 1016 mm/s) past the tubing, removed from the oven, and conditioned for not less than 4 hr at $23^{\circ}\text{C} \pm 2$ ($73.4^{\circ}\text{F} \pm 3.6$) and 45 - 55% relative humidity.

3.3.1 Tensile Strength, min	1500 psi (10.3 MPa)	ASTM D412 (See 4.5.1)
Ø 3.3.2 Elongation, min	225%	ASTM D412 (See 4.5.1)
Ø 3.3.3 Tensile Stress at 200% Elongation, max	2000 psi (13.8 MPa)	ASTM D412 (See 4.5.1)
3.3.4 Hardness, Durometer A or Equiv.	80 ± 5	ASTM D2240
3.3.5 Heat Shock	No dripping, flowing, or cracking	4.5.2
3.3.6 Flammability, Burning Time, max	15 sec	ASTM D876
3.3.7 Low-Temperature Flexibility	No cracks	4.5.3
3.3.8 Heat Aging		4.5.4
3.3.8.1 Tensile Strength, min	1200 psi (8.27 MPa)	
Ø 3.3.8.2 Elongation, min	175%	
Ø 3.3.9 Copper Stability	Pass	4.5.5
3.3.9.1 Elongation, min	150%	
Ø 3.3.10 Corrosion	Pass	4.5.6

Ø 3.3.11	Solvent Resistance		4.5.7
Ø 3.3.11.1	Tensile Strength, min	1200 psi (8.27 MPa)	
Ø 3.3.11.2	Elongation, min	150%	
3.3.11.3	Dielectric Strength, min	200 V/mil (7,870 V/mm)	
Ø 3.3.12	Fungus Resistance	Rating of 1 or less	4.5.8
Ø 3.3.13	Restricted Shrinkage, Withstand 2000 V for 1 min.	No cracks	4.5.9
3.3.14	Specific Gravity, max	1.50	ASTM D792, Method A
3.3.15	Water Absorption in 24 hr, max	1.00%	ASTM D570
3.3.16	Dielectric Strength (Short Time Test), min	200 V/mil (7,870 V/mm)	ASTM D876
Ø 3.3.17	Volume Resistivity, min	10 ¹¹ ohm-cm	ASTM D257
3.3.18	Dimensional Change on Heating		ASTM D876 (See 4.5.10)
3.3.18.1	Diametral	In accordance with Table I	
3.3.18.2	Longitudinal, max	-10%, +1%	
3.3.19	Shelf Life	Pass	4.5.11
3.4	<u>Marking</u> : Prior to and after shrinkage, tubing shall be suitable for having numbers or characters printed on it with conventional tubing marking techniques.		
3.5	<u>Quality</u> : The product shall be uniform in quality and condition, clean, smooth, and free from foreign materials and from imperfections detrimental to fabrication, appearance, or performance of parts.		
3.6	<u>Standard Sizes and Tolerances</u> : Unless otherwise specified, tubing shall be supplied in the Ø standard sizes and to the tolerances shown in Table I. Tolerances apply at 23° - 30° C (73.4° - 86° F). Measurements shall be made in accordance with ASTM D876.		

TABLE I

Size	Expanded (As Supplied) ID, Inches min	Recovered Dimensions (After Heating)		
		ID, Inches max	Nominal Wall Thickness, Inch	Wall Thickness Tolerance, Inch plus and minus
1/4	0.250	0.143	0.035	0.010
3/8	0.375	0.214	0.040	0.010
1/2	0.500	0.286	0.048	0.015
5/8	0.625	0.357	0.052	0.015
3/4	0.750	0.429	0.057	0.015
7/8	0.875	0.500	0.065	0.015
1	1.000	0.571	0.070	0.020
1-1/4	1.250	0.714	0.087	0.020
1-1/2	1.500	0.857	0.095	0.020
1-3/4	1.750	1.000	0.107	0.020
2	2.000	1.143	0.110	0.020
3	3.000	1.713	0.125	0.020
4	4.000	2.284	0.140	0.020

TABLE I (SI)

Size	Expanded (As Supplied) ID, Millimetres min	Recovered Dimensions (After Heating)		
		ID, Millimetres max	Wall Thickness Millimetres	Wall Thickness Tolerance, Millimetre plus and minus
1/4	6.35	3.63	0.89	0.25
3/8	9.52	5.44	1.02	0.25
1/2	12.70	7.26	1.22	0.38
5/8	15.88	9.07	1.32	0.38
3/4	19.05	10.90	1.45	0.38
7/8	22.22	12.70	1.65	0.38
1	25.40	14.50	1.78	0.51
1-1/4	31.75	18.14	2.21	0.51
1-1/2	38.10	21.77	2.41	0.51
1-3/4	44.45	25.40	2.72	0.51
2	50.80	29.03	2.79	0.51
3	76.20	43.51	3.18	0.51
4	101.60	58.01	3.56	0.51

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of tubing shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to assure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to tensile strength (3.3.1), elongation (3.3.2), tensile stress (3.3.3), hardness (3.3.4), heat shock (3.3.5), flammability (3.3.6), dimensional change on heating (3.3.18), and size and tolerance (3.6) requirements are classified as acceptance or routine control tests.

4.2.2 Qualification Tests: Tests to determine conformance to low temperature flexibility (3.3.7), heat aging (3.3.8), copper stability (3.3.9), corrosion (3.3.10), solvent resistance (3.3.11), fungus resistance (3.3.12), restricted shrinkage (3.3.13), specific gravity (3.3.14), water absorption (3.3.15), dielectric strength (3.3.16), volume resistivity (3.3.17), and shelf life (3.3.19) requirements are classified as qualification or periodic control tests.

4.3 Sampling: Shall be in accordance with the following; a lot shall be all tubing of the same size from the same production run offered for inspection at the same time.

4.3.1 Acceptance Tests: Not less than 16 ft (4.88 m) of tubing from each lot.

4.3.2 Qualification Tests: Not less than 50 ft (15.25 m) of tubing of each size or size range. Certain sizes will qualify additional sizes as shown below:

Range of Sizes	Qualification Size
1/4 - 7/8, incl	7/8
1 - 4, incl	4

4.4 Approval:

4.4.1 Sample tubing shall be approved by purchaser before tubing for production use is supplied, unless such approval be waived. Results of tests on production tubing shall be essentially equivalent to those on the approved sample.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production tubing which are essentially the same as those used on the approved sample tubing. If any change is necessary in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material and processing and, when requested, sample revised tubing. No tubing made by the revised procedure shall be shipped prior to receipt of reapproval.

4.5 Test Methods:

4.5.1 Tensile Strength, Elongation, and Tensile Stress: Three specimens shall be tested for tensile strength, tensile stress, and elongation using 1-in. (25-mm) bench marks and a jaw separation speed of 20 in. $\pm$ 2 or 500 mm $\pm$ 50 per minute. For sizes 3/8 and smaller, the specimens shall be full sections of tubing and the initial jaw separation shall be 1 in. (25 mm). For sizes larger than 3/8, the specimens shall be cut from tubing using die D and the initial jaw separation shall be 2 in. (51 mm). The die D specimens shall be obtained by cutting the tubing wall along its entire length, flattening the piece, and applying the die with its long dimension parallel to the longitudinal axis of the tubing.

4.5.2 Heat Shock: Three specimens in the expanded form (as supplied), each approximately 12 in. (305 mm) long, shall be conditioned for 4 hr $\pm$ 0.2 in a mechanical convection oven which is at 200° C $\pm$ 5 (392° F $\pm$ 9) with an air velocity of 100 - 200 ft per min. (508 - 1016 mm/s) past the specimens. After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and examined visually. Tubing shall then be bent through 360 deg (6.28 rad) over a mandrel of the diameter shown in Table II. The tubing shall remain free from cracks except that any side cracking caused by flattening of the specimen on the mandrel shall be disregarded.

TABLE II

Size	Diameter of Mandrel	
	Inches	(Millimetres)
1/4 to 1/2, incl	3/8	(9.5)
5/8 to 1, incl	5/8	(15.9)
1-1/4 to 2, incl	7/8	(22.2)
2-1/4 to 4, incl	1-1/8	(28.6)

- 4.5.3 Low-Temperature Flexibility: Three specimens, each approximately 12 in. (305 mm) long, shall be conditioned at $-70^{\circ}\text{C} \pm 3$ ($-94^{\circ}\text{F} \pm 5.4$) for $4\text{ hr} \pm 0.2$. The specimens shall be full sections of tubing for sizes 3/8 and smaller. For sizes above 3/8, 12 in. (305 mm) x 1/4 in. (6.4 mm) strips shall be cut from the tubing. A fixed steel mandrel, selected in accordance with Table II, shall be conditioned at $-70^{\circ}\text{C} \pm 3$ ($-94^{\circ}\text{F} \pm 5.4$). Upon completion of this conditioning and at this same temperature, the specimens shall be wrapped not less than 360 deg (6.28 rad) about the mandrel in approximately 2 seconds. The specimens shall be free from cracks except that any side cracking caused by flattening of the specimen on the mandrel shall be disregarded.
- 4.5.4 Heat Aging: Three specimens shall be prepared as in 4.5.1 and shall be conditioned for $168\text{ hr} \pm 2$ in a mechanical convection oven which is at $121^{\circ}\text{C} \pm 3$ or $250^{\circ}\text{F} \pm 5$, with an air velocity of 100 - 200 ft per min. (508 - 1016 mm/s) past the specimens. After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and tested for tensile strength and elongation in accordance with ASTM D412.
- 4.5.5 Copper Stability: A specimen of tubing, approximately 6 in. (152 mm) long, shall be slid over a straight, clean, unplated, uninsulated, solid, copper conductor. For size 1/4, a single copper conductor shall be used; for sizes 3/8 and larger, several copper conductors shall be used, each conductor being AWG 18 (0.0403 in.) (1.024 mm) or smaller. The specimens, on horizontally suspended conductors, shall be conditioned for not less than 24 hr in a humidity chamber at 90% - 95% relative humidity and $25^{\circ}\text{C} \pm 3$ ($77^{\circ}\text{F} \pm 5.4$). The specimens, on horizontally suspended conductors, shall then be conditioned in accordance with ASTM D573 for $168\text{ hr} \pm 2$ in an oven which is at $121^{\circ}\text{C} \pm 3$ or $250^{\circ}\text{F} \pm 5$, cooled to room temperature, visually examined, and tested for elongation in accordance with ASTM D412. The tubing shall not be brittle, glazed, cracked, severely discolored, or otherwise deteriorated by direct contact with copper. The copper shall not be pitted or blackened. Darkening of the copper due to normal air oxidation shall be disregarded.
- 4.5.6 Corrosion: A strip specimen, approximately 1 in. (25 mm) long x 1/4 in. (6.4 mm) wide cut from the tubing, shall be placed in the bottom of each of two clean 1/2 x 12 in. (12.7 x 305 mm) test tubes. A third tube shall be used for control. A copper-glass mirror about 1/4 in. (6.4 mm) wide x 1 in. (25 mm) long shall be suspended 6 - 7 in. (152 - 178 mm) above the bottom of each tube by fine copper wire attached to a silicone rubber stopper wrapped in aluminum foil. The mirrors shall be vacuum-deposited copper, on one side only, with a thickness equal to $10\% \pm 5$ transmission of normal incident light of 5000 angstroms. The coated mirrors shall be stored in vacuum and may be used for test only if no oxide film is present and the copper is not visibly damaged. The three test tubes shall be tightly sealed. The lower 2 in. (51 mm) of each tube shall be placed in an oven or oil bath at $150^{\circ}\text{C} \pm 3$ ($302^{\circ}\text{F} \pm 5.4$) for $16\text{ hr} \pm 0.5$. After cooling, the mirrors shall be examined in a good light against a white background. The copper shall not have been removed from a mirror leaving an area of transparency greater than 5% of the total area, disregarding the bottom 1/16 in. (1.6 mm) of the mirror. Discoloration of the copper film shall not be considered corrosion.

- 4.5.7 Solvent Resistance: Tubing shall be immersed for 24 hr $\pm$ 2 at 23° C $\pm$ 3 (73.4° F $\pm$ 5.4) in (MIL-T-5624) JP-4 fuel, MIL-H-5606 hydraulic fluid, SAE phosphate ester test fluid No. 1A (see 8.2), aviation gasoline 100/130, MIL-L-7808 lubricating oil, MIL-A-8243 de-icing fluid, and water. Six specimens (a total of 42), each approximately 6 in. (152 mm) long, shall be immersed in each of the fluids. The volume of fluid shall be not less than 20 times that of the specimens. After immersion, the specimens shall be lightly wiped and air dried for 30 - 60 min. at room temperature. After drying, three of each group of six specimens shall be tested in accordance with ASTM D412 for tensile strength; the other three shall have inner electrodes inserted as specified in ASTM D876 and shall be tested in accordance with ASTM D149 for dielectric strength.
- 4.5.8 Fungus Resistance: Shall be determined in accordance with ASTM G21 except that the incubation period shall be 28 days $\pm$ 0.5 and the test organisms shall be *Aspergillus niger*, *Aspergillus flavus*, *Penicillium funiculosum*, and *Trichoderma* sp. Three specimens, each approximately 3 in. (76 mm) long, shall be used for each organism.
- 4.5.9 Restricted Shrinkage: A specimen in the expanded form (as supplied) shall be shrunk onto a clean metallic mandrel of the configuration and size shown in Fig. 1. The tubing on the mandrel shall then be conditioned for not less than 30 min. in an oven which is at 175° C $\pm$ 5 (347° F $\pm$ 9), in accordance with ASTM D573, and cooled to room temperature. The tubing shall be examined visually and then subjected to the following voltage withstand test: The tubing shall snugly fit the mandrel and shall not be cracked. The test potential shall be applied between the mandrel and a metal foil electrode wrapped around the largest diameter of the tubing, in accordance with ASTM D876. The test potential shall then be applied in accordance with the short-time test of ASTM D149 using a 500 V per sec rate of rise.
- 4.5.10 Dimensional Change: Three specimens in the expanded form (as supplied), each approximately 6 in. (152 mm) long, shall be measured for length and inside diameter. The specimens shall be conditioned for 10 min. $\pm$ 0.5 in a mechanical convection oven which is at 175° C $\pm$ 5 (347° F $\pm$ 9) with an air velocity of 100 - 200 ft per min. (508 - 1016 mm/s) past the specimens. After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and remeasured. Longer heating at such temperature shall cause no additional shrinkage. Prior to and after conditioning, the dimensions of the tubing shall be in accordance with Table I. Measurements shall be made in accordance with ASTM D876. Longitudinal change shall be computed as follows:
- $$\% \text{ Change} = \frac{\text{Length after heating} - \text{Length before heating}}{\text{Length before heating}} \times 100$$
- 4.5.11 Shelf Life: Three specimens, each approximately 6 in. (152 mm) long, shall be tested in accordance with ASTM D2671. Tubing shall meet expanded (as supplied) dimensions shown in Table I after conditioning for not less than 2 weeks at 60° C $\pm$ 1 (140° F $\pm$ 1.8) and shall meet recovered dimensions shown in Table I after heat shrinking as described in 4.5.10.

4.6 Reports:

- 4.6.1 The vendor of tubing shall furnish with each shipment three copies of a report showing the results of tests made on the lot to determine conformance to the acceptance test requirements of this specification and a statement that the tubing conforms to the other technical requirements. This report shall include the purchase order number, material specification number and its revision letter, vendor's compound number, lot number, size, and quantity.

4.6.2 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of tubing, supplier's compound number, part number, and quantity. When tubing for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of tubing to determine conformance to the requirements of this specification, and shall include in the report a statement that the tubing conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.7 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the tubing may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the tubing represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Each package shall be permanently and legibly marked with AMS 3623A, size, quantity, purchase order number, manufacturer's identification, and date of manufacture.

5.2 Packaging:

5.2.1 Packaging shall be accomplished in such a manner as will insure that the tubing, during shipment and storage, will not be permanently distorted and will be protected against damage from exposure to weather or any normal hazard. Standard packages shall each contain the following quantities in one continuous length:

Size	Quantity
1/4 to 2, incl	100 ft (30.5 m)
3 and 4	50 ft (15.3 m)

5.2.2 Packages shall be prepared for shipment in accordance with commercial practice to assure carrier acceptance and safe transportation to the point of delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Tubing not conforming to this specification or to authorized modifications will be subject to rejection.

8. NOTES:

8.1 Marginal Indicia: The phi (ϕ) symbol is used to indicate technical changes from the previous issue of this specification.

8.2 SAE phosphate ester test fluid No. 1A is available from:

Monsanto Chemical Company
Organic Chemical Division
800 North Lindbergh Boulevard
St. Louis, Missouri 63166