



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.

400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

SPECIFICATION

AMS 3674A

Superseding AMS 3674

Issued 5-15-71

Revised 7-15-80

PLASTIC MOLDINGS, ELECTRICAL INSULATION Cross-linked Polyolefin, Pigmented, Flexible, Heat Shrinkable

1. SCOPE:

1.1 Form: This specification covers a cross-linked, thermally-stabilized, modified polyolefin plastic in the form of flexible, electrically-insulating, heat-shrinkable molded components.

1.2 Application: Primarily for parts whose expanded dimensions can be reduced to a predetermined size upon exposure to 100°C (212°F) or higher. This product is stable for continuous exposure from -55°C (-65°F) to +135°C (+275°F).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350 - Standards and Test Methods

AMS 3032 - Aviation Fuel, Grade 100/130

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D635 - Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position

ASTM D747 - Stiffness of Plastics by Means of a Cantilever Beam

ASTM D2240 - Rubber Property - Durometer Hardness

ASTM D2671 - Testing Heat-Shrinkable Tubing for Electrical Use

ASTM G21 - Determining Resistance of Synthetic Polymeric Materials to Fungi

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

MIL-H-5606 - Hydraulic Fluid, Petroleum Base, Aircraft, Missiles and Ordnance

MIL-T-5624 - Turbine Fuel, Aviation, Grades JP-4 and JP-5

2.3.2 Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

3. TECHNICAL REQUIREMENTS:

3.1 Material: Shall be a cross-linked, thermally-stabilized, flame-resistant, modified polyolefin.

3.2 Color: Shall be black, unless otherwise specified.

3.3 Properties: Moldings shall conform to the following requirements; reported values shall be the average of all specimens tested for each requirement. Except as otherwise specified, tests shall be performed in accordance with ASTM D2671, insofar as practicable. Tests except dimensions and dimensional recovery (3.3.15) shall be conducted on molded slabs (See 4.3.1 and 4.3.2).

3.3.1 Tensile Strength, min Jaw separation rate at 20 in. per min. (8.5 mm/sec)	1200 psi (8.27 MPa)	4.5.2
3.3.2 Elongation, min	250%	4.5.2
3.3.3 Heat Shock	No dripping, flowing, or cracking	4.5.3
3.3.4 Low-Temperature Flexibility	No cracks	4.5.4
3.3.5 Heat Aging, Method A and B		4.5.5
3.3.5.1 Tensile Strength, min	1000 psi (6.90 MPa)	
3.3.5.2 Elongation, min	200%	
3.3.6 Flame Retardance		ASTM D635
3.3.6.1 Time of Burning, max	30 sec	
3.3.6.2 Extent of Burning, max	1.2 in. (30 mm)	
3.3.7 Hardness, D	40 ± 10	ASTM D2240
3.3.8 Stiffness, max	10,000 psi (69.0 MPa)	ASTM D747
3.3.9 Specific Gravity, max	1.40	
3.3.10 Water Absorption in 24 hr, max	0.50%	
3.3.11 Dielectric Strength	200 V/mil (7874 V/mm)	
3.3.12 Volume Resistivity, min	¹² 10 ohm-cm	
3.3.13 Fungus Resistance	Rating of 1 or less	ASTM G21
3.3.14 Corrosion, Method A after 16 hr ± 0.25 at 175°C ± 3 (347°F ± 5)	Less than 5% removal of copper	

3.3.15 Solvent Resistance

4.5.6

3.3.15.1 Tensile Strength, min 1000 psi
(6.89 MPa)

3.3.15.2 Elongation, min 200%

3.3.16 Elastic Memory

4.5.7

Expansion, max 275%

Retraction, min 93%

3.3.17 Dimensions and Dimensional Recovery: Shall be as specified on the drawing or purchase order. The samples shall be measured and then conditioned for 10 min. in an oven which is at $150^{\circ}\text{C} \pm 2$ ($302^{\circ}\text{F} \pm 4$). After conditioning, the samples shall be removed from the oven, held for not less than 4 hr at $23^{\circ}\text{C} \pm 2$ ($73^{\circ}\text{F} \pm 4$) and 45 - 55% relative humidity, and remeasured.

3.4 Quality: Moldings shall be uniform in quality and condition, clean, smooth, and free from foreign materials and from internal and external imperfections detrimental to fabrication, appearance, or performance of parts.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of moldings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.6. Purchaser reserves the right to sample and to perform such confirmatory testing as he deems necessary to ensure that the moldings conform to the requirements of this specification and the applicable drawing.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for tensile strength (3.3.1), elongation (3.3.2), heat shock (3.3.3), flame retardance (3.3.6), hardness (3.3.7), and dimensional recovery (3.3.17) are classified as acceptance tests and shall be performed to represent each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for low-temperature flexibility (3.3.4), Method A heat aging (3.3.5), stiffness (3.3.8), specific gravity (3.3.9), water absorption (3.3.10), dielectric strength (3.3.11), volume resistivity (3.3.12), fungus resistance (3.3.13), corrosion (3.3.14), solvent resistance (3.3.15), and elastic memory (3.3.16) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the initial shipment of molded components to a purchaser, when a change in material or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be as follows; a lot shall be all molded components of the same part number from the same production run presented for vendor's inspection at one time. The number of specimens for each test shall be as specified in the applicable test procedure or, if not specified therein, not less than three. A lot may be packaged in small quantities as noted in 5.2.1 under a basic lot approval as long as lot identification is maintained.

4.3.1 For Acceptance Tests: Not less than one molded slab as in 4.5.1 plus molded components selected at random in accordance with MIL-STD-105, inspection level S-2, AQL 6.5%. When purchased, molded slabs shall be supplied to the purchaser with the molded components.

4.3.1.1 When a statistical sampling plan and acceptance quality level (AQL) other than as specified in 4.3.1 have been agreed upon by purchaser and vendor, sampling shall be in accordance with such plan in lieu of sampling as in 4.3.1 and the report of 4.6.1 shall state that such plan was used.

4.3.2 For Periodic Tests and Preproduction Tests: Not less than six molded slabs as in 4.5.1 plus molded components as specified by purchaser.

4.4 Approval:

4.4.1 Sample moldings shall be approved by purchaser before moldings for production use are supplied, unless such approval be waived. Results of tests on production moldings shall be essentially equivalent to those on the approved samples.

4.4.2 Vendor shall use ingredients, manufacturing procedures, processes, and methods of inspection on production moldings which are essentially the same as those used on the approved sample moldings. If any change is necessary in ingredients, in type of equipment for processing, or in manufacturing procedures, vendor shall submit for reapproval a statement of the proposed changes in material and processing, and when requested sample moldings. Moldings made by the revised procedure shall not be shipped prior to receipt of reapproval.

4.5 Test Methods:

4.5.1 Specimen Preparation: Specimens for the tests of 4.5.2 through 4.5.7 shall be cut from molded slabs nominally 6 in. (150 mm) square by 0.075 in. $\pm$ 0.010 (1.90 mm $\pm$ 0.25) thick fabricated from the same batch of compound and subjected to the same degree of crosslinking as the molded components represented.

4.5.2 Tensile Strength and Elongation: Three specimens, cut using die D of ASTM D412, shall be tested for tensile strength and elongation in accordance with ASTM D2671.

4.5.3 Heat Shock: Three specimens, 6 x 1/4 in. (150 x 6.4 mm), shall be conditioned for 4 hr $\pm$ 0.1 in an oven which is at 225°C $\pm$ 5 (437°F $\pm$ 9). After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and examined visually for evidence of dripping, flowing, or cracking.

4.5.4 Low-Temperature Flexibility: Three specimens 6 x 1/4 in. (150 x 6.4 mm), and a mandrel 1.125 in. $\pm$ 0.005 (28.58 mm) $\pm$ 0.13 in diameter, shall be conditioned for 4 hr $\pm$ 0.1 at -55°C $\pm$ 2 (-67°F $\pm$ 4). While still at this temperature, the specimens shall be bent around the mandrel for not less than 360 deg within 10 sec $\pm$ 2, and visually examined for cracks.

4.5.5 Heat Aging:

4.5.5.1 Method A: Three specimens, prepared and measured as in 4.5.1, shall be conditioned for 168 hr $\pm$ 2 in an oven which is at 175°C $\pm$ 5 (347°F $\pm$ 9). After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and tested for tensile strength and elongation in accordance with 4.5.2.

4.5.5.2 Method B: Three specimens, prepared and measured as in 4.5.1, shall be conditioned for 1000 hr $\pm$ 10 in an oven which is at 150°C $\pm$ 3 (302°F $\pm$ 5). After conditioning, the specimens shall be removed from the oven, cooled to room temperature, and tested for tensile strength and elongation in accordance with 4.5.2.